


PROCESS DETAILS

Process	EPITAXIAL PLANAR
Die Size	22 x 22 MILS
Die Thickness	9.0 MILS
Base Bonding Pad Area	3.7 X 3.7 MILS
Emitter Bonding Pad Area	4.2 X 4.2 MILS
Top Side Metalization	Al - 30,000Å
Back Side Metalization	Au - 18,000Å

GEOMETRY



BACKSIDE COLLECTOR

GROSS DIE PER 4 INCH WAFER


23,450

PRINCIPAL DEVICE TYPES

MPSA55
MPSA56

145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R2 (23 -August 2006)



145 Adams Avenue
Hauppauge, NY 11788 USA
Tel: (631) 435-1110
Fax: (631) 435-1824
www.centalsemi.com

R2 (23 -August 2006)