

DATA SHEET

Microwave Ferrites

Applications

- Point-to-point radio
- Radar and switching
- · Latching devices

Description

Skyworks, through its wholly owned subsidiary, Trans-Tech, offers a line of microwave ferrites that are designed to meet the needs of below-resonance applications from X band to millimetric frequencies. The table below provides the specifications for Magnesium, Nickel, and Millimeterwave Ferrites.



Specifications for Microwave Ferrites (1 of 2)

Composition and Type Number	Saturation Magnetization 4πMs (Gauss)	Lande' [§] G-factor g-eff	Line Width [§] Δh 0e @ -3 dB	Dielectric [§] Constant ε'	Dielectric Loss Tangent Tan δ = ε"/ε'	Curie Temperature T° (°C) (Nominal Value)	Spin Wave Line Width ΔH _k oe (Nominal Value)	Remanent Induction* B _r (Gauss) (Nominal Value)	Coercive Force* H _c (oe) (Nominal Value)	Initial Permeability† µo (Nominal Value)	
Magnesium Ferrites											
TTI-105	1750 ± 5%	1.98	<270	12.2 ± 5%	<0.00025	225	2.2	1220	1.20	55	
TTI-2000	2000 ± 5%	1.98	<300	12.4 ± 5%	<0.00025	290	2.1	1385	1.60	52	
TT1-390	2150 ± 5%	2.04	<648	12.7 ± 5%	<0.00025	320	2.5	1288	1.80	50	
TT1-2500	2500 ± 5%	2.03	<624	12.9 ± 5%	<u><</u> 0.0005	275	3.0	1410	1.33	57	
TT1-2650	2650 ± 5%	2.02	<636	13.0 ± 5%	<0.0005	245	2.8	1511	1.33	85	
TT1-2800	2800 ± 5%	2.01	<648	13.1 ± 5%	<0.0005	225	2.2	1477	0.83	140	
TT1-3000	3000 ± 5%	1.99	<228	12.9 ± 5%	<0.0005	240	3.2	2100	0.85	54	
Nickel Ferrites											
TT2-125	2100 ± 10%	2.30	<575	12.6 ± 5%	<u><</u> 0.0002	560	6.1	1426	4.42	26	
TT2-102	2500 ± 10%	2.25	<610	12.7 ± 5%	<0.0020	570	6.9	1485	4.42	23	
TT2-2750	2750 ± 10%	2.20	<540	12.8 ± 5%	< 0.0025	580	9.0	1130	3.00	20	
TT2-101	3000 ± 10%	2.19	<375	13.0 ± 5%	< 0.0025	585	12.4	1853	5.70	17	
TT2-3250	3250 ± 10%	2.10	<440	12.8 ± 5%	<0.0025	550	10.5	1200	2.20	36	
TT2-3500	3500 ± 10%	2.10	<500	12.8 ± 5%	<0.0025	540	9.0	1260	2.40	50	
TT2-4000	4000 ± 10%	2.22	<425	12.3 ±10%	<0.0025	470	7.0	1800	3.00	93	
TT2-4500	4500 ± 10%	2.22	<425	12.3 ±10%	<u><</u> 0.0015	-	-	-	-	-	

Specifications for Microwave Ferrites (2 of 2)

Composition and Type Number	Saturation Magnetization 4πM _s (Gauss)	Lande' [§] G-factor g-eff	Line Width [§] ∆h 0e @ -3 dB	Dielectric [§] Constant ε'	Dielectric Loss Tangent Tan δ = ε"/ε'	Curie Temperature T° (°C) (Nominal Value)	Spin Wave Line Width ΔH _k oe (Nominal Value)	Remanent Induction* Br (Gauss) (Nominal Value)	Coercive Force* H _c (oe) (Nominal Value)	Initial Permeability† µo (Nominal Value)	
Millimeterwave Ferrites											
TT2-111	5000 ± 10%	2.11	<200	12.9 ±6.8%	<0.0010 @9300	375	6.0	1956	0.96	317	
TT86-6000	5000 ± 10%	2.11	<200	12.5 ± 5%	<0.0002	363	6.0	3800	1.50	317	

[§] Measured @ 9.4 GHz

Bars and Rods are Available for All Material Types

Copyright © 2006-2010, 2015, 2017, Trans-Tech Inc., Inc. All Rights Reserved.

Information in this document is provided in connection with Trans-Tech, Inc. ("Trans-Tech"), a wholly-owned subsidiary of Skyworks Solutions, Inc. These materials, including the information contained herein, are provided by Trans-Tech as a service to its customers and may be used for informational purposes only by the customer. Trans-Tech assumes no responsibility for errors or omissions in these materials or the information contained herein. Trans-Tech may change its documentation, products, services, specifications or product descriptions at any time, without notice. Trans-Tech makes no commitment to update the materials or information and shall have no responsibility whatsoever for conflicts, incompatibilities, or other difficulties arising from any future changes.

No license, whether express, implied, by estoppel or otherwise, is granted to any intellectual property rights by this document. Trans-Tech assumes no liability for any materials, products or information provided hereunder, including the sale, distribution, reproduction or use of Trans-Tech products, information or materials, except as may be provided in Trans-Tech Terms and Conditions of Sale.

THE MATERIALS, PRODUCTS, AND INFORMATION ARE PROVIDED "AS IS" WITHOUT WARRANTY OF ANY KIND, WHETHER EXPRESS, IMPLIED, STATUTORY, OR OTHERWISE, INCLUDING FITNESS FOR A PARTICULAR PURPOSE OR USE, MERCHANTABILITY, PERFORMANCE, QUALITY, OR NON-INFRINGEMENT OF ANY INTELLECTUAL PROPERTY RIGHT; ALL SUCH WARRANTIES ARE HEREBY EXPRESSLY DISCLAIMED. TRANS-TECH DOES NOT WARRANT THE ACCURACY OR COMPLETENESS OF THE INFORMATION, TEXT, GRAPHICS, OR OTHER ITEMS CONTAINED WITHIN THESE MATERIALS. TRANS-TECH SHALL NOT BE LIABLE FOR ANY DAMAGES, INCLUDING BUT NOT LIMITED TO ANY SPECIAL, INDIRECT, INCIDENTAL, STATUTORY, OR CONSEQUENTIAL DAMAGES, INCLUDING WITHOUT LIMITATION, LOST REVENUES OR LOST PROFITS THAT MAY RESULT FROM THE USE OF THE MATERIALS OR INFORMATION, WHETHER OR NOT THE RECIPIENT OF MATERIALS HAS BEEN ADVISED OF THE POSSIBILITY OF SUCH DAMAGE.

Trans-Tech products are not intended for use in medical, lifesaving, or life-sustaining applications, or other equipment in which the failure of the Trans-Tech products could lead to personal injury, death, or physical or environmental damage. Trans-Tech customers using or selling Trans-Tech products for use in such applications do so at their own risk and agree to fully indemnify Trans-Tech for any damages resulting from such improper use or sale.

Customers are responsible for their products and applications using Trans-Tech products, which may deviate from published specifications as a result of design defects, errors, or operation of products outside of published parameters or design specifications. Customers should include design and operating safeguards to minimize these and other risks. Trans-Tech assumes no liability for applications assistance, customer product design, or damage to any equipment resulting from the use of Trans-Tech products outside of stated published specifications or parameters.

Skyworks and the Skyworks symbol are trademarks or registered trademarks of Skyworks Solutions, Inc., in the United States and other countries. Third-party brands and names are for identification purposes only, and are the property of their respective owners.

[†] Measured @ 1 KHz

^{*} Measured @ 60 Hz or 2 KHz with Happ = 5xHc

^{**} Anneal @ 1100 ° C in oxygen after machining