

Strain Gage Adhesive



OTHER ACCESSORIES USED IN A P ADHESIVE INSTALLATION:

- CSM Degreaser or GC-6 Isopropyl Alcohol
- Silicon-Carbide Paper
- M-Prep Conditioner A
- M-Prep Neutralizer 5A
- CSP-1 Cotton Swabs
- GSP-1 Gauze Sponges
- MJG-2 Mylar® Tape
- TFE-1 Teflon® Film
- HSC Spring Clamp
- GT-14 Pressure Pads and Backup Plates



RoHS
COMPLIANT

DESCRIPTION

Single-part, solvent-thinned, polyimide adhesive. Results in a strong, thin, near-creep-free, adhesive layer.

CHARACTERISTICS

Operating Temperature Range:
-452° to +700°F [-270° to +370°C].

Upper limit:
+800°F [+425°C] for 1 to 2 hours.

Elongation Capabilities:
±2% at +75°F [+24°C].

Shelf Life:
Minimum 4 months at +75°F [+24°C].

Pot Life:
Minimum 4 months at +75°F [+24°C].

Clamping Pressure:
20 to 40psi [140 to 280kN/m²].

Cure Requirements:

For two minutes, expose the adhesive on the strain gage and test article to an infrared lamp or other heat source until the materials are dry. Monitor the temperature of the surface and do not allow materials to exceed +250°F [+120°C].

After clamping, cure 2 hours at +250°F [+120°C], increase temperature to +300°F [+150°C] for 2 hours, increase temperature to +340°F [+170°C] for 2 hours and finish cure with 4 hours at +380°F [+195°C].

Recommended Postcure (Unclamped):

1 hour at +300°F [+150°C], followed by 2 hours at +400°F [+205°C], and then 4 hours at +500°F [+260°C].

PACKAGING OPTIONS

Kits:
1 brush-cap bottle [1oz/30ml]

Mylar and Teflon are Registered Trademarks of DuPont

Disclaimer

All product specifications and data are subject to change without notice.

Vishay Precision Group, Inc., its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "Vishay Precision Group"), disclaim any and all liability for any errors, inaccuracies or incompleteness contained herein or in any other disclosure relating to any product.

Vishay Precision Group disclaims any and all liability arising out of the use or application of any product described herein or of any information provided herein to the maximum extent permitted by law. The product specifications do not expand or otherwise modify Vishay Precision Group's terms and conditions of purchase, including but not limited to the warranty expressed therein, which apply to these products.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted by this document or by any conduct of Vishay Precision Group.

The products shown herein are not designed for use in medical, life-saving, or life-sustaining applications unless otherwise expressly indicated. Customers using or selling Vishay Precision Group products not expressly indicated for use in such applications do so entirely at their own risk and agree to fully indemnify Vishay Precision Group for any damages arising or resulting from such use or sale. Please contact authorized Vishay Precision Group personnel to obtain written terms and conditions regarding products designed for such applications.

Product names and markings noted herein may be trademarks of their respective owners.