

## Special Use Sensors - Residual Stress Strain Gages

The most widely used practical technique for determining residual stresses is the hole-drilling strain gage method described in ASTM Standard E837. With this method, a specially configured strain gage rosette is bonded to the surface of the test object; and a small, shallow hole is introduced into the structure, through the center of the gage, with a precision drilling apparatus. Strains in the immediate vicinity of the hole are measured, and the relaxed residual stresses are computed from these measurements. The general theory of making residual stress measurements is covered in Micro-Measurements Tech Note TN-503, Measurement of Residual Stresses by the Hole-Drilling Strain Gage Method and the requisite hardware is described in Bulletin 304.

### CONSTRUCTION

All gages are constructed of self-temperature-compensated foil (06 and 13 S-T-C) on a flexible polyimide carrier, and incorporate a centering target for use with a precision milling guide. EA-Series (A-Alloy) gages are available "open-faced" or with solder dots and encapsulation (Option SE); CEA-Series (A-Alloy) gages have encapsulated grids, and rugged, copper-coated solder tabs. Construction of the N2K Series (K-alloy) is similar to the N2A Series and includes copper pads (DP) on the solder tabs. The 062UM gage permits installation adjacent to weldments and intersecting surfaces.

| GAGE PATTERN AND DESIGNATION<br>Insert Desired S-T-C No. in Spaces Marked XX.<br>See Note 1 |  | RES. IN OHMS             | DIMENSIONS  |                    |                   |       |        |       |
|---|--|--------------------------|---|--------------------|-------------------|-------|--------|-------|
|   |  |                          | GAGE LENGTH   | GRID CTR'LINE DIA. | TYPICAL HOLE DIA. |       | MATRIX |       |
|   |  |                          |   |                    | Min.              | Max   | Length | Width |
| EA-XX-031RE-120<br>EA-XX-031RE-120/SE   |  | 120 ± 0.2%<br>120 ± 0.4% | 0.031   | 0.101              | 0.03              | 0.04  | 0.29   | 0.29  |
|   |  |                          | 0.79  | 2.56               | 0.8               | 1.0   | 7.4    | 7.04  |
|   |  |                          | Due to small pattern size, measurement error can be magnified by slight mislocation of drill hole. Pattern not recommended for general-purpose applications.  |                    |                   |       |        |       |
| N2K-XX-030RR-350/DP   |  | 350 ± 0.4%               | 0.30  | 0.170              | 0.090             | 0.100 | 0.37   | 0.37  |
|   |  |                          | 0.76  | 4.32               | 2.3               | 2.5   | 9.4    | 9.4   |
|   |  |                          | Special six-element configuration that provides somewhat higher output than three-element designs.  |                    |                   |       |        |       |
| EA-XX-062RE-120<br>EA-XX-062RE-120/SE   |  | 120 ± 0.2%<br>120 ± 0.4% | 0.062   | 0.202              | 0.06              | 0.08  | 0.42   | 0.42  |
|   |  |                          | 1.57  | 5.13               | 1.5               | 2.0   | 10.7   | 10.7  |
|   |  |                          | Most widely used RE pattern for general-purpose residual stress measurement applications.   |                    |                   |       |        |       |
| EA-XX-125RE-120<br>EA-XX-125RE-120/SE   |  | 120 ± 0.2%<br>120 ± 0.4% | 0.125   | 0.404              | 0.12              | 0.16  | 0.78   | 0.78  |
|   |  |                          | 3.18  | 10.26              | 3.0               | 4.1   | 19.8   | 19.8  |
|   |  |                          | Larger version of the 062RE pattern.  |                    |                   |       |        |       |
| CEA-XX-062UL-120  |  | 120 ± 0.4%               | 0.062   | 0.202              | 0.06              | 0.08  | 0.50   | 0.62  |
|   |  |                          | 1.57  | 5.13               | 1.5               | 2.0   | 12.7   | 15.7  |
|   |  |                          | Fully encapsulated with large copper-coated soldering tabs. Same pattern geometry as 062RE pattern.   |                    |                   |       |        |       |
| CEA-XX-062UM-120  |  | 120 ± 0.4%               | 0.062   | 0.202              | 0.06              | 0.08  | 0.38   | 0.48  |
|   |  |                          | 1.57  | 5.13               | 1.5               | 2.0   | 9.6    | 12.2  |
|   |  |                          | Fully encapsulated with large copper-coated soldering tabs and special trim alignment marks. Trim line spaced 0.068 in [1.73 mm] from hole center. Limitations may exist in data reduction equations. |                    |                   |       |        |       |

**Note 1:** Products with designations and options shown in bold are not RoHS compliant.

## Disclaimer

All product specifications and data are subject to change without notice.

Vishay Precision Group, Inc., its affiliates, agents, and employees, and all persons acting on its or their behalf (collectively, "Vishay Precision Group"), disclaim any and all liability for any errors, inaccuracies or incompleteness contained herein or in any other disclosure relating to any product.

Vishay Precision Group disclaims any and all liability arising out of the use or application of any product described herein or of any information provided herein to the maximum extent permitted by law. The product specifications do not expand or otherwise modify Vishay Precision Group's terms and conditions of purchase, including but not limited to the warranty expressed therein, which apply to these products.

No license, express or implied, by estoppel or otherwise, to any intellectual property rights is granted by this document or by any conduct of Vishay Precision Group.

The products shown herein are not designed for use in medical, life-saving, or life-sustaining applications unless otherwise expressly indicated. Customers using or selling Vishay Precision Group products not expressly indicated for use in such applications do so entirely at their own risk and agree to fully indemnify Vishay Precision Group for any damages arising or resulting from such use or sale. Please contact authorized Vishay Precision Group personnel to obtain written terms and conditions regarding products designed for such applications.

Product names and markings noted herein may be trademarks of their respective owners.