

Table 1. DSC and XRD data for several substituted pentaerythritol compounds

Compound	-R	DSC data				XRD data	
		$T_{ir}$ (°K)	$\Delta H_{ir}$ (kcal.mole <sup>-1</sup> )	$T_{m.p.}$ (°K)	$\Delta H_m$ (kcal.mole <sup>-1</sup> )	$T$ (°K)	$a$ (Å) (e.s.d.)
I	-COOH	394.7	6.89	492	decomposition	415	8.93 (5)
II	-CH <sub>3</sub>	351.3	5.14	497.0	1.23	373	8.86 (5)
III	-NO <sub>2</sub>	347.4	5.30	438	decomposition	355	8.89 (5)
IV	-NH <sub>2</sub>	407.3	7.87	446.0	0.71	—	see text

normally behaving melting points, with completely reversible transitions between phases I and II and between phase I and the melt. Compounds I and III undergo reversible transitions between phases I and II, but decompose without melting at higher temperatures.

Compounds II, III, and IV have been previously studied with DSC (Murrill & Breed, 1970). The results of the two investigations are in good agreement.

The X-ray study of IV deserves special mention. The X-ray pattern of the high-temperature phase has only one line. This was the only line observed, even though many photographs were taken of several specimens at a number of temperatures between 407.3 and 446.0°K. This line is characteristic of a crystalline material, appearing as either a sharp line or one showing evidence of preferred orientation. It has a  $d$  spacing of 4.97 Å. When the temperature was raised above 446.0°K, a broad diffuse band ( $d=5.1-5.2$  Å), characteristic of a liquid, appeared.

The other compounds all show two or more unique reflections in the high-temperature phase. They were indexed and unit-cell and space-group assignments were made in the usual manner (Rudman & Post, 1968). However, no conclusions concerning the lattice parameters or space group of IV can be made on the basis of a single observation. We can only state that the high-temperature phase is crystalline and can be differentiated from the liquid phase. It is possible that the rate of molecular reorientation in this phase is so great that only nearest neighbor effects (similar to that observed for a liquid) are apparent. A study of the rate of reorientation in this phase, using nuclear magnetic resonance or neutron inelastic scattering methods, would be of interest.

Room-temperature single-crystal data for this compound (IV) have been determined by Rose & Van Camp (1955). They reported the space group as  $P2_12_12_1$ . A re-investigation of this phase revealed the following systematic ab-

sences:  $0kl$ ,  $k+l$  odd and  $hk0$ ,  $h$  odd. These absences are consistent with space groups  $Pnma$  (No. 62) or  $Pn2_1a$  (No. 33). The lattice parameters, obtained from precession photographs, were refined from powder data using a modified version of the program *PIRUM* (Werner, 1970) on a CDC 3300 computer. These values,  $a=7.816$  (5),  $b=8.822$  (3) and  $c=8.867$  (4) Å, are in good agreement with the results of the earlier investigation (7.80, 8.82 and 8.89 Å respectively).

In conclusion, we find that each of the compounds investigated forms a highly disordered crystalline phase just below the melting point, as does pentaerythritol itself. With the exception of IV, they form face-centered cubic phases with similar lattice constants ( $a$  for R = -CH<sub>2</sub>OH is 8.963 Å, Nitta & Watanabé, 1938). The deviations from the spherical character of the molecules caused by the substitution of these four functional groups does not prevent the formation of a plastic-crystal phase. Even in the cases of I and III, where the introduction of a highly polar group results in decomposition rather than melting, the X-ray study indicates that crystals of phase I are plastic in nature.

## References

- MURRILL, E. & BREED, L. (1970). *Thermochim. Acta*, **1**, 239-246.  
 NITTA, I. & WATANABÉ, T. (1938). *Bull. Chem. Soc. Japan*, **13**, 28-35.  
 ROSE, H. & VAN CAMP, A. (1955). *Anal. Chem.* **27**, 1356.  
 RUBIN, K. & RUDMAN, R. (1973). *J. Phys. Chem.* In the press.  
 RUDMAN, R. & POST, B. (1968). *Mol. Cryst.* **5**, 95-110.  
 SILVER, L. & RUDMAN, R. (1970). *J. Phys. Chem.* **74**, 3134-3139.  
 TIMMERMANS, J. (1961). *Phys. Chem. Solids*, **18**, 1-8.  
 WERNER, P. (1970). *Ark. Kem.* **31**, 513-516.

## Notes and News

*Announcements and other items of crystallographic interest will be published under this heading at the discretion of the Editorial Board. The notes (in duplicate) should be sent to the Executive Secretary of the International Union of Crystallography (J. N. King, International Union of Crystallography, 13 White Friars, Chester CH1 1NZ, England).*

### Acta Crystallographica Duplicate publication of papers

As stated in *Notes for Authors* (this issue, p. 145, §1.3), it is not the policy of *Acta Crystallographica* to publish material that has already appeared, or is intended to appear, in any other journal in any language. A paper showing a significant advance on results published in preliminary form will be considered by the Editors; authors of such papers are requested to provide copies of the preliminary note along

with the paper intended for publication. Papers showing only a marginal advance on the earlier publication will be rejected.

This reminder is considered desirable as there has recently been an increase in the submission of papers duplicating material already published and the Editors have not always recognized the duplication. It does not mark a change in editorial policy; essentially the same condition has appeared in earlier *Notes for Authors* [see, for example, *Acta Cryst.* (1965), **18**, 134 (first paragraph)].