

2-(1*H*-Benzimidazol-2-yl)-6-ethoxyphenol

Chin Sing Yeap,^a Hadi Kargar,^b‡ Reza Kia,^a Arezoo Jamshidvand^b and Hoong-Kun Fun^{a*}

^aX-ray Crystallography Unit, School of Physics, Universiti Sains Malaysia, 11800 USM, Penang, Malaysia, and ^bDepartment of Chemistry, School of Science, Payame Noor University (PNU), Ardakan, Yazd, Iran
Correspondence e-mail: hkfun@usm.my


Received 2 March 2009; accepted 5 March 2009

Key indicators: single-crystal X-ray study; $T = 100$ K; mean $\sigma(C-C) = 0.004$ Å; disorder in main residue; R factor = 0.067; wR factor = 0.151; data-to-parameter ratio = 13.9.

The title Schiff base compound, $C_{15}H_{14}N_2O_2$, consists of two crystallographically independent molecules, *A* and *B*. Molecule *A* is almost planar, whereas molecule *B* is slightly twisted, the dihedral angles between the benzimidazole group and the benzene rings being 2.65 (12) and 13.17 (15)°, respectively. The methyl group of molecule *B* is disordered over two positions, with a refined site-occupancy ratio of 0.581 (7):0.419 (7). In each molecule, intramolecular O—H···N hydrogen bonds generate *S*(6) ring motifs. In the crystal structure, both types of molecules are linked via intermolecular bifurcated N—H···O hydrogen bonds into one-dimensional extended chains along [010] and form $R_1^2(5)$ ring motifs. The crystal structure is further stabilized by intermolecular C—H···π and π—π interactions [centroid–centroid distances = 3.4758 (16)–3.596 (2) Å].

Related literature

For hydrogen-bond motifs, see: Bernstein *et al.* (1995). For benzimidazole chemistry, reaction mechanisms and bioactivity, see, for example: Latif *et al.* (1983); Craig *et al.* (1999); Gudmundsson *et al.* (2000); Trivedi *et al.* (2006); Kim *et al.* (1996); Ramlal *et al.* (2006). For the stability of the temperature controller used in the data collection, see: Cosier & Glazer (1986).



Experimental

Crystal data

$C_{15}H_{14}N_2O_2$
 $M_r = 254.28$
Monoclinic, $C2/c$
 $a = 22.5305$ (4) Å
 $b = 12.0113$ (2) Å
 $c = 21.4241$ (3) Å
 $\beta = 120.449$ (1)°

$V = 4998.17$ (14) Å³
 $Z = 16$
Mo $K\alpha$ radiation
 $\mu = 0.09$ mm⁻¹
 $T = 100$ K
 $0.38 \times 0.23 \times 0.18$ mm

Data collection

Bruker SMART APEXII CCD area-detector diffractometer
Absorption correction: multi-scan (*SADABS*; Bruker, 2005)
 $T_{min} = 0.966$, $T_{max} = 0.984$

49947 measured reflections
5171 independent reflections
4238 reflections with $I > 2\sigma(I)$
 $R_{int} = 0.043$

Refinement

$R[F^2 > 2\sigma(F^2)] = 0.067$
 $wR(F^2) = 0.151$
 $S = 1.19$
5171 reflections
372 parameters
1 restraint

H atoms treated by a mixture of independent and constrained refinement
 $\Delta\rho_{\text{max}} = 0.57$ e Å⁻³
 $\Delta\rho_{\text{min}} = -0.48$ e Å⁻³

Table 1
Hydrogen-bond geometry (Å, °).

D—H···A	D—H	H···A	D···A	D—H···A
O1A—H1OA···N1A	0.91 (4)	1.67 (4)	2.557 (4)	164 (4)
N2A—H1NA···O1B	0.81 (4)	2.14 (4)	2.865 (3)	149 (3)
N2A—H1NA···O2B	0.81 (4)	2.57 (4)	3.199 (3)	136 (3)
O1B—H1OB···N1B	0.97 (4)	1.67 (4)	2.567 (3)	151 (3)
N2B—H1NB···O1A ⁱ	0.94 (4)	1.95 (4)	2.877 (3)	167 (4)
N2B—H1NB···O2A ⁱ	0.94 (4)	2.55 (4)	3.136 (3)	121 (3)
C4A—H4AA···Cg1 ⁱⁱ	0.93	2.80	3.590 (4)	143
C14B—H14C···Cg2 ⁱⁱⁱ	0.97	2.84	3.721 (5)	152
C15B—H15D···Cg3 ^{iv}	0.96	2.76	3.715 (8)	176

Symmetry codes: (i) $-x, y+1, -z+\frac{1}{2}$; (ii) $x, -y-1, z-\frac{1}{2}$; (iii) $-x, y, -z+\frac{1}{2}$; (iv) $-x+\frac{1}{2}, -y+\frac{1}{2}, -z+1$. Cg1, Cg2 and Cg3 are the centroids of the C8B—C13B, C1B—C6B and N1A—C1A—C6A—N2A—C7A rings, respectively.

Data collection: *APEX2* (Bruker, 2005); cell refinement: *SAINT* (Bruker, 2005); data reduction: *SAINT*; program(s) used to solve structure: *SHELXTL* (Sheldrick, 2008); program(s) used to refine structure: *SHELXTL*; molecular graphics: *SHELXTL*; software used to prepare material for publication: *SHELXTL* and *PLATON* (Spek, 2009).

HKF and RK thank the Malaysian Government and Universiti Sains Malaysia for the Science Fund grant No. 305/PFIZIK/613312. RK thanks Universiti Sains Malaysia for a post-doctoral research fellowship. YCS thanks Universiti

‡ Additional correspondence author: e-mail: hkargar@pnu.ac.ir.

Sains Malaysia for a studentship award. HK and AJ thank PNU for financial support. HKF also thanks Universiti Sains Malaysia for the Research University Golden Goose grant No. 1001/PFIZIK/811012.

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: LH2781).

References

- Bernstein, J., Davis, R. E., Shimoni, L. & Chang, N.-L. (1995). *Angew. Chem. Int. Ed. Engl.* **34**, 1555–1573.
- Bruker (2005). *APEX2, SAINT and SADABS*. Bruker AXS Inc., Madison, Wisconsin, USA.
- Cosier, J. & Glazer, A. M. (1986). *J. Appl. Cryst.* **19**, 105–107.
- Craig, W. A., LeSueur, B. W. & Skibo, E. B. (1999). *J. Med. Chem.* **42**, 3324–3333.
- Gudmundsson, K. S., Tidwell, J., Lippa, N., Koszalka, G. W., van Draanen, N., Ptak, R. G., Drach, J. C. & Townsend, L. B. (2000). *J. Med. Chem.* **43**, 2464–2472.
- Kim, J. S., Gatto, B., Yu, C., Liu, A., Liu, L. F. & LaVoie, E. J. (1996). *J. Med. Chem.* **39**, 992–998.
- Latif, N., Mishriky, N. & Assad, F. M. (1983). *Recl Trav. Chim. Pays-Bas*, **102**, 73–77.
- Ramla, M. M., Omer, M. A., El-Khamry, A. M. & El-Diwani, H. I. (2006). *Bioorg. Med. Chem.* **14**, 7324–7332.
- Sheldrick, G. M. (2008). *Acta Cryst. A* **64**, 112–122.
- Spek, A. L. (2009). *Acta Cryst. D* **65**, 148–155.
- Trivedi, R., De, S. K. & Gibbs, R. A. (2006). *J. Mol. Catal. A Chem.* **245**, 8–11.

supplementary materials

Acta Cryst. (2009). E65, o745-o746 [doi:10.1107/S1600536809008071]

2-(1H-Benzimidazol-2-yl)-6-ethoxyphenol

C. S. Yeap, H. Kargar, R. Kia, A. Jamshidvand and H.-K. Fun

Comment

Benzimidazoles are used widely in biological applications and as pharmaceutical agents (Craigo *et al.*, 1999; Gudmundsson *et al.*, 2000; Trivedi *et al.*, 2006). They are also used as topoisomerase I inhibitors (Kim *et al.*, 1996) and for antitumor activity (Ramla *et al.*, 2006). Due to these important applications, many synthetic routes towards benzimidazoles have been developed. They can, for example, be synthesized by the reaction of phenolic aldehydes with *o*-phenylenediamine (Latif *et al.*, 1983). Based on this route the title compound was synthesized and its crystal structure is reported here.

The asymmetric unit of the title compound, Fig. 1, consists of two crystallographically independent molecules, *A* and *B* with a slightly different conformations due to a disordered group. Intramolecular O—H···N hydrogen bonds generate S(6) ring motifs (Bernstein *et al.*, 1995). The two molecules *A* and *B* are linked together by a bifurcated hydrogen bond involving the two oxygen atoms of the hydroxy and ethoxy groups with a $R_1^{2}(5)$ ring motif. The molecule *A* is almost planar whereas the molecule *B* is slightly twisted with the dihedral angles between the benzimidazole and the phenyl rings being 2.65 (12) and 13.17 (15) °, respectively. The methyl group of molecule *B* is disordered over two positions with a refined site-occupancy ratio of 0.581 (7):0.419 (7). The crystal structure is further stabilized by intermolecular C—H··· π [Cg_1 , Cg_2 and Cg_3 are the centroids of the C8B—C13B, C1B—C6B and N1A/C1A/C6A/N2A/C7A rings] (Table 1) and π — π interactions [$Cg_1\cdots Cg_4^{iii} = 3.596$ (2) and $Cg_3\cdots Cg_5^{iii} = 3.4758$ (16) Å; (iii) -x, y, 1/2 - z; Cg_4 and Cg_5 are the centroids of the N1B/C1B/C6B/N2B/C7B and C8A—C13A rings]. In the crystal structure, molecules are linked together into 1-D extended chains along the [0 1 0] direction (Fig. 2).

Experimental

An ethanolic solution (50 ml) of 3-ethoxy-salicylaldehyde (2 mmol, 332 mg) was added to 1,2-phenylenediamine (1 mmol, 217 mg). The mixture was refluxed for 2 h, and cooled to room temperature. The resulting colourless powder was filtered, washed with cooled ethanol and dried in *vacuo*. Single crystals suitable for X-ray diffraction were obtained from an methanol solution at room temperature.

Refinement

O1A, O1B and N-bound hydrogen atoms were located from the difference Fourier map and refined freely. The rest of the hydrogen atoms were positioned geometrically with a riding model approximation with C—H = 0.93–0.97 Å and $U_{iso}(H) = 1.2$ or 1.5 (C & O). A rotating group model was used for methyl group.

supplementary materials

Figures




Fig. 1. The molecular structure of the title compound with atom labels and 50% probability ellipsoids for non-H atoms. Intra- and intermolecular hydrogen bonds are shown as dashed lines. The open bond indicates the minor component of disorder.




Fig. 2. Part of the crystal structure of the title compound with hydrogen bonds shown as dashed lines. The disorder is not shown and only H atoms involved in hydrogen bonds are drawn.

2-(1*H*-Benzoimidazol-2-yl)-6-ethoxyphenol

Crystal data

C ₁₅ H ₁₄ N ₂ O ₂	$F_{000} = 2144$
$M_r = 254.28$	$D_x = 1.352 \text{ Mg m}^{-3}$
Monoclinic, C2/c	Mo $K\alpha$ radiation
Hall symbol: -C 2yc	$\lambda = 0.71073 \text{ \AA}$
$a = 22.5305 (4) \text{ \AA}$	Cell parameters from 9961 reflections
$b = 12.0113 (2) \text{ \AA}$	$\theta = 2.5\text{--}32.2^\circ$
$c = 21.4241 (3) \text{ \AA}$	$\mu = 0.09 \text{ mm}^{-1}$
$\beta = 120.449 (1)^\circ$	$T = 100 \text{ K}$
$V = 4998.17 (14) \text{ \AA}^3$	Block, yellow
$Z = 16$	$0.38 \times 0.23 \times 0.18 \text{ mm}$

Data collection

Bruker SMART APEXII CCD area-detector diffractometer	5171 independent reflections
Radiation source: fine-focus sealed tube	4238 reflections with $I > 2\sigma(I)$
Monochromator: graphite	$R_{\text{int}} = 0.043$
$T = 100 \text{ K}$	$\theta_{\text{max}} = 26.5^\circ$
φ and ω scans	$\theta_{\text{min}} = 2.0^\circ$
Absorption correction: multi-scan (<i>SADABS</i> ; Bruker, 2005)	$h = -28 \rightarrow 28$
$T_{\text{min}} = 0.966, T_{\text{max}} = 0.984$	$k = -14 \rightarrow 15$
49947 measured reflections	$l = -26 \rightarrow 26$

Refinement

Refinement on F^2	Secondary atom site location: difference Fourier map
Least-squares matrix: full	Hydrogen site location: inferred from neighbouring sites
$R[F^2 > 2\sigma(F^2)] = 0.067$	H atoms treated by a mixture of independent and constrained refinement
$wR(F^2) = 0.151$	$w = 1/[\sigma^2(F_o^2) + (0.022P)^2 + 16.3221P]$ where $P = (F_o^2 + 2F_c^2)/3$
$S = 1.19$	$(\Delta/\sigma)_{\max} < 0.001$
5171 reflections	$\Delta\rho_{\max} = 0.57 \text{ e \AA}^{-3}$
372 parameters	$\Delta\rho_{\min} = -0.48 \text{ e \AA}^{-3}$
1 restraint	Extinction correction: none
Primary atom site location: structure-invariant direct methods	

Special details

Experimental. The crystal was placed in the cold stream of an Oxford Cyrosystems Cobra open-flow nitrogen cryostat (Cosier & Glazer, 1986) operating at 100.0 (1) K.

Geometry. All esds (except the esd in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell esds are taken into account individually in the estimation of esds in distances, angles and torsion angles; correlations between esds in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell esds is used for estimating esds involving l.s. planes.

Refinement. Refinement of F^2 against ALL reflections. The weighted R-factor wR and goodness of fit S are based on F^2 , conventional R-factors R are based on F, with F set to zero for negative F^2 . The threshold expression of $F^2 > 2\text{sigma}(F^2)$ is used only for calculating R-factors(gt) etc. and is not relevant to the choice of reflections for refinement. R-factors based on F^2 are statistically about twice as large as those based on F, and R- factors based on ALL data will be even larger.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2)

	x	y	z	$U_{\text{iso}}^*/U_{\text{eq}}$	Occ. (<1)
O1A	0.04313 (11)	-0.05359 (15)	0.34802 (11)	0.0343 (5)	
O2A	-0.04669 (10)	-0.05371 (16)	0.38878 (11)	0.0352 (5)	
N1A	0.12309 (11)	0.04703 (18)	0.31444 (12)	0.0278 (5)	
N2A	0.12918 (13)	0.2321 (2)	0.31223 (14)	0.0328 (5)	
C1A	0.16902 (14)	0.0757 (2)	0.29195 (14)	0.0280 (6)	
C2A	0.20683 (15)	0.0094 (2)	0.27078 (16)	0.0345 (6)	
H2AA	0.2047	-0.0678	0.2714	0.041*	
C3A	0.24743 (16)	0.0632 (3)	0.24891 (17)	0.0389 (7)	
H3AA	0.2731	0.0209	0.2346	0.047*	
C4A	0.25106 (16)	0.1776 (3)	0.24763 (18)	0.0413 (7)	
H4AA	0.2792	0.2104	0.2326	0.050*	
C5A	0.21403 (16)	0.2450 (3)	0.26805 (17)	0.0408 (7)	
H5AA	0.2165	0.3222	0.2670	0.049*	
C6A	0.17291 (14)	0.1923 (2)	0.29023 (15)	0.0318 (6)	

supplementary materials

C7A	0.09976 (13)	0.1427 (2)	0.32507 (13)	0.0267 (5)	
C8A	0.04901 (13)	0.1485 (2)	0.34835 (14)	0.0257 (5)	
C9A	0.02514 (14)	0.2496 (2)	0.36000 (15)	0.0319 (6)	
H9AA	0.0424	0.3165	0.3540	0.038*	
C10A	-0.02370 (15)	0.2501 (2)	0.38028 (16)	0.0362 (7)	
H10A	-0.0398	0.3175	0.3873	0.043*	
C11A	-0.04945 (14)	0.1499 (2)	0.39045 (15)	0.0328 (6)	
H11A	-0.0824	0.1511	0.4043	0.039*	
C12A	-0.02616 (14)	0.0499 (2)	0.38002 (14)	0.0290 (6)	
C13A	0.02312 (13)	0.0480 (2)	0.35843 (13)	0.0255 (5)	
C14A	-0.09118 (15)	-0.0595 (3)	0.41821 (17)	0.0405 (7)	
H14A	-0.1346	-0.0230	0.3863	0.049*	
H14B	-0.0700	-0.0237	0.4652	0.049*	
C15A	-0.10244 (18)	-0.1825 (3)	0.4250 (2)	0.0546 (9)	
H15A	-0.1308	-0.1911	0.4463	0.082*	
H15B	-0.0588	-0.2181	0.4553	0.082*	
H15C	-0.1248	-0.2163	0.3779	0.082*	
O1B	0.08605 (12)	0.45323 (16)	0.25795 (12)	0.0409 (5)	
O2B	0.17852 (13)	0.46703 (18)	0.39287 (12)	0.0530 (6)	
N1B	0.00726 (12)	0.54159 (19)	0.13347 (13)	0.0332 (5)	
N2B	-0.01822 (12)	0.72236 (19)	0.12353 (13)	0.0303 (5)	
C1B	-0.04540 (15)	0.5626 (2)	0.06352 (16)	0.0335 (6)	
C2B	-0.08028 (17)	0.4918 (3)	0.00407 (17)	0.0438 (8)	
H2BA	-0.0692	0.4166	0.0075	0.053*	
C3B	-0.13164 (17)	0.5368 (3)	-0.06005 (17)	0.0461 (8)	
H3BA	-0.1548	0.4912	-0.1005	0.055*	
C4B	-0.14955 (16)	0.6492 (3)	-0.06553 (17)	0.0448 (8)	
H4BA	-0.1852	0.6762	-0.1092	0.054*	
C5B	-0.11554 (16)	0.7216 (3)	-0.00752 (17)	0.0393 (7)	
H5BA	-0.1274	0.7965	-0.0112	0.047*	
C6B	-0.06268 (14)	0.6763 (2)	0.05654 (15)	0.0313 (6)	
C7B	0.02231 (14)	0.6394 (2)	0.16742 (15)	0.0295 (6)	
C8B	0.07626 (14)	0.6529 (2)	0.24254 (15)	0.0286 (6)	
C9B	0.10079 (14)	0.7581 (2)	0.27454 (16)	0.0303 (6)	
H9BA	0.0819	0.8224	0.2475	0.036*	
C10B	0.15256 (15)	0.7658 (2)	0.34562 (16)	0.0332 (6)	
H10B	0.1688	0.8356	0.3660	0.040*	
C11B	0.18127 (16)	0.6703 (2)	0.38783 (16)	0.0357 (7)	
H11B	0.2165	0.6764	0.4358	0.043*	
C12B	0.15684 (16)	0.5670 (2)	0.35757 (16)	0.0368 (7)	
C13B	0.10542 (15)	0.5578 (2)	0.28474 (16)	0.0319 (6)	
C14B	0.2276 (2)	0.4683 (3)	0.46948 (18)	0.0576 (10)	
H14C	0.2090	0.5088	0.4949	0.069*	0.581 (7)
H14D	0.2698	0.5046	0.4788	0.069*	0.581 (7)
H14E	0.2218	0.4028	0.4915	0.069*	0.419 (7)
H14F	0.2208	0.5323	0.4920	0.069*	0.419 (7)
C15B	0.2415 (4)	0.3527 (6)	0.4943 (4)	0.070 (2)	0.581 (7)
H15D	0.2734	0.3510	0.5456	0.104*	0.581 (7)
H15E	0.2609	0.3139	0.4697	0.104*	0.581 (7)

H15F	0.1993	0.3172	0.4841	0.104*	0.581 (7)
C15C	0.2967 (3)	0.4728 (8)	0.4792 (5)	0.063 (3)	0.419 (7)
H15G	0.3303	0.4739	0.5300	0.095*	0.419 (7)
H15H	0.3012	0.5390	0.4568	0.095*	0.419 (7)
H15I	0.3039	0.4085	0.4573	0.095*	0.419 (7)
H1OA	0.0731 (18)	-0.030 (3)	0.3339 (18)	0.052 (10)*	
H1NA	0.1191 (17)	0.297 (3)	0.3128 (18)	0.048 (10)*	
H1OB	0.0555 (19)	0.462 (3)	0.206 (2)	0.061 (11)*	
H1NB	-0.0186 (17)	0.797 (3)	0.1365 (18)	0.052 (10)*	

Atomic displacement parameters (\AA^2)

	U^{11}	U^{22}	U^{33}	U^{12}	U^{13}	U^{23}
O1A	0.0431 (12)	0.0193 (9)	0.0518 (13)	-0.0025 (8)	0.0323 (11)	-0.0009 (8)
O2A	0.0383 (11)	0.0298 (10)	0.0448 (12)	-0.0082 (9)	0.0264 (10)	-0.0019 (9)
N1A	0.0325 (12)	0.0206 (11)	0.0335 (12)	-0.0002 (9)	0.0191 (10)	-0.0002 (9)
N2A	0.0359 (13)	0.0209 (12)	0.0431 (14)	0.0007 (10)	0.0210 (12)	0.0060 (10)
C1A	0.0303 (14)	0.0240 (13)	0.0278 (13)	-0.0017 (11)	0.0133 (11)	0.0029 (10)
C2A	0.0376 (16)	0.0281 (14)	0.0389 (16)	0.0001 (12)	0.0202 (13)	0.0017 (12)
C3A	0.0388 (16)	0.0428 (17)	0.0399 (16)	0.0019 (14)	0.0236 (14)	0.0032 (13)
C4A	0.0374 (16)	0.0426 (18)	0.0490 (18)	-0.0001 (14)	0.0256 (14)	0.0123 (14)
C5A	0.0425 (17)	0.0315 (16)	0.0520 (19)	-0.0031 (13)	0.0265 (15)	0.0102 (14)
C6A	0.0302 (14)	0.0306 (15)	0.0331 (15)	0.0008 (11)	0.0149 (12)	0.0082 (12)
C7A	0.0263 (13)	0.0243 (13)	0.0247 (13)	-0.0020 (10)	0.0092 (11)	0.0019 (10)
C8A	0.0277 (13)	0.0202 (12)	0.0259 (13)	-0.0006 (10)	0.0111 (11)	0.0019 (10)
C9A	0.0359 (15)	0.0231 (13)	0.0357 (15)	0.0007 (11)	0.0174 (13)	0.0030 (11)
C10A	0.0429 (17)	0.0242 (14)	0.0427 (17)	0.0071 (12)	0.0226 (14)	-0.0007 (12)
C11A	0.0321 (14)	0.0343 (15)	0.0339 (15)	0.0000 (12)	0.0182 (13)	-0.0027 (12)
C12A	0.0287 (14)	0.0277 (14)	0.0273 (14)	-0.0035 (11)	0.0117 (11)	0.0006 (11)
C13A	0.0288 (13)	0.0202 (12)	0.0246 (13)	-0.0017 (10)	0.0115 (11)	0.0000 (10)
C14A	0.0353 (16)	0.0524 (19)	0.0362 (16)	-0.0049 (14)	0.0199 (14)	0.0054 (14)
C15A	0.049 (2)	0.059 (2)	0.059 (2)	-0.0151 (17)	0.0297 (18)	0.0116 (18)
O1B	0.0528 (13)	0.0209 (10)	0.0370 (12)	0.0008 (9)	0.0139 (10)	-0.0005 (8)
O2B	0.0737 (17)	0.0314 (12)	0.0355 (12)	0.0072 (11)	0.0143 (12)	0.0051 (9)
N1B	0.0361 (13)	0.0250 (12)	0.0356 (13)	0.0000 (10)	0.0159 (11)	-0.0009 (10)
N2B	0.0370 (13)	0.0203 (11)	0.0390 (13)	0.0024 (10)	0.0233 (11)	0.0035 (10)
C1B	0.0365 (15)	0.0277 (14)	0.0379 (16)	0.0032 (12)	0.0200 (13)	0.0030 (12)
C2B	0.0485 (19)	0.0346 (17)	0.0410 (17)	-0.0007 (14)	0.0172 (15)	-0.0021 (13)
C3B	0.0463 (18)	0.0474 (19)	0.0372 (17)	-0.0037 (15)	0.0158 (15)	-0.0010 (14)
C4B	0.0397 (17)	0.055 (2)	0.0370 (17)	0.0017 (15)	0.0172 (14)	0.0107 (15)
C5B	0.0436 (17)	0.0351 (16)	0.0449 (18)	0.0063 (13)	0.0265 (15)	0.0145 (13)
C6B	0.0328 (14)	0.0309 (14)	0.0370 (15)	-0.0007 (12)	0.0228 (13)	0.0043 (12)
C7B	0.0326 (14)	0.0255 (14)	0.0380 (15)	0.0012 (11)	0.0234 (13)	0.0011 (11)
C8B	0.0314 (14)	0.0243 (13)	0.0384 (15)	0.0001 (11)	0.0237 (12)	-0.0023 (11)
C9B	0.0370 (15)	0.0202 (13)	0.0438 (16)	0.0021 (11)	0.0278 (14)	0.0009 (11)
C10B	0.0397 (16)	0.0238 (14)	0.0452 (17)	-0.0052 (12)	0.0282 (14)	-0.0108 (12)
C11B	0.0402 (16)	0.0329 (15)	0.0348 (15)	0.0002 (12)	0.0196 (13)	-0.0061 (12)
C12B	0.0462 (17)	0.0288 (15)	0.0373 (16)	0.0029 (13)	0.0225 (14)	-0.0005 (12)

supplementary materials

C13B	0.0383 (15)	0.0231 (13)	0.0390 (16)	-0.0022 (11)	0.0230 (13)	-0.0051 (11)
C14B	0.071 (3)	0.046 (2)	0.0390 (19)	0.0051 (18)	0.0161 (18)	0.0034 (16)
C15B	0.067 (5)	0.070 (5)	0.044 (4)	0.014 (4)	0.008 (3)	0.013 (3)
C15C	0.062 (6)	0.049 (5)	0.068 (6)	0.014 (4)	0.024 (5)	0.009 (4)

Geometric parameters (\AA , $^\circ$)

O1A—C13A	1.358 (3)	N1B—C7B	1.332 (3)
O1A—H1OA	0.91 (4)	N1B—C1B	1.384 (4)
O2A—C12A	1.374 (3)	N2B—C7B	1.356 (3)
O2A—C14A	1.431 (3)	N2B—C6B	1.383 (4)
N1A—C7A	1.330 (3)	N2B—H1NB	0.94 (4)
N1A—C1A	1.388 (3)	C1B—C2B	1.396 (4)
N2A—C7A	1.361 (3)	C1B—C6B	1.407 (4)
N2A—C6A	1.376 (4)	C2B—C3B	1.381 (4)
N2A—H1NA	0.82 (4)	C2B—H2BA	0.9300
C1A—C2A	1.399 (4)	C3B—C4B	1.397 (5)
C1A—C6A	1.404 (4)	C3B—H3BA	0.9300
C2A—C3A	1.381 (4)	C4B—C5B	1.387 (5)
C2A—H2AA	0.9300	C4B—H4BA	0.9300
C3A—C4A	1.378 (4)	C5B—C6B	1.393 (4)
C3A—H3AA	0.9300	C5B—H5BA	0.9300
C4A—C5A	1.383 (4)	C7B—C8B	1.453 (4)
C4A—H4AA	0.9300	C8B—C13B	1.396 (4)
C5A—C6A	1.390 (4)	C8B—C9B	1.410 (4)
C5A—H5AA	0.9300	C9B—C10B	1.374 (4)
C7A—C8A	1.463 (4)	C9B—H9BA	0.9300
C8A—C9A	1.400 (4)	C10B—C11B	1.400 (4)
C8A—C13A	1.404 (3)	C10B—H10B	0.9300
C9A—C10A	1.373 (4)	C11B—C12B	1.378 (4)
C9A—H9AA	0.9300	C11B—H11B	0.9300
C10A—C11A	1.400 (4)	C12B—C13B	1.399 (4)
C10A—H10A	0.9300	C14B—C15C	1.4633 (10)
C11A—C12A	1.373 (4)	C14B—C15B	1.464 (7)
C11A—H11A	0.9300	C14B—H14C	0.9700
C12A—C13A	1.403 (4)	C14B—H14D	0.9700
C14A—C15A	1.519 (5)	C14B—H14E	0.9599
C14A—H14A	0.9700	C14B—H14F	0.9600
C14A—H14B	0.9700	C15B—H14E	0.7332
C15A—H15A	0.9600	C15B—H15D	0.9600
C15A—H15B	0.9600	C15B—H15E	0.9600
C15A—H15C	0.9600	C15B—H15F	0.9600
O1B—C13B	1.358 (3)	C15C—H15G	0.9600
O1B—H1OB	0.97 (4)	C15C—H15H	0.9600
O2B—C12B	1.370 (4)	C15C—H15I	0.9600
O2B—C14B	1.441 (4)		
C13A—O1A—H1OA	98 (2)	C3B—C2B—C1B	118.0 (3)
C12A—O2A—C14A	117.6 (2)	C3B—C2B—H2BA	121.0
C7A—N1A—C1A	105.9 (2)	C1B—C2B—H2BA	121.0

C7A—N2A—C6A	107.6 (2)	C2B—C3B—C4B	121.5 (3)
C7A—N2A—H1NA	126 (2)	C2B—C3B—H3BA	119.3
C6A—N2A—H1NA	126 (2)	C4B—C3B—H3BA	119.3
N1A—C1A—C2A	130.9 (2)	C5B—C4B—C3B	121.7 (3)
N1A—C1A—C6A	108.9 (2)	C5B—C4B—H4BA	119.1
C2A—C1A—C6A	120.2 (3)	C3B—C4B—H4BA	119.1
C3A—C2A—C1A	117.5 (3)	C4B—C5B—C6B	116.5 (3)
C3A—C2A—H2AA	121.3	C4B—C5B—H5BA	121.8
C1A—C2A—H2AA	121.3	C6B—C5B—H5BA	121.8
C4A—C3A—C2A	121.9 (3)	N2B—C6B—C5B	132.4 (3)
C4A—C3A—H3AA	119.0	N2B—C6B—C1B	105.2 (2)
C2A—C3A—H3AA	119.0	C5B—C6B—C1B	122.4 (3)
C3A—C4A—C5A	121.7 (3)	N1B—C7B—N2B	111.9 (2)
C3A—C4A—H4AA	119.1	N1B—C7B—C8B	122.8 (2)
C5A—C4A—H4AA	119.1	N2B—C7B—C8B	125.3 (2)
C4A—C5A—C6A	117.1 (3)	C13B—C8B—C9B	118.6 (3)
C4A—C5A—H5AA	121.5	C13B—C8B—C7B	118.8 (2)
C6A—C5A—H5AA	121.5	C9B—C8B—C7B	122.7 (2)
N2A—C6A—C5A	132.5 (3)	C10B—C9B—C8B	120.2 (3)
N2A—C6A—C1A	105.8 (2)	C10B—C9B—H9BA	119.9
C5A—C6A—C1A	121.6 (3)	C8B—C9B—H9BA	119.9
N1A—C7A—N2A	111.8 (2)	C9B—C10B—C11B	121.0 (3)
N1A—C7A—C8A	123.0 (2)	C9B—C10B—H10B	119.5
N2A—C7A—C8A	125.2 (2)	C11B—C10B—H10B	119.5
C9A—C8A—C13A	119.4 (2)	C12B—C11B—C10B	119.3 (3)
C9A—C8A—C7A	122.6 (2)	C12B—C11B—H11B	120.3
C13A—C8A—C7A	118.0 (2)	C10B—C11B—H11B	120.3
C10A—C9A—C8A	120.2 (3)	O2B—C12B—C11B	125.7 (3)
C10A—C9A—H9AA	119.9	O2B—C12B—C13B	114.1 (3)
C8A—C9A—H9AA	119.9	C11B—C12B—C13B	120.2 (3)
C9A—C10A—C11A	120.5 (3)	O1B—C13B—C8B	122.5 (3)
C9A—C10A—H10A	119.8	O1B—C13B—C12B	116.8 (3)
C11A—C10A—H10A	119.8	C8B—C13B—C12B	120.6 (3)
C12A—C11A—C10A	120.2 (3)	O2B—C14B—C15C	108.0 (5)
C12A—C11A—H11A	119.9	O2B—C14B—C15B	107.6 (4)
C10A—C11A—H11A	119.9	C15C—C14B—C15B	88.1 (5)
C11A—C12A—O2A	126.0 (2)	O2B—C14B—H14C	110.2
C11A—C12A—C13A	120.0 (2)	C15C—C14B—H14C	129.3
O2A—C12A—C13A	114.1 (2)	C15B—C14B—H14C	110.2
O1A—C13A—C12A	117.0 (2)	O2B—C14B—H14D	110.2
O1A—C13A—C8A	123.3 (2)	C15B—C14B—H14D	110.2
C12A—C13A—C8A	119.8 (2)	H14C—C14B—H14D	108.5
O2A—C14A—C15A	106.2 (3)	O2B—C14B—H14E	109.5
O2A—C14A—H14A	110.5	C15C—C14B—H14E	111.1
C15A—C14A—H14A	110.5	H14C—C14B—H14E	85.9
O2A—C14A—H14B	110.5	H14D—C14B—H14E	129.1
C15A—C14A—H14B	110.5	O2B—C14B—H14F	110.8
H14A—C14A—H14B	108.7	C15C—C14B—H14F	109.1
C14A—C15A—H15A	109.5	C15B—C14B—H14F	129.5

supplementary materials

C14A—C15A—H15B	109.5	H14D—C14B—H14F	85.8
H15A—C15A—H15B	109.5	H14E—C14B—H14F	108.3
C14A—C15A—H15C	109.5	C14B—C15B—H15D	109.5
H15A—C15A—H15C	109.5	H14E—C15B—H15D	100.5
H15B—C15A—H15C	109.5	C14B—C15B—H15E	109.5
C13B—O1B—H1OB	106 (2)	H14E—C15B—H15E	141.2
C12B—O2B—C14B	118.2 (3)	C14B—C15B—H15F	109.5
C7B—N1B—C1B	105.8 (2)	H14E—C15B—H15F	81.8
C7B—N2B—C6B	107.8 (2)	C14B—C15C—H15G	109.5
C7B—N2B—H1NB	127 (2)	C14B—C15C—H15H	109.5
C6B—N2B—H1NB	125 (2)	H15G—C15C—H15H	109.5
N1B—C1B—C2B	130.9 (3)	C14B—C15C—H15I	109.5
N1B—C1B—C6B	109.4 (3)	H15G—C15C—H15I	109.5
C2B—C1B—C6B	119.8 (3)	H15H—C15C—H15I	109.5
C7A—N1A—C1A—C2A	-177.4 (3)	C7B—N1B—C1B—C6B	-1.1 (3)
C7A—N1A—C1A—C6A	0.6 (3)	N1B—C1B—C2B—C3B	179.8 (3)
N1A—C1A—C2A—C3A	178.1 (3)	C6B—C1B—C2B—C3B	-0.6 (5)
C6A—C1A—C2A—C3A	0.3 (4)	C1B—C2B—C3B—C4B	-1.2 (5)
C1A—C2A—C3A—C4A	-0.1 (5)	C2B—C3B—C4B—C5B	1.7 (5)
C2A—C3A—C4A—C5A	-0.2 (5)	C3B—C4B—C5B—C6B	-0.1 (5)
C3A—C4A—C5A—C6A	0.2 (5)	C7B—N2B—C6B—C5B	178.4 (3)
C7A—N2A—C6A—C5A	177.6 (3)	C7B—N2B—C6B—C1B	-0.6 (3)
C7A—N2A—C6A—C1A	-1.1 (3)	C4B—C5B—C6B—N2B	179.3 (3)
C4A—C5A—C6A—N2A	-178.5 (3)	C4B—C5B—C6B—C1B	-1.8 (4)
C4A—C5A—C6A—C1A	0.0 (4)	N1B—C1B—C6B—N2B	1.1 (3)
N1A—C1A—C6A—N2A	0.3 (3)	C2B—C1B—C6B—N2B	-178.6 (3)
C2A—C1A—C6A—N2A	178.6 (2)	N1B—C1B—C6B—C5B	-178.1 (2)
N1A—C1A—C6A—C5A	-178.6 (3)	C2B—C1B—C6B—C5B	2.2 (4)
C2A—C1A—C6A—C5A	-0.3 (4)	C1B—N1B—C7B—N2B	0.7 (3)
C1A—N1A—C7A—N2A	-1.3 (3)	C1B—N1B—C7B—C8B	-179.1 (2)
C1A—N1A—C7A—C8A	179.1 (2)	C6B—N2B—C7B—N1B	0.0 (3)
C6A—N2A—C7A—N1A	1.5 (3)	C6B—N2B—C7B—C8B	179.7 (2)
C6A—N2A—C7A—C8A	-178.9 (2)	N1B—C7B—C8B—C13B	-11.6 (4)
N1A—C7A—C8A—C9A	179.5 (3)	N2B—C7B—C8B—C13B	168.7 (3)
N2A—C7A—C8A—C9A	0.0 (4)	N1B—C7B—C8B—C9B	168.0 (3)
N1A—C7A—C8A—C13A	-1.2 (4)	N2B—C7B—C8B—C9B	-11.8 (4)
N2A—C7A—C8A—C13A	179.3 (2)	C13B—C8B—C9B—C10B	0.4 (4)
C13A—C8A—C9A—C10A	-0.7 (4)	C7B—C8B—C9B—C10B	-179.2 (2)
C7A—C8A—C9A—C10A	178.5 (3)	C8B—C9B—C10B—C11B	-0.9 (4)
C8A—C9A—C10A—C11A	0.9 (4)	C9B—C10B—C11B—C12B	-0.4 (4)
C9A—C10A—C11A—C12A	-0.2 (4)	C14B—O2B—C12B—C11B	4.6 (5)
C10A—C11A—C12A—O2A	179.4 (3)	C14B—O2B—C12B—C13B	-175.3 (3)
C10A—C11A—C12A—C13A	-0.6 (4)	C10B—C11B—C12B—O2B	-177.9 (3)
C14A—O2A—C12A—C11A	-6.6 (4)	C10B—C11B—C12B—C13B	2.1 (4)
C14A—O2A—C12A—C13A	173.4 (2)	C9B—C8B—C13B—O1B	-178.5 (3)
C11A—C12A—C13A—O1A	-179.0 (2)	C7B—C8B—C13B—O1B	1.1 (4)
O2A—C12A—C13A—O1A	1.0 (3)	C9B—C8B—C13B—C12B	1.3 (4)
C11A—C12A—C13A—C8A	0.7 (4)	C7B—C8B—C13B—C12B	-179.1 (3)
O2A—C12A—C13A—C8A	-179.3 (2)	O2B—C12B—C13B—O1B	-2.8 (4)

C9A—C8A—C13A—O1A	179.7 (2)	C11B—C12B—C13B—O1B	177.3 (3)
C7A—C8A—C13A—O1A	0.4 (4)	O2B—C12B—C13B—C8B	177.4 (3)
C9A—C8A—C13A—C12A	0.0 (4)	C11B—C12B—C13B—C8B	-2.5 (4)
C7A—C8A—C13A—C12A	-179.4 (2)	C12B—O2B—C14B—C15C	-87.0 (5)
C12A—O2A—C14A—C15A	-177.4 (2)	C12B—O2B—C14B—C15B	179.2 (4)
C7B—N1B—C1B—C2B	178.6 (3)		

Hydrogen-bond geometry (Å, °)

<i>D</i> —H··· <i>A</i>	<i>D</i> —H	H··· <i>A</i>	<i>D</i> ··· <i>A</i>	<i>D</i> —H··· <i>A</i>
O1A—H1OA···N1A	0.91 (4)	1.67 (4)	2.557 (4)	164 (4)
N2A—H1NA···O1B	0.81 (4)	2.14 (4)	2.865 (3)	149 (3)
N2A—H1NA···O2B	0.81 (4)	2.57 (4)	3.199 (3)	136 (3)
O1B—H1OB···N1B	0.97 (4)	1.67 (4)	2.567 (3)	151 (3)
N2B—H1NB···O1A ⁱ	0.94 (4)	1.95 (4)	2.877 (3)	167 (4)
N2B—H1NB···O2A ⁱ	0.94 (4)	2.55 (4)	3.136 (3)	121 (3)
C4A—H4AA···Cg1 ⁱⁱ	0.93	2.80	3.590 (4)	143
C14B—H14C···Cg2 ⁱⁱⁱ	0.97	2.84	3.721 (5)	152
C15B—H15D···Cg3 ^{iv}	0.96	2.76	3.715 (8)	176

Symmetry codes: (i) $-x, y+1, -z+1/2$; (ii) $x, -y-1, z-1/2$; (iii) $-x, y, -z+1/2$; (iv) $-x+1/2, -y+1/2, -z+1$.

supplementary materials

Fig. 1




Fig. 2

