

# Bis[4-hydroxy-*N'*-(4-methoxy-2-oxido-benzylidene- $\kappa^2O,N'$ )benzohydrazidato- $\kappa^2O,N'$ ]cadmium(II) dimethyl sulfoxide disolvate

Nooraziah Mohd Lair, Hapipah Mohd Ali and Seik Weng Ng\*

Department of Chemistry, University of Malaya, 50603 Kuala Lumpur, Malaysia  
Correspondence e-mail: seikweng@um.edu.my


Received 12 April 2009; accepted 13 April 2009

Key indicators: single-crystal X-ray study;  $T = 118$  K; mean  $\sigma(\text{C}-\text{C}) = 0.009$  Å;  $R$  factor = 0.059;  $wR$  factor = 0.153; data-to-parameter ratio = 15.4.

The metal atom in the title compound,  $[\text{Cd}(\text{C}_{15}\text{H}_{13}\text{N}_2\text{O}_4)_2] \cdot 2\text{C}_2\text{H}_6\text{OS}$ , is twice  $O,N,O'$ -chelated by two symmetry-related Schiff base ligands to define a *trans*- $\text{N}_2\text{O}_4$  octahedral geometry. Each anion occupies meridional sites of the octahedron; the metal atom lies on a special position of site symmetry 2. The dimethyl sulfoxide molecule is a hydrogen-bond acceptor to the  $-\text{NH}-$  unit, and  $\text{O}-\text{H} \cdots \text{O}$  hydrogen bonds link molecules into a supramolecular chain.

## Related literature

For the monohydrated Schiff base ligand, see: Mohd Lair *et al.* (2009).



## Experimental

### Crystal data

$[\text{Cd}(\text{C}_{15}\text{H}_{13}\text{N}_2\text{O}_4)_2] \cdot 2\text{C}_2\text{H}_6\text{OS}$   
 $M_r = 839.20$   
Monoclinic,  $C2/c$   
 $a = 23.891$  (2) Å  
 $b = 10.439$  (1) Å  
 $c = 19.874$  (1) Å  
 $\beta = 132.137$  (4)°

$V = 3675.3$  (4) Å<sup>3</sup>  
 $Z = 4$   
Mo  $K\alpha$  radiation  
 $\mu = 0.77$  mm<sup>-1</sup>  
 $T = 118$  K  
 $0.12 \times 0.06 \times 0.03$  mm

### Data collection

Bruker SMART APEX  
diffractometer  
Absorption correction: multi-scan  
(*SADABS*; Sheldrick, 1996)  
 $T_{\text{min}} = 0.507$ ,  $T_{\text{max}} = 0.745$   
(expected range = 0.665–0.977)

10208 measured reflections  
3243 independent reflections  
2147 reflections with  $I > 2\sigma(I)$   
 $R_{\text{int}} = 0.103$

### Refinement

$R[F^2 > 2\sigma(F^2)] = 0.059$   
 $wR(F^2) = 0.153$   
 $S = 1.02$   
3243 reflections

211 parameters  
H-atom parameters constrained  
 $\Delta\rho_{\text{max}} = 1.31$  e Å<sup>-3</sup>  
 $\Delta\rho_{\text{min}} = -0.90$  e Å<sup>-3</sup>

**Table 1**

Hydrogen-bond geometry (Å, °).

$D-H \cdots A$	$D-H$	$H \cdots A$	$D \cdots A$	$D-H \cdots A$
$\text{O4}-\text{H4} \cdots \text{O1}^i$	0.84	1.79	2.603 (6)	163
$\text{N2}-\text{H2} \cdots \text{O5}$	0.88	1.93	2.766 (6)	159

Symmetry code: (i)  $x, -y + 1, z + \frac{1}{2}$ .

Data collection: *APEX2* (Bruker, 2008); cell refinement: *SAINT* (Bruker, 2008); data reduction: *SAINT*; program(s) used to solve structure: *SHELXS97* (Sheldrick, 2008); program(s) used to refine structure: *SHELXL97* (Sheldrick, 2008); molecular graphics: *X-SEED* (Barbour, 2001); software used to prepare material for publication: *pubCIF* (Westrip, 2009).

We thank the University of Malaya for supporting this study.

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: TK2421).

## References

- Barbour, L. J. (2001). *J. Supramol. Chem.* **1**, 189–191.  
Bruker (2008). *APEX2* and *SAINT*. Bruker AXS Inc., Madison, Wisconsin, USA.  
Mohd Lair, N., Mohd Ali, H. & Ng, S. W. (2009). *Acta Cryst.* **E65**, o189.  
Sheldrick, G. M. (1996). *SADABS*. University of Göttingen, Germany.  
Sheldrick, G. M. (2008). *Acta Cryst.* **A64**, 112–122.  
Westrip, S. P. (2009). *pubCIF*. In preparation.

**supplementary materials**

*Acta Cryst.* (2009). E65, m541 [ doi:10.1107/S1600536809013774 ]

**Bis[4-hydroxy-*N'*-(4-methoxy-2-oxidobenzylidene- $\kappa O^2$ )benzohydrazidato- $\kappa^2 O, N'$ ]cadmium(II) dimethyl sulfoxide disolvate**

**N. Mohd Lair, H. Mohd Ali and S. W. Ng**

**Comment**

(type here to add)

**Experimental**

4-Hydroxy-*N'*-(2-hydroxy-4-methoxybenzylidene)benzohydrazide monohydrate (0.30 g, 1 mmol) and cadmium diacetate (0.14 g, 0.5 mmol) were heated in ethanol (50 ml) for 4 h. The solvent was removed and the product was recrystallized from DMSO to give prismatic crystals.

**Refinement**

Owing to the small number of observed reflections, the aromatic rings were refined as rigid hexagons with sides of 1.39 Å in order to reduce the number of refined parameters. Hydrogen atoms were placed at calculated positions (C–H 0.95–0.98, N–H 0.88, O–H 0.84 Å) and were treated as riding on their parent carbon atoms, with  $U(H)$  set to 1.2–1.5 times  $U_{eq}(C, N, O)$ . The final difference Fourier map had a large peak/deep hole in the vicinity of the Cd atom.

**Figures**




Fig. 1. Thermal ellipsoid plot (Barbour, 2001) of  $Cd(C_{15}H_{13}N_2O_4)_2 \cdot 2DMSO$  at the 70% probability level. Hydrogen atoms are drawn as spheres of arbitrary radius.

**Bis[4-hydroxy-*N'*-(4-methoxy-2-oxidobenzylidene- $\kappa O^2$ )benzohydrazidato- $\kappa^2 O, N'$ ]cadmium(II) dimethyl sulfoxide disolvate**

*Crystal data*

$[Cd(C_{15}H_{13}N_2O_4)_2] \cdot 2C_2H_6OS$

$M_r = 839.20$

Monoclinic,  $C2/c$

$F_{000} = 1720$

$D_x = 1.517 \text{ Mg m}^{-3}$

Mo  $K\alpha$  radiation

$\lambda = 0.71073 \text{ \AA}$

# supplementary materials

Hall symbol: -C 2yc  
 $a = 23.891$  (2) Å  
 $b = 10.439$  (1) Å  
 $c = 19.874$  (1) Å  
 $\beta = 132.137$  (4)°  
 $V = 3675.3$  (4) Å<sup>3</sup>  
 $Z = 4$

Cell parameters from 638 reflections  
 $\theta = 2.2$ – $18.8^\circ$   
 $\mu = 0.77$  mm<sup>-1</sup>  
 $T = 118$  K  
Prism, yellow  
 $0.12 \times 0.06 \times 0.03$  mm

## Data collection

Bruker SMART APEX  
diffractometer  
Radiation source: fine-focus sealed tube  
Monochromator: graphite  
 $T = 118$  K  
 $\omega$  scans  
Absorption correction: Multi-scan  
(SADABS; Sheldrick, 1996)  
 $T_{\min} = 0.507$ ,  $T_{\max} = 0.745$   
10208 measured reflections

3243 independent reflections  
2147 reflections with  $I > 2\sigma(I)$   
 $R_{\text{int}} = 0.103$   
 $\theta_{\text{max}} = 25.0^\circ$   
 $\theta_{\text{min}} = 2.1^\circ$   
 $h = -28 \rightarrow 28$   
 $k = -12 \rightarrow 12$   
 $l = -23 \rightarrow 23$

## Refinement

Refinement on  $F^2$   
Least-squares matrix: full  
 $R[F^2 > 2\sigma(F^2)] = 0.059$   
 $wR(F^2) = 0.153$   
 $S = 1.02$   
3243 reflections  
211 parameters  
Primary atom site location: structure-invariant direct  
methods

Secondary atom site location: difference Fourier map  
Hydrogen site location: inferred from neighbouring  
sites  
H-atom parameters constrained  
 $w = 1/[\sigma^2(F_o^2) + (0.0692P)^2 + 0.0136P]$   
where  $P = (F_o^2 + 2F_c^2)/3$   
 $(\Delta/\sigma)_{\text{max}} = 0.001$   
 $\Delta\rho_{\text{max}} = 1.31$  e Å<sup>-3</sup>  
 $\Delta\rho_{\text{min}} = -0.90$  e Å<sup>-3</sup>  
Extinction correction: none

## Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (Å<sup>2</sup>)

	<i>x</i>	<i>y</i>	<i>z</i>	$U_{\text{iso}}^*/U_{\text{eq}}$
Cd1	0.5000	0.32500 (7)	0.7500	0.0253 (2)
S1	0.18289 (10)	0.48574 (18)	0.67220 (12)	0.0335 (5)
O1	0.4272 (2)	0.1893 (4)	0.6323 (3)	0.0276 (10)
O2	0.2426 (3)	-0.1133 (5)	0.4273 (3)	0.0373 (12)
O3	0.5137 (2)	0.4972 (4)	0.8391 (3)	0.0264 (10)
O4	0.4911 (2)	0.8669 (4)	1.0697 (3)	0.0304 (11)
H4	0.4624	0.8507	1.0791	0.046*
N1	0.3944 (3)	0.3437 (5)	0.7273 (3)	0.0227 (12)
N2	0.3971 (3)	0.4373 (5)	0.7788 (4)	0.0262 (13)
H2	0.3589	0.4493	0.7755	0.031*

O5	0.2603 (2)	0.4283 (5)	0.7353 (4)	0.0432 (13)
C1	0.35890 (17)	0.1366 (4)	0.5922 (3)	0.0261 (16)
C2	0.3336 (2)	0.0367 (4)	0.5313 (3)	0.0291 (16)
H2A	0.3643	0.0060	0.5204	0.035*
C3	0.2633 (2)	-0.0181 (4)	0.4865 (3)	0.0295 (16)
C4	0.21840 (18)	0.0268 (4)	0.5025 (3)	0.0339 (17)
H4A	0.1704	-0.0107	0.4719	0.041*
C5	0.2437 (2)	0.1267 (4)	0.5634 (3)	0.0326 (17)
H5	0.2130	0.1574	0.5743	0.039*
C6	0.3140 (2)	0.1815 (4)	0.6082 (3)	0.0286 (15)
C7	0.1732 (4)	-0.1797 (8)	0.3856 (5)	0.0438 (19)
H7A	0.1662	-0.2488	0.3471	0.066*
H7B	0.1309	-0.1196	0.3484	0.066*
H7C	0.1754	-0.2159	0.4328	0.066*
C8	0.3314 (4)	0.2851 (6)	0.6694 (5)	0.0269 (16)
H8	0.2915	0.3119	0.6658	0.032*
C9	0.4604 (4)	0.5100 (6)	0.8344 (4)	0.0269 (15)
C10	0.4616 (2)	0.6071 (4)	0.8911 (2)	0.0236 (15)
C11	0.5075 (2)	0.7141 (4)	0.9198 (3)	0.0289 (16)
H11	0.5330	0.7276	0.8990	0.035*
C12	0.5159 (2)	0.8012 (3)	0.9790 (3)	0.0314 (17)
H12	0.5472	0.8743	0.9986	0.038*
C13	0.4785 (2)	0.7813 (4)	1.0094 (3)	0.0282 (16)
C14	0.4326 (2)	0.6744 (4)	0.9807 (3)	0.0241 (14)
H14	0.4071	0.6609	1.0015	0.029*
C15	0.4242 (2)	0.5873 (3)	0.9215 (3)	0.0244 (15)
H15	0.3929	0.5142	0.9019	0.029*
C16	0.1442 (4)	0.4487 (8)	0.7214 (5)	0.0372 (18)
H16A	0.1335	0.3567	0.7154	0.056*
H16B	0.0974	0.4970	0.6902	0.056*
H16C	0.1805	0.4720	0.7858	0.056*
C17	0.1980 (4)	0.6515 (7)	0.6951 (5)	0.0424 (19)
H17A	0.2175	0.6882	0.6690	0.064*
H17B	0.2346	0.6653	0.7609	0.064*
H17C	0.1502	0.6932	0.6682	0.064*

Atomic displacement parameters ( $\text{\AA}^2$ )

	$U^{11}$	$U^{22}$	$U^{33}$	$U^{12}$	$U^{13}$	$U^{23}$
Cd1	0.0238 (4)	0.0338 (4)	0.0243 (4)	0.000	0.0186 (3)	0.000
S1	0.0368 (10)	0.0355 (11)	0.0337 (11)	-0.0019 (8)	0.0259 (9)	-0.0040 (9)
O1	0.025 (2)	0.037 (3)	0.027 (3)	0.000 (2)	0.019 (2)	0.000 (2)
O2	0.041 (3)	0.041 (3)	0.032 (3)	-0.010 (2)	0.026 (3)	-0.012 (2)
O3	0.025 (2)	0.035 (3)	0.029 (3)	-0.001 (2)	0.022 (2)	-0.003 (2)
O4	0.034 (3)	0.038 (3)	0.032 (3)	-0.007 (2)	0.028 (2)	-0.010 (2)
N1	0.024 (3)	0.026 (3)	0.020 (3)	-0.001 (2)	0.016 (2)	0.000 (2)
N2	0.030 (3)	0.033 (3)	0.025 (3)	0.000 (3)	0.022 (3)	-0.005 (3)
O5	0.035 (3)	0.042 (3)	0.061 (4)	0.004 (2)	0.036 (3)	0.002 (3)

## supplementary materials

C1	0.025 (3)	0.031 (4)	0.020 (4)	0.006 (3)	0.014 (3)	0.007 (3)
C2	0.034 (4)	0.033 (4)	0.027 (4)	0.007 (3)	0.024 (3)	0.002 (3)
C3	0.037 (4)	0.025 (4)	0.032 (4)	-0.003 (3)	0.025 (4)	0.000 (3)
C4	0.024 (3)	0.045 (5)	0.021 (4)	-0.012 (3)	0.010 (3)	-0.006 (3)
C5	0.030 (4)	0.044 (5)	0.026 (4)	0.005 (3)	0.019 (3)	0.003 (3)
C6	0.027 (3)	0.035 (4)	0.026 (4)	0.007 (3)	0.018 (3)	0.010 (4)
C7	0.047 (4)	0.044 (5)	0.035 (4)	-0.004 (4)	0.025 (4)	-0.002 (4)
C8	0.027 (4)	0.024 (4)	0.035 (4)	0.003 (3)	0.024 (3)	0.005 (3)
C9	0.027 (4)	0.027 (4)	0.022 (4)	0.007 (3)	0.015 (3)	0.006 (3)
C10	0.021 (3)	0.029 (4)	0.020 (4)	-0.002 (3)	0.014 (3)	0.000 (3)
C11	0.035 (4)	0.034 (4)	0.029 (4)	-0.001 (3)	0.026 (3)	-0.002 (3)
C12	0.033 (4)	0.036 (5)	0.035 (4)	-0.006 (3)	0.027 (3)	0.001 (3)
C13	0.035 (4)	0.033 (4)	0.022 (4)	0.005 (3)	0.021 (3)	0.002 (3)
C14	0.025 (3)	0.029 (4)	0.021 (3)	0.004 (3)	0.017 (3)	0.003 (3)
C15	0.026 (3)	0.026 (4)	0.020 (4)	-0.002 (3)	0.015 (3)	0.001 (3)
C16	0.031 (4)	0.051 (5)	0.037 (5)	-0.004 (3)	0.025 (4)	-0.006 (4)
C17	0.050 (4)	0.039 (5)	0.047 (5)	0.004 (4)	0.035 (4)	-0.001 (4)

### Geometric parameters ( $\text{\AA}$ , $^\circ$ )

Cd1—O1	2.246 (4)	C4—H4A	0.9500
Cd1—O1 <sup>i</sup>	2.246 (4)	C5—C6	1.3900
Cd1—N1 <sup>i</sup>	2.254 (5)	C5—H5	0.9500
Cd1—N1	2.254 (5)	C6—C8	1.464 (7)
Cd1—O3	2.386 (4)	C7—H7A	0.9800
Cd1—O3 <sup>i</sup>	2.386 (4)	C7—H7B	0.9800
S1—O5	1.497 (5)	C7—H7C	0.9800
S1—C17	1.764 (7)	C8—H8	0.9500
S1—C16	1.782 (6)	C9—C10	1.500 (7)
O1—C1	1.362 (5)	C10—C11	1.3900
O2—C3	1.355 (5)	C10—C15	1.3900
O2—C7	1.439 (8)	C11—C12	1.3900
O3—C9	1.221 (7)	C11—H11	0.9500
O4—C13	1.356 (5)	C12—C13	1.3900
O4—H4	0.8400	C12—H12	0.9500
N1—C8	1.280 (8)	C13—C14	1.3900
N1—N2	1.385 (7)	C14—C15	1.3900
N2—C9	1.356 (8)	C14—H14	0.9500
N2—H2	0.8800	C15—H15	0.9500
C1—C2	1.3900	C16—H16A	0.9800
C1—C6	1.3900	C16—H16B	0.9800
C2—C3	1.3900	C16—H16C	0.9800
C2—H2A	0.9500	C17—H17A	0.9800
C3—C4	1.3900	C17—H17B	0.9800
C4—C5	1.3900	C17—H17C	0.9800
O1—Cd1—O1 <sup>i</sup>	101.8 (2)	C5—C6—C8	112.7 (3)
O1—Cd1—N1 <sup>i</sup>	104.12 (16)	C1—C6—C8	127.3 (3)
O1 <sup>i</sup> —Cd1—N1 <sup>i</sup>	82.26 (16)	O2—C7—H7A	109.5

O1—Cd1—N1	82.26 (16)	O2—C7—H7B	109.5
O1 <sup>i</sup> —Cd1—N1	104.12 (16)	H7A—C7—H7B	109.5
N1 <sup>i</sup> —Cd1—N1	170.1 (3)	O2—C7—H7C	109.5
O1—Cd1—O3	150.75 (14)	H7A—C7—H7C	109.5
O1 <sup>i</sup> —Cd1—O3	94.45 (15)	H7B—C7—H7C	109.5
N1 <sup>i</sup> —Cd1—O3	102.05 (16)	N1—C8—C6	127.4 (5)
N1—Cd1—O3	70.17 (16)	N1—C8—H8	116.3
O1—Cd1—O3 <sup>i</sup>	94.45 (15)	C6—C8—H8	116.3
O1 <sup>i</sup> —Cd1—O3 <sup>i</sup>	150.75 (14)	O3—C9—N2	122.3 (6)
N1 <sup>i</sup> —Cd1—O3 <sup>i</sup>	70.17 (16)	O3—C9—C10	121.5 (6)
N1—Cd1—O3 <sup>i</sup>	102.05 (16)	N2—C9—C10	116.1 (5)
O3—Cd1—O3 <sup>i</sup>	82.3 (2)	C11—C10—C15	120.0
O5—S1—C17	104.7 (3)	C11—C10—C9	117.7 (3)
O5—S1—C16	104.9 (3)	C15—C10—C9	122.0 (4)
C17—S1—C16	99.3 (4)	C12—C11—C10	120.0
C1—O1—Cd1	130.6 (3)	C12—C11—H11	120.0
C3—O2—C7	117.6 (5)	C10—C11—H11	120.0
C9—O3—Cd1	114.2 (4)	C11—C12—C13	120.0
C13—O4—H4	109.5	C11—C12—H12	120.0
C8—N1—N2	116.5 (5)	C13—C12—H12	120.0
C8—N1—Cd1	128.4 (4)	O4—C13—C14	122.6 (3)
N2—N1—Cd1	114.9 (3)	O4—C13—C12	117.3 (3)
C9—N2—N1	118.2 (5)	C14—C13—C12	120.0
C9—N2—H2	120.9	C13—C14—C15	120.0
N1—N2—H2	120.9	C13—C14—H14	120.0
O1—C1—C2	117.6 (3)	C15—C14—H14	120.0
O1—C1—C6	122.4 (3)	C14—C15—C10	120.0
C2—C1—C6	120.0	C14—C15—H15	120.0
C1—C2—C3	120.0	C10—C15—H15	120.0
C1—C2—H2A	120.0	S1—C16—H16A	109.5
C3—C2—H2A	120.0	S1—C16—H16B	109.5
O2—C3—C2	116.1 (3)	H16A—C16—H16B	109.5
O2—C3—C4	123.9 (3)	S1—C16—H16C	109.5
C2—C3—C4	120.0	H16A—C16—H16C	109.5
C5—C4—C3	120.0	H16B—C16—H16C	109.5
C5—C4—H4A	120.0	S1—C17—H17A	109.5
C3—C4—H4A	120.0	S1—C17—H17B	109.5
C4—C5—C6	120.0	H17A—C17—H17B	109.5
C4—C5—H5	120.0	S1—C17—H17C	109.5
C6—C5—H5	120.0	H17A—C17—H17C	109.5
C5—C6—C1	120.0	H17B—C17—H17C	109.5
O1 <sup>i</sup> —Cd1—O1—C1	90.7 (4)	C3—C4—C5—C6	0.0
N1 <sup>i</sup> —Cd1—O1—C1	175.5 (4)	C4—C5—C6—C1	0.0
N1—Cd1—O1—C1	-12.2 (4)	C4—C5—C6—C8	180.0 (4)
O3—Cd1—O1—C1	-31.7 (6)	O1—C1—C6—C5	178.1 (4)
O3 <sup>i</sup> —Cd1—O1—C1	-113.8 (4)	C2—C1—C6—C5	0.0

## supplementary materials

O1—Cd1—O3—C9	24.1 (6)	O1—C1—C6—C8	-1.8 (6)
O1 <sup>i</sup> —Cd1—O3—C9	-99.9 (4)	C2—C1—C6—C8	-179.9 (5)
N1 <sup>i</sup> —Cd1—O3—C9	177.1 (4)	N2—N1—C8—C6	-178.8 (5)
N1—Cd1—O3—C9	3.5 (4)	Cd1—N1—C8—C6	6.1 (9)
O3 <sup>i</sup> —Cd1—O3—C9	109.4 (5)	C5—C6—C8—N1	171.3 (6)
O1—Cd1—N1—C8	2.3 (5)	C1—C6—C8—N1	-8.8 (9)
O1 <sup>i</sup> —Cd1—N1—C8	-97.9 (5)	Cd1—O3—C9—N2	-3.9 (8)
O3—Cd1—N1—C8	172.4 (6)	Cd1—O3—C9—C10	175.5 (4)
O3 <sup>i</sup> —Cd1—N1—C8	95.3 (5)	N1—N2—C9—O3	1.4 (9)
O1—Cd1—N1—N2	-172.8 (4)	N1—N2—C9—C10	-178.1 (5)
O1 <sup>i</sup> —Cd1—N1—N2	86.9 (4)	O3—C9—C10—C11	25.7 (7)
O3—Cd1—N1—N2	-2.8 (4)	N2—C9—C10—C11	-154.8 (4)
O3 <sup>i</sup> —Cd1—N1—N2	-79.9 (4)	O3—C9—C10—C15	-148.5 (5)
C8—N1—N2—C9	-173.7 (6)	N2—C9—C10—C15	31.0 (7)
Cd1—N1—N2—C9	2.1 (7)	C15—C10—C11—C12	0.0
Cd1—O1—C1—C2	-168.0 (3)	C9—C10—C11—C12	-174.3 (4)
Cd1—O1—C1—C6	13.8 (6)	C10—C11—C12—C13	0.0
O1—C1—C2—C3	-178.2 (4)	C11—C12—C13—O4	177.6 (4)
C6—C1—C2—C3	0.0	C11—C12—C13—C14	0.0
C7—O2—C3—C2	174.7 (5)	O4—C13—C14—C15	-177.4 (4)
C7—O2—C3—C4	-6.5 (7)	C12—C13—C14—C15	0.0
C1—C2—C3—O2	178.9 (5)	C13—C14—C15—C10	0.0
C1—C2—C3—C4	0.0	C11—C10—C15—C14	0.0
O2—C3—C4—C5	-178.8 (5)	C9—C10—C15—C14	174.1 (4)
C2—C3—C4—C5	0.0		

Symmetry codes: (i)  $-x+1, y, -z+3/2$ .

### Hydrogen-bond geometry ( $\text{\AA}, ^\circ$ )

$D-H\cdots A$	$D-H$	$H\cdots A$	$D\cdots A$	$D-H\cdots A$
O4—H4 <sup>iii</sup> —O1 <sup>ii</sup>	0.84	1.79	2.603 (6)	163
N2—H2 <sup>iii</sup> —O5	0.88	1.93	2.766 (6)	159

Symmetry codes: (ii)  $x, -y+1, z+1/2$ .

Fig. 1

