

catena-Poly[[copper(II)-bis[μ -bis(3,5-dimethyl-1*H*-pyrazol-4-yl) selenide]] bis(perchlorate)]

Maksym Seredyuk,^{a*} Matti Haukka,^b Vadim A. Pavlenko^a and Igor O. Fritsky^a

^aNational Taras Shevchenko University, Department of Chemistry, Volodymyrska str. 64, 01033 Kyiv, Ukraine, and ^bDepartment of Chemistry, University of Joensuu, PO Box 111, 80101 Joensuu, Finland
Correspondence e-mail: mcs@univ.kiev.ua


Received 30 September 2009; accepted 13 October 2009

Key indicators: single-crystal X-ray study; $T = 120$ K; mean $\sigma(\text{C}-\text{C}) = 0.011$ Å; R factor = 0.047; wR factor = 0.115; data-to-parameter ratio = 17.9.

In the title compound, $\{[\text{Cu}(\text{C}_{10}\text{H}_{14}\text{N}_4\text{Se})_2](\text{ClO}_4)_2\}_n$, the Cu^{II} ion is located on a twofold rotation axis and has a tetragonally distorted square-planar geometry constituted by four N atoms. A pair of bis(3,5-dimethyl-1*H*-pyrazol-4-yl) selenide (*L*) ligands bridges the copper centers into a polymeric chain extending along [001]. The perchlorate anions are involved in intermolecular $\text{N}-\text{H}\cdots\text{O}$ hydrogen bonding, which links the chains into layers parallel to the *bc* plane.

Related literature

For the potential applications of coordination polymers, see: Farha *et al.* (2009); Ohba *et al.* (2009); Shibahara *et al.* (2007). For our studies of similar complexes with different dimensionality, see Seredyuk *et al.* (2007).



Experimental

Crystal data

$[\text{Cu}(\text{C}_{10}\text{H}_{14}\text{N}_4\text{Se})_2](\text{ClO}_4)_2$
 $M_r = 800.86$
 Monoclinic, $C2/c$
 $a = 28.398$ (6) Å
 $b = 7.5865$ (15) Å
 $c = 18.517$ (4) Å
 $\beta = 130.69$ (3)°
 $V = 3025.1$ (17) Å³
 $Z = 4$
 Mo $K\alpha$ radiation
 $\mu = 3.36$ mm⁻¹
 $T = 120$ K
 $0.20 \times 0.15 \times 0.05$ mm

Data collection

Nonius KappaCCD diffractometer
 Absorption correction: multi-scan (*SADABS*; Sheldrick, 1996)
 $T_{\text{min}} = 0.552$, $T_{\text{max}} = 0.845$
 13077 measured reflections
 3415 independent reflections
 2799 reflections with $I > 2\sigma(I)$
 $R_{\text{int}} = 0.074$

Refinement

$R[F^2 > 2\sigma(F^2)] = 0.047$
 $wR(F^2) = 0.115$
 $S = 1.04$
 3415 reflections
 191 parameters
 H-atom parameters constrained
 $\Delta\rho_{\text{max}} = 2.18$ e Å⁻³
 $\Delta\rho_{\text{min}} = -1.00$ e Å⁻³

Table 1

Hydrogen-bond geometry (Å, °).

| $D-\text{H}\cdots A$ | $D-\text{H}$ | $\text{H}\cdots A$ | $D\cdots A$ | $D-\text{H}\cdots A$ |
|--|--------------|--------------------|-------------|----------------------|
| $\text{N2}-\text{H4}\cdots\text{O3}^{\text{i}}$ | 0.88 | 2.06 | 2.912 (6) | 161 |
| $\text{N4}-\text{H3}\cdots\text{O2}^{\text{ii}}$ | 0.88 | 2.02 | 2.879 (6) | 166 |

Symmetry codes: (i) $x, -y + 1, z - \frac{1}{2}$; (ii) $x, y - 1, z$.

Data collection: *COLLECT* (Bruker–Nonius, 2004); cell refinement: *DENZO/SCALEPACK* (Otwinowski & Minor, 1997); data reduction: *DENZO/SCALEPACK*; program(s) used to solve structure: *SHELXS97* (Sheldrick, 2008); program(s) used to refine structure: *SHELXL97* (Sheldrick, 2008); molecular graphics: *ORTEP-3 for Windows* (Farrugia, 1997); software used to prepare material for publication: *DIAMOND* (Brandenburg, 2006).

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: CV2624).

References

- Brandenburg, K. (2006). *DIAMOND*. Crystal Impact GbR, Bonn, Germany.
 Bruker–Nonius (2004). *COLLECT*. Bruker–Nonius BV, Delft, The Netherlands.
 Farha, O. K., Spokoyny, A. M., Mulfort, K. L., Galli, S., Hupp, J. T. & Mirkin, C. A. (2009). *Small*, **5**, 1727–1731.
 Farrugia, L. J. (1997). *J. Appl. Cryst.* **30**, 565.
 Ohba, M., Yoneda, K., Agusí, G., Munoz, M. C., Gaspar, A. B., Real, J. A., Yamasaki, M., Ando, H., Nakao, Y., Sakaki, S. & Kitagawa, S. (2009). *Angew. Chem., Int. Ed. Engl.* **48**, 4767–4771.
 Otwinowski, Z. & Minor, W. (1997). *Methods in Enzymology*, Vol. 276, *Macromolecular Crystallography*, Part A, edited by C. W. Carter Jr & R. M. Sweet, pp. 307–326. New York: Academic Press.
 Seredyuk, M., Haukka, M., Fritsky, I. O., Kozłowski, H., Krämer, R., Pavlenko, V. A. & Gütlich, P. (2007). *Dalton Trans.* pp. 3183–3194.
 Sheldrick, G. M. (1996). *SADABS*. University of Göttingen, Germany.
 Sheldrick, G. M. (2008). *Acta Cryst.* **A64**, 112–122.
 Shibahara, S., Kitagawa, H., Kubo, T. & Nakasuji, K. (2007). *Inorg. Chem. Commun.* **10**, 860–862.

supplementary materials

Acta Cryst. (2009). E65, m1396 [doi:10.1107/S1600536809042056]

***catena*-Poly[[copper(II)-bis[μ -bis(3,5-dimethyl-1*H*-pyrazol-4-yl) selenide]] bis(perchlorate)]**

M. Seredyuk, M. Haukka, V. A. Pavlenko and I. O. Fritsky

Comment

Molecular self-assembly through donor-acceptor interactions becomes one of the most elaborated research areas in coordination chemistry. The primary interest here is the development of functional materials with useful properties. Particularly, infinite molecular polymeric arrays are potentially applicable as specifically ordered crystalline substances with reversible selective sorption (Farha *et al.*, 2009), electrical conductivity (Shibahara *et al.*, 2007) and molecular magnetism functionality (Ohba *et al.*, 2009).

The title compound, [Cu(*cis*- μ -*L*)₂](ClO₄)₂, was readily prepared by mixing aqueous solution of Cu(ClO₄)₂·6H₂O and methanolic solution of the ligand bis(3,5-dimethyl-1*H*-pyrazolyl)selenide (*L*) prepared according to Seredyuk *et al.* (2007). A tetragonally distorted square-planar environment of the Cu^{II} ion is formed by four non-coplanar nitrogen atoms of propeller-like arranged pyrazolyl cycles (distances Cu–N are 1.982 (5) and 1.967 (5) Å, two diagonal angles N–Cu–N are 163.6 (3) and 168.8 (3)°, respectively). Symmetrically equivalent ligand molecules in *cis*-bonding configuration are linked to Cu^{II} ion in a double-stranded bridge fashion (Fig. 1.). By repeats, they form linear chain running along the *c* axis within which each copper atom deviates from the average position by a value of ± 0.068 (5) Å (Fig. 2). The NH group of each pyrazole cycle is involved in hydrogen bonding with perchlorate group resulting in the formation of a three-dimensional hybrid network.

Experimental

A solution of Cu(ClO₄)₂·6H₂O (0.065 g) in water (10 ml) was mixed with a solution of L·H₂O (0.1 g) in methanol (10 ml) and was set aside for one week after which brown crystals of the title compound were isolated. Found C, 29.83, H, 3.65, N, 13.81. C₂₀H₂₈Cl₂CuN₈O₈Se₂ requires C, 29.99, H, 3.52, N, 13.99.

Refinement

All H atoms were geometrically positioned (C–H 0.98 Å; N–H 0.88 Å), and refined as riding, with U_{iso}(H) = 1.2–1.5 U_{eq}(C, N). The crystal studied was a twin, so matrix (100) was used in the refinement of the crystal structure.

Figures




Fig. 1. A portion of the crystal structure of the title compound showing the labeling scheme and 50% probability displacement ellipsoids [symmetry codes: (i) $-x, 1-y, -z$, (ii) $-x, y, -0.5-z$, (iii) $x, 1-y, -1/2+z$]. H atoms are omitted for clarity.




Fig. 2. A packing diagram of the title compound viewed along the *b*-axis. H atoms are omitted for clarity.

catena-Poly[[copper(II)-bis[μ -bis(3,5-dimethyl-1*H*-pyrazol-4-yl) selenide]] bis(perchlorate)]

Crystal data

| | |
|--|---|
| $[\text{Cu}(\text{C}_{10}\text{H}_{14}\text{N}_4\text{Se})_2](\text{ClO}_4)_2$ | $F_{000} = 1596$ |
| $M_r = 800.86$ | $D_x = 1.758 \text{ Mg m}^{-3}$ |
| Monoclinic, <i>C2/c</i> | Mo $K\alpha$ radiation, $\lambda = 0.71073 \text{ \AA}$ |
| Hall symbol: - <i>C</i> 2yc | Cell parameters from 3400 reflections |
| $a = 28.398 (6) \text{ \AA}$ | $\theta = 2.9\text{--}27.5^\circ$ |
| $b = 7.5865 (15) \text{ \AA}$ | $\mu = 3.36 \text{ mm}^{-1}$ |
| $c = 18.517 (4) \text{ \AA}$ | $T = 120 \text{ K}$ |
| $\beta = 130.69 (3)^\circ$ | Plates, brown |
| $V = 3025.1 (17) \text{ \AA}^3$ | $0.2 \times 0.15 \times 0.05 \text{ mm}$ |
| $Z = 4$ | |

Data collection

| | |
|---|--|
| Nonius KappaCCD diffractometer | 3415 independent reflections |
| Radiation source: fine-focus sealed tube | 2799 reflections with $I > 2\sigma(I)$ |
| Monochromator: graphite | $R_{\text{int}} = 0.074$ |
| $T = 120 \text{ K}$ | $\theta_{\text{max}} = 27.5^\circ$ |
| ω -scans | $\theta_{\text{min}} = 1.5^\circ$ |
| Absorption correction: multi-scan (SADABS; Sheldrick, 1996) | $h = -36 \rightarrow 34$ |
| $T_{\text{min}} = 0.552$, $T_{\text{max}} = 0.845$ | $k = -9 \rightarrow 9$ |
| 13077 measured reflections | $l = -24 \rightarrow 22$ |

Refinement

| | |
|--|--|
| Refinement on F^2 | Secondary atom site location: difference Fourier map |
| Least-squares matrix: full | Hydrogen site location: inferred from neighbouring sites |
| $R[F^2 > 2\sigma(F^2)] = 0.047$ | H-atom parameters constrained |
| $wR(F^2) = 0.115$ | $w = 1/[\sigma^2(F_o^2) + (0.0574P)^2 + 8.3063P]$ |
| $S = 1.04$ | where $P = (F_o^2 + 2F_c^2)/3$ |
| 3415 reflections | $(\Delta/\sigma)_{\text{max}} < 0.001$ |
| 191 parameters | $\Delta\rho_{\text{max}} = 2.18 \text{ e \AA}^{-3}$ |
| Primary atom site location: structure-invariant direct methods | $\Delta\rho_{\text{min}} = -1.00 \text{ e \AA}^{-3}$ |
| | Extinction correction: none |

Special details

Geometry. All e.s.d.'s (except the e.s.d. in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell e.s.d.'s are taken into account individually in the estimation of e.s.d.'s in distances, angles and torsion angles; correlations between e.s.d.'s in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell e.s.d.'s is used for estimating e.s.d.'s involving l.s. planes.

Refinement. Refinement of F^2 against ALL reflections. The weighted R -factor wR and goodness of fit S are based on F^2 , conventional R -factors R are based on F , with F set to zero for negative F^2 . The threshold expression of $F^2 > \sigma(F^2)$ is used only for calculating R -factors(gt) *etc.* and is not relevant to the choice of reflections for refinement. R -factors based on F^2 are statistically about twice as large as those based on F , and R -factors based on ALL data will be even larger.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2)

| | <i>x</i> | <i>y</i> | <i>z</i> | $U_{\text{iso}}^*/U_{\text{eq}}$ |
|------|-------------|--------------|--------------|----------------------------------|
| Cu1 | 0.0000 | 0.48037 (13) | -0.2500 | 0.0124 (2) |
| Se1 | 0.15222 (2) | 0.73993 (6) | 0.14892 (4) | 0.01476 (14) |
| Cl1 | 0.13436 (8) | 0.99852 (19) | 0.36166 (12) | 0.0307 (4) |
| O1 | 0.1340 (3) | 1.0280 (6) | 0.2844 (4) | 0.0369 (12) |
| O2 | 0.1537 (3) | 1.1562 (6) | 0.4173 (3) | 0.0430 (13) |
| O3 | 0.1753 (2) | 0.8577 (5) | 0.4177 (4) | 0.0410 (14) |
| O4 | 0.0732 (2) | 0.9468 (7) | 0.3248 (4) | 0.0510 (14) |
| N1 | 0.0655 (2) | 0.5177 (6) | -0.1109 (3) | 0.0144 (10) |
| N2 | 0.1167 (2) | 0.4166 (6) | -0.0546 (3) | 0.0146 (10) |
| H4 | 0.1257 | 0.3301 | -0.0755 | 0.017* |
| N3 | 0.0637 (2) | 0.5450 (6) | 0.2384 (3) | 0.0125 (10) |
| N4 | 0.1183 (2) | 0.4511 (6) | 0.2931 (3) | 0.0131 (10) |
| H3 | 0.1284 | 0.3739 | 0.3367 | 0.016* |
| C1 | 0.0190 (3) | 0.7707 (8) | -0.0923 (4) | 0.0237 (14) |
| H11A | 0.0036 | 0.8098 | -0.1548 | 0.036* |
| H11B | 0.0367 | 0.8713 | -0.0486 | 0.036* |
| H11C | -0.0155 | 0.7211 | -0.0987 | 0.036* |
| C2 | 0.0679 (3) | 0.6330 (7) | -0.0538 (4) | 0.0141 (12) |
| C3 | 0.1216 (3) | 0.6022 (7) | 0.0402 (4) | 0.0128 (12) |
| C4 | 0.1526 (3) | 0.4643 (7) | 0.0377 (4) | 0.0146 (11) |
| C5 | 0.2128 (3) | 0.3741 (9) | 0.1141 (5) | 0.0268 (15) |
| H19A | 0.2057 | 0.2792 | 0.1420 | 0.040* |
| H19B | 0.2422 | 0.4595 | 0.1637 | 0.040* |
| H19C | 0.2300 | 0.3245 | 0.0867 | 0.040* |
| C6 | 0.0155 (3) | 0.7705 (8) | 0.1110 (5) | 0.0217 (14) |
| H8A | -0.0160 | 0.7091 | 0.0508 | 0.033* |
| H8B | 0.0328 | 0.8680 | 0.1000 | 0.033* |
| H8C | -0.0035 | 0.8168 | 0.1362 | 0.033* |
| C7 | 0.0657 (3) | 0.6460 (7) | 0.1804 (4) | 0.0140 (12) |
| C8 | 0.1218 (3) | 0.6135 (7) | 0.1993 (4) | 0.0128 (11) |
| C9 | 0.1539 (3) | 0.4907 (7) | 0.2723 (4) | 0.0148 (12) |
| C10 | 0.2162 (3) | 0.4049 (8) | 0.3247 (5) | 0.0250 (14) |
| H17A | 0.2105 | 0.2792 | 0.3088 | 0.037* |

supplementary materials

| | | | | |
|------|--------|--------|--------|--------|
| H17B | 0.2407 | 0.4188 | 0.3935 | 0.037* |
| H17C | 0.2380 | 0.4608 | 0.3061 | 0.037* |

Atomic displacement parameters (\AA^2)

| | U^{11} | U^{22} | U^{33} | U^{12} | U^{13} | U^{23} |
|-----|------------|------------|------------|-------------|------------|--------------|
| Cu1 | 0.0104 (4) | 0.0185 (5) | 0.0111 (5) | 0.000 | 0.0082 (4) | 0.000 |
| Se1 | 0.0156 (2) | 0.0179 (3) | 0.0128 (3) | -0.0062 (2) | 0.0101 (3) | -0.0039 (2) |
| Cl1 | 0.0342 (8) | 0.0231 (7) | 0.0390 (9) | 0.0019 (7) | 0.0258 (8) | 0.0063 (7) |
| O1 | 0.052 (3) | 0.032 (3) | 0.038 (3) | -0.003 (2) | 0.034 (3) | -0.001 (2) |
| O2 | 0.068 (4) | 0.030 (2) | 0.027 (3) | 0.000 (3) | 0.029 (3) | 0.003 (2) |
| O3 | 0.055 (4) | 0.022 (2) | 0.064 (4) | 0.013 (2) | 0.048 (3) | 0.016 (2) |
| O4 | 0.037 (3) | 0.070 (4) | 0.048 (3) | -0.017 (3) | 0.029 (3) | -0.011 (3) |
| N1 | 0.015 (3) | 0.016 (2) | 0.012 (2) | 0.002 (2) | 0.008 (2) | -0.0016 (18) |
| N2 | 0.013 (3) | 0.016 (2) | 0.012 (2) | 0.0048 (19) | 0.007 (2) | -0.0009 (18) |
| N3 | 0.012 (2) | 0.018 (2) | 0.010 (2) | 0.004 (2) | 0.008 (2) | 0.0002 (18) |
| N4 | 0.011 (2) | 0.015 (2) | 0.010 (2) | 0.0013 (19) | 0.005 (2) | 0.0022 (17) |
| C1 | 0.024 (4) | 0.021 (3) | 0.017 (3) | 0.009 (3) | 0.010 (3) | 0.001 (2) |
| C2 | 0.012 (3) | 0.017 (3) | 0.016 (3) | 0.001 (2) | 0.011 (3) | 0.001 (2) |
| C3 | 0.015 (3) | 0.014 (3) | 0.011 (3) | -0.003 (2) | 0.009 (2) | 0.001 (2) |
| C4 | 0.015 (3) | 0.017 (2) | 0.014 (3) | 0.001 (2) | 0.011 (3) | 0.001 (2) |
| C5 | 0.021 (4) | 0.033 (4) | 0.024 (3) | 0.007 (3) | 0.013 (3) | 0.003 (3) |
| C6 | 0.015 (3) | 0.026 (3) | 0.022 (3) | 0.004 (3) | 0.010 (3) | 0.011 (2) |
| C7 | 0.017 (3) | 0.014 (3) | 0.011 (3) | -0.001 (2) | 0.009 (3) | -0.001 (2) |
| C8 | 0.014 (3) | 0.015 (3) | 0.010 (3) | -0.001 (2) | 0.009 (2) | -0.003 (2) |
| C9 | 0.012 (3) | 0.017 (3) | 0.016 (3) | -0.001 (2) | 0.009 (2) | -0.001 (2) |
| C10 | 0.020 (3) | 0.031 (3) | 0.029 (3) | 0.006 (3) | 0.018 (3) | 0.008 (3) |

Geometric parameters (\AA , $^\circ$)

| | | | |
|-----------------------|-----------|----------|-----------|
| Cu1—N3 ⁱ | 1.967 (5) | C1—H11A | 0.9800 |
| Cu1—N3 ⁱⁱ | 1.967 (5) | C1—H11B | 0.9800 |
| Cu1—N1 | 1.982 (5) | C1—H11C | 0.9800 |
| Cu1—N1 ⁱⁱⁱ | 1.982 (5) | C2—C3 | 1.396 (8) |
| Se1—C8 | 1.893 (5) | C3—C4 | 1.387 (8) |
| Se1—C3 | 1.902 (5) | C4—C5 | 1.497 (8) |
| Cl1—O3 | 1.413 (5) | C5—H19A | 0.9800 |
| Cl1—O2 | 1.434 (5) | C5—H19B | 0.9800 |
| Cl1—O1 | 1.442 (5) | C5—H19C | 0.9800 |
| Cl1—O4 | 1.447 (5) | C6—C7 | 1.478 (8) |
| N1—C2 | 1.339 (7) | C6—H8A | 0.9800 |
| N1—N2 | 1.347 (6) | C6—H8B | 0.9800 |
| N2—C4 | 1.349 (7) | C6—H8C | 0.9800 |
| N2—H4 | 0.8800 | C7—C8 | 1.413 (8) |
| N3—C7 | 1.349 (7) | C8—C9 | 1.386 (8) |
| N3—N4 | 1.373 (6) | C9—C10 | 1.502 (8) |
| N3—Cu1 ⁱ | 1.967 (5) | C10—H17A | 0.9800 |
| N4—C9 | 1.330 (7) | C10—H17B | 0.9800 |

| | | | |
|---|-------------|----------------------------|------------|
| N4—H3 | 0.8800 | C10—H17C | 0.9800 |
| C1—C2 | 1.497 (8) | | |
| N3 ⁱ —Cu1—N3 ⁱⁱ | 168.8 (3) | C4—C3—C2 | 106.5 (5) |
| N3 ⁱ —Cu1—N1 | 91.28 (16) | C4—C3—Se1 | 126.0 (4) |
| N3 ⁱⁱ —Cu1—N1 | 90.32 (16) | C2—C3—Se1 | 127.0 (4) |
| N3 ⁱ —Cu1—N1 ⁱⁱⁱ | 90.32 (16) | N2—C4—C3 | 105.9 (5) |
| N3 ⁱⁱ —Cu1—N1 ⁱⁱⁱ | 91.28 (16) | N2—C4—C5 | 121.9 (5) |
| N1—Cu1—N1 ⁱⁱⁱ | 163.6 (3) | C3—C4—C5 | 132.2 (5) |
| C8—Se1—C3 | 101.66 (19) | C4—C5—H19A | 109.5 |
| O3—C11—O2 | 110.9 (3) | C4—C5—H19B | 109.5 |
| O3—C11—O1 | 108.4 (3) | H19A—C5—H19B | 109.5 |
| O2—C11—O1 | 109.5 (3) | C4—C5—H19C | 109.5 |
| O3—C11—O4 | 107.6 (3) | H19A—C5—H19C | 109.5 |
| O2—C11—O4 | 110.2 (4) | H19B—C5—H19C | 109.5 |
| O1—C11—O4 | 110.2 (4) | C7—C6—H8A | 109.5 |
| C2—N1—N2 | 106.7 (5) | C7—C6—H8B | 109.5 |
| C2—N1—Cu1 | 129.9 (4) | H8A—C6—H8B | 109.5 |
| N2—N1—Cu1 | 123.3 (3) | C7—C6—H8C | 109.5 |
| N1—N2—C4 | 111.7 (4) | H8A—C6—H8C | 109.5 |
| N1—N2—H4 | 124.1 | H8B—C6—H8C | 109.5 |
| C4—N2—H4 | 124.1 | N3—C7—C8 | 109.2 (5) |
| C7—N3—N4 | 105.7 (4) | N3—C7—C6 | 122.5 (5) |
| C7—N3—Cu1 ⁱ | 131.4 (4) | C8—C7—C6 | 128.3 (5) |
| N4—N3—Cu1 ⁱ | 122.9 (3) | C9—C8—C7 | 106.1 (5) |
| C9—N4—N3 | 112.0 (4) | C9—C8—Se1 | 126.9 (4) |
| C9—N4—H3 | 124.0 | C7—C8—Se1 | 126.3 (4) |
| N3—N4—H3 | 124.0 | N4—C9—C8 | 107.1 (5) |
| C2—C1—H11A | 109.5 | N4—C9—C10 | 120.8 (5) |
| C2—C1—H11B | 109.5 | C8—C9—C10 | 132.0 (5) |
| H11A—C1—H11B | 109.5 | C9—C10—H17A | 109.5 |
| C2—C1—H11C | 109.5 | C9—C10—H17B | 109.5 |
| H11A—C1—H11C | 109.5 | H17A—C10—H17B | 109.5 |
| H11B—C1—H11C | 109.5 | C9—C10—H17C | 109.5 |
| N1—C2—C3 | 109.1 (5) | H17A—C10—H17C | 109.5 |
| N1—C2—C1 | 121.8 (5) | H17B—C10—H17C | 109.5 |
| C3—C2—C1 | 129.1 (5) | | |
| N3 ⁱ —Cu1—N1—C2 | -53.2 (5) | N1—N2—C4—C5 | -178.8 (5) |
| N3 ⁱⁱ —Cu1—N1—C2 | 138.0 (5) | C2—C3—C4—N2 | -1.3 (6) |
| N1 ⁱⁱⁱ —Cu1—N1—C2 | 42.3 (5) | Se1—C3—C4—N2 | -174.1 (4) |
| N3 ⁱ —Cu1—N1—N2 | 122.9 (4) | C2—C3—C4—C5 | 178.5 (6) |
| N3 ⁱⁱ —Cu1—N1—N2 | -45.9 (4) | Se1—C3—C4—C5 | 5.7 (9) |
| N1 ⁱⁱⁱ —Cu1—N1—N2 | -141.6 (4) | N4—N3—C7—C8 | 0.3 (6) |
| C2—N1—N2—C4 | -0.4 (6) | Cu1 ⁱ —N3—C7—C8 | -179.0 (4) |
| Cu1—N1—N2—C4 | -177.3 (4) | N4—N3—C7—C6 | -178.8 (5) |
| C7—N3—N4—C9 | 0.7 (6) | Cu1 ⁱ —N3—C7—C6 | 2.0 (9) |

supplementary materials

| | | | |
|----------------------------|------------|---------------|------------|
| Cu1 ⁱ —N3—N4—C9 | 180.0 (4) | N3—C7—C8—C9 | -1.0 (6) |
| N2—N1—C2—C3 | -0.4 (6) | C6—C7—C8—C9 | 177.9 (6) |
| Cu1—N1—C2—C3 | 176.2 (4) | N3—C7—C8—Se1 | -172.0 (4) |
| N2—N1—C2—C1 | 178.4 (5) | C6—C7—C8—Se1 | 7.0 (9) |
| Cu1—N1—C2—C1 | -5.0 (8) | C3—Se1—C8—C9 | 97.2 (5) |
| N1—C2—C3—C4 | 1.1 (6) | C3—Se1—C8—C7 | -93.7 (5) |
| C1—C2—C3—C4 | -177.6 (6) | N3—N4—C9—C8 | -1.3 (6) |
| N1—C2—C3—Se1 | 173.8 (4) | N3—N4—C9—C10 | 179.1 (5) |
| C1—C2—C3—Se1 | -4.9 (9) | C7—C8—C9—N4 | 1.4 (6) |
| C8—Se1—C3—C4 | -91.4 (5) | Se1—C8—C9—N4 | 172.3 (4) |
| C8—Se1—C3—C2 | 97.3 (5) | C7—C8—C9—C10 | -179.1 (6) |
| N1—N2—C4—C3 | 1.1 (6) | Se1—C8—C9—C10 | -8.3 (9) |

Symmetry codes: (i) $-x, -y+1, -z$; (ii) $x, -y+1, z-1/2$; (iii) $-x, y, -z-1/2$.

Hydrogen-bond geometry ($\text{\AA}, ^\circ$)

| $D-H\cdots A$ | $D-H$ | $H\cdots A$ | $D\cdots A$ | $D-H\cdots A$ |
|---------------------------------|-------|-------------|-------------|---------------|
| N2—H4 \cdots O3 ⁱⁱ | 0.88 | 2.06 | 2.912 (6) | 161 |
| N4—H3 \cdots O2 ^{iv} | 0.88 | 2.02 | 2.879 (6) | 166 |

Symmetry codes: (ii) $x, -y+1, z-1/2$; (iv) $x, y-1, z$.

Fig. 1




Fig. 2

