

Bis(pyridine- κN) $\{N^2,N^{2'}-[1,1'-(\text{pyridine}-2,6\text{-diyl})\text{diethylidyne}]\text{benzenesulfono-hydrazoneato-}\kappa^5 O,N,N',N'',O'\}$ nickel(II)

Juhir Yusnita,^a Hapipah Mohd Ali,^a Mahmood A. Abdulla,^b Ward T. Robinson^a and Hamid Khaledi^{a*}

^aDepartment of Chemistry, University of Malaya, 50603 Kuala Lumpur, Malaysia, and ^bDepartment of Molecular Medicine, University of Malaya, 50603 Kuala Lumpur, Malaysia

Correspondence e-mail: khaledi@perdana.um.edu.my


Received 14 December 2009; accepted 28 December 2009

Key indicators: single-crystal X-ray study; $T = 100$ K; mean $\sigma(\text{C-C}) = 0.003$ Å; R factor = 0.024; wR factor = 0.065; data-to-parameter ratio = 13.1.

In the crystal structure of the title compound, $[\text{Ni}(\text{C}_{21}\text{H}_{19}\text{N}_5\text{O}_4\text{S}_2)(\text{C}_5\text{H}_5\text{N})_2]$, the metal center is seven-coordinate, with an approximate pentagonal-bipyramidal configuration. The Ni atom is chelated by a dianionic pentadentate Schiff base *via* the pyridine N atom, the two azomethine N atoms and the two sulfonyl O atoms. The latter coordinate to Ni at different distances, *viz.* 2.3337 (12) and 2.7988 (12) Å. Two apically coordinated pyridine molecules complete the seven-coordinate geometry. The dihedral angle between the two pyridine ring planes is 68.25 (6)°.

Related literature

For the structure of the ligand and its zinc(II) complex, see: Yusnita *et al.* (2009a). For the structure of copper(II) complex of a similar ligand, see: Yusnita *et al.* (2009b).



Experimental

Crystal data



$M_r = 686.44$

Monoclinic, $P2_1/n$

$a = 11.6029$ (2) Å

$b = 15.8298$ (3) Å

$c = 16.4156$ (3) Å

$\beta = 91.823$ (2)°

$V = 3013.55$ (9) Å³

$Z = 4$

Mo $K\alpha$ radiation

$\mu = 0.83$ mm⁻¹

$T = 100$ K

0.30 × 0.22 × 0.19 mm

Data collection

Bruker APEXII CCD diffractometer

Absorption correction: multi-scan (*SADABS*; Sheldrick, 1996)

$T_{\min} = 0.788$, $T_{\max} = 0.858$

22997 measured reflections

5308 independent reflections

4815 reflections with $I > 2\sigma(I)$

$R_{\text{int}} = 0.020$

Refinement

$R[F^2 > 2\sigma(F^2)] = 0.024$

$wR(F^2) = 0.065$

$S = 1.05$

5308 reflections

406 parameters

H-atom parameters constrained

$\Delta\rho_{\text{max}} = 0.34$ e Å⁻³

$\Delta\rho_{\text{min}} = -0.36$ e Å⁻³

Data collection: *APEX2* (Bruker, 2007); cell refinement: *SAINT* (Bruker, 2007); data reduction: *SAINT* program(s) used to solve structure: *SHELXS97* (Sheldrick, 2008); program(s) used to refine structure: *SHELXL97* (Sheldrick, 2008); molecular graphics: *X-SEED* (Barbour, 2001); software used to prepare material for publication: *publCIF* (Westrip, 2010).

The authors thank the University of Malaya for funding this study (UMRG grant No. RG136/09HTM).

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: OM2309).

References

- Barbour, L. J. (2001). *J. Supramol. Chem.* **1**, 189–191.
- Bruker (2007). *APEX2* and *SAINT*. Bruker AXS Inc., Madison, Wisconsin, USA.
- Sheldrick, G. M. (1996). *SADABS*. University of Göttingen, Germany.
- Sheldrick, G. M. (2008). *Acta Cryst. A* **64**, 112–122.
- Westrip, S. P. (2010). *publCIF*. In preparation.
- Yusnita, J., Puvaneswary, S., Abdulla, M. A., Robinson, W. T. & Ali, H. M. (2009a). *J. Chem. Crystallogr.* **39**, 615–618.
- Yusnita, J., Puvaneswary, S., Ali, H. M., Robinson, W. T. & Kwai-Lin, T. (2009b). *Polyhedron*, **28**, 3050–3054.

supplementary materials

Acta Cryst. (2010). E66, m129 [doi:10.1107/S1600536809055639]

Bis(pyridine- $\kappa N\right)\{N^2,N^{2'}-[1,1'-(pyridine-2,6-diyl)diethylidyne]benzenesulfonohydrazoneato- $\kappa^5O,N,N',N'',O'\}nickel(II)$$

J. Yusnita, H. Mohd Ali, M. A. Abdulla, W. T. Robinson and H. Khaledi

Experimental

2,6-Diacetylpyridinebis(benzenesulfonylhydrazide) (1.413 g, 3 mmol) was dissolved in ethanol (50 ml) and three droplets of triethylamine were added, followed by addition of an ethanolic solution of stoichiometric amount of hydrated nickel (II) acetate. The mixture was refluxed for 5 h. The resulting dark brown solids were filtered and dried over silica gel. Brown crystals of the title compound were grown by slow evaporation of a pyridine solution.

Refinement

Hydrogen atoms were placed at calculated positions (C–H 0.95–0.98 Å), and were treated as riding on their parent atoms, with $U(H)$ set to 1.2–1.5 times $U_{eq}(C)$.

Figures




Fig. 1. Thermal ellipsoid plot of the title compound at the 40% probability level. Hydrogen atoms are drawn as spheres of arbitrary radius.

Bis(pyridine- $\kappa N\right)\{N^2,N^{2'}-[1,1'-(pyridine-2,6-diyl)diethylidyne]benzenesulfonohydrazoneato- $\kappa^5O,N,N',N'',O'\}nickel(II)$$

Crystal data

[Ni(C₂₁H₁₉N₅O₄S₂)(C₅H₅N)₂]

$F(000) = 1428$

$M_r = 686.44$

$D_x = 1.515 \text{ Mg m}^{-3}$

Monoclinic, $P2_1/n$

Mo $K\alpha$ radiation, $\lambda = 0.71073 \text{ \AA}$

Hall symbol: -P 2yn

Cell parameters from 9879 reflections

$a = 11.6029 (2) \text{ \AA}$

$\theta = 2.5\text{--}28.3^\circ$

$b = 15.8298 (3) \text{ \AA}$

$\mu = 0.83 \text{ mm}^{-1}$

$c = 16.4156 (3) \text{ \AA}$

$T = 100 \text{ K}$

$\beta = 91.823 (2)^\circ$

Block, brown

supplementary materials

$V = 3013.55(9) \text{ \AA}^3$

$Z = 4$

$0.30 \times 0.22 \times 0.19 \text{ mm}$

Data collection

Bruker APEXII CCD diffractometer	5308 independent reflections
Radiation source: fine-focus sealed tube graphite	4815 reflections with $I > 2\sigma(I)$
φ and ω scans	$R_{\text{int}} = 0.020$
Absorption correction: multi-scan (<i>SADABS</i> ; Sheldrick, 1996)	$\theta_{\max} = 25.0^\circ, \theta_{\min} = 1.8^\circ$
$T_{\min} = 0.788, T_{\max} = 0.858$	$h = -13 \rightarrow 13$
22997 measured reflections	$k = -18 \rightarrow 18$
	$l = -19 \rightarrow 19$

Refinement

Refinement on F^2	Primary atom site location: structure-invariant direct methods
Least-squares matrix: full	Secondary atom site location: difference Fourier map
$R[F^2 > 2\sigma(F^2)] = 0.024$	Hydrogen site location: inferred from neighbouring sites
$wR(F^2) = 0.065$	H-atom parameters constrained
$S = 1.05$	$w = 1/[\sigma^2(F_o^2) + (0.0291P)^2 + 2.4638P]$ where $P = (F_o^2 + 2F_c^2)/3$
5308 reflections	$(\Delta/\sigma)_{\max} = 0.001$
406 parameters	$\Delta\rho_{\max} = 0.34 \text{ e \AA}^{-3}$
0 restraints	$\Delta\rho_{\min} = -0.36 \text{ e \AA}^{-3}$

Special details

Geometry. All e.s.d.'s (except the e.s.d. in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell e.s.d.'s are taken into account individually in the estimation of e.s.d.'s in distances, angles and torsion angles; correlations between e.s.d.'s in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell e.s.d.'s is used for estimating e.s.d.'s involving l.s. planes.

Refinement. Refinement of F^2 against ALL reflections. The weighted R -factor wR and goodness of fit S are based on F^2 , conventional R -factors R are based on F , with F set to zero for negative F^2 . The threshold expression of $F^2 > \sigma(F^2)$ is used only for calculating R -factors(gt) etc. and is not relevant to the choice of reflections for refinement. R -factors based on F^2 are statistically about twice as large as those based on F , and R -factors based on ALL data will be even larger.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2)

	x	y	z	$U_{\text{iso}}^*/U_{\text{eq}}$
Ni	0.410517 (18)	0.141485 (13)	0.215880 (12)	0.01157 (7)
S1	0.59292 (4)	-0.00687 (3)	0.18463 (3)	0.01400 (10)
S2	0.27045 (4)	0.12194 (3)	0.40344 (2)	0.01272 (10)
O1	0.60699 (11)	-0.09339 (8)	0.16025 (8)	0.0207 (3)

O2	0.49868 (10)	0.01082 (7)	0.23919 (7)	0.0157 (3)
O3	0.33543 (10)	0.06141 (7)	0.35665 (7)	0.0166 (3)
O4	0.17478 (10)	0.08872 (8)	0.44772 (7)	0.0174 (3)
N1	0.38858 (12)	0.24587 (9)	0.14898 (8)	0.0127 (3)
N2	0.28461 (12)	0.21687 (9)	0.28339 (8)	0.0125 (3)
N3	0.22201 (12)	0.19994 (9)	0.35170 (8)	0.0137 (3)
N4	0.52548 (12)	0.12310 (9)	0.12007 (9)	0.0134 (3)
N5	0.58722 (12)	0.05107 (9)	0.10487 (9)	0.0156 (3)
N6	0.53749 (12)	0.19065 (9)	0.29575 (9)	0.0143 (3)
N7	0.27701 (12)	0.07348 (9)	0.15452 (9)	0.0140 (3)
C1	0.25986 (14)	0.28945 (11)	0.24972 (10)	0.0131 (3)
C2	0.17637 (15)	0.35009 (11)	0.28509 (11)	0.0169 (4)
H2A	0.1036	0.3209	0.2948	0.025*
H2B	0.1623	0.3968	0.2469	0.025*
H2C	0.2084	0.3723	0.3367	0.025*
C3	0.32043 (14)	0.30847 (11)	0.17453 (10)	0.0131 (3)
C4	0.31328 (15)	0.38448 (11)	0.13167 (11)	0.0166 (4)
H4	0.2653	0.4290	0.1494	0.020*
C5	0.37776 (15)	0.39357 (11)	0.06257 (11)	0.0182 (4)
H5	0.3742	0.4450	0.0328	0.022*
C6	0.44751 (15)	0.32834 (11)	0.03648 (10)	0.0163 (4)
H6	0.4913	0.3342	-0.0111	0.020*
C7	0.45153 (14)	0.25424 (11)	0.08200 (10)	0.0139 (3)
C8	0.52355 (14)	0.18075 (11)	0.06381 (10)	0.0145 (4)
C9	0.58566 (16)	0.17241 (12)	-0.01367 (11)	0.0209 (4)
H9A	0.5851	0.2268	-0.0421	0.031*
H9B	0.5473	0.1297	-0.0483	0.031*
H9C	0.6655	0.1551	-0.0017	0.031*
C10	0.72211 (15)	0.02117 (11)	0.24006 (11)	0.0169 (4)
C11	0.78134 (15)	0.09477 (12)	0.22277 (11)	0.0208 (4)
H11	0.7556	0.1304	0.1793	0.025*
C12	0.87894 (17)	0.11586 (14)	0.26986 (12)	0.0275 (5)
H12	0.9197	0.1665	0.2590	0.033*
C13	0.91686 (16)	0.06321 (15)	0.33268 (12)	0.0305 (5)
H13	0.9841	0.0775	0.3642	0.037*
C14	0.85730 (17)	-0.00988 (14)	0.34959 (12)	0.0288 (5)
H14	0.8834	-0.0455	0.3930	0.035*
C15	0.75943 (16)	-0.03152 (13)	0.30345 (11)	0.0227 (4)
H15	0.7183	-0.0818	0.3150	0.027*
C16	0.36809 (14)	0.16219 (11)	0.48003 (10)	0.0140 (3)
C17	0.41986 (15)	0.10464 (12)	0.53378 (11)	0.0192 (4)
H17	0.4048	0.0459	0.5280	0.023*
C18	0.49334 (17)	0.13345 (13)	0.59570 (11)	0.0233 (4)
H18	0.5288	0.0945	0.6328	0.028*
C19	0.51522 (16)	0.21932 (13)	0.60359 (11)	0.0236 (4)
H19	0.5656	0.2392	0.6461	0.028*
C20	0.46384 (17)	0.27609 (12)	0.54965 (12)	0.0235 (4)
H20	0.4792	0.3348	0.5553	0.028*
C21	0.39001 (15)	0.24778 (11)	0.48730 (11)	0.0188 (4)

supplementary materials

H21	0.3550	0.2867	0.4501	0.023*
C22	0.57825 (16)	0.26962 (12)	0.28800 (12)	0.0211 (4)
H22	0.5490	0.3033	0.2442	0.025*
C23	0.66049 (17)	0.30403 (13)	0.34058 (13)	0.0277 (5)
H23	0.6867	0.3603	0.3331	0.033*
C24	0.70418 (17)	0.25566 (13)	0.40424 (12)	0.0267 (4)
H24	0.7616	0.2776	0.4409	0.032*
C25	0.66268 (15)	0.17464 (12)	0.41350 (11)	0.0205 (4)
H25	0.6906	0.1400	0.4571	0.025*
C26	0.57989 (15)	0.14469 (11)	0.35850 (10)	0.0161 (4)
H26	0.5516	0.0889	0.3654	0.019*
C27	0.28759 (15)	0.04331 (11)	0.07836 (11)	0.0170 (4)
H27	0.3566	0.0548	0.0508	0.020*
C28	0.20283 (16)	-0.00357 (11)	0.03843 (11)	0.0197 (4)
H28	0.2130	-0.0225	-0.0158	0.024*
C29	0.10303 (16)	-0.02267 (12)	0.07827 (11)	0.0203 (4)
H29	0.0444	-0.0561	0.0526	0.024*
C30	0.09044 (16)	0.00798 (12)	0.15641 (12)	0.0205 (4)
H30	0.0227	-0.0039	0.1854	0.025*
C31	0.17797 (15)	0.05617 (11)	0.19157 (11)	0.0178 (4)
H31	0.1677	0.0782	0.2447	0.021*

Atomic displacement parameters (\AA^2)

	U^{11}	U^{22}	U^{33}	U^{12}	U^{13}	U^{23}
Ni	0.01215 (12)	0.01122 (12)	0.01132 (12)	0.00032 (8)	0.00009 (8)	0.00054 (8)
S1	0.0129 (2)	0.0136 (2)	0.0155 (2)	0.00219 (16)	0.00011 (16)	-0.00047 (16)
S2	0.0127 (2)	0.0124 (2)	0.0131 (2)	-0.00030 (16)	0.00112 (16)	-0.00026 (16)
O1	0.0209 (7)	0.0145 (6)	0.0266 (7)	0.0039 (5)	-0.0017 (5)	-0.0031 (5)
O2	0.0139 (6)	0.0156 (6)	0.0177 (6)	0.0009 (5)	0.0019 (5)	0.0016 (5)
O3	0.0159 (6)	0.0149 (6)	0.0191 (6)	0.0006 (5)	0.0013 (5)	-0.0028 (5)
O4	0.0165 (6)	0.0180 (6)	0.0180 (6)	-0.0024 (5)	0.0031 (5)	0.0015 (5)
N1	0.0128 (7)	0.0137 (7)	0.0113 (7)	0.0001 (6)	-0.0011 (6)	-0.0001 (6)
N2	0.0125 (7)	0.0146 (7)	0.0104 (7)	-0.0016 (6)	-0.0004 (5)	-0.0016 (6)
N3	0.0140 (7)	0.0162 (7)	0.0110 (7)	0.0011 (6)	0.0018 (6)	-0.0008 (6)
N4	0.0117 (7)	0.0145 (7)	0.0140 (7)	0.0014 (6)	0.0000 (6)	-0.0017 (6)
N5	0.0153 (7)	0.0167 (8)	0.0149 (7)	0.0040 (6)	0.0022 (6)	-0.0016 (6)
N6	0.0126 (7)	0.0154 (7)	0.0150 (7)	0.0002 (6)	0.0025 (6)	-0.0004 (6)
N7	0.0150 (7)	0.0122 (7)	0.0147 (7)	0.0027 (6)	-0.0009 (6)	-0.0003 (6)
C1	0.0129 (8)	0.0146 (8)	0.0116 (8)	0.0003 (7)	-0.0024 (6)	-0.0024 (7)
C2	0.0184 (9)	0.0177 (9)	0.0146 (9)	0.0042 (7)	0.0006 (7)	-0.0011 (7)
C3	0.0117 (8)	0.0134 (8)	0.0140 (8)	-0.0004 (7)	-0.0029 (7)	-0.0022 (7)
C4	0.0180 (9)	0.0134 (9)	0.0181 (9)	0.0013 (7)	-0.0025 (7)	0.0001 (7)
C5	0.0211 (9)	0.0150 (9)	0.0183 (9)	-0.0024 (7)	-0.0037 (7)	0.0042 (7)
C6	0.0171 (9)	0.0177 (9)	0.0138 (9)	-0.0024 (7)	-0.0005 (7)	0.0029 (7)
C7	0.0121 (8)	0.0169 (9)	0.0126 (8)	-0.0023 (7)	-0.0018 (7)	-0.0004 (7)
C8	0.0133 (8)	0.0167 (9)	0.0136 (9)	-0.0022 (7)	0.0002 (7)	0.0007 (7)
C9	0.0228 (10)	0.0223 (10)	0.0179 (9)	0.0012 (8)	0.0058 (8)	0.0013 (8)

C10	0.0131 (8)	0.0220 (9)	0.0156 (9)	0.0043 (7)	0.0018 (7)	-0.0046 (7)
C11	0.0159 (9)	0.0259 (10)	0.0207 (10)	0.0005 (8)	0.0034 (7)	-0.0033 (8)
C12	0.0169 (9)	0.0357 (12)	0.0301 (11)	-0.0047 (8)	0.0054 (8)	-0.0115 (9)
C13	0.0138 (9)	0.0548 (14)	0.0226 (10)	0.0055 (9)	-0.0012 (8)	-0.0169 (10)
C14	0.0240 (10)	0.0454 (13)	0.0168 (10)	0.0133 (10)	-0.0029 (8)	-0.0057 (9)
C15	0.0223 (10)	0.0274 (10)	0.0184 (10)	0.0060 (8)	0.0023 (8)	-0.0016 (8)
C16	0.0124 (8)	0.0177 (9)	0.0120 (8)	0.0006 (7)	0.0021 (6)	-0.0001 (7)
C17	0.0200 (9)	0.0176 (9)	0.0201 (10)	-0.0009 (7)	0.0014 (7)	0.0039 (7)
C18	0.0224 (10)	0.0284 (11)	0.0188 (10)	0.0011 (8)	-0.0038 (8)	0.0077 (8)
C19	0.0223 (10)	0.0307 (11)	0.0173 (9)	-0.0025 (8)	-0.0058 (8)	-0.0014 (8)
C20	0.0268 (10)	0.0180 (9)	0.0254 (10)	-0.0020 (8)	-0.0055 (8)	-0.0034 (8)
C21	0.0202 (9)	0.0170 (9)	0.0191 (9)	0.0018 (7)	-0.0028 (7)	0.0012 (7)
C22	0.0206 (9)	0.0197 (10)	0.0228 (10)	-0.0045 (8)	-0.0012 (8)	0.0045 (8)
C23	0.0260 (10)	0.0245 (10)	0.0324 (11)	-0.0115 (8)	-0.0042 (9)	0.0029 (9)
C24	0.0200 (10)	0.0345 (12)	0.0251 (11)	-0.0067 (9)	-0.0054 (8)	-0.0033 (9)
C25	0.0161 (9)	0.0290 (10)	0.0164 (9)	0.0024 (8)	-0.0012 (7)	0.0020 (8)
C26	0.0144 (9)	0.0183 (9)	0.0158 (9)	0.0021 (7)	0.0038 (7)	0.0000 (7)
C27	0.0188 (9)	0.0163 (9)	0.0160 (9)	0.0020 (7)	0.0019 (7)	-0.0006 (7)
C28	0.0234 (10)	0.0200 (9)	0.0156 (9)	0.0048 (8)	-0.0018 (7)	-0.0053 (7)
C29	0.0180 (9)	0.0174 (9)	0.0249 (10)	0.0018 (7)	-0.0062 (8)	-0.0059 (8)
C30	0.0152 (9)	0.0235 (10)	0.0227 (10)	0.0003 (8)	0.0012 (7)	-0.0034 (8)
C31	0.0184 (9)	0.0189 (9)	0.0163 (9)	0.0018 (7)	0.0015 (7)	-0.0036 (7)

Geometric parameters (\AA , $^\circ$)

Ni—N1	1.9959 (14)	C9—H9C	0.9800
Ni—N6	2.0910 (14)	C10—C11	1.387 (3)
Ni—N4	2.1145 (14)	C10—C15	1.392 (3)
Ni—N7	2.1152 (14)	C11—C12	1.391 (3)
Ni—N2	2.2111 (14)	C11—H11	0.9500
Ni—O2	2.3337 (12)	C12—C13	1.387 (3)
Ni—O3	2.7988 (12)	C12—H12	0.9500
S1—O1	1.4376 (13)	C13—C14	1.380 (3)
S1—O2	1.4624 (12)	C13—H13	0.9500
S1—N5	1.5984 (15)	C14—C15	1.388 (3)
S1—C10	1.7847 (18)	C14—H14	0.9500
S2—O4	1.4450 (12)	C15—H15	0.9500
S2—O3	1.4538 (12)	C16—C21	1.383 (3)
S2—N3	1.5911 (15)	C16—C17	1.391 (2)
S2—C16	1.7832 (17)	C17—C18	1.383 (3)
N1—C3	1.343 (2)	C17—H17	0.9500
N1—C7	1.346 (2)	C18—C19	1.388 (3)
N2—C1	1.303 (2)	C18—H18	0.9500
N2—N3	1.3816 (19)	C19—C20	1.383 (3)
N4—C8	1.298 (2)	C19—H19	0.9500
N4—N5	1.374 (2)	C20—C21	1.388 (3)
N6—C26	1.342 (2)	C20—H20	0.9500
N6—C22	1.344 (2)	C21—H21	0.9500
N7—C31	1.345 (2)	C22—C23	1.378 (3)

supplementary materials

N7—C27	1.348 (2)	C22—H22	0.9500
C1—C3	1.471 (2)	C23—C24	1.379 (3)
C1—C2	1.494 (2)	C23—H23	0.9500
C2—H2A	0.9800	C24—C25	1.380 (3)
C2—H2B	0.9800	C24—H24	0.9500
C2—H2C	0.9800	C25—C26	1.381 (3)
C3—C4	1.395 (2)	C25—H25	0.9500
C4—C5	1.386 (3)	C26—H26	0.9500
C4—H4	0.9500	C27—C28	1.381 (3)
C5—C6	1.388 (3)	C27—H27	0.9500
C5—H5	0.9500	C28—C29	1.381 (3)
C6—C7	1.391 (2)	C28—H28	0.9500
C6—H6	0.9500	C29—C30	1.384 (3)
C7—C8	1.469 (2)	C29—H29	0.9500
C8—C9	1.488 (2)	C30—C31	1.382 (3)
C9—H9A	0.9800	C30—H30	0.9500
C9—H9B	0.9800	C31—H31	0.9500
N1—Ni—N6	96.42 (6)	N4—C8—C7	114.16 (15)
N1—Ni—N4	77.12 (6)	N4—C8—C9	123.23 (16)
N6—Ni—N4	93.96 (5)	C7—C8—C9	122.58 (15)
N1—Ni—N7	94.63 (6)	C8—C9—H9A	109.5
N6—Ni—N7	168.17 (6)	C8—C9—H9B	109.5
N4—Ni—N7	92.61 (5)	H9A—C9—H9B	109.5
N1—Ni—N2	75.77 (5)	C8—C9—H9C	109.5
N6—Ni—N2	87.04 (5)	H9A—C9—H9C	109.5
N4—Ni—N2	152.81 (5)	H9B—C9—H9C	109.5
N7—Ni—N2	91.59 (5)	C11—C10—C15	120.81 (17)
N1—Ni—O2	150.64 (5)	C11—C10—S1	121.21 (14)
N6—Ni—O2	86.02 (5)	C15—C10—S1	117.93 (14)
N4—Ni—O2	73.52 (5)	C10—C11—C12	119.19 (18)
N7—Ni—O2	86.42 (5)	C10—C11—H11	120.4
N2—Ni—O2	133.58 (5)	C12—C11—H11	120.4
N1—Ni—O3	142.34 (5)	C13—C12—C11	120.2 (2)
N6—Ni—O3	83.25 (5)	C13—C12—H12	119.9
N4—Ni—O3	140.54 (5)	C11—C12—H12	119.9
N7—Ni—O3	85.42 (5)	C14—C13—C12	120.28 (18)
N2—Ni—O3	66.59 (4)	C14—C13—H13	119.9
O2—Ni—O3	67.02 (4)	C12—C13—H13	119.9
O1—S1—O2	116.53 (7)	C13—C14—C15	120.23 (19)
O1—S1—N5	108.70 (8)	C13—C14—H14	119.9
O2—S1—N5	112.31 (7)	C15—C14—H14	119.9
O1—S1—C10	106.14 (8)	C14—C15—C10	119.33 (19)
O2—S1—C10	105.81 (8)	C14—C15—H15	120.3
N5—S1—C10	106.69 (8)	C10—C15—H15	120.3
O4—S2—O3	116.46 (7)	C21—C16—C17	120.82 (16)
O4—S2—N3	106.68 (7)	C21—C16—S2	121.46 (13)
O3—S2—N3	114.18 (7)	C17—C16—S2	117.71 (14)
O4—S2—C16	104.86 (7)	C18—C17—C16	119.59 (17)
O3—S2—C16	106.23 (7)	C18—C17—H17	120.2

N3—S2—C16	107.75 (8)	C16—C17—H17	120.2
S1—O2—Ni	113.69 (7)	C17—C18—C19	119.87 (17)
S2—O3—Ni	108.55 (6)	C17—C18—H18	120.1
C3—N1—C7	121.51 (15)	C19—C18—H18	120.1
C3—N1—Ni	120.33 (11)	C20—C19—C18	120.18 (18)
C7—N1—Ni	117.91 (11)	C20—C19—H19	119.9
C1—N2—N3	113.63 (14)	C18—C19—H19	119.9
C1—N2—Ni	113.80 (11)	C19—C20—C21	120.38 (18)
N3—N2—Ni	132.44 (11)	C19—C20—H20	119.8
N2—N3—S2	113.45 (11)	C21—C20—H20	119.8
C8—N4—N5	116.85 (14)	C16—C21—C20	119.16 (17)
C8—N4—Ni	115.81 (11)	C16—C21—H21	120.4
N5—N4—Ni	126.47 (11)	C20—C21—H21	120.4
N4—N5—S1	109.62 (11)	N6—C22—C23	123.16 (17)
C26—N6—C22	117.09 (15)	N6—C22—H22	118.4
C26—N6—Ni	120.89 (12)	C23—C22—H22	118.4
C22—N6—Ni	122.00 (12)	C22—C23—C24	119.05 (18)
C31—N7—C27	116.84 (15)	C22—C23—H23	120.5
C31—N7—Ni	120.77 (12)	C24—C23—H23	120.5
C27—N7—Ni	122.36 (12)	C23—C24—C25	118.58 (18)
N2—C1—C3	115.57 (15)	C23—C24—H24	120.7
N2—C1—C2	122.58 (15)	C25—C24—H24	120.7
C3—C1—C2	121.85 (15)	C24—C25—C26	118.99 (17)
C1—C2—H2A	109.5	C24—C25—H25	120.5
C1—C2—H2B	109.5	C26—C25—H25	120.5
H2A—C2—H2B	109.5	N6—C26—C25	123.11 (17)
C1—C2—H2C	109.5	N6—C26—H26	118.4
H2A—C2—H2C	109.5	C25—C26—H26	118.4
H2B—C2—H2C	109.5	N7—C27—C28	123.12 (17)
N1—C3—C4	120.33 (15)	N7—C27—H27	118.4
N1—C3—C1	114.38 (15)	C28—C27—H27	118.4
C4—C3—C1	125.27 (15)	C27—C28—C29	119.21 (17)
C5—C4—C3	118.51 (16)	C27—C28—H28	120.4
C5—C4—H4	120.7	C29—C28—H28	120.4
C3—C4—H4	120.7	C28—C29—C30	118.49 (17)
C4—C5—C6	120.69 (16)	C28—C29—H29	120.8
C4—C5—H5	119.7	C30—C29—H29	120.8
C6—C5—H5	119.7	C31—C30—C29	118.88 (17)
C5—C6—C7	118.14 (16)	C31—C30—H30	120.6
C5—C6—H6	120.9	C29—C30—H30	120.6
C7—C6—H6	120.9	N7—C31—C30	123.42 (16)
N1—C7—C6	120.81 (16)	N7—C31—H31	118.3
N1—C7—C8	114.53 (15)	C30—C31—H31	118.3
C6—C7—C8	124.65 (15)		
O1—S1—O2—Ni	-145.14 (7)	O3—Ni—N7—C31	33.11 (13)
N5—S1—O2—Ni	-18.82 (10)	N1—Ni—N7—C27	72.98 (14)
C10—S1—O2—Ni	97.20 (8)	N6—Ni—N7—C27	-128.0 (3)
N1—Ni—O2—S1	8.70 (14)	N4—Ni—N7—C27	-4.30 (14)
N6—Ni—O2—S1	-87.33 (8)	N2—Ni—N7—C27	148.83 (13)

supplementary materials

N4—Ni—O2—S1	7.99 (7)	O2—Ni—N7—C27	-77.61 (13)
N7—Ni—O2—S1	101.78 (8)	O3—Ni—N7—C27	-144.81 (13)
N2—Ni—O2—S1	-169.43 (6)	N3—N2—C1—C3	-177.23 (13)
O3—Ni—O2—S1	-171.68 (8)	Ni—N2—C1—C3	-0.80 (18)
O4—S2—O3—Ni	145.87 (6)	N3—N2—C1—C2	3.3 (2)
N3—S2—O3—Ni	20.78 (9)	Ni—N2—C1—C2	179.72 (12)
C16—S2—O3—Ni	-97.82 (7)	C7—N1—C3—C4	0.0 (2)
N1—Ni—O3—S2	-12.32 (11)	Ni—N1—C3—C4	174.16 (12)
N6—Ni—O3—S2	79.45 (7)	C7—N1—C3—C1	-178.66 (15)
N4—Ni—O3—S2	167.49 (7)	Ni—N1—C3—C1	-4.52 (19)
N7—Ni—O3—S2	-103.97 (7)	N2—C1—C3—N1	3.3 (2)
N2—Ni—O3—S2	-10.24 (6)	C2—C1—C3—N1	-177.22 (15)
O2—Ni—O3—S2	167.98 (8)	N2—C1—C3—C4	-175.31 (16)
N6—Ni—N1—C3	-82.17 (13)	C2—C1—C3—C4	4.2 (3)
N4—Ni—N1—C3	-174.78 (13)	N1—C3—C4—C5	0.0 (3)
N7—Ni—N1—C3	93.59 (13)	C1—C3—C4—C5	178.56 (16)
N2—Ni—N1—C3	3.12 (12)	C3—C4—C5—C6	0.3 (3)
O2—Ni—N1—C3	-175.48 (10)	C4—C5—C6—C7	-0.6 (3)
O3—Ni—N1—C3	5.10 (17)	C3—N1—C7—C6	-0.4 (2)
N6—Ni—N1—C7	92.18 (12)	Ni—N1—C7—C6	-174.65 (12)
N4—Ni—N1—C7	-0.43 (12)	C3—N1—C7—C8	178.48 (14)
N7—Ni—N1—C7	-92.05 (12)	Ni—N1—C7—C8	4.20 (19)
N2—Ni—N1—C7	177.47 (13)	C5—C6—C7—N1	0.6 (3)
O2—Ni—N1—C7	-1.13 (19)	C5—C6—C7—C8	-178.08 (16)
O3—Ni—N1—C7	179.45 (10)	N5—N4—C8—C7	177.13 (14)
N1—Ni—N2—C1	-1.11 (11)	Ni—N4—C8—C7	7.13 (19)
N6—Ni—N2—C1	96.28 (12)	N5—N4—C8—C9	-1.0 (2)
N4—Ni—N2—C1	3.37 (19)	Ni—N4—C8—C9	-171.04 (13)
N7—Ni—N2—C1	-95.48 (12)	N1—C7—C8—N4	-7.5 (2)
O2—Ni—N2—C1	177.94 (10)	C6—C7—C8—N4	171.34 (16)
O3—Ni—N2—C1	-179.80 (13)	N1—C7—C8—C9	170.72 (16)
N1—Ni—N2—N3	174.46 (15)	C6—C7—C8—C9	-10.5 (3)
N6—Ni—N2—N3	-88.15 (14)	O1—S1—C10—C11	130.91 (15)
N4—Ni—N2—N3	178.94 (12)	O2—S1—C10—C11	-104.67 (15)
N7—Ni—N2—N3	80.09 (14)	N5—S1—C10—C11	15.11 (17)
O2—Ni—N2—N3	-6.49 (17)	O1—S1—C10—C15	-51.50 (16)
O3—Ni—N2—N3	-4.23 (13)	O2—S1—C10—C15	72.92 (15)
C1—N2—N3—S2	-167.49 (12)	N5—S1—C10—C15	-167.30 (14)
Ni—N2—N3—S2	16.94 (18)	C15—C10—C11—C12	-0.2 (3)
O4—S2—N3—N2	-155.04 (11)	S1—C10—C11—C12	177.28 (14)
O3—S2—N3—N2	-24.92 (14)	C10—C11—C12—C13	0.7 (3)
C16—S2—N3—N2	92.82 (12)	C11—C12—C13—C14	-0.8 (3)
N1—Ni—N4—C8	-3.93 (12)	C12—C13—C14—C15	0.5 (3)
N6—Ni—N4—C8	-99.62 (13)	C13—C14—C15—C10	0.0 (3)
N7—Ni—N4—C8	90.22 (13)	C11—C10—C15—C14	-0.1 (3)
N2—Ni—N4—C8	-8.4 (2)	S1—C10—C15—C14	-177.72 (14)
O2—Ni—N4—C8	175.71 (13)	O4—S2—C16—C21	-112.94 (15)
O3—Ni—N4—C8	176.19 (10)	O3—S2—C16—C21	123.19 (15)
N1—Ni—N4—N5	-172.83 (14)	N3—S2—C16—C21	0.43 (17)

N6—Ni—N4—N5	91.48 (13)	O4—S2—C16—C17	65.61 (15)
N7—Ni—N4—N5	-78.68 (13)	O3—S2—C16—C17	-58.26 (15)
N2—Ni—N4—N5	-177.28 (11)	N3—S2—C16—C17	178.98 (13)
O2—Ni—N4—N5	6.81 (12)	C21—C16—C17—C18	0.6 (3)
O3—Ni—N4—N5	7.29 (17)	S2—C16—C17—C18	-177.96 (14)
C8—N4—N5—S1	172.91 (12)	C16—C17—C18—C19	-0.2 (3)
Ni—N4—N5—S1	-18.29 (16)	C17—C18—C19—C20	-0.1 (3)
O1—S1—N5—N4	153.45 (11)	C18—C19—C20—C21	0.1 (3)
O2—S1—N5—N4	23.01 (13)	C17—C16—C21—C20	-0.6 (3)
C10—S1—N5—N4	-92.48 (12)	S2—C16—C21—C20	177.89 (14)
N1—Ni—N6—C26	176.50 (13)	C19—C20—C21—C16	0.3 (3)
N4—Ni—N6—C26	-106.03 (13)	C26—N6—C22—C23	0.4 (3)
N7—Ni—N6—C26	17.5 (3)	Ni—N6—C22—C23	178.89 (15)
N2—Ni—N6—C26	101.19 (13)	N6—C22—C23—C24	0.3 (3)
O2—Ni—N6—C26	-32.88 (13)	C22—C23—C24—C25	-0.8 (3)
O3—Ni—N6—C26	34.42 (12)	C23—C24—C25—C26	0.5 (3)
N1—Ni—N6—C22	-1.92 (14)	C22—N6—C26—C25	-0.7 (2)
N4—Ni—N6—C22	75.54 (14)	Ni—N6—C26—C25	-179.16 (13)
N7—Ni—N6—C22	-160.9 (2)	C24—C25—C26—N6	0.2 (3)
N2—Ni—N6—C22	-77.23 (14)	C31—N7—C27—C28	-0.2 (3)
O2—Ni—N6—C22	148.70 (14)	Ni—N7—C27—C28	177.80 (13)
O3—Ni—N6—C22	-144.00 (14)	N7—C27—C28—C29	-1.6 (3)
N1—Ni—N7—C31	-109.10 (13)	C27—C28—C29—C30	1.7 (3)
N6—Ni—N7—C31	49.9 (3)	C28—C29—C30—C31	-0.2 (3)
N4—Ni—N7—C31	173.62 (13)	C27—N7—C31—C30	1.8 (3)
N2—Ni—N7—C31	-33.25 (13)	Ni—N7—C31—C30	-176.19 (14)
O2—Ni—N7—C31	100.31 (13)	C29—C30—C31—N7	-1.7 (3)

supplementary materials

Fig. 1

