

Praseodymium(III) sulfate hydroxide, $\text{Pr}(\text{SO}_4)(\text{OH})$

Xiao-Juan Wang and Jian-Wen Cheng*

Zhejiang Key Laboratory for Reactive Chemistry on Solid Surfaces, Institute of Physical Chemistry, Zhejiang Normal University, Jinhua, Zhejiang 321004, People's Republic of China
Correspondence e-mail: jwcheng@zjnu.cn

Received 22 December 2010; accepted 5 January 2011

Key indicators: single-crystal X-ray study; $T = 293$ K; mean $\sigma(\text{S}-\text{O}) = 0.005$ Å; R factor = 0.033; wR factor = 0.080; data-to-parameter ratio = 12.9.

The title compound, $\text{Pr}(\text{SO}_4)(\text{OH})$, obtained under hydrothermal conditions, consists of Pr^{III} ions coordinated by nine O atoms from six sulfate groups and three hydroxide anions. The bridging mode of the O atoms results in the formation of a three-dimensional framework, stabilized by two $\text{O}-\text{H}\cdots\text{O}$ hydrogen-bonding interactions.

Related literature

Lanthanide sulfate hydroxides exhibit a variety of architectures, see: Xu *et al.* (2007); Zhang *et al.* (2004). For related structures, see: Yang *et al.* (2005); Ding *et al.* (2006); Zhang *et al.* (2004); Zhang & Lu (2008).

Experimental

Crystal data

$\text{Pr}(\text{SO}_4)(\text{OH})$	$V = 370.8$ (3) Å ³
$M_r = 253.98$	$Z = 4$
Monoclinic, $P2_1/n$	Mo $K\alpha$ radiation
$a = 4.4891$ (18) Å	$\mu = 13.59$ mm ⁻¹
$b = 12.484$ (5) Å	$T = 293$ K
$c = 6.894$ (3) Å	$0.20 \times 0.10 \times 0.10$ mm
$\beta = 106.310$ (7)°	

Data collection

Bruker APEXII CCD diffractometer	2849 measured reflections
Absorption correction: multi-scan (<i>SADABS</i> ; Sheldrick, 1996)	840 independent reflections
$T_{\min} = 0.213$, $T_{\max} = 0.257$	813 reflections with $I > 2\sigma(I)$
	$R_{\text{int}} = 0.053$

Refinement

$R[F^2 > 2\sigma(F^2)] = 0.033$	65 parameters
$wR(F^2) = 0.080$	H-atom parameters constrained
$S = 1.09$	$\Delta\rho_{\max} = 1.73$ e Å ⁻³
840 reflections	$\Delta\rho_{\min} = -2.15$ e Å ⁻³

Table 1
Hydrogen-bond geometry (Å, °).

$D-\text{H}\cdots A$	$D-\text{H}$	$\text{H}\cdots A$	$D\cdots A$	$D-\text{H}\cdots A$
O5—H5A···O3 ⁱ	0.85	2.20	2.630 (7)	111
O5—H5A···O2 ⁱⁱ	0.85	2.31	3.082 (7)	152

Symmetry codes: (i) $-x, -y + 2, -z$; (ii) $-x + \frac{1}{2}, y + \frac{1}{2}, -z + \frac{1}{2}$.

Data collection: *APEX2* (Bruker, 2006); cell refinement: *SAINT* (Bruker, 2006); data reduction: *SAINT*; program(s) used to solve structure: *SHELXS97* (Sheldrick, 2008); program(s) used to refine structure: *SHELXL97* (Sheldrick, 2008); molecular graphics: *SHELXTL* (Sheldrick, 2008); software used to prepare material for publication: *SHELXTL*.

Supplementary data and figures for this paper are available from the IUCr electronic archives (Reference: MG2113).

References

- Bruker (2006). *APEX2* and *SAINT*. Bruker AXS Inc., Madison, Wisconsin, USA.
Ding, S.-H., Sun, X.-C., Zhu, Y.-L., Chen, Q. & Xu, Y. (2006). *Acta Cryst. E62*, i269–i271.
Sheldrick, G. M. (1996). *SADABS*. University of Göttingen, Germany.
Sheldrick, G. M. (2008). *Acta Cryst. A64*, 112–122.
Xu, Y., Ding, S. & Zheng, X. (2007). *J. Solid State Chem.* **180**, 2020–2025.
Yang, Y., Zhu, L.-H., Zeng, M.-H. & Feng, X.-L. (2005). *Acta Cryst. E61*, i41–i43.
Zhang, T. & Lu, J. (2008). *Acta Cryst. E64*, i49.
Zhang, Q., Lu, C., Yang, W., Chen, S. & Yu, Y. (2004). *Inorg. Chem. Commun.* **7**, 889–892.

supplementary materials

Acta Cryst. (2011). E67, i12 [doi:10.1107/S1600536811000298]

Praseodymium(III) sulfate hydroxide, Pr(SO₄)(OH)

X.-J. Wang and J.-W. Cheng

Comment

Lanthanide sulfate hydroxides exhibit a variety of architectures (Xu *et al.*, 2007; Zhang *et al.*, 2004). We report here the compound Pr(SO₄)(OH), which is isostructural to *Ln*(SO₄)(OH) (*Ln* = La, Ce, Eu, Nd) (Zhang *et al.*, 2004; Yang *et al.*, 2005; Ding *et al.*, 2006; Zhang *et al.*, 2008). The Pr^{III} ion is coordinated in a distorted tricapped trigonal prismatic geometry by the oxygen atoms from six sulfate groups and three hydroxide anions (Fig. 1). All oxygen atoms of the sulfate groups take part in the coordination. The S atom makes four S—O—La linkages through two 2-coordinated oxygen atoms [S—O—La] and two 3-coordinated oxygen atoms [S—(μ₃-O)—La₂]. The oxygen atoms of the hydroxide groups are four-coordinate, [HO—μ₃-La₃], linking three different Pr ions. The bridging mode of the oxygen atoms results in a three-dimensional framework, with the H atom of hydroxide anions forming weak O—H···O hydrogen bonds with two O atoms of sulfate groups (Fig. 2).

Experimental

A mixture of Pr(NO₃)₃·6H₂O (0.25 mmol, 0.1088 g), MnSO₄·H₂O (0.2 mmol, 0.0338 g), and H₂O (15 mL) was sealed in a 25-mL Teflon-lined stainless steel reactor and heated at 443 K for 72 h, and then cooled to room temperature over 3 days. Light-green prismatic crystals were obtained (yield: 32% based on Pr(NO₃)₃·6H₂O).

Refinement

The oxygen-bound H-atoms were located in the difference Fourier map and refined with the O—H distance restrained to 0.85 Å [$U_{\text{iso}}(\text{H}) = 1.2U_{\text{eq}}(\text{O})$].

Figures




Fig. 1. Coordination of Pr in Pr(SO₄)(OH). Displacement ellipsoids are drawn at the 30% probability level. [Symmetry codes: (i) x-1/2, -y+3/2, z+1/2; (ii) -x+1, -y+2, -z+1; (iii) x-1, y, z; (iv) -x, -y+2, -z+1; (v) -x+1, -y+2, -z; (vi) -x, -y+2, -z; (vii) x, y, z+1.]




Fig. 2. Three-dimensional network in Pr(SO₄)(OH).

supplementary materials

Praseodymium(III) sulfate hydroxide

Crystal data

Pr(SO ₄)(OH)	<i>F</i> (000) = 464
<i>M_r</i> = 253.98	<i>D_x</i> = 4.550 Mg m ⁻³
Monoclinic, <i>P2₁/n</i>	Mo <i>Kα</i> radiation, λ = 0.71073 Å
Hall symbol: -P 2yn	Cell parameters from 1066 reflections
<i>a</i> = 4.4891 (18) Å	θ = 3.3–27.4°
<i>b</i> = 12.484 (5) Å	μ = 13.59 mm ⁻¹
<i>c</i> = 6.894 (3) Å	<i>T</i> = 293 K
β = 106.310 (7)°	Prism, light green
<i>V</i> = 370.8 (3) Å ³	0.20 × 0.10 × 0.10 mm
<i>Z</i> = 4	

Data collection

Bruker APEXII CCD diffractometer	840 independent reflections
Radiation source: fine-focus sealed tube graphite	813 reflections with $I > 2\sigma(I)$
ω scans	$R_{\text{int}} = 0.053$
Absorption correction: multi-scan (<i>SADABS</i> ; Sheldrick, 1996)	$\theta_{\text{max}} = 27.4^\circ$, $\theta_{\text{min}} = 3.3^\circ$
$T_{\text{min}} = 0.213$, $T_{\text{max}} = 0.257$	$h = -5 \rightarrow 5$
2849 measured reflections	$k = -14 \rightarrow 16$
	$l = -8 \rightarrow 8$

Refinement

Refinement on F^2	Secondary atom site location: difference Fourier map
Least-squares matrix: full	Hydrogen site location: inferred from neighbouring sites
$R[F^2 > 2\sigma(F^2)] = 0.033$	H-atom parameters constrained
$wR(F^2) = 0.080$	$w = 1/[\sigma^2(F_o^2) + (0.0348P)^2 + 1.2539P]$
$S = 1.09$	where $P = (F_o^2 + 2F_c^2)/3$
840 reflections	$(\Delta/\sigma)_{\text{max}} = 0.001$
65 parameters	$\Delta\rho_{\text{max}} = 1.73 \text{ e \AA}^{-3}$
0 restraints	$\Delta\rho_{\text{min}} = -2.15 \text{ e \AA}^{-3}$
Primary atom site location: structure-invariant direct methods	Extinction correction: <i>SHELXL97</i> (Sheldrick, 2008), $F_c^* = kF_c[1 + 0.001xF_c^2\lambda^3/\sin(2\theta)]^{1/4}$
	Extinction coefficient: 0.0303 (17)

Special details

Geometry. All e.s.d.'s (except the e.s.d. in the dihedral angle between two l.s. planes) are estimated using the full covariance matrix. The cell e.s.d.'s are taken into account individually in the estimation of e.s.d.'s in distances, angles and torsion angles; correlations between e.s.d.'s in cell parameters are only used when they are defined by crystal symmetry. An approximate (isotropic) treatment of cell e.s.d.'s is used for estimating e.s.d.'s involving l.s. planes.

Refinement. Refinement of F^2 against ALL reflections. The weighted R -factor wR and goodness of fit S are based on F^2 , conventional R -factors R are based on F , with F set to zero for negative F^2 . The threshold expression of $F^2 > \sigma(F^2)$ is used only for calculating R -factors(gt) etc. and is not relevant to the choice of reflections for refinement. R -factors based on F^2 are statistically about twice as large as those based on F , and R -factors based on ALL data will be even larger.

Fractional atomic coordinates and isotropic or equivalent isotropic displacement parameters (\AA^2)

	x	y	z	$U_{\text{iso}}^*/U_{\text{eq}}$
Pr	0.14215 (8)	0.93511 (2)	0.30120 (5)	0.0103 (2)
S	0.4863 (3)	0.85448 (11)	-0.1115 (2)	0.0100 (3)
O1	0.3690 (11)	0.8345 (4)	0.0615 (6)	0.0156 (9)
O2	0.5908 (12)	0.7551 (4)	-0.1798 (7)	0.0189 (10)
O3	0.2507 (11)	0.9045 (4)	-0.2785 (7)	0.0179 (10)
O4	0.7557 (12)	0.9298 (3)	-0.0482 (8)	0.0137 (10)
O5	0.3035 (11)	1.0859 (4)	0.5390 (7)	0.0141 (9)
H5A	0.1434	1.1193	0.5488	0.021*

Atomic displacement parameters (\AA^2)

	U^{11}	U^{22}	U^{33}	U^{12}	U^{13}	U^{23}
Pr	0.0129 (3)	0.0104 (3)	0.0083 (3)	0.00025 (10)	0.00418 (19)	-0.00100 (9)
S	0.0118 (7)	0.0098 (7)	0.0091 (7)	-0.0002 (5)	0.0041 (6)	0.0002 (5)
O1	0.020 (2)	0.020 (2)	0.012 (2)	0.002 (2)	0.0142 (19)	0.0010 (17)
O2	0.027 (2)	0.014 (2)	0.020 (2)	0.001 (2)	0.011 (2)	-0.0016 (17)
O3	0.017 (2)	0.023 (2)	0.015 (2)	0.005 (2)	0.0060 (19)	0.0030 (19)
O4	0.013 (2)	0.013 (2)	0.016 (2)	-0.0039 (15)	0.005 (2)	-0.0022 (14)
O5	0.014 (2)	0.017 (2)	0.012 (2)	0.0037 (18)	0.0044 (18)	-0.0042 (17)

Geometric parameters (\AA , $^\circ$)

Pr—O2 ⁱ	2.393 (5)	S—O1	1.455 (5)
Pr—O5 ⁱⁱ	2.436 (5)	S—O3	1.466 (5)
Pr—O5	2.468 (5)	S—O4	1.497 (5)
Pr—O1	2.508 (4)	O2—Pr ^{viii}	2.393 (5)
Pr—O4 ⁱⁱⁱ	2.543 (5)	O3—Pr ^{vi}	2.643 (5)
Pr—O5 ^{iv}	2.554 (5)	O3—Pr ^{ix}	2.826 (5)
Pr—O4 ^v	2.558 (5)	O4—Pr ^x	2.543 (5)
Pr—O3 ^{vi}	2.643 (5)	O4—Pr ^v	2.558 (5)
Pr—O3 ^{vii}	2.826 (5)	O5—Pr ⁱⁱ	2.436 (5)

supplementary materials

Pr—Pr ^{iv}	3.7056 (12)	O5—Pr ^{iv}	2.554 (5)
Pr—Pr ⁱⁱ	3.9388 (12)	O5—H5A	0.8500
S—O2	1.450 (5)		
O2 ⁱ —Pr—O5 ⁱⁱ	88.30 (16)	O5—Pr—Pr ^{iv}	43.35 (12)
O2 ⁱ —Pr—O5	137.33 (16)	O1—Pr—Pr ^{iv}	173.83 (10)
O5 ⁱⁱ —Pr—O5	73.13 (18)	O4 ⁱⁱⁱ —Pr—Pr ^{iv}	115.28 (12)
O2 ⁱ —Pr—O1	66.58 (17)	O5 ^{iv} —Pr—Pr ^{iv}	41.55 (10)
O5 ⁱⁱ —Pr—O1	72.04 (15)	O4 ^v —Pr—Pr ^{iv}	112.38 (11)
O5—Pr—O1	136.21 (16)	O3 ^{vi} —Pr—Pr ^{iv}	49.45 (10)
O2 ⁱ —Pr—O4 ⁱⁱⁱ	88.59 (15)	O3 ^{vii} —Pr—Pr ^{iv}	45.31 (10)
O5 ⁱⁱ —Pr—O4 ⁱⁱⁱ	139.79 (17)	O2 ⁱ —Pr—Pr ⁱⁱ	116.25 (12)
O5—Pr—O4 ⁱⁱⁱ	130.10 (14)	O5 ⁱⁱ —Pr—Pr ⁱⁱ	36.83 (11)
O1—Pr—O4 ⁱⁱⁱ	70.01 (15)	O5—Pr—Pr ⁱⁱ	36.29 (11)
O2 ⁱ —Pr—O5 ^{iv}	77.01 (17)	O1—Pr—Pr ⁱⁱ	105.16 (11)
O5 ⁱⁱ —Pr—O5 ^{iv}	128.20 (19)	O4 ⁱⁱⁱ —Pr—Pr ⁱⁱ	151.15 (10)
O5—Pr—O5 ^{iv}	84.90 (16)	O5 ^{iv} —Pr—Pr ⁱⁱ	109.08 (11)
O1—Pr—O5 ^{iv}	138.17 (15)	O4 ^v —Pr—Pr ⁱⁱ	86.32 (11)
O4 ⁱⁱⁱ —Pr—O5 ^{iv}	89.84 (16)	O3 ^{vi} —Pr—Pr ⁱⁱ	97.46 (11)
O2 ⁱ —Pr—O4 ^v	136.90 (16)	O3 ^{vii} —Pr—Pr ⁱⁱ	57.99 (11)
O5 ⁱⁱ —Pr—O4 ^v	91.33 (16)	Pr ^{iv} —Pr—Pr ⁱⁱ	71.85 (3)
O5—Pr—O4 ^v	82.80 (16)	O2—S—O1	110.1 (3)
O1—Pr—O4 ^v	72.38 (15)	O2—S—O3	109.7 (3)
O4 ⁱⁱⁱ —Pr—O4 ^v	64.96 (17)	O1—S—O3	111.7 (3)
O5 ^{iv} —Pr—O4 ^v	132.35 (15)	O2—S—O4	108.9 (3)
O2 ⁱ —Pr—O3 ^{vi}	132.98 (17)	O1—S—O4	108.5 (3)
O5 ⁱⁱ —Pr—O3 ^{vi}	133.47 (15)	O3—S—O4	107.9 (3)
O5—Pr—O3 ^{vi}	61.84 (16)	S—O1—Pr	139.7 (3)
O1—Pr—O3 ^{vi}	136.71 (14)	S—O2—Pr ^{viii}	155.7 (3)
O4 ⁱⁱⁱ —Pr—O3 ^{vi}	72.40 (15)	S—O3—Pr ^{vi}	133.7 (3)
O5 ^{iv} —Pr—O3 ^{vi}	60.84 (15)	S—O3—Pr ^{ix}	137.8 (3)
O4 ^v —Pr—O3 ^{vi}	72.83 (16)	Pr ^{vi} —O3—Pr ^{ix}	85.24 (13)
O2 ⁱ —Pr—O3 ^{vii}	78.53 (16)	S—O4—Pr ^x	125.0 (3)
O5 ⁱⁱ —Pr—O3 ^{vii}	70.23 (15)	S—O4—Pr ^y	120.0 (3)
O5—Pr—O3 ^{vii}	59.19 (16)	Pr ^x —O4—Pr ^y	115.04 (17)
O1—Pr—O3 ^{vii}	128.53 (14)	Pr ⁱⁱ —O5—Pr	106.87 (18)
O4 ⁱⁱⁱ —Pr—O3 ^{vii}	147.45 (16)	Pr ⁱⁱ —O5—Pr ^{iv}	128.20 (19)
O5 ^{iv} —Pr—O3 ^{vii}	58.29 (15)	Pr—O5—Pr ^{iv}	95.10 (16)
O4 ^v —Pr—O3 ^{vii}	140.86 (15)	Pr ⁱⁱ —O5—H5A	142.8
O3 ^{vi} —Pr—O3 ^{vii}	94.76 (13)	Pr—O5—H5A	109.3
O2 ⁱ —Pr—Pr ^{iv}	109.56 (13)	Pr ^{iv} —O5—H5A	40.0
O5 ⁱⁱ —Pr—Pr ^{iv}	103.47 (11)		

O2—S—O1—Pr	179.4 (4)	O1—S—O4—Pr ^x	33.7 (4)
O3—S—O1—Pr	-58.5 (5)	O3—S—O4—Pr ^x	154.9 (3)
O4—S—O1—Pr	60.3 (5)	O2—S—O4—Pr ^v	93.2 (3)
O2 ⁱ —Pr—O1—S	167.8 (5)	O1—S—O4—Pr ^v	-147.0 (3)
O5 ⁱⁱ —Pr—O1—S	-96.1 (4)	O3—S—O4—Pr ^v	-25.8 (4)
O5—Pr—O1—S	-57.3 (5)	O2 ⁱ —Pr—O5—Pr ⁱⁱ	68.0 (3)
O4 ⁱⁱⁱ —Pr—O1—S	70.4 (4)	O5 ⁱⁱ —Pr—O5—Pr ⁱⁱ	0.0
O5 ^{iv} —Pr—O1—S	136.1 (4)	O1—Pr—O5—Pr ⁱⁱ	-38.5 (3)
O4 ^v —Pr—O1—S	1.3 (4)	O4 ⁱⁱⁱ —Pr—O5—Pr ⁱⁱ	-141.99 (18)
O3 ^{vi} —Pr—O1—S	39.2 (5)	O5 ^{iv} —Pr—O5—Pr ⁱⁱ	132.5 (2)
O3 ^{vii} —Pr—O1—S	-140.6 (4)	O4 ^v —Pr—O5—Pr ⁱⁱ	-93.60 (19)
Pr ^{iv} —Pr—O1—S	-140.0 (7)	O3 ^{vi} —Pr—O5—Pr ⁱⁱ	-167.9 (2)
Pr ⁱⁱ —Pr—O1—S	-79.7 (4)	O3 ^{vii} —Pr—O5—Pr ⁱⁱ	76.67 (19)
O1—S—O2—Pr ^{viii}	13.5 (8)	Pr ^{iv} —Pr—O5—Pr ⁱⁱ	132.5 (2)
O3—S—O2—Pr ^{viii}	-109.8 (7)	O2 ⁱ —Pr—O5—Pr ^{iv}	-64.5 (3)
O4—S—O2—Pr ^{viii}	132.3 (7)	O5 ⁱⁱ —Pr—O5—Pr ^{iv}	-132.5 (2)
O2—S—O3—Pr ^{vi}	168.4 (4)	O1—Pr—O5—Pr ^{iv}	-171.07 (15)
O1—S—O3—Pr ^{vi}	46.0 (5)	O4 ⁱⁱⁱ —Pr—O5—Pr ^{iv}	85.5 (2)
O4—S—O3—Pr ^{vi}	-73.1 (4)	O5 ^{iv} —Pr—O5—Pr ^{iv}	0.0
O2—S—O3—Pr ^{ix}	-39.4 (5)	O4 ^v —Pr—O5—Pr ^{iv}	133.87 (16)
O1—S—O3—Pr ^{ix}	-161.8 (4)	O3 ^{vi} —Pr—O5—Pr ^{iv}	59.53 (16)
O4—S—O3—Pr ^{ix}	79.1 (5)	O3 ^{vii} —Pr—O5—Pr ^{iv}	-55.86 (15)
O2—S—O4—Pr ^x	-86.1 (4)	Pr ⁱⁱ —Pr—O5—Pr ^{iv}	-132.5 (2)

Symmetry codes: (i) $x-1/2, -y+3/2, z+1/2$; (ii) $-x+1, -y+2, -z+1$; (iii) $x-1, y, z$; (iv) $-x, -y+2, -z+1$; (v) $-x+1, -y+2, -z$; (vi) $-x, -y+2, -z$; (vii) $x, y, z+1$; (viii) $x+1/2, -y+3/2, z-1/2$; (ix) $x, y, z-1$; (x) $x+1, y, z$.

Hydrogen-bond geometry (\AA , $^\circ$)

$D\text{—H}\cdots A$	$D\text{—H}$	$H\cdots A$	$D\cdots A$	$D\text{—H}\cdots A$
O5—H5A \cdots O3 ^{vi}	0.85	2.20	2.630 (7)	111
O5—H5A \cdots O2 ^{xi}	0.85	2.31	3.082 (7)	152

Symmetry codes: (vi) $-x, -y+2, -z$; (xi) $-x+1/2, y+1/2, -z+1/2$.

supplementary materials

Fig. 1




Fig. 2

