


Acta Cryst. (1954). 7, 772

A sanidine from Ordovician bentonite beds. By ANN MARIE BYSTRÖM, *Geological Survey of Sweden, Stockholm 50, Sweden*

(Received 21 July 1954)

During an investigation of the Ordovician bentonite beds at Kinnekulle, Sweden (Byström, 1954), there was isolated among the phenocrysts an unweathered glassy sanidine. It was considered to be of such interest to find an absolutely fresh sanidine in these old layers that the mineral was isolated and subjected to a more detailed study, which gave the following results:

Chemical data (Composition by weight):



Specific gravity: 2.57.

Optical data:

$$\begin{array}{l} n_\alpha = 1.519, \quad n_\beta = 1.523 \text{ (calc.)}, \quad n_\gamma = 1.524; \\ 2V_\alpha = \sim 15^\circ; \quad \alpha \wedge a = 3^\circ; \quad \beta = b. \end{array}$$

A powder photograph taken with monochromatized copper radiation gave:

$$\begin{array}{l} a = 8.48 \pm 0.02, \quad b = 12.97 \pm 0.05, \quad c = 7.16 \pm 0.02 \text{ kX.}; \\ \beta = 116.1^\circ. \end{array}$$

Weissenberg photographs of the $h0l$ and $0kl$ zones were also taken, and the intensities were compared with those found by Cole, Sörum & Kennard (1949) for a sanidinized orthoclase. As far as could be judged from the visually estimated intensities there were no remarkable discrepancies. There was no sign of perthitization in the crystals.

References

- BYSTRÖM, A. M. (1954). *Nature, Lond.* **173**, 783.
 COLE, W. F., SÖRUM, H. & KENNARD, O. (1949). *Acta Cryst.* **2**, 280.

Acta Cryst. (1954). 7, 772

Aging of crushed silicon and germanium crystals. By S. B. BRODY,* *Brooklyn College, Brooklyn, N. Y., U.S.A.*

(Received 27 July 1953 and in revised form 29 March 1954)

Studies of the disorientated surface layer on abraded crystals show that when different crystals are subjected to the same treatment, both the depth (Gay, Hirsch & Kellar, 1952) and the time of formation (D'Eustachio & Brody, 1945) of the disorientated layer have a considerable range of values, depending on the crystalline material used. To make a start on the general problem of correlation of the depth, degree of disorientation and speed of formation of the layer, with physical crystal properties, a study of the substances isomorphous with diamond appears promising. Silicon and germanium have been investigated for the occurrence of time-dependent changes in the X-ray diagrams of freshly crushed crystals. Germanium does not show these changes, but silicon does.

As described in the earlier paper (D'Eustachio & Brody, 1945), aging changes occur in the powder diagram of a coarse powder during the first hour or so after crushing as follows: new spots appear which are at first strong and not well resolved; later they become weaker and sharper; sometimes, if the combination of intensity and exposure time is fortunate, they disappear.

The method of preparation of materials was to crush several single crystals in a mortar, sift the coarse powder in a sieve, selecting a sample of the size wanted, and mounting it in the camera by means of a suitable adhesive. Powders of satisfactory coarseness were obtained from that fraction of the grind which passed through a 270 mesh screen but not through a 375, during one minute of vigorous shaking. Electron-microscope pictures showed that a large number of smaller particles failed to fall through the smaller mesh, but this inefficient method of screening was retained because of its speed. Four-minute

exposures were taken, at intervals ranging from two minutes after the crushing was started, to several days. Preliminary runs were made with a back-reflection focusing camera. In order to follow the history of individual spots, a defocusing arrangement was preferred.

This arrangement is a forward transmission picture. The sample-to-film distance was 3 cm.; unfiltered copper radiation was used; a flat film holder, divided into 60° sectors, was rotated in a counterclockwise direction, as viewed from the sample, between exposures. In Fig. 1(a) is shown a typical run on germanium. In the overall view, the first picture shows good register with the rest. Most of the spots are present on all exposures. Fig. 1(b), which is an enlargement of the area enclosed in a rectangle, shows a group of spots which are typical of germanium. Three of the four are about constant in intensity and resolution, even after 23 hr. This is the predominant feature of germanium runs. Also common in the germanium runs are spots like the encircled group, enlarged in Fig. 1(c), showing streaks, which may be radial or tangential, and which show some recovery. In Fig. 1(d) is shown a rarity in the germanium runs: the appearance and subsequent sharpening and weakening of a spot not initially present. There are two such in the figure: one in the upper right corner and one at the middle of the left side.

The results for silicon are more typical of the aging changes found in quartz and calcite. In Fig. 2(a) is shown the first, second and last of a run consisting of five exposures. The history of several sets of spots is shown in the enlargement in the next figure. Unlike the germanium pictures, here the first exposure shows poor register compared to subsequent ones. Very many spots appear in later exposures which cannot be found on the first (Fig. 2(c, d, e)). Many of these get sharper and weaker

* On leave at Department of Physics, University of Connecticut, Storrs, Conn., U.S.A.