

Bonds within the chain are formed by inserting one end of a stud into an atom, locking the stud in place by inserting a locking rod as shown in Fig. 2, then inserting the other end of the stud in the second atom, pressing the two atoms firmly together so as to bring the keyway in the stud in line with the hole in the second atom, and finally by pushing in the second locking rod. The distance between the two keyways is designed so as to require a slight compression of the atoms at the interface when the bond is made. The resulting friction between the surfaces of adjacent atoms prevents too much freedom of rotation around the bonds, so that the chain will tend to retain desired configurations. Bonds in the chain can be broken by poking the locking rods out of the atoms with a separate rod of the same diameter or with an appropriate tool.

It may be noted that the carbon atom described here for constructing a peptide chain can also be used for building a linear carbon-carbon chain.

We are indebted to Mr Delmer D. Dill for his cooperation and excellent workmanship in the construction of the models. The development of these models was supported by grant No. G-1265 from the National Science Foundation.

References

- COREY, R. B. & CASLER, L. (1958). *Acta Cryst.* **11**, 448.
 COREY, R. B. & PAULING, L. (1953). *Rev. Sci. Instrum.* **24**, 621.

Acta Cryst. (1959). **12**, 257

The lattice constant of strontium nitrate, $\text{Sr}(\text{NO}_3)_2$. By V. T. DESHPANDE, D. B. SIRDESHMUKH and V. M. MUDHOLKER, *Physics Department, College of Science, Osmania University, Hyderabad-7 India*

(Received 17 September 1958 and in revised form 14 November 1958)

An accurate determination of the lattice constant of strontium nitrate has been made, following an observation by one of the authors (Deshpande, 1955) that the value reported in literature is too high. The value reported by Vegard (1922) is 7.81 Å and that reported by Jaeger & Van Melle (1928) is 7.80 Å. Deshpande (1955) gives a value of 7.7794 ± 0.0003 Å at 20° C. in terms of $\text{Cu } K\alpha_2 = 1.54434$ Å and $\text{Cu } K\alpha_1 = 1.54050$ Å.

In the present investigation the lattice parameter was determined from powder photographs, obtained with a Debye-Scherrer camera of 11.46 cm. diameter. The photographs gave eight sharp and well resolved $\alpha_1\alpha_2$ doublets in the high-angle region. Filtered copper radiation was used and the values of the wavelengths were the same as given above. Pure salt supplied by Merck was recrystallized and used for the preparation of the specimens. Photographs were taken with different samples and measurements were made independently by the authors. The values of the lattice parameter obtained from the various reflections on a film were extrapolated to $\theta = 90^\circ$, using Nelson & Riley's (1945) error function. The best straight line was fitted by the least-squares method.

Since, with the particular camera used, it was not possible to measure the specimen temperature directly, the lattice constant of NaCl was used as an indicator of temperature.

Powder photographs of sodium chloride were taken under identical conditions and the temperature of the specimen was estimated from the results so obtained. As the temperature of the specimens varied from film to film, the values of the lattice parameter were reduced to 20° C., the value of the coefficient of thermal expansion used being $30 \times 10^{-6} \text{ }^\circ\text{C}^{-1}$ (Deshpande, 1955). The mean of the values thus obtained is 7.7798 Å. The maximum deviation of the individual values from the mean is 0.0002 Å. This value is found to be in good agreement with the one obtained by Deshpande (1955). The data for some of the films are given in Table 1.

Table 1. *Lattice constant of $\text{Sr}(\text{NO}_3)_2$*

Film No.	Temperature (°C.)	Extrapolated a	a at 20° C.
8	36	7.7833 Å	7.7796 Å
9	36	7.7835	7.7798
23	32	7.7828	7.7800
27	33	7.7830	7.7800
40	31	7.7825	7.7799

Mean of several values of a 7.7798 ± 0.0002 Å.

The density of the substance was also calculated from the relation $\rho = Mn/(NV)$, where M is the molecular weight, n is the number of molecules in the unit cell, N is Avogadro's number and V is the volume of the unit cell. Taking $M = 211.65$ and $N = 6.02385 \times 10^{23}$, after Straumanis (1949), the present value of a gives the density as 2.985. The experimental value reported in *International Critical Tables* is 2.986 g.cm.⁻³ at 20° C. Vegard reports the calculated density as 2.930 g.cm.⁻³. It is obvious from these figures that the present value of a is more accurate than that of Vegard.

Thanks are due to the Osmania University for the award of Research Fellowships to two of the authors (D. B. S. and V. M. M.).

References

- DESHPANDE, V. T. (1955). Ph.D. Thesis, Osmania University.
 JAEGER, F. M. & VAN MELLE, F. A. (1928). *Proc. Acad. Sci. Amsterdam*, **31**, 651.
 NELSON, J. B. & RILEY, D. P. (1945). *Proc. Phys. Soc.* **57**, 160.
 STRAUMANIS, M. E. (1949). *Acta Cryst.* **2**, 82.
 VEGARD, L. (1922). *Z. Phys.* **9**, 395.