Selective Promotion of the Catalytic Ethene Homologation Reaction by KOH on an MoO_x/SiO₂ Catalyst

Katsumi Tanaka* and Ken-ichi Tanakab

- a Research Institute for Catalysis, Hokkaido University, Kita-ku, Sapporo 060, Japan
- b The Institute for Solid State Physics, The University of Tokyo, 7-22-1 Roppongi, Minato-ku, Tokyo 106, Japan

Ethene homologation activity on a reduced MoO_x/SiO_2 catalyst was enhanced more than 10 times by a modification of the catalyst with KOH, while activity and selectivity in alkene metathesis were unaffected.

Since the discovery of the unique reaction of ethene to form propene by Rooney *et al.*, ¹ homologation reactions of alkenes² and alkanes³ have attracted much interest because these reactions are presumed to occur *via* metal carbene and metallacyclobutane intermediates which are the most plausible species for alkene metathesis reactions. ⁴ In this paper, we report that addition of potassium to an MoO_x/SiO₂ catalyst greatly enhanced ethene homologation reaction activity without any change in alkene metathesis activity or hyperfine selectivities.

Kiesel gel 60 silica was immersed in an aqueous solution of ammonium molybdate and dried in air at 120 °C overnight to obtain a loading of 2.8 mol % MoO₃/SiO₂. KOH-doped silica (from aqueous KOH, calcined in air at 600 °C for 6 h) was used to prepare MoO₃/K–SiO₂ (containing 2.8 mol % of MoO₃ and 0.28 mol % of K), by heating slowly from room temperature to 500 °C *in vacuo*. Catalysts A, B, and C were then obtained as follows. Catalyst A was MoO_x/SiO₂ treated with H₂ at 500 °C for 1 h. Catalyst B was MoO_x/SiO₂ obtained by the reoxidation of catalyst A with a 1:1 mixture of N₂O and H₂ at 200 °C for 1 h. Catalyst C was MoO_x/K–SiO₂ reduced with H₂ at 500 °C for 1 h. The catalysts were finally evacuated at 500 °C for 1 h. The catalyst treatment and the reactions were carried out in a closed glass circulation system with a volume of 260 ml.

When a mixture of $[^{12}C_2]$ - and $[^{13}C_2]$ -ethene was contacted with the catalysts A—C, the metathesis reaction giving $[^{13}C_1]$ -ethene and the homologation reaction forming propene were found to occur (Figure 1). An induction period was observed for the homologation reaction, but not for the

metathesis reaction. It is noteworthy that the ethene homologation reaction was considerably increased by an addition of potassium (catalyst C), but the metathesis reaction was not influenced at all. After 180 min of the reaction with ethene containing 9.1% [\(^{13}C_1\)]- and 42.3% [\(^{13}C_2\)]-ethene on catalyst C, propene comprised 12.5% of the total gas, with isotopic distribution [\(^{13}C_0\)], 17.9%; [\(^{13}C_1\)], 40.3%; [\(^{13}C_2\)], 32.7%; and [\(^{13}C_3\)], 9.1%. If propene is formed by the reaction of either \(^{12}CH_2\) or \(^{13}CH_2\) with ethene, approximately equal amounts of \(^{13}C\)-isotopomers of propene would be formed provided there is no isotope effect. This was not the case, and intramolecular hydrogen shift reactions as well as degenerate metathesis of the propene are presumed to be responsible for the \(^{13}C\) distribution obtained.

Table 1 shows the results of the metathesis reaction of a 1:1 mixture of $[^{12}C_3]$ - and $[^{13}C_3]$ -propene on catalysts A and C. Turnover frequency was evaluated by assuming that all Mo atoms participate in the formation of ethene. One can evaluate the relative contributions of degenerate and produc-

Table 1. Turnover frequencies (T.F.), *cis/trans* ratios of but-2-ene formed, and V_D/V_P ratios (see text) in the metathesis reaction of a 1:1 mixture of $[^{12}C_3]$ - and $[^{13}C_3]$ -propene at room temperature.

Catalysta	T.F.b	cis/transe	$V_{ m D}/V_{ m P}$
A	4.5×10^{-4}	0.5	7.6
C	5.0×10^{-4}	0.5	8.1

 a Catalyst, 20 mg; total pressure 6.9 mmHg. b Rate of formation of ethene (molecules per Mo atom s $^{-1}$). c Equilibrium value is 0.3.




Figure 1. The reaction of a 1:1 mixture of [${}^{12}C_2$]- and [${}^{13}C_2$]-ethene at room temperature. $\bigcirc \bullet$: catalyst, A, 0.5 g; total ethene, 10.2 mmHg, $\square \blacksquare$: catalyst B, 0.5 g; 14.5 mmHg, $\triangle \blacktriangle$: catalyst C, 0.5 g; 14.6 mmHg.

tive metathesis $(V_{\rm D}/V_{\rm P})$ by comparing the amount of $[^{13}{\rm C_1}]$ -and $[^{13}{\rm C_2}]$ -propene with the amount of ethene and but-2-ene. Since $V_{\rm D}/V_{\rm P}$ ratios are almost equal on catalysts A (7.6) and C (8.1), and the turnover frequencies on these two catalysts are similar, we concluded that potassium has no effect on the alkene metathesis reaction.

In conclusion, addition of potassium to MoO_x/SiO_2 has a marked influence on alkene homologation reactions but no effect on metathesis reactions, an important finding with respect to reactivity and selectivity.

Received, 29th August 1984; Com. 1239

References

- 1 P. P. O'Neil and J. J. Rooney, J. Am. Chem. Soc., 1972, 94, 4383.
- F. Hughes, B. Besson, and J. M. Basset, J. Chem. Soc., Chem. Commun., 1980, 719; T. Yamaguchi, S. Nakamura, and K. Tanabe, ibid., 1982, 621; R. A. Strehlow and E. C. Douglas, ibid., 1983, 259; M. Anpo and Y. Kubokawa, J. Catal., 1982, 75, 204.
- 3 C. O'Donohoe, J. K. A. Clarke, and J. J. Rooney, *J. Chem. Soc.*, *Faraday Trans. 1*, 1980, **76**, 345.
- 4 K. J. Ivin, 'Olefin Metathesis,' Academic Press, London, 1983; J. J. Rooney and A. Stewart, in 'Catalysis' (Specialist Periodical Report), vol. 1, ed. C. Kemball, The Chemical Society, 1977, p. 277.