

Triplet ground state ($S = 1$) pegylated bis(aminoxyl) diradical: synthesis and the effect of water on magnetic properties†

Gaëlle Spagnol, Kouichi Shiraishi, Suchada Rajca and Andrzej Rajca*

Received (in Cambridge, UK) 9th June 2005, Accepted 26th August 2005

First published as an Advance Article on the web 16th September 2005

DOI: 10.1039/b508094k

The synthesis and magnetic characterization of pegylated bis(aminoxyl) diradical with an $S = 1$ ground state are presented, revealing water-induced changes in the molecular conformation and magnetic properties.


Triplet ground state ($S = 1$) organic diradicals with strong ferromagnetic coupling are widely used as building blocks for organic and organometallic magnets.^{1–3} Only a few diradicals are both stable at ambient conditions and possess ferromagnetic coupling of such strength that the singlet–triplet energy gap ($2J$) is far greater than the thermal energy at room temperature.^{1,3} Nonadditive properties of such strongly-coupled $S = 1$ diradicals, which are enhanced compared to those of two independent (or weakly coupled) $S = 1/2$ radicals, have not been significantly explored beyond organic magnetism. In particular, understanding of the effect of water on structure and magnetic properties of $S = 1$ diradicals (and high-spin polyradicals) is important for their applications in biological media.⁴

In biological and polymer sciences, organic radicals, especially aminoxyls, are intensively studied as spin labels, contrast agents for magnetic resonance imaging (MRI), antioxidants, and mediators for controlled radical polymerization.^{5–9} Numerous synthetic approaches to water soluble aminoxyls have been reported,⁹ to facilitate biological applications and polymerization in water. Recently, water soluble bis(aminoxyls) and oligo(aminoxyls) were investigated in biological sensing and magnetic imaging,^{6–8,10} however, only weakly-coupled bis(aminoxyls) and oligo(aminoxyls), which may be viewed as ensembles of independent $S = 1/2$ radicals at room temperature (above ~ 1 K), were prepared and studied.

One of the specific areas, in which water-soluble and strongly-coupled $S = 1$ diradicals would be of great interest, includes contrast agents for MRI, currently dominated by the complexes of $S = 7/2$ Gd^{III} and other paramagnetic metal ions.¹¹ In conjunction with the favorable *in vivo* properties of aminoxyls and theoretically predicted proportionality of relaxivity to $S(S + 1)$,^{12,13} bis(aminoxyls) and oligo(aminoxyls) with $S > 1/2$ at room temperature provide novel insight into the design and understanding of contrast agents for MRI.^{6,7}


In this paper, we describe the synthesis of polyethylene glycol (PEG) functionalized (pegylated) $S = 1$ diradical **1** and $S = 1/2$

monoradical **2**, and their magnetic characterization in various media, including water.



The synthesis of diradical **1** is outlined in Scheme 1.† The Li–Br exchange on bromobenzene **3**,¹⁴ followed by the addition of pegylated ketone **4**, provides alcohol **5**. After etherification of **5**, the ether **6** is treated with TBAF, to give dihydroxylamine **7**. Oxidation of **7** with Ag_2O yields diradical **1**. An analogous synthetic route, starting from **8**¹⁵ (Scheme 1), provides monoradical **2** in overall yield of 33% for four steps.† This synthetic approach should be readily applicable to the preparation of pegylated radicals.

The EPR spectra of 1 mM **1** in toluene, ethanol, water–ethanol (1 : 2), and water–glycerol (2 : 1) at 140 or 135 K show the expected dipolar patterns for $S = 1$ states, including a moderately intense half-field signal. The spectra in toluene, obtained after slow cooling from room temperature to 140 K, are assigned to a single $S = 1$ diradical, with zero-field splitting (zfs) parameters,



Scheme 1 Reagents and conditions: (a) *n*-BuLi (1.2 equiv.), THF, -78 °C to room temperature (65%); (b) NaH (5 equiv.), MeI (5 equiv.), THF, 0 °C to 45 °C (90%); (c) TBAF (4.6 equiv.), THF, room temperature (95%); (d) Ag_2O (10 equiv.), $CHCl_3$, room temperature (44%).

Department of Chemistry, University of Nebraska, Lincoln, Nebraska 68588-0304, USA. E-mail: arajca1@unl.edu; Fax: +1 402 472 9402; Tel: +1 402 472 9196

† Electronic supplementary information (ESI) available: Experimental section, including 1H NMR spectra (synthetic intermediates and the aminoxyls) and selected EPR spectra of the aminoxyls. See <http://dx.doi.org/10.1039/b508094k>

$|D/hc| = 1.24 \times 10^{-2} \text{ cm}^{-1}$ and $|E/hc| = 1.13 \times 10^{-3} \text{ cm}^{-1}$ (Fig. 1). For rapidly cooled water-containing solutions of **1** (water-ethanol and water-glycerol), the EPR spectra may be assigned to two $S = 1$ diradicals, presumably conformers. The spectral simulations of the $\Delta m_s = 1$ regions show that the major and the minor $S = 1$ diradicals have relatively smaller ($\sim 1.2 \times 10^{-2} \text{ cm}^{-1}$) and larger ($\sim 1.7 \times 10^{-2} \text{ cm}^{-1}$) values of $|D/hc|$, respectively. For **1** in water-ethanol (1 : 2), the relative content of the $|D/hc| \approx 1.7 \times 10^{-2} \text{ cm}^{-1}$ diradical is about 10% vs. 30% in water-glycerol (2 : 1). These results suggest that **1** in water at room temperature may exist as two conformers (diastereomers) with different dihedral angles between the nitroxide moieties and 1,3-phenylene.¹⁶ Such conformers would possess, in principle, different singlet-triplet energy gaps ($2J$).

The $S = 1$ ground state and the value of $2J$ were determined by SQUID magnetometry. Plots of χT vs. T (χ , molar magnetic susceptibility) for neat diradical **1** show a maximum of $\chi T_{\text{max}} = 0.91 \text{ emu K mol}^{-1}$ near 100 K, with significant drop-offs at both higher and lower temperatures (Fig. 2). An excellent numerical fit to these data is obtained with three variable parameters (eqn (1S), ESI†): singlet-triplet energy gap ($2J/k = 650 \text{ K}$ or $2J = 1.3 \text{ kcal mol}^{-1}$), mean-field parameter for intermolecular interactions ($\theta = -2.2 \text{ K}$), and mass factor ($w = 0.93$).¹⁷ These results indicate that diradical **1** possesses the $S = 1$ ground state. However, the singlet-triplet energy gap of **1** exceeds RT at room temperature by a factor of 2–3 only, leading




Fig. 1 X-Band EPR spectra for diradical **1** in toluene (plots A for $\Delta m_s = 1$ and B for $\Delta m_s = 2$) and EtOH-water (2 : 1, plots C for $\Delta m_s = 1$ and D for $\Delta m_s = 2$) at 135–140 K. In plots A and C, the simulations correspond to one $S = 1$ diradical and a mixture of two $S = 1$ diradicals, respectively. The center lines, most likely corresponding to $S = 1/2$ monoradical impurities, are not simulated. Parameters for the simulations are shown in Fig. 11S–13S (ESI).†




Fig. 2 Plots of χT vs. T for diradical **1**. For the plot at magnetic field $H = 500 \text{ Oe}$, the temperature range is $T = 1.8\text{--}60 \text{ K}$; for all other plots, $T = 1.8\text{--}290 \text{ K}$. The solid line shows an example of numerical fit to the experimental data at $H = 30000 \text{ Oe}$, using eqn (1S) (ESI).†

to significant population of the singlet excited state at room temperature. The value of $2J/k$ may be affected by out-of-plane twisting of the aminoxyl moieties, caused by the sterically large PEG-based substituent.¹⁶

For 17–25 mM **1** in D_2O , qualitatively similar χT vs. T plots are obtained. Notably, intermolecular antiferromagnetic interactions remain significant ($\theta \approx -2 \text{ K}$), suggesting aggregation of **1** in water. Partial population of the singlet excited state at room temperature is also consistent with the values of magnetic susceptibility obtained from ^1H NMR using the Evans method: $\chi T = 0.81 \pm 0.03 \text{ emu K mol}^{-1}$ for 15–21 mM **1** in $\text{H}_2\text{O}\text{--}\text{D}_2\text{O}$ ($\sim 1 : 1$) at 295–298 K is obtained.¹⁸ Notably, a ^1H NMR resonance for the *tert*-butyl groups of the aminoxyl moieties appears at -6.9 ppm in D_2O vs. at -2.3 ppm in CDCl_3 . The upfield ^1H chemical shift in D_2O suggests increased localization of spin density at the aminoxyl moieties, as observed in sterically hindered bis(aminoxyls), in which aminoxyl moieties are twisted out of the plane of the 1,3-phenylene.¹⁹ This out-of-plane twisting is also consistent with the EPR spectra of **1** in water-containing matrices showing the presence of a conformer with relatively large value of $|D/hc| \approx 1.7 \times 10^{-2} \text{ cm}^{-1}$.²⁰

We postulate that strong solvation of the PEG moiety of **1** in the presence of water increases its effective volume, to increase the twisting of the aminoxyls out of the plane of the 1,3-phenylene. This in turn, weakens the exchange coupling between the aminoxyls, thus decreasing the singlet-triplet energy gap for **1** in water.

Longitudinal relaxation times (T_1) of protons in water were measured at 200 MHz, as a function of the concentration of **1** and **2** at 298 K. Relaxivities are obtained from the slopes of $1/T_1$ vs. concentration plots (Fig. 3). Relaxivities of 0.20 and $0.14 \text{ s}^{-1} \text{ mM}^{-1}$ are obtained for **1** and **2**, respectively.²¹ Therefore, the experimental relaxivity per aminoxyl moiety is significantly lower in diradical **1** vs. monoradical **2**. This is in contrast to the higher relaxivity per aminoxyl in an $S = 1$ diradical predicted from the relative values of $S(S + 1) = 0.75, 1.5,$ and 2.0 for an $S = 1/2$ monoradical, a weakly coupled diradical, and an $S = 1$ diradical, respectively. This is consistent with the weakened exchange coupling for **1** in water but it implies that other factors decrease




Fig. 3 Plots of $1/T_1$ (for protons of water) vs. mM concentration of diradical **1** and monoradical **2** in H₂O or phosphate buffer (50 mM, pH 7.2).

the relaxivity in **1** as well. Aggregation of **1** would affect both rotational correlation time and access of water (the exchange rate of water). Furthermore, the electronic T_1 of **1** may be lowered, due to modulation of zfs and/or $2J$.¹³

In summary, a versatile synthetic route to pegylated aminoxylys is developed, making available water-soluble high-spin diradicals for biologically related studies. Furthermore, discovery of the water-induced changes in molecular conformation and magnetic properties in the present work suggests that structures with constrained, planarized conformations may be required to obtain high-spin diradicals with $2J \gg RT$ in water at room temperature. The synthesis of such diradicals and their assembly into well-defined, water accessible, high-symmetry structures with negligible zfs is in progress in this laboratory.

This research was supported by the National Science Foundation (grant No. CHE-0414936), including the purchase of the Electron Paramagnetic Resonance (EPR) spectrometer (grant No. DMR-0216788). We thank Sara Basiaga and Dr. Joseph Dumais for their help with the NMR spectroscopy. We thank Sumit Mukherjee and Kausik Das for their help with the synthesis.

Notes and references

‡ For details of synthesis and characterization of compounds **1**, **2** and their synthetic intermediates (e.g., **4–6** for **1**), see ESI.

- (a) *Magnetic Properties of Organic Materials*, ed. P. M. Lahti, Marcel Dekker, New York, 1999; (b) *Molecular Magnetism, New Magnetic Materials*, ed. K. Itoh and M. Kinoshita, Gordon and Breach, Amsterdam, 2000; (c) A. Rajca, *Chem. Rev.*, 1994, **94**, 871–893.
- (a) A. Rajca, J. Wongsriratanakul and S. Rajca, *Science*, 2001, **294**, 1503–1505; (b) S. Rajca, A. Rajca, J. Wongsriratanakul, P. Butler and S. Choi, *J. Am. Chem. Soc.*, 2004, **126**, 6972–6986; (c) A. Rajca, J. Wongsriratanakul and S. Rajca, *J. Am. Chem. Soc.*, 2004, **126**, 6608–6626; (d) A. Rajca, J. Wongsriratanakul, S. Rajca and R. L. Cerny,

Chem. Eur. J., 2004, **10**, 3144–3157; (e) A. Rajca, K. Shiraishi, M. Vale, H. Han and S. Rajca, *J. Am. Chem. Soc.*, 2005, **127**, 9014–9020.

- (a) H. Iwamura, K. Inoue and N. Koga, *New J. Chem.*, 1998, 201–210; (b) M. Tanaka, K. Matsuda, T. Itoh and H. Iwamura, *J. Am. Chem. Soc.*, 1998, **120**, 7168–7173.
- The effect of organic matrices on exchange coupling: D. A. Shultz, A. K. Boal and G. T. Farmer, *J. Am. Chem. Soc.*, 1997, **119**, 3846–3847.
- (a) *Bioactive Spin Labels*, ed. R. I. Zhdanov, Springer-Verlag, Berlin, 1992; (b) W. L. Hubbell, D. S. Cafiso and C. Altenbach, *Nature Struct. Biol.*, 2000, **7**, 735–739; (c) L. J. Berliner, S. S. Eaton and G. R. Eaton, *Distance Measurements in Biological Systems by EPR*, in *Magnetic Resonance*, Kluwer Academic/Plenum, New York, 2000, vol. 19.
- (a) C. S. Winalski, S. Shortkroff, R. V. Mulkern, E. Schneider and G. M. Rosen, *Magn. Reson. Med.*, 2002, **48**, 965–972; (b) G. M. Rosen, E. Schneider, S. Shortkroff, P. Tsai and C. S. Winalski, *J. Chem. Soc., Perkin Trans 1*, 2002, 2663–2667.
- (a) A. J. Maliakal, N. J. Turro, A. W. Bosman, J. Cornel and E. W. Meijer, *J. Phys. Chem. A*, 2003, **107**, 8467–8475; (b) G. Francese, F. A. Dunand, C. Loosli, A. E. Merbach and S. Decurtins, *Magn. Reson. Chem.*, 2003, **41**, 81–83.
- A. T. Yordanov, K. Yamada, M. C. Krishna, J. B. Mitchell, E. Woller, M. Cloninger and M. W. Brechbiel, *Angew. Chem., Int. Ed.*, 2001, **40**, 2690–2692.
- (a) L. Marx and A. Rassat, *Chem. Commun.*, 2002, 632–633; (b) W. Huang, B. Charleux, R. Chiarelli, L. Marx, A. Rassat and J.-P. Vairon, *Macromol. Chem. Phys.*, 2002, **203**, 1715–1723.
- G. M. Rosen, S. Porasuphatana, P. Tsai, N. P. Ambulos, V. E. Galtsev, K. Ichikawa and H. J. Halpern, *Macromolecules*, 2003, **36**, 1021–1027.
- J. B. Livramento, E. Toth, A. Sour, A. Borel, A. E. Merbach and R. Ruloff, *Angew. Chem., Int. Ed.*, 2005, **44**, 1480–1484.
- Toxicity of aminoxylys: S. Sosnovsky, *J. Pharm. Sci.*, 1992, **81**, 496–499.
- L. Banci, I. Bertini and C. Luchinat, *Nuclear and Electron Relaxation*, VCH, Weinheim, 1991.
- F. Kanno, K. Inoue, N. Koga and H. Iwamura, *J. Phys. Chem.*, 1993, **97**, 13267–13272.
- K. Inoue and H. Iwamura, *Angew. Chem., Int. Ed. Engl.*, 1995, **34**, 927–928.
- M. Dvolutzky, R. Chiarelli and A. Rassat, *Angew. Chem., Int. Ed. Engl.*, 1992, **31**, 180–181.
- (a) The actual singlet–triplet energy gap may be somewhat smaller than the fitted value of $2J/k = 650$ K, because of the possible slight over-correction for diamagnetism using point-by-point correction and full values of Pascal constants for **1** (ESI†); (b) The mass parameter w accounts mainly for incomplete mass transfer of **1** to the SQUID sample tube.
- The values of χT measured by the Evans method are relatively less accurate, e.g., due to strong interaction of water with the diradical or incomplete mass transfer of **1**.
- A. Rajca, K. Lu, S. Rajca and C. R. Ross, *Chem. Commun.*, 1999, 1249–1250. The aminoxylys moieties in the 4,6-bis(trifluoromethyl)-*N,N'*-di-*tert*-butyl-1,3-phenylenebis(aminoxylys) diradical are expected to be more sterically hindered (significantly twisted out-of-plane) than in **1**; consequently, thermal population of the singlet excited state already above 40 K was detectable by EPR spectroscopy, the value of $|D/hc| = 1.5 \times 10^{-2} \text{ cm}^{-1}$ was relatively large, and the ¹H resonance corresponding to the *tert*-butyl groups of the aminoxylys moieties at –16 ppm was relatively upfield shifted.
- A. Rajca, S. Utamapanya and J. Xu, *J. Am. Chem. Soc.*, 1991, **113**, 9235–9241.
- (a) Relaxivity of 3-carboxyl-2,2,5,5-tetramethylpyrrolidine-1-oxyl under identical conditions is $0.15 \text{ s}^{-1} \text{ mM}^{-1}$; (b) Relaxivities of piperidine and pyrrolidine $S = \frac{1}{2}$ aminoxylys: P. Vallet, Y. Van Haverbeke, P. A. Bonnet, G. Subra, J.-P. Chapat and R. N. Muller, *Magn. Reson. Med.*, 1994, **32**, 11–15.