

## Papers

## C6

## Neodymium Catalyzed Diolefin Polymerization

A. CARBONARO\* and M. BRUZZONE

*ASSORENI, Polymer Research Laboratories, San Donato Milanese, 20097, Italy*

After about thirty years since the Ziegler-Natta discoveries, the multifaceted aspects of stereo-specific catalysis have been hardly clarified, notwithstanding the large amount of research devoted to this subject.

In the same time, extremely active catalysts and simplified processes have been pointed out, particularly in the field of monoolefins. As far as conjugated diolefins are concerned, U [1] and Nd [2] based catalysts have been developed in the last years, besides to more conventional systems based on Ti, V, Co and Ni.

A general characteristic of the quoted catalyst systems is the remarkable amount of alkyl-Al as cocatalyst, required for achieving the best behaviour. Therefore an insight on the reasons of such a large stoichiometric excess is both of theoretical and economical relevance. The possibility of obtaining catalytic complexes with Al/Co = 2 for instance, was early described [3].

Nd catalyst behaves similarly to other systems but shows unusual peculiarities such as: low chain transfer activity with diolefin monomer as well as with monoolefins (ethylene, propene, 1-butene), hydrogen and  $\text{Et}_2\text{Zn}$ ; very high sensitivity to cyclopentadiene; low sensitivity to CO; poisoning with alkyl-Mg and  $\text{NaAlEt}_2\text{H}_2$ ; partial deactivation with hydrocarbons; capability of homo and copolymerizing both butadiene and isoprene to high *cis* polymers, surprising thermal stability. A Nd catalyst is composed of: i) Nd compound, halogen containing or not, able to react with; ii) alkyl-Al unhalogenated compound and iii) metallic halide or organic halogen-derivative, when halogen is absent in i).

The halogen function can be partially displayed by water. By carrying out the catalyst preparation from different Nd and Al compounds and from different halogen donors in hexane and/ or in THF solution, variously active mixtures are obtained. In some cases complexes containing Nd, Al, Cl and alkyl groups in simple ratios to each other can be isolated which are able to polymerize butadiene.

The activity of the above mentioned complexes changes with composition and in some cases is

comparable with that of the corresponding homogeneous system in which Al/Nd ratio is extremely higher.

- 1 M. Bruzzone, A. Mazzei and G. Giuliani, *Rubber Chem. Technol.*, **47**, 1175 (1974).
- 2 Sheng Tse-Chuan *et al.*, *Scientia Sinica*, **13**, (8), 1339 (1964); *ibidem*, **17** (5) 656 (1974); Shen Zhiquan *et al.* *J. Polym. Sci., Polym. Chem. Ed.*, **18**, 3345 (1980); S. R. Rañikov *et al.*, *Dokl. Akad. Nauk SSSR*, **229** (5) 1174 (1976); G. Lugli, U. Pedretti and M. Bruzzone, *Assoc. Ital. Macrom. Meet.*, Milan, 1981; G. Sylvester and W. Wieder, *182nd ACS Nat. Meet.*, New York 1981; *Polymer Prepr.* **22** (2) 142 (1981); Wang Fosong *et al.*, *Makromol. Chem.*, **182**, 3617 (1981); Ji-Hua Yang *et al.*, *Makromol. Chem.*, **15**, 230 (1982).
- 3 G. Natta, L. Porri and A. Carbonaro, *Ass. Naz. Lincei, Sc. Fis. Mat. Nat.*, **29**, 491 (1960).

## C7

## Catalytic Effect of Uranium Compounds on Alkene Hydrogenation

J. F. LE MARECHAL\* and G. FOLCHER

*L.A. 331 - Département de Physico-Chimie, Centre d'Etudes Nucléaires de Saclay, Gif/Yvette, 91191 Cedex, France*

The reagent ( $\text{UCl}_3\text{LiAlH}_4$ ) was shown [1] to reduce both aromatic and non-aromatic alkenes, among them terpenes.

Among the very surprising results, there is evidence that the closeness of the uranium catalytic cycle depends on the alkene. Some alkenes are fully hydrogenated into the corresponding alkane during the reaction without hydrolysis, for example ethene, propene. Others are found to be partly deuteriated after hydrolysis with deuterium oxide, for example diphenyl-1,1-ethene. In both these cases, the catalytic uranium center is regenerated and less than 10% of uranium per equivalent of alkene is needed. In the other cases, the reduction proceeds, but an intermediate uranium complex (which has not yet been isolated) accumulates and stops the reaction. Thus the full alkene reduction consumes one equivalent of uranium.

It is a contribution to uranium organometallic chemistry as well as to recently developed hydride [3] chemistry. The species ' $\text{UCl}_2\text{H}$ ' formulated by Evans [2] seems to be a possible intermediate in our