



Letter

Calculating the optimum pressure and temperature for vacancy minimization from theory: Niobium is an example

Jozsef Garai*

Department of Mechanical and Materials Engineering, Florida International University, Miami, USA

ARTICLE INFO

Article history:

Received 10 February 2010

Received in revised form 8 May 2010

Accepted 20 May 2010

Available online 27 May 2010

Keywords:

Nb

Vacancy

Thermodynamic properties

Mechanical properties

Superconductivity

ABSTRACT

Self-resonance in the atomic vibration occurs when the average wavelength of the phonon thermal vibration is equivalent or harmonic of the diameters of the atoms. It is suggested that applying pressure at temperature corresponding to the self-resonance should effectively reduce the number of vacancies. This theoretical prediction is tested on Niobium by measuring the magnetic susceptibility of the untreated and treated samples. The applied pressure–temperature treatment increased the critical temperature of Niobium by about 30%.

© 2010 Elsevier B.V. All rights reserved.

1. Introduction

The reduction of the number of vacancy in a substance improves the physical properties of the materials. Traditionally pressure and temperature treatments are employed to achieve this goal. The optimum treatments are usually determined by try and error method.

When the wavelength of the average thermal phonon vibration is equal to or harmonic with the atomic diameter then self-resonance occurs. It is suggested that the application of pressure at the temperature corresponding to self-resonance should result in the reduction of the number of vacancies. The same approach can also be applied to enhance diffusion. Using fundamental thermodynamic relationships the equations calculating the pressure and temperature for self-resonance are derived here.

2. Calculations

The average wavelength [$\bar{\lambda}$] of the phonon frequency at a given temperature can be calculated [1] as

$$\bar{\lambda} = \frac{h\nu_B}{k_B T} \quad (1)$$

where h is the Planck constant, k_B is the Boltzmann constant, ν_B is the bulk sound velocity and T is the temperature. The bulk sound

velocity is calculated as

$$\nu_B = \sqrt{\frac{B_T}{\rho}} = \sqrt{\frac{V_m B_T}{N_A M}}, \quad (2)$$

where B_T is the isothermal bulk modulus, ρ is the density, V_m is the molar volume, N_A is the Avogadro's number and M is the mass of the atom. In Eq. (2) the isothermal bulk modulus is used instead of the adiabatic. The difference between the isothermal and the adiabatic bulk modulus is usually under 1% which is ignored in this study.

The effect of temperature on the bulk modulus at 1 bar pressure is calculated [2] as

$$B_{0T} = B_0 \exp \left[- \int_{T=0}^T \alpha_V \delta dT \right] \quad (3)$$

where B_0 is the bulk modulus at zero pressure and temperature, α_V is the volume coefficient of thermal expansion and δ is the Anderson–Grüneisen parameter, which defined as

$$\delta \equiv \left(\frac{\partial \ln B_T}{\partial \ln V} \right)_P = - \frac{1}{\alpha_{V_P}} \left(\frac{\partial \ln B_T}{\partial T} \right)_P = - \frac{1}{\alpha_{V_P} B_T} \left(\frac{\partial B_T}{\partial T} \right)_P. \quad (4)$$

Assuming that the temperature and pressure effect on the volume coefficient of thermal expansion and bulk modulus is linear, respectively then Eq. (3) can be written as

$$B_{P,T} = (B_0 + B'_0 P) \exp[-(\alpha_0 + \alpha_1 T) \delta T] \quad (5)$$

where P is the pressure where B'_0 is the linear term for the pressure dependence of the bulk modulus, α_0 is the projected value of

* Tel.: +1 786 247 5414.

E-mail address: jozsef.garai@fiu.edu.

Table 1
Thermodynamic parameters for the Garai (G) and Birch-Murnaghan (B-M) equation of states.

	V_0 [cm ³]	B_0 [GPa]	B_0	α_0 [10 ⁻⁵ K ⁻¹]	α_1 [10 ⁻⁹ K ⁻²]	B_{1P}	B_{2P} [$\times 10^{-3}$ GPa ⁻¹]	α_{1P} [$\times 10^{-7}$ GPa ⁻¹ K ⁻¹]	α_{2P} [10 ⁻¹⁰ GPa ⁻² K ⁻¹]	a	δ	RMS misfit
0–134 GPa, 293–2470 K [N = 77]	10.736	182.23	3.570	2.512	2.961	1.137	0.074	-18.16	0.881	12.0	20.03	0.0288 cm ³ 0.96 GPa
V(p, T) (G)	10.789	177.88		1.850								
P(V, T) (B-M)												

the volume coefficient of thermal expansion at zero pressure and temperature and α_1 is the linear term for the volume coefficient of thermal expansion. Even though, the temperature dependence of the coefficient below the Debye temperature is not linear [3], the linear approximation and Eq. (5) can be used for ambient conditions and at higher temperatures [4] because the introduced error is minor.

The molar volume of the solid at the temperature of interest is calculated by using the EoS of Garai [4], which is given as

$$V_m = V_0 \exp \left[\frac{-P}{B_0 + B_{1P}P + B_{2P}P^2} + (\alpha_0 + \alpha_{1P}P + \alpha_{2P}P^2)T + \left(1 + \frac{\alpha_{1P}P + \alpha_{2P}P^2}{\alpha_0} \right)^a \alpha_{1T}T^2 \right] \quad (6)$$

where V_0 is the molar volume at zero pressure and temperature, B_{1P} is a linear, B_{2P} is a quadratic term for the pressure dependence of the bulk modulus, α_{1P} is a linear and α_{2P} is a quadratic term for the pressure dependence of the volume coefficient of thermal expansion, α_{1T} is a linear term for the temperature dependence of the volume coefficient of thermal expansion and a is constant, characteristic of the substance. The theoretical explanations for Eq. (6) and the physics of the parameters are discussed in detail [4].

The atomic diameter [d] corresponding to the size of the vacancy is approximated as

$$d = \sqrt[3]{\frac{V_m(T, P)}{N_A}} \quad (7)$$

Self-resonance can occur when

$$\frac{n}{2}\tilde{\lambda} = d(T, P) \quad \text{where } n \in \mathbb{N}^* \quad (8)$$

If the thermodynamic parameters are available then the P - T curve for the atomic self-vibration can be calculated by using Eqs. (1)–(8).

The vibrational motion of crystals is very complex and idealized approach is valid only for monoatomic highly symmetrical atomic arrangement. Niobium, which satisfies this criterion, has been selected to test the proposed hypothesis because of its importance in superconductivity.

3. Testing the theoretical predictions

The thermodynamic parameters required for Eqs. (1)–(8) are determined by unrestricted fitting using the available experimental data [5–7]. The 77 experiments cover the temperature and pressure range 293–2470 K and 0–134 GPa, respectively. The determined parameters for the Birch Murnaghan and the Garai EoSs are given in Table 1. The P-V-T version of the isothermal Birch Murnaghan EoS is given in ref. [8]. The temperatures for the fundamental and the second harmonics at atmospheric pressure and at 10 GPa are calculated by using Eqs. (1)–(8). Using atomic radius 1.46 Å for Niobium [9] the temperatures for the first harmonic at atmospheric pressure and 10 GPa are 340 and 360 K, respectively while for the second harmonic the temperatures are 640 and 681 K.

The 1/4 in. \times 0.5 mm Nb (99.95%) samples were bought from Smart Elements. The approximately 0.1 GPa pressure was achieved by screws in a pressure vessel. The sample under pressure was heated up from room temperature to the targeted temperature (640 K) in 15 h. The sample was annealed at 640 K for 8 h and cool down to room temperature in 15 h. The sample was taken out from the pressure vessel right before the experiment. The effectiveness of the treatment was tested by measuring the critical temperature of the untreated and the treated samples.

The temperature dependence of the ac susceptibility from the treated and untreated Nb sample, performed by using a mutual inductance technique at an applied field of $H = 20$ Oe and frequency




Fig. 1. Magnetic measurement of the treated and untreated samples.

of $f=1$ kHz is shown in Fig. 1. The real part, χ' , reveals a large diamagnetic signal below 6.8 and 8.8 K marking the superconducting transition for the untreated and treated sample, respectively. Below 6.0 and 8.0 K, χ' is flat, indicating that the superconducting transition is complete for both the untreated and the treated samples. The critical temperature of Nb reported in the literature [10] is lower than 6.8 K measured for untreated sample. The most likely explanation for the reduction of the critical temperature is the presence of iron in the Nb sample. Comparing the untreated and treated samples it is evident that the treatment increased both the critical temperature and the volume by about 30% (Fig. 1).

4. Conclusion

It is suggested that compressing a substance at temperature corresponding to thermal phonon vibration with wavelength equal to or harmonics with the atomic diameter should effectively reduce the number of vacancies. Using conventional thermodynamic relationships the equations calculating the optimum pressure and temperature for vacancy minimization are derived. The parameters of the P - V - T equation of state are required for the calculations. The theoretical predictions are tested on Niobium by measuring the critical temperature of the untreated and treated samples. The treatment increased both the critical temperature and the volume by about 30%. It is concluded that the presented theoretical approach can successfully be applied to calculate the optimum pressure and temperature conditions for vacancy minimization.

Acknowledgements

I would like to thank Rongying Jin for conducting the magnetic susceptibility experiments and Andriy Durygin for helping in the design and in the manufacturing of the pressure vessel.

References

- [1] C. Kittel, Introduction to Solid State Physics, 8th ed., Wiley, New York, 2004.
- [2] J. Garai, A. Laugier, J. Appl. Phys. 101 (2007) 023514.
- [3] J. Garai, CALPHAD: Computer Coupling of Phase Diagrams and Thermochemistry 30 (2006) 354.
- [4] J. Garai, J. Appl. Phys. 102 (2007) 123506.
- [5] L.-C. Ming, M.H. Manghani, J. Appl. Phys. 49 (1978) 208.
- [6] T. Kenichi, A.K. Singh, Phys. Rev. B 73 (2006) 224119.
- [7] J.W. Edwards, R. Speiser, H.L. Johnston, J. App. Phys. 22 (1951) 424.
- [8] J. Garai, J. Chen, G. Telekes, CALPHAD: Computer Coupling of Phase Diagrams and Thermochemistry 33 (2009) 737.
- [9] J.A. Dean, Lange's Handbook of Chemistry, 15th ed., McGraw-Hill, Inc., New York, 1999.
- [10] J. Eisenstein, Modern Phys. 26 (1954) 277.