

Study on Ozone Treatment of Water-Soluble Polymers. II. Utilization of Ozonized Polyethylene Glycol by Bacteria

JUNZON SUZUKI, HISAKO NAKAGAWA, and HARUO ITO, *Faculty of
Pharmaceutical Science, Science University of Tokyo, Ichigaya
Funagawara-machi, Shinjuku-ku, Tokyo, Japan*

(article in *J. Appl. Polym. Sci.*, **20**, 2791, 1976)

Table I, which appears on p. 2794, is incorrect and not related to the article. The correct Table I appears below.

TABLE I
Characterization of Ozonized PEG

Reaction time, min	Ozone consumed, (moles/l.) $\times 10^3$	Intrinsic viscosity, [η]	Aldehyde, (moles/l.) $\times 10^3$	
			Original	Treated with H_2O_2
0	0	0.206	0	0
15	20.4	0.104	2.08	0.52
30	36.4	0.081	3.23	0.98
45	56.0	0.064	4.42	1.29
60	71.6	0.057	5.32	2.00
90	100.4	0.044	7.60	2.26