

Erratum

Liquid-Rubber-Modified Epoxy Adhesives Cured with Dicyandiamide. I. Preparation and Characterization

YU-DER LEE, SHI-KWUN WANG, and WEI-KUO CHIN, *Institute of Chemical Engineering, National Tsing Hua University, Hsinchu, Taiwan, Republic of China*

[article in J. Appl. Polym. Sci., 32, 6317-6327 (1986)]

Correct Table II:

TABLE II
Characteristic Properties of Synthetic Liquid Rubbers

Sample	nBA/AA (v/v)	\bar{M}_n^a	\bar{M}_n^b	\bar{M}_w/\bar{M}_n^b	Conc of COOH (mol/kg)	Functionality (eg/mol)	Yield (%)
LR 1	50/0	5100	2180	8.79	0.3179	1.62	85
LR 2	50/2	5140	2090	10.59	0.8378	4.31	83
LR 3	50/4	4830	1840	9.08	1.4819	7.16	87
LR 4	50/6	6020	2140	18.50	1.5015	9.93	78

^aMeasured by VPO.

^bMeasured by GPC.