

aqueous solutions of  $\text{HNO}_3$  in concentrations of 2.2 to 8.2 moles/L was studied. The reaction was first order relative to hydrazine, and third order relative to acid. At  $97^\circ$  the reaction rate constant is  $(2.7 \pm 0.2) (10^{-5}) \text{ mole}^{-2}\text{L}^3\text{min}^{-1}$  and the activation energy is  $27.2 \pm 0.8 \text{ kcal/mole}$ . Also established were the stoichiometry for the process and the composition of the reaction products.

A possible reaction mechanism is proposed which assumes the formation as intermediates of nitrous acid, tetrazine, isotetrazine, etc. The reaction between  $\text{N}_2\text{H}_4$  and  $\text{NO}_2$  is the rate limiting step.

#### Reduction of Uranium Trioxide by Ammonia

By V. G. VLASOV AND V. M. JOOKOVSKII  
*S. M. Karpov Polytechnic Institute for Ural Region*

The kinetics of reduction of uranium trioxide by ammonia was studied at temperatures of  $300^\circ$  to  $425^\circ$  and reducing gas pressures of 10 to 600 mm Hg. An equation correlating the rate to pressure is proposed. An apparent activation energy was determined. A mechanism is proposed, and desorption of molecular nitrogen from the oxide surface shown to be rate limiting.

#### Effect of Pre-Irradiation on the Subsequent Thermal Decomposition of Permanganates of Metals of the First Group in the Periodic Table

By V. V. BOLDIRIEV AND  
A. N. OBLEEVANTZEV  
*Scientific Research Institute of Nuclear Physics at S. M. Keerov Polytechnic Institute of the City of Tomsk*

The effect of 200 keV X-ray exposure upon subsequent thermal decomposition rates of permanganates of lithium, potassium, rubidium, cesium, and silver was studied. Irradiation increases thermal decomposition rates of the various permanganates in the order in which they are listed.

The results disagree with Prout's Theory, according to which the acceleration of thermal decomposition is due to production of dislocations. The theory is critically re-examined in the light of the new experimental data. It is proposed that the observed increase in thermal decomposition of the irradiated samples is caused by the catalytic action of radiolysis products observed in the lattice of the solids.

The overall product yields are proportional to the amount of products formed in the irradiation step. The yield depends on free volume, ionization potential of the cation, and the polarizing interaction between the cation and the permanganate anion.

#### Reaction Kinetics Including Participation of the Solid Phase: Kinetic Equations and Determination of Specific Reaction Rates

By A. YA. ROSOVSKII  
*The Institute for Petrochemical Synthesis of the Academy of Sciences of U.S.S.R.*

The kinetics of heterogeneous catalytic reactions were examined to establish empirical laws for the formation and behavior of the intermediate product complexes ("the nucleous stage of product formation"). Kinetic equations convenient for treatment of experimental data are presented. A unified method is proposed to determine specific rates of heterogeneous catalytic reactions with different kinetic mechanisms suitable for comparing reactivities of various substances.

Experimental data for the oxidation of an iron catalyst by water in a carbon monoxide-hydrogen synthesis process are used as an example.

#### A Theory of Chemisorption on Polar Crystals

By E. L. NAGAYEV  
*The Scientific Research Institute for Electrotechnical Glass*

The adsorptive properties of ionic crystals are determined by the nature of chemical bonding, i.e., by the degree of ionic and homeopolar bonding. Since electrical properties of crystals are also related to the nature of their chemical bonds, a correlation exists between the electrical and the chemisorptive properties of crystals.

Surface defects of crystals change the nature of the neighboring chemical bonds. Thus conditions arise which either favor or hinder chemisorption and modify catalytic activity.

#### Soluble Complexes of Unsaturated Hydrocarbons and Metallic Salts and Their Role in Catalytic Reactions: Soluble Compounds of Acetylene and Silver Salts

By O. N. TIOMKEEN, R. M. FLEED,  
AND A. M. MALAKHOV  
*M. V. Lomonosov Institute of Fine Chemical Technology*

The thermodynamics of the system acetylene with silver sulfate in  $\text{H}_2\text{SO}_4$  was studied with the aid of potentiometric technique, over wide ranges of temperatures and concentrations, with respect to formation of the  $\pi$ -complex,  $\text{AgC}_2\text{H}_2^+$ , and of asymmetric acetylenide,  $\text{AgC}_2\text{H}$ . The poor catalytic activity of silver salts for hydration of acetylene, as compared to that of copper salts, is explained by the relatively small value of the equilibrium constant for formation of the silver-acetylene  $\pi$ -complex.