

is believed that the promoters serve to decrease concentrations of the surface-deactivating intermediates chemisorbed on the catalyst surface.

Adsorption and Isotopic Exchange of CO₂ on MgO and Mg(OH)₂

O. V. KRILOV, Z. A. MARKOVA,
I. I. TR'YET'YAKOV, AND
E. A. FOKEENA

*Institute of Chemical Physics of the
Academy of Sciences of USSR*

The results of differential isotopic analyses show that in terms of the activation energies the surface of MgO is homogeneous but that in terms of the heats of adsorption, it is heterogeneous. The kinetics of isotopic exchange between gaseous and adsorbed phases of a CO — COO¹⁸ system shows that the rate of isotopic exchange is increased by increasing the reaction temperature and by addition of water; variation of partial pressure of CO₂ has little effect on the rate.

Inspection of the infrared spectra discloses presence of three different forms of CO₂ bonding to Mg(OH)₂, corresponding to three distinct mechanisms of adsorption and exchange of CO₂.

The types of active centers present in alkaline catalysts are speculated upon and their functions in acid-base catalysis are discussed.

Effects of Sintering and Oxygen Sorption by Nickel Catalyst on Kinetics of Para-Ortho Conversion and Isotopic Exchange of Hydrogen

I. R. DAVIDOVA AND S. L. KEEPERMAN

*N. D. Z'yeleensky Institute of
Physical Chemistry of the Acad-
emy of Sciences of USSR*

The effects of oxygen preadsorption on a nickel catalyst upon different kinetic factors were determined in para-ortho conversion of hydrogen and in deuterium-hydrogen exchange reactions. The effects uncovered are attributed to stable adsorption of oxygen by the portions of the catalyst surface with high adsorption properties; the gas diffuses through the rest of the catalyst surface into the interior of the surface layer. The results obtained are in good agreement with the adsorption-chemisorption equilibrium data for oxygen by the catalyst.

Processes of Catalytic Conversion of Ethanol to Butadiene

S. K. BHATTACHARIYA, N. D. GANGOOLI,
AND B. N. AVASTKHI

*Department of Applied Chemistry
of Indian Technological Institute,
Karagpoor, India*

A systematic study of conversion of ethanol to butadiene was carried out in one-stage and two-stage units, using static and fluidized beds of catalysts of different composition. In the systems of either type, a 60/40 Al₂O₃/ZnO catalyst was found to be the most active. In one-stage boiling-bed systems, the butadiene yields are very high, the optimum yield being 72.8%. The optimum yield for the one-stage static bed unit is only 55.8%. The results show that processing of ethanol in two-stage fluidized bed units does not improve the butadiene yields per unit of fresh feed; however, it does significantly improve the through-put rates.

An analysis of the experimental data indicates that use of fluidized catalyst beds is advantageous in one-stage operation; on the other hand, the use of static beds is probably preferable in two-stage processing systems.

Decomposition of Hydrogen Over Germanium Catalyst

V. M. FROLOV

*Institute of Chemical Physics of the
Academy of Sciences of USSR*

Catalytic decomposition of hydrazine over a powdered germanium catalyst is a reaction of zero order. The reaction activation energy is 20-22 kcal/mole. The decomposition products are ammonia and nitrogen. Catalytic properties of germanium are not predictable from the character of its conductivity.

BRIEF COMMUNICATIONS

Effect of Preparation Methods on Porous Structure of Beryllium Oxide

I. B. SLEEN'YAKOVA

*L. V. Peesarijevsky Institute of Physical Chemistry
of the Academy of Sciences of Ukrainian SSR*

The character of porous structure of beryllium oxide is strongly influenced by the reactions occurring during formation and maturation of the suspended product. Precipitation at pH values of 7.7 to 8.5 results in beryllium oxide xerogels of high specific surfaces. The xerogels precipitated at a pH of 5.5 have small specific surfaces, relatively small pore adsorption capacity, and a relatively large number of macropores. Increasing calcination