



Available online at www.sciencedirect.com

SCIENCE  DIRECT<sup>®</sup>

Journal of Molecular Catalysis A: Chemical 200 (2003) 333

  
JOURNAL OF  
MOLECULAR  
CATALYSIS  
A: CHEMICAL

www.elsevier.com/locate/molcata

## Corrigendum

# Corrigendum to “Generating palladium nanoclusters inside functional cross-linked polymer frameworks” [J. Mol. Catal. A: Chem. 173 (2001) 99–115]<sup>☆</sup>

Benedetto Corain <sup>a,\*</sup>, Milan Kralik <sup>b,1</sup><sup>a</sup> Dipartimento di Chimica Inorganica, Metallorganica e Analitica and Centro per lo Studio della Stabilità e Reattività dei Composti di Coordinazione, Università di Padova, C.N.R., via Marzolo 1, 35131 Padova, Italy<sup>b</sup> Department of Organic Technology, Slovak University of Technology, Radlinského 9, 812 37 Bratislava 1, Slovak Republic

The authors wish to replace **Table 2** with an amended version published here.

Table 2

Gel-type resins synthesized as model supports or as actual supports of catalytically active palladium nanoclusters [38–46]

Entry (code)	DMAA (%) <sup>a</sup>	SS-Na <sup>+</sup> (%) <sup>b</sup>	MA (%) <sup>c</sup>	HEMA (%) <sup>d</sup>	SEMA-K <sup>+</sup> (%) <sup>e</sup>	SEMA (%) <sup>f</sup>	STY (%) <sup>g</sup>	MBA (%) <sup>h</sup>	DVB (%) <sup>i</sup>	Solvent (%)
P4N	68	28	—	—	—	—	—	4	—	Water (68% w/w)
M4K	65	—	—	—	31	—	—	4	—	Water (35% w/w)
M4A	70	—	—	—	—	26	—	4	—	Water (35% w/w)
M1–M8	99–92	—	—	—	—	—	—	1–8	—	None
P8N	66	26	—	—	—	—	—	8	—	Water (40% w/w)
SS1MH	—	—	—	—	—	22	77	1	—	None
SS2MH	—	—	—	—	—	22	76	2	—	None
SS3MH	—	—	—	—	—	22	75	3	—	None
SS6MH	—	—	—	—	—	22	72	6	—	None
SPI	92	—	—	—	—	4	—	4	—	None
MPI	92	—	4	—	—	—	—	4	—	None
HPI	92	—	—	4	—	—	—	4	—	None
M2GB	—	—	—	—	—	4	94	—	2	DMSO (30% w/w)
M4GB	—	—	—	—	—	4	92	—	4	DMSO (30% w/w)
A1–A9	87–95	—	—	—	—	4	—	9–1	—	DMF (10% w/w)
AH	33	—	—	—	—	26	37	4	—	DMF (10% w/w)
BH	—	—	—	—	—	28	68	4	—	Idem
CH	—	—	—	—	—	37	58	—	5	Idem
DH	—	—	—	—	—	17	78	—	5	Idem

<sup>a</sup> *N,N'*-dimethylacrylamide.<sup>b</sup> Styrene sulfonate sodium form.<sup>c</sup> Methacrylic acid.<sup>d</sup> Hydroxyethylmethacrylate.<sup>e</sup> Sulfoethylmethacrylate potassium form (i.e. methacryloylethylsulfonate (K<sup>+</sup>)).<sup>f</sup> Sulfoethylmethacrylate (i.e. methacryloylethylsulfonate (H<sup>+</sup>)).<sup>g</sup> Styrene.<sup>h</sup> *N,N'*-methylenebisacrylamide.<sup>i</sup> Divinylbenzene.

☆ PII of original article: S1381-1169(01)00147-9.

\* Corresponding author. Tel.: +39-049-8275211; fax: +39-049-8275223.

E-mail addresses: benedetto.corain@unipd.it (B. Corain), kralik@chtf.stuba.sk (M. Kralik).

1 Co-corresponding author. Tel.: +421-7-52495242; fax: +421-7-52493198.