



Corrigendum

Corrigendum to “Application of the direct exchange method in the preparation of gold catalysts supported on different oxide materials” [J. Mol. Catal. A: Chem. 256 (1–2) (2006) 278–283]

Svetlana Ivanova *, Véronique Pitchon, Corinne Petit *

*Laboratoire des Matériaux, Surfaces et Procédés pour la Catalyse, UMR 7515 du CNRS 25 rue de Becquerel, 67087 Strasbourg, France*Received 30 January 2007; accepted 3 March 2007
Available online 15 March 2007

The authors regret that in the above article some values in Table 4 were incorrect. The corrected values are given below in Table 4.

Table 4
Rate of reaction for the catalysts prepared by DAE as a function of support and washing agent

Catalyst	Washing agent	r (mol CO min ⁻¹ g Au ⁻¹)
2% Au/Al ₂ O ₃	H ₂ O	1.8×10^{-3}
1.97% Au/CeO ₂	H ₂ O	2.3×10^{-2}
1.53% Au/TiO ₂	H ₂ O	2.1×10^{-2}
1.63% Au/ZrO ₂	H ₂ O	8.7×10^{-3}
1.35% Au/Al ₂ O ₃	4 mol L ⁻¹ NH ₃	1.9×10^{-2}
1.93% Au/CeO ₂	4 mol L ⁻¹ NH ₃	4×10^{-2}
1.19% Au/TiO ₂	4 mol L ⁻¹ NH ₃	2.7×10^{-2}
1.56% Au/ZrO ₂	4 mol L ⁻¹ NH ₃	8.2×10^{-3}
1.37% Au/Al ₂ O ₃	25 mol L ⁻¹ NH ₃	2.7×10^{-2}
1.95% Au/CeO ₂	25 mol L ⁻¹ NH ₃	3.2×10^{-2}
1.50% Au/TiO ₂	25 mol L ⁻¹ NH ₃	1.8×10^{-2}
1.34% Au/ZrO ₂	25 mol L ⁻¹ NH ₃	2.9×10^{-2}

DOI of original article:10.1016/j.molcata.2006.05.006.

* Corresponding author. Tel.: +33 3 90 24 26 76; fax: +33 3 90 24 26 74.

E-mail addresses: ivanovas@ecpm.u-strasbg.fr (S. Ivanova), petitc@ecpm.u-strasbg.fr (C. Petit).