

Editors

L.K. Mansur (Chairman)
Materials Science and Technology Division
Oak Ridge National Laboratory
P.O. Box 2008
Oak Ridge, TN 37831-6138
USA

C. Lemaignan
CEA-Grenoble DEC-Dir
17 rue des Martyrs
38045 Grenoble Cedex 9
France

S. Ishino
Nuclear Materials Office
13-4, Iwado-Minami 3-chome
Komae-shi
Tokyo 201-0005
Japan

L.O. Werme
Svensk Kärnbränslehantering AB
Swedish Nuclear Fuel and Waste Management Co.
Box 250
SE-101 24 Stockholm, Sweden

Advisory Editorial Board

D.J. Bacon, Liverpool, UK
A. Barbu, Gif-sur-Yvette, France
T.D. Burchell, Oak Ridge, TN, USA
R.A. Causey, Livermore, CA, USA
V.M. Chernov, Moscow, Russia
C.E. Coleman, Chalk River, Canada
R. Finch, Albuquerque, NM, USA
T. Fujino, Ibaraki-ken, Japan
F.A. Garner, Richland, WA, USA
N.M. Ghoniem, Los Angeles, CA, USA
J.-M. Gras, Moret-sur-Loing, France
M. Griffiths, Chalk River, Canada
R.W. Grimes, London, UK
A. Hishinuma, Ibaraki-ken, Japan

E.R. Hodgson, Madrid, Spain
S.I. Hong, Taejon, South Korea
K. Ishigure, Saitami-ken, Japan
P. Jung, Jülich, Germany
C. Kinoshita, Fukuoka, Japan
R.J.M. Konings, Karlsruhe, Germany
E. Kuramoto, Fukuoka-ken, Japan
J. Linke, Jülich, Germany
Hj. Matzke, Karlsruhe, Germany
A. Möslang, Karlsruhe, Germany
A.T. Motta, University Park, PA, USA
T. Muroga, Gifu-ken, Japan
G.R. Odette, Santa Barbara, CA, USA
D.R. Olander, Berkeley, USA

J. Roth, Garching, Germany
G. Saada, Châtillon, France
K.E. Sickafus, Los Alamos, NM, USA
P. Spätig, Villigen, Switzerland
G. Szenes, Budapest, Hungary
P. Toulhoat, Lyon, France
E.R. Vance, Sydney, Australia
P.R. Vasudeva Rao, Kalpakkam, India
V.N. Voyevodin, Kharkov, Ukraine
G.S. Was, Ann Arbor, MI, USA
F.P. Weiß, Dresden, Germany
B.D. Wirth, Berkeley, CA, USA
M. Yamawaki, Tokyo, Japan