A Triarylamine—Triarylborane Dyad with a Photochromic Dithienylethene Bridge

Andreas K. C. Mengel, Bice He, and Oliver S. Wenger*

Georg-August-Universität Göttingen, Institut für Anorganische Chemie, Tammannstrasse 4, D-37077 Göttingen, Germany

Supporting Information

ABSTRACT: A molecular triad composed of a triarylamine donor, a triarylborane acceptor, and a photoisomerizable dithienylethene bridge has been synthesized and explored by cyclic voltammetry, UV–vis, and luminescence spectroscopy. The effects of irradiation with UV light and fluoride addition on the electrochemical and optical spectroscopic properties of the donor–bridge–acceptor molecule were investigated. Photoisomerization of the dithienylethene bridge affects the triarylboron reduction potential, but not the triarylamine oxidation potential. UV–vis experiments reveal that the association constant for fluoride binding at the triarylboron



association constant for fluoride binding at the triarylborane site is independent of the isomerization state of the bridge. Irradiation of a THF solution of our donor-bridge-acceptor molecule with UV light, followed by F^- addition, leads to a different color of the sample than UV irradiation alone or F^- addition alone.

INTRODUCTION

Triarylboranes have received much attention in the context of fluoride sensing in recent years,¹⁻¹² but also their possible application as light-emitting materials or as electron-deficient π -conjugated units of conducting polymers has stimulated much work.^{13–22} One branch of research in this multifaceted area deals with intramolecular charge transfer between electron-rich triarylamine groups and electron-poor triarylborane moieties.^{23–29} In systems with π -conjugated bridges, amine-to-borane charge transfer commonly manifests as an absorption band in the electronic (UV–vis) spectrum.^{1,24–26,28–34} There have been recent studies of triarylborane-containing dithieny-lethenes,^{35,36} but we are unaware of prior investigations of triarylamine–triarylborane donor–acceptor systems with photochromic bridges.

In this work, we aimed to explore to what extent the isomerization state of a photochromic bridge affects intramolecular charge transfer between amine and borane groups. The issue of controlling π -conjugation pathways for electron transfer in photochromic systems is of long-standing interest.³⁷⁻⁴⁴ However, it is not trivial to investigate photoinduced electron transfer in photochromic donor-bridgeacceptor molecules because the light energy that is used to trigger electron transfer in many cases also induces photoisomerization.^{38,40,42,44} Recent studies on photoswitchable mixed-valence systems demonstrated that the extent of charge delocalization between two redox-active centers can be controlled by light when the two redox moieties are connected covalently via a photoisomerizable unit.^{45–52} In our own work, we had explored the monocationic forms of the dithienylethene-bridged bis(triarylamine) molecules shown on the left of Scheme 1 (n = 0, 1),⁵³ and we found that, by using UV and

visible light, it is possible to switch between class I, class II, and class III mixed-valence behavior,⁵⁴ that is, from complete charge localization to either partial or full charge delocalization. In the present study, we synthesized and investigated the chemically related triarylamine—dithienylethene—triarylborane molecule shown in the right half of Scheme 1 (molecule 1), and we explored the effects of photoisomerization and fluoride addition on the electrochemical, optical absorption, and luminescence properties of this compound.

The design principle of the investigated molecule is simple. The triarylamine with two *p*-anisyl substituents is a popular electron donor because of its comparatively high chemical stability and relatively low oxidation potential;^{55,56} dimesitylborane is a suitable acceptor because the electron-deficient boron atom is sterically protected from its environment and, therefore, relatively stable, yet, at the same time, is a reasonably good electron acceptor.¹ The photoisomerization reactions of dithienylethenes are highly reversible in many systems; hence, this particular photochromic unit appeared as an attractive choice, ^{57–63} also in light of a recent study of fluoride and mercuric(II) cation sensing by a photochromic organoboron compound.³⁶

RESULTS AND DISCUSSION

Synthesis. The photochromic backbone of donor-bridgeacceptor molecule **1** is built into the overall system using dithienylperfluorocyclopentene building block **2**, which has been previously described in the literature (Scheme 2).^{37,53} Trimethylsilyl-halogen exchange on molecule **2** yields diiodo

Received: June 1, 2012 Published: July 16, 2012 Scheme 1. (a) Open and Photocyclized Forms of Two Dithienylethene-Bridged Bis(triarylamines) (n = 0, 1; R = C₆H₄OCH₃), the One-Electron Oxidized Forms of Which Were Previously Investigated in the Context of Photoswitchable Organic Mixed Valence.^{45,53} (b) Open and Closed Forms of the Donor–Bridge–Acceptor Molecule of Central Interest in This Study



Scheme 2. Synthetic Steps Leading to the Donor-Bridge-Acceptor Molecule 1^a



"(a) ICl, CH₂Cl₂, -5 °C; (b) bis(pinacolato)diboron, Pd(PPh₃)Cl₂, NaOAc, PEG600, 90 °C; (c) Pd(PPh₃)₄, THF, Na₂CO₃ (aq), 80 °C.

compound 3, which can subsequently be used for Suzuki-type C–C couplings with suitable reagents. The first coupling partner was molecule 5, which is a boronic acid pinacol ester of the triarylamine unit, prepared in one step from di-*p*-anisyl-*p*-bromophenylamine (4).⁶⁴ The resulting coupling product is molecule 6. A boronic acid pinacol ester of the triarylborane unit (8), prepared from previously known (4-bromophenyl)-dimesitylborane (7),^{65,66} was subsequently coupled to molecule 6, yielding the target molecule 1. Detailed synthetic protocols and product characterization data of all new compounds are given in the Experimental Section. In addition, selected NMR

and ESI-TOF-HRMS spectra are shown in the Supporting Information.

Electrochemistry. Figure 1 shows cyclic voltammograms of the donor-bridge-acceptor molecule 1. We have found that triarylamine oxidation is best monitored in CH_2Cl_2 or CH_3CN , whereas triarylborane reduction is much more cleanly detectable in dry THF solution. The upper half of Figure 1 shows oxidative voltage sweeps recorded from a $5 \cdot 10^{-4}$ M solution of molecule 1 in dry and deoxygenated CH_2Cl_2 in the presence of 0.1 M tetrabutylammonium hexafluorophosphate (TBAPF₆), while the lower half of Figure 1 shows reductive



Figure 1. Cyclic voltammograms of the open (blue traces) and closed (red traces) forms of **1**. (a) Oxidative sweeps with 100 mV/s in dry CH_2Cl_2 . (b) Reductive sweeps with 100 mV/s in dry THF. 0.1 M TBAPF₆ was used as an electrolyte in both cases; the waves at -0.51 V vs Fc⁺/Fc are due to the decamethylferrocene internal reference. The waves marked by the asterisks are assumed to be due to electrochemical decomposition products.⁶⁷

voltage sweeps obtained from a 10^{-3} M solution of molecule 1 in dry and deoxygenated THF in the presence of 0.1 M TBAPF₆ electrolyte. Trace amounts of decamethylferrocene were added for internal voltage calibration, and this causes the reversible redox waves at -0.51 V vs Fc⁺/Fc in all four voltammograms (dashed vertical line).

The blue traces in Figure 1 are voltammograms obtained from the open form of molecule 1, whereas the red traces are voltammograms of the photocyclized (closed) form. For photoisomerization, the samples were irradiated with a handheld 8 W UV lamp. According to ¹H NMR experiments, this leads to a photostationary state composed of 15% open and Article

85% closed isomer.⁶⁸ The voltammograms in the upper half of Figure 1 are virtually identical to each other. Triarylamine oxidation occurs in a reversible fashion at 0.27 V vs Fc⁺/Fc in both the open and the closed isomers of 1, in agreement with previously reported oxidation potentials for this particular redox-active unit.^{69,70} Thiophene oxidations in dithienylcyclopentenes are known to occur at significantly higher potentials and are outside the potential range considered here; 44,53,71,72 electrocyclization is not observed. ⁷¹⁻⁷⁴ The reductive sweeps in the lower half of Figure 1 are significantly different from each other. While the weak currents between -1.5 and -2.0 V vs Fc^+/Fc are probably caused by impurities, the strong irreversible waves below -2.5 V vs Fc⁺/Fc are attributed to triarylborane reduction, in agreement with literature values for comparable systems.⁷⁵⁻⁷⁷ It is obvious from Figure 1 that triarylborane reduction occurs at somewhat less negative potentials for the closed form of 1 than for its open isomer: The peak currents are at -2.6 V vs Fc⁺/Fc for the closed form and at -2.7 V vs Fc⁺/Fc for the open isomer. Addition of TBAF (as a fluoride source) has led to very low quality voltammograms, which do not permit any meaningful conclusions except that triarylborane reduction cannot be detected any more (data not shown).

Reverse photoisomerization from the closed to the open form is possible when using a 610 nm cutoff filter in front of an incandescent lamp as an irradiation source. However, this process is extremely slow for solutions with millimolar concentrations (>hours), presumably due to the relatively low photon flux and the low quantum yield for closed-to-open isomerization, which is not an uncommon phenomenon for dithienylethenes.^{41,42} What is more, the sample suffers from photodegradation, and therefore, it has not been possible to demonstrate that the photoinduced changes in the voltammogram of Figure 1b are indeed reversible.

UV–vis Spectroscopy. The blue trace in Figure 2a is the optical absorption spectrum of a $3.2 \cdot 10^{-5}$ M solution of the open form of molecule 1 in THF. This sample is essentially colorless because there are no absorptions in the visible spectral range. Upon irradiation with UV light, the sample turns blue



Figure 2. UV–vis spectra of **1** in THF. (a) Photoisomerization of the open form (blue trace) to the closed form (red trace) upon UV irradiation. (b) Effect of fluoride addition to the closed form. (c) Titration of the open form (blue trace) with TBAF. (d) Photoisomerization of the open fluoride adduct (orange trace) to the closed fluoride adduct (green trace). Note that the green traces in (b) and (d) are identical.

because of increasing absorptions at 643, 452, and 398 nm (dotted black traces and upward arrows in Figure 2a); at the same time, the absorbance at 352 nm is decreasing. Ultimately, a photostationary state (with 85% closed and 15% open form; see above) is reached (red trace). Figure 2b illustrates the effect of fluoride addition on the optical absorption spectrum of the photocyclized solution; the red trace in Figure 2b is the same spectrum as the red trace in Figure 2a. When adding tetrabutylammonium fluoride (TBAF), the maximum of the longest-wavelength absorption shifts from 643 to 620 nm, resulting in a color change from blue to blue-green. In addition, there are spectral changes between 500 and 250 nm with clean isosbestic points at 514, 465, and 373 nm. After 1 equiv of F^- has been added, no further spectral changes are observed and the green trace in Figure 2b is obtained.

When reversing the sequence of light irradiation and F⁻ addition, one ultimately arrives at exactly the same spectrum, a fact that is illustrated by the lower half of Figure 2: The blue trace in Figure 2c is the same spectrum as the blue trace in Figure 2a, that is, the spectral signature of the open form of molecule 1 in THF. When adding F⁻ to this solution, the absorbance at 353 nm decreases, whereas a band at 302 nm gains intensity. After addition of 1 equiv of TBAF, the spectrum represented by the orange trace in Figure 2c is obtained. The spectrum of this sample is shown again in Figure 2d (orange trace), and when irradiated subsequently with UV light, it undergoes the spectral changes shown in Figure 2d. The green trace in Figure 2d is the spectrum of the final photostationary state and corresponds precisely to the green spectrum of Figure 2b, that is, the solution that has been irradiated prior to fluoride addition. We note that, in Figure 2c, the band of the closed form at 642 nm is already detectable because part of the sample unavoidably photoisomerizes in the absorption spectrometer.

The photograph in Figure 3 illustrates the color changes that are associated with UV irradiation and fluoride addition to a



Figure 3. Photograph showing (a) the open form of 1, (b) the open fluoride adduct of 1, (c) the closed form of 1, and (d) the closed fluoride adduct of 1.

THF solution of molecule 1: Adding F^- to the open isomer has essentially no influence on the color of the solution; the light yellowish appearance of the solution (Figure 3b) is mostly due to TBAF itself. Photoisomerization alone will produce a blue solution (Figure 3c); photoisomerization combined with fluoride addition leads to a blue-green color (Figure 3d).

From the F⁻ titrations in Figure 2b,c, it is possible to determine fluoride binding constants for the closed and open forms of molecule 1. Figure 4a plots the absorbance of a $3.2 \cdot 10^{-5}$ M THF solution of the *open* isomer at 353 nm as a



ò

10

20

[F⁻] / μM⁻¹

30

4r

22

2.0

<mark>@</mark>1.8

1.6

1 2

E

353 |

Figure 4. Absorbance changes at (a) 353 and (b) 335 nm in the course of TBAF addition to $3.2 \cdot 10^{-5}$ M solutions of the open (a) and closed (b) forms of 1 in THF. The solid lines are least-squares fits to the experimental data with eq 1.^{12,78}

30

20

[F] / μM⁻¹

10

function of the total (free and bound) F⁻ concentration. An analogous fluoride titration curve monitoring the absorbance at 335 nm of an equally dilute THF solution of the *closed* form of 1 is shown in Figure 4b. The solid lines in Figure 4 are the results of least-squares fits to the experimental data with eq 1, which is appropriate for determination of binding constants (K_s) of 1:1 adducts.^{12,78}

$$A = A_0 + [(A_{\rm lim} - A_0)/2 \cdot c_0] \cdot [c_0 + c_{\rm F} + K_{\rm s}^{-1} - [(c_0 + c_{\rm F} + K_{\rm s}^{-1})^2 - 4 \cdot c_0 \cdot c_{\rm F}]^{1/2}]$$
(1)

In eq 1, A_0 is the absorbance of the sample at a selected wavelength in the absence of any titrant, A is the absorbance at the same wavelength in the presence of titrant, and $A_{\rm lim}$ is the limiting absorbance value obtained once the solution has been saturated with titrant. c_0 is the concentration of molecule 1 (3.2·10⁻⁵ M), and $c_{\rm F}$ is the concentration of added F⁻ (see xaxes in Figure 4). Fits to the two data sets in Figure 4 yield $K_{\rm s}$ values of $(1.6 \pm 0.8) \cdot 10^7 \, {\rm M}^{-1}$ (Figure 4a) and $(2.3 \pm 1.0) \cdot 10^7 \, {\rm M}^{-1}$ (Figure 4b). Thus, the fluoride binding constants of the open and closed forms of molecule 1 are identical within experimental accuracy. The magnitude of our $K_{\rm s}$ values (10⁷ ${\rm M}^{-1}$) is similar to that reported previously for comparable triarylborane systems.¹ We note that fluoride binding constants may be strongly susceptible to trace water impurities in the solvent.

¹⁹F and ¹¹B NMR Spectroscopy. The ¹⁹F NMR spectrum of the closed form of molecule 1 in CHCl₃ exhibits resonances at -110 and -131 ppm due to the fluorine atoms on the perfluorocyclopentene backbone (see the Supporting Information). Upon addition of TBAF, an additional resonance shows up at -172 ppm, which is typical for F⁻ bound to a triarylamine group.^{1,29} In the ¹¹B NMR spectrum of the same sample, there is a broad resonance at -74 ppm, which is typical for triarylborane (see the Supporting Information).^{1,29} Upon fluoride addition, this resonance shifts to 4 ppm, in agreement with previously reported chemical shifts for fluorinated dimesitylboryl groups.^{1,29} No attempts to determine fluoride binding constants from NMR experiments were made; in light of the high K_s values found above, this did not appear to be meaningful.

Discussion of Charge-Transfer Properties. We now turn our attention back to the UV–vis data in Figure 2. The fluoride titration experiment in Figure 2c suggests that the absorbance at 353 nm of the open isomer is caused, at least in part, by an electronic transition involving the boron center. Indeed, in aromatic nitrogen–boron systems, there are frequently $N \rightarrow B$ charge-transfer transitions in this spectral range.^{1,25,26,28} The difference in triarylamine oxidation and triarylborane reduction potentials found above amounts to ~3 V. On this basis, one might expect the N \rightarrow B charge-transfer transition at ~24 000 cm⁻¹ or ~410 nm, but this represents obviously a crude estimate at best. Nevertheless, it appears reasonable to conclude that the absorption band at 353 nm (open isomer) has significant N \rightarrow B charge-transfer character.⁷⁹

As outlined in the Introduction, we anticipated that photocyclization of the dithienylethene bridge would affect N \rightarrow B charge transfer. However, it is not straightforward to identify the respective electronic transition in the closed isomer. One would expect $N \rightarrow B$ charge transfer to be suppressed when F⁻ is added, and consequently, we are searching for spectral regions in the UV-vis data of Figure 2b in which the absorbance is decreasing upon fluoride addition. This turns out to be the case between 514 and 466 nm, as well as between 372 and 273 nm; the spectral changes beyond 514 nm are not considered here because the longest-wavelength absorption is quite clearly caused by dithienylperfluorocyclopentene-localized $\pi - \pi^*$ transitions that may be perturbed by F⁻ complexation.^{40,44,57,61,62,71,72} From the electrochemical data in Figure 1, we learn that triarylborane reduction is ~ 0.1 V easier in the closed form of molecule 1 than in its open isomer. One might thus expect a red shift of the $N \rightarrow B$ charge-transfer transition by ~800 cm^{-1} following photoisomerization, but this cannot be reconciled with the UV-vis data in Figure 2b. The strongly F⁻sensitive bands between 372 and 273 nm are at higher energy than the $N \rightarrow B$ transition in the open form, whereas the weakly F⁻-sensitive absorbance between 514 and 466 nm seems too weak and too red shifted in order to be assigned to the N \rightarrow B transition of the closed isomer. Given the more extensive π -conjugation of the photocyclized bridge, we would have expected the oscillator strength of the $N \rightarrow B$ transition to be even higher in the closed form than in the open isomer. Thus, contrary to what we originally hoped, it appears that in-depth computational studies are necessary to gain insight into $N \rightarrow B$ charge transfer in the two isomers of molecule 1, but this is beyond the scope of our experimental investigations.

Luminescence Spectroscopy. The open form of molecule **1** is emissive when irradiated with UV light. Figure 5 shows a series of luminescence spectra that were obtained from a THF solution of the open form of **1**. With increasing irradiation time, the emission intensity decreases, which is a manifestation of



Figure 5. Luminescence of molecule 1 in THF solution measured after different time intervals following irradiation at 355 nm in the fluorimeter. The initial spectrum (solid trace) is from a solution containing mostly the open isomer. Subsequent spectra (dotted traces) contain an increasing proportion of the nonemissive closed isomer. Intensities are normalized arbitrarily to the first spectrum.

photocyclization. The closed form of 1 is nonemissive because of energetically low-lying $\pi - \pi^*$ transitions on the dithienylperfluorocyclopentene bridge (Figure 2a).⁴¹ At long irradiation times, a photostationary state is reached (see above), and the remaining percentage ($\sim 15\%$) of open isomer accounts for the residual emission intensity. Compared to the initial luminescence intensity detected from a freshly prepared solution of the open form of 1, the emission intensity decreases only by a factor of \sim 3, but it should be kept in mind that our samples are highly sensitive to UV light and photoisomerize to a significant extent already in the course of recording the very first luminescence spectrum. This difficulty precludes verification of the F⁻ binding constants from above by complementary luminescence titration experiments. Samples to which F⁻ has been added are nonemissive, and it appears plausible to assign the luminescence of the open (and unfluorinated) form of molecule 1 to a charge-transfer transition involving the triarylamine and triarylborane moieties.

SUMMARY AND CONCLUSIONS

The N \rightarrow B charge-transfer transition can be easily identified in the open form of molecule 1, but for its closed isomer, this seems impossible with experimental means alone. Thus, we conclude that photoisomerizable organic mixed-valence systems, such as those shown on the left of Scheme 1, 45,53 represent more attractive models for investigating charge transfer across photoswitchable bridges than our triarylamine-triarylborane donor-acceptor system. In molecule 1, there is a small influence of photoisomerization on the triarylborane reduction potential, but virtually none on the triarylamine oxidation. We anticipate that this influence would be significantly greater in a molecule in which the N and B atoms of the respective redox-active groups would be attached directly to the two different thiophene units of the photoisomerizable bridge. However, in our hands, such a molecule turned out to be synthetically much less easily accessible than molecule 1, despite a prior report of an analogous compound with an organoboron unit attached directly to a thiophene of a dithienylethene bridge.³⁶

An interesting finding from our study is that addition of F^- to a solution of molecule 1 induces no significant color change, whereas photoisomerization alone produces a blue solution. Only the combined input of UV light and F^- ions leads to a blue-green color.

EXPERIMENTAL SECTION

Dithienylperfluorocyclopentene building block **2** was synthesized following previously published protocols.^{37,53} Briefly, 2-methylthiophene was brominated,⁸⁰ and the resulting 3,5-dibromo-2-methyl-thiophene molecule was reacted with *n*-butyllithium and trimethylsilane to produce 3-bromo-2-methyl-5-trimethylsilylthiophene.⁸¹ Subsequent treatment with *n*-butyllithium and perfluorocyclopentene yielded molecule **2** (4.93 g/9.6 mmol, 17% yield; starting from 13.9 g/ 56.1 mmol of 3-bromo-2-methyl-5-trimethylsilylthiophene and 4.51 mL/33.6 mmol of perfluorocyclopentene).³⁷ ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 0.37 (s, 18H), 2.49 (s, 6H), 7.11 (s, 2H). Deprotection of the trimethylsilyl groups occurred with iodine monochloride following standard protocols,^{82,838586} and this gave molecule **3** in 72% yield (650 mg/1.05 mmol, starting from 750 mg/ 1.46 mmol of compound 2).^{53,82,84} ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 1.91 (s, 6H), 7.20 (s, 2H).

For the synthesis of molecule 4, 4-bromoaniline (5.00 g, 29.2 mmol) and 4-iodoanisole (14.4 g, 61.3 mmol) were reacted in toluene (30 mL) in the presence of CuI (0.28 g, 1.46 mmol), KOH (12.8 g,

228 mmol), and 1,10-phenanthroline (0.26 g, 1.46 mmol). After heating to 90 °C for 3 days, the reaction mixture was cooled to room temperature, diluted with CH₂Cl₂ (200 mL), and washed four times with 150 mL portions of water. The combined organic phases were dried over anhydrous MgSO₄, and the solvent was evaporated subsequently. Purification of the raw product occurred by column chromatography on silica gel using an eluent mixture composed of CH₂Cl₂ and pentane (1:1). This procedure afforded molecule 4 in 57% yield (6.35 g, 16.6 mmol).⁶⁴ ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 3.82 (s, 6H), 6.83 (m, 2H), 6.85 (m, 4H), 7.06 (m, 4H), 7.26 (m, 2H).

Compound 4 (1.77 g, 4.60 mmol) was dissolved in PEG600 (23 mL) along with bis(pinacolato)diboron (1.75 g, 6.90 mmol), bis(triphenylphosphine)palladium(II) chloride (0.16 g, 0.23 mmol), and sodium acetate (1.77 g, 18.4 mmol). After stirring the reaction mixture at 85 °C overnight, water was added (50 mL), and the cooled solution was extracted with diethyl ether (50 mL). The resulting organic phase was washed three times with 75 mL portions of water, and the aqueous phases were re-extracted subsequently with diethyl ether $(3 \times 100 \text{ mL})$. The combined ether phases were dried over anhydrous MgSO₄, and the solvent was removed on a rotary evaporator. The raw product was purified by column chromatography on silica gel using a 1:1 (v:v) mixture of CH₂Cl₂ and pentane as an eluent. Subsequent washing of the dry product with pentane gave pure compound 5 in 32% yield (0.63 g, 1.46 mmol).^{66 1}H NMR (300 MHz, $CDCl_3$: δ (ppm) = 1.34 (s, 12H), 3.82 (s, 6H), 6.85 (d, J = 8.9 Hz, 4H), 6.89 (d, J = 8.6 Hz, 2H), 7.09 (d, J = 8.9 Hz, 4H), 7.62 (d, J = 8.6 Hz, 2H).

Dithienylethene compound 3 (893 mg, 1.44 mmol) and triarylamine unit 5 (388 mg, 0.90 mmol) were dissolved in a mixture of THF (6 mL) and 1 M aqueous sodium carbonate solution (10 mL). After bubbling with N2 during 20 min, tetrakis(triphenylphosphine)palladium(0) (160 mg, 0.14 mmol) was added, and the reaction mixture was heated to 80 °C under N2 overnight. Diethyl ether (25 mL) was added after cooling to room temperature, and the reaction mixture was washed with water $(3 \times 25 \text{ mL})$. The organic phase was dried over anhydrous MgSO4 prior to evaporating the solvent under reduced pressure. Purification of the raw product occurred using column chromatography on silica gel using a 9:1 (v:v) mixture of pentane and diethyl ether. Molecule 6 was obtained in 32% yield (370 mg, 0.46 mmol) as an amorphous solid. ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 1.90 (s, 3H), 1.92 (s, 3H), 3.80 (s, 6H), 6.84 (d, J = 9.0 Hz, 3H), 6.90 (d, J = 8.7 Hz, 2H), 7.06 (d, J = 9.0 Hz, 4H), 7.09 (s, 1H), 7.22 (s, 1H), 7.31 (d, J = 8.7 Hz, 2H). ¹³C NMR (300 MHz, CDCl₃): δ (ppm) = 14.3, 14.5, 29.7, 55.5, 114.8, 119.5, 120.3, 120.6, 126.8, 128.5, 128.7, 133.6, 133.9, 136.2, 140.5, 148.7, 156.1. HRMS (ESI-TOF) m/z [M⁺] Calcd for C₃₅H₂₆NO₂F₆IS₂: 797.0354. Found: 797.0347.

For the synthesis of triarylborane unit 7, *p*-dibromobenzene (1.75 g, 7.57 mmol) was dissolved in dry diethyl ether (20 mL). After cooling to -78 °C, a 1.6 M solution of *n*-butyllithium in hexane was added dropwise (3.4 mL, 6.6 mmol), and the reaction mixture was stirred for 3 h at this temperature. Trimesitylboron fluoride was then added slowly (1.56 g, 5.5 mmol). After stirring the mixture at room temperature overnight, it was washed with aqueous NH₄Cl solution (100 mL) and water (100 mL). The organic phase was dried over anhydrous MgSO₄, and the solvent was removed on a rotary evaporator. After recrystallization from pentane, molecule 7 was obtained in 67% yield (2.05 g, 5.1 mmol).^{65 1}H NMR (300 MHz, CDCl₃): δ (ppm) = 2.00 (s, 12H), 2.31 (s, 6H), 6.83 (s, 4H), 7.37 (d, J = 8.2 Hz, 2H), 7.49 (d, J = 8.2 Hz, 2H).

Molecule 7 (1.35 g, 3.3 mmol) was dissolved in PEG600 (60 mL) along with bis(pinacolato)diboron (1.26 g, 4.95 mmol), bis-(triphenylphosphine)palladium(II) chloride (0.20 g, 0.28 mmol), and sodium acetate (10.8 g, 130 mmol). After heating to 90 °C for 4 h, the reaction mixture was cooled to room temperature, diluted with water (300 mL), and extracted with diethyl ether (3×200 mL). The combined organic phases were dried over anhydrous MgSO₄, and the solvent was removed subsequently on a rotary evaporator. Column chromatography on silica gel using a 9:1 (v:v) mixture of pentane and

diethyl ether afforded pure product **8** in 90% yield (1.36 g, 3.0 mmol).⁶⁶ ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 1.36 (s, 12H), 1.98 (s, 12H), 2.31 (s, 6H), 6.82 (s, 4H), 7.50 (d, *J* = 8.0 Hz, 2H), 7.77 (d, *J* = 8.0 Hz, 2H).

Compound 8 (259 mg, 0.57 mmol) and dithienylethene unit 6 (370 mg, 0.46 mmol) were dissolved together in THF (4 mL) and 1 M aqueous Na2CO3 solution (3 mL). Prior to adding tetrakis-(triphenylphosphine)palladium(0) (120 mg, 0.10 mmol), the reaction mixture was bubbled with N2 during 20 min. After heating to 80 °C under N2 overnight, the mixture was cooled to room temperature and diethyl ether (50 mL) was added. The mixture was then washed with water (3 \times 50 mL), and the combined aqueous phases were reextracted with diethyl ether (2 \times 50 mL). The combined organic phases were dried over anhydrous MgSO4 before evaporating the solvent under reduced pressure. Column chromatography on silica gel using a 9:1 (v:v) mixture of pentane and diethyl ether afforded the open form of molecule 1 in 57% yield (262 mg, 0.26 mmol). ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 1.96 (s, 3H), 1.97 (s, 3H), 2.00 (s, 12H), 2.34 (s, 6H), 3.82 (s, 6H), 6.81–6.91 (m, 8H), 6.93 (d, J = 8.7 Hz, 2H), 7.09 (d, J = 8.9 Hz, 2H), 7.16 (s, 1H), 7.35 (d, J = 8.7 Hz, 2H), 7.41 (s, 1H), 7.54 (s, 4H). ¹¹B NMR (160 MHz, CDCl₃): δ (ppm) = 73.9 (s, 1B). ¹⁹F NMR (282 MHz, CDCl₃): δ (ppm) = -110.0 (m, 4F), -131.9 (m, 2F). HRMS (ESI-TOF-MS) m/z [M⁺] Calcd for C59H52NO2BF6S2: 995.3437. Found: 995.3451. Anal. Calcd for C₅₉H₅₂NO₂BF₆S₂·0.2 C₄H₈O (%): C, 71.07; H, 5.37; N, 1.38; S, 6.32. Found: C, 71.27; H, 5.67; N, 1.21; S, 6.58. Closed isomer: ¹H NMR (300 MHz, CDCl₃): δ (ppm) = 2.03 (s, 12H), 2.15 (s, 6H), 2.33 (s, 6H), 3.83 (s, 6H), 6.74–6.93 (m, 12H), 7.11 (d, J = 8.7 Hz, 4H), 7.36 (d, J = 8.9 Hz, 2H), 7.50–7.58 (m, 4H). ¹³C NMR (300 MHz, CDCl₃): δ (ppm) = 14.2, 15.8, 19.8, 20.4, 21.1, 23.5, 24.9, 55.5, 60.4, 115.0, 118.2, 122.8, 127.4, 127.7, 128.1, 128.3, 129.1, 129.3, 136.4, 139.0, 140.8, 141.5, 149.9, 156.9. Melting point: (78 ± 4) °C.

Cyclic voltammetry was performed using a glassy carbon working electrode and a silver counter electrode, and a silver wire served as a quasi-reference electrode. The supporting electrolyte was 0.1 M tetrabutylammonium hexafluorophosphate (TBAPF₆); decamethylferrocene was added in small quantities for internal voltage calibration. Nitrogen was bubbled through the dried solvents before initiating voltage sweeps at 100 mV/s. UV–vis spectra were recorded on a diode array spectrophotometer; luminescence was measured on a commercial fluorimeter equipped with a double monochromator. Quartz cuvettes were used for all optical spectroscopic experiments.

ASSOCIATED CONTENT

S Supporting Information

¹H and ¹³C NMR spectra of all new compounds, ¹¹B and ¹⁹F NMR spectra of molecule **1**, and ESI-TOF-MS spectra of the new compounds **1** and **6**. This material is available free of charge via the Internet at http://pubs.acs.org.

AUTHOR INFORMATION

Corresponding Author

*E-mail: oliver.wenger@chemie.uni-goettingen.de.

Notes

The authors declare no competing financial interest.

ACKNOWLEDGMENTS

Funding from the Deutsche Forschungsgemeinschaft (DFG) through grant number WE4815/3-1 is acknowledged.

REFERENCES

(1) Wade, C. R.; Broomsgrove, A. E. J.; Aldridge, S.; Gabbaï, F. P. *Chem. Rev.* **2010**, *110*, 3958–3984.

(2) Dusemund, C.; Sandanayake, K.; Shinkai, S. J. Chem. Soc., Chem. Commun. 1995, 333–334.

(3) Aldridge, S.; Bresner, C.; Fallis, I. A.; Coles, S. J.; Hursthouse, M. B. *Chem. Commun.* **2002**, 740–741.

- (4) Bresner, C.; Day, J. K.; Coombs, N. D.; Fallis, I. A.; Aldridge, S.; Coles, S. J.; Hursthouse, M. B. *Dalton Trans.* **2006**, 3660–3667.
- (5) Lee, M. H.; Agou, T.; Kobayashi, J.; Kawashima, T.; Gabbaï, F. P. *Chem. Commun.* **2007**, 1133–1135.
- (6) Hudnall, T. W.; Gabbaï, F. P. J. Am. Chem. Soc. 2007, 129, 11978–11986.
- (7) Hudnall, T. W.; Kim, Y. M.; Bebbington, M. W. P.; Bourissou, D.; Gabbaï, F. P. J. Am. Chem. Soc. **2008**, 130, 10890–10891.
- (8) Broomsgrove, A. E. J.; Addy, D. A.; Bresner, C.; Fallis, I. A.; Thompson, A. L.; Aldridge, S. Chem.—Eur. J. 2008, 14, 7525-7529.
- (9) You, Y. M.; Park, S. Y. Adv. Mater. 2008, 20, 3820-3826.
- (10) Kim, Y.; Gabbai, F. P. J. Am. Chem. Soc. 2009, 131, 3363–3369.
 (11) Hudnall, T. W.; Chiu, C. W.; Gabbaï, F. P. Acc. Chem. Res. 2009, 42, 388–397.
- (12) Lam, S. T.; Zhu, N. A. Y.; Yam, V. W.-W. Inorg. Chem. 2009, 48, 9664–9670.
- (13) Kinoshita, M.; Kita, H.; Shirota, Y. Adv. Funct. Mater. 2002, 12, 780–786.
- (14) Entwistle, C. D.; Marder, T. B. Angew. Chem., Int. Ed. 2002, 41, 2927–2931.
- (15) Entwistle, C. D.; Marder, T. B. Chem. Mater. 2004, 16, 4574–4585.
- (16) Yamaguchi, S.; Wakamiya, A. Pure Appl. Chem. 2006, 78, 1413–1424.
- (17) Sundararaman, A.; Venkatasubbaiah, K.; Victor, M.; Zakharov,
- L. N.; Rheingold, A. L.; Jäkle, F. J. Am. Chem. Soc. 2006, 128, 16554-16565.
- (18) Zhao, C. H.; Wakamiya, A.; Inukai, Y.; Yamaguchi, S. J. Am. Chem. Soc. 2006, 128, 15934–15935.
- (19) Parab, K.; Venkatasubbaiah, K.; Jäkle, F. J. Am. Chem. Soc. 2006, 128, 12879–12885.
- (20) Li, H. Y.; Sundararaman, A.; Venkatasubbaiah, K.; Jäkle, F. J. Am. Chem. Soc. 2007, 129, 5792–5793.
- (21) Elbing, M.; Bazan, G. C. Angew. Chem., Int. Ed. 2008, 47, 834–838.
- (22) Lorbach, A.; Bolte, M.; Li, H. Y.; Lerner, H. W.; Holthausen, M. C.; Jäkle, F.; Wagner, M. Angew. Chem., Int. Ed. 2009, 48, 4584–4588.
- (23) Liu, X. Y.; Bai, D. R.; Wang, S. N. Angew. Chem., Int. Ed. 2006, 45, 5475-5478.
- (24) Stahl, R.; Lambert, C.; Kaiser, C.; Wortmann, R.; Jakober, R. *Chem.—Eur. J.* **2006**, *12*, 2358–2370.
- (25) Yuan, M. S.; Liu, Z. Q.; Fang, Q. J. Org. Chem. 2007, 72, 7915–7922.
- (26) Zhou, G.; Baumgarten, M.; Müllen, K. J. Am. Chem. Soc. 2008, 130, 12477–12484.
- (27) Sun, Y.; Wang, S. N. Inorg. Chem. 2009, 48, 3755-3767.
- (28) Pron, A.; Zhou, G.; Norouzi-Arasi, H.; Baumgarten, M.; Müllen, K. Org. Lett. **2009**, *11*, 3550–3553.
- (29) Schmidt, H. C.; Reuter, L. G.; Hamacek, J.; Wenger, O. S. J. Org. Chem. 2011, 76, 9081–9085.
- (30) Liu, Z. Q.; Shi, M.; Li, F. Y.; Fang, Q.; Chen, Z. H.; Yi, T.; Huang, C. H. Org. Lett. **2005**, *7*, 5481–5484.
- (31) Zhou, Z. G.; Li, F. Y.; Yi, T.; Huang, C. H. Tetrahedron Lett. 2007, 48, 6633–6636.
- (32) Cao, D. X.; Liu, Z. Q.; Li, G. Z. Sens. Actuators, B 2008, 133, 489–492.
- (33) Hudson, Z. M.; Liu, X. Y.; Wang, S. N. Org. Lett. 2011, 13, 300– 303.
- (34) Li, H. Y.; Jäkle, F. Macromol. Rapid Commun. 2010, 31, 915–920.
- (35) Poon, C. T.; Lam, W. H.; Yam, V. W. W. J. Am. Chem. Soc. 2011, 133, 19622–19625.
- (36) Zhou, Z. G.; Yang, H.; Shi, M.; Xiao, S. Z.; Li, F. Y.; Yi, T.; Huang, C. H. *ChemPhysChem* **2007**, *8*, 1289–1292.
- (37) Gilat, S. L.; Kawai, S. H.; Lehn, J. M. Chem.—Eur. J. 1995, 1, 275–284.
- (38) Endtner, J. M.; Effenberger, F.; Hartschuh, A.; Port, H. J. Am. Chem. Soc. 2000, 122, 3037-3046.

- (39) Liddell, P. A.; Kodis, G.; Moore, A. L.; Moore, T. A.; Gust, D. J. Am. Chem. Soc. **2002**, 124, 7668–7669.
- (40) Jukes, R. T. F.; Adamo, V.; Hartl, F.; Belser, P.; De Cola, L. Inorg. Chem. **2004**, 43, 2779–2792.
- (41) Wenger, O. S.; Henling, L. M.; Day, M. W.; Winkler, J. R.; Gray, H. B. *Polyhedron* **2004**, *23*, 2955–2958.
- (42) Jukes, R. T. F.; Adamo, V.; Hartl, F.; Belser, P.; De Cola, L. Coord. Chem. Rev. 2005, 249, 1327–1335.
- (43) Roberts, M. N.; Nagle, J. K.; Finden, J. G.; Branda, N. R.; Wolf, M. O. Inorg. Chem. 2009, 48, 19–21.
- (44) He, B.; Wenger, O. S. Inorg. Chem. 2012, 51, 4335-4342.
- (45) Wenger, O. S. Chem. Soc. Rev. 2012, 41, 3772-3779.
- (46) Fraysse, S.; Coudret, C.; Launay, J.-P. Eur. J. Inorg. Chem. 2000, 1581–1590.
- (47) Kurihara, M.; Matsuda, T.; Hirooka, A.; Yutaka, T.; Nishihara, H. J. Am. Chem. Soc. **2000**, *122*, 12373–12374.
- (48) Motoyama, K.; Koike, T.; Akita, M. Chem. Commun. 2008, 5812-5814.
- (49) Motoyama, K.; Li, H. F.; Koike, T.; Hatakeyama, M.; Yokojima, S.; Nakamura, S.; Akita, M. *Dalton Trans.* **2011**, *40*, 10643–10657.
- (50) Tanaka, Y.; Inagaki, A.; Akita, M. Chem. Commun. 2007, 1169–1171.
- (51) Tanaka, Y.; Ishisaka, T.; Inagaki, A.; Koike, T.; Lapinte, C.; Akita, M. Chem.—Eur. J. 2010, 16, 4762–4776.
- (52) Sakamoto, R.; Murata, M.; Nishihara, H. Angew. Chem., Int. Ed. 2006, 45, 4793-4795.
- (53) He, B.; Wenger, O. S. J. Am. Chem. Soc. 2011, 133, 17027–17036.
- (54) Robin, M. B.; Day, P. Adv. Inorg. Chem. Radiochem. 1967, 10, 247-422.
- (55) Heckmann, A.; Lambert, C. Angew. Chem., Int. Ed. 2012, 51, 326–392.
- (56) Hankache, J.; Wenger, O. S. Chem. Rev. 2011, 111, 5138-5178.
- (57) Feringa, B. L. *Molecular Switches;* Wiley-VCH: Weinheim, Germany, 2001.
- (58) Irie, M. Chem. Rev. **2000**, 100, 1685–1716.
- (59) Raymo, F. M.; Tomasulo, M. J. Phys. Chem. A 2005, 109, 7343-7352.
- (60) Murguly, E.; Norsten, T. B.; Branda, N. R. Angew. Chem., Int. Ed. **2001**, 40, 1752–1755.
- (61) Peters, A.; McDonald, R.; Branda, N. R. *Chem. Commun.* 2002, 2274–2275.
- (62) Belser, P.; De Cola, L.; Hartl, F.; Adamo, V.; Bozic, B.; Chriqui, Y.; Iyer, V. M.; Jukes, R. T. F.; Kuhni, J.; Querol, M.; Roma, S.; Salluce, N. *Adv. Funct. Mater.* **2006**, *16*, 195–208.
- (63) Areephong, J.; Hurenkamp, J. H.; Milder, M. T. W.; Meetsma, A.; Herek, J. L.; Browne, W. R.; Feringa, B. L. *Org. Lett.* **2009**, *11*, 721–724.
- (64) Bushby, R. J.; McGill, D. R.; Ng, K. M.; Taylor, N. J. Chem. Soc., Perkin Trans. 2 1997, 1405–1414.
- (65) Mutaguchi, D.; Okumoto, K.; Ohsedo, Y.; Moriwaki, K.; Shirota, Y. Org. Electron. 2003, 4, 49–59.
- (66) Lu, J.; Guan, Z. Z.; Gao, J. W.; Zhang, Z. H. Appl. Organomet. Chem. 2011, 25, 537–541.
- (67) We note that the respective waves become increasingly important when performing a series of repeated voltage sweeps on the same solution; moreover, a new wave appears at -0.85 V vs Fc⁺/ Fc.
- (68) Particularly diagnostic for distinguishing between the two forms is the resonance from the methyl groups in the ortho position to the C-B bond because the respective signal does not overlap with any other resonances.
- (69) Sreenath, K.; Suneesh, C. V.; Gopidas, K. R.; Flowers, R. A. J. Phys. Chem. A 2009, 113, 6477–6483.
- (70) Sreenath, K.; Thomas, T. G.; Gopidas, K. R. Org. Lett. 2011, 13, 1134–1137.
- (71) Browne, W. R.; de Jong, J. J. D.; Kudernac, T.; Walko, M.; Lucas, L. N.; Uchida, K.; van Esch, J. H.; Feringa, B. L. *Chem.—Eur. J.* **2005**, *11*, 6414–6429.

(72) Browne, W. R.; de Jong, J. J. D.; Kudernac, T.; Walko, M.; Lucas, L. N.; Uchida, K.; van Esch, J. H.; Feringa, B. L. *Chem.—Eur. J.* **2005**, *11*, 6430–6441.

(73) Peters, A.; Branda, N. R. Chem. Commun. 2003, 954-955.

(74) Peters, A.; Branda, N. R. J. Am. Chem. Soc. 2003, 125, 3404–3405.

(75) Yamaguchi, S.; Akiyama, S.; Tamao, K. J. Am. Chem. Soc. 2000, 122, 6335-6336.

- (76) Kaim, W.; Schulz, A. Angew. Chem., Int. Ed. 1984, 23, 615-616.
- (77) Zális, S.; Kaim, W. Main Group Chem. 2006, 5, 267-276.

(78) Bourson, J.; Pouget, J.; Valeur, B. J. Phys. Chem. 1993, 97, 4552-4557.

(79) In an attempt to test our hypothesis, we tried to suppress the N \rightarrow B charge-transfer transition by adding Brönsted acids to our solutions; but unfortunately, this seemed to induce sample decomposition.

(80) Pu, S. Z.; Liu, G.; Li, G. Z.; Wang, R. J.; Yang, T. S. J. Mol. Struct. 2007, 833, 23–29.

(81) de Meijere, A.; Zhao, L. G.; Belov, V. N.; Bossi, M.; Noltemeyer, M.; Hell, S. W. *Chem.—Eur. J.* **2007**, *13*, 2503–2516.

(82) Hensel, V.; Schlüter, A. D. Liebigs Ann. 1997, 303-309.

(83) Hanss, D.; Wenger, O. S. Eur. J. Inorg. Chem. 2009, 3778-3790. (84) Hensel, V.; Lutzow, K.; Jacob, J.; Gessler, K.; Saenger, W.;

Schlüter, A. D. Angew. Chem., Int. Ed. 1997, 36, 2654–2656.

(85) Walther, M. E.; Wenger, O. S. Dalton Trans. 2008, 6311–6318.
(86) Hanss, D.; Walther, M. E.; Wenger, O. S. Coord. Chem. Rev. 2010, 254, 2584–2592.