

Magnetic properties of disordered Ising ternary alloys

This article has been downloaded from IOPscience. Please scroll down to see the full text article.

1998 J. Phys.: Condens. Matter 10 5359

(<http://iopscience.iop.org/0953-8984/10/24/013>)

View [the table of contents for this issue](#), or go to the [journal homepage](#) for more

Download details:

IP Address: 171.66.16.209

The article was downloaded on 14/05/2010 at 16:32

Please note that [terms and conditions apply](#).

Magnetic properties of disordered Ising ternary alloys

T Kaneyoshi and Y Nakamura

Department of Natural Science Informatics, School of Informatics and Sciences, Nagoya University, 464-01, Nagoya, Japan

Received 29 December 1997, in final form 10 February 1998

Abstract. A theoretical framework for treating a disordered Ising ternary alloy $(A_p B_{1-p})_r C_{1-r}$ where A and B represent magnetic atoms and C represents non-magnetic atoms is discussed within the effective-field theory with correlations. The magnetic properties of some disordered alloys with spins $S_A = \frac{1}{2}$ and $S_B = \frac{1}{2}$ (or $S_B = \frac{3}{2}$) are investigated within the framework. We find some characteristic phenomena for a ferrimagnetic alloy with $S_B = \frac{3}{2}$, such as an interesting effect of non-magnetic atoms on a compensation point (or points).

1. Introduction

The magnetic properties of a disordered Ising binary alloy $A_p B_{1-p}$ in which the lattice sites are randomly occupied by two different types of magnetic atom (A and B, with spins S_A and S_B) have been investigated by many authors, using a variety of theoretical methods (molecular-field theory, effective-field theory, CPA, Monte Carlo simulation). In these studies, there has been some interest shown in the phase diagrams of a disordered binary alloy consisting of spins $S_A = S_B = \frac{1}{2}$, with a transition temperature $T_C(p)$ as a function of concentration p [1–3]. The phase diagrams have been usefully classified in terms of the initial slopes $\partial \ln T_C(p)/\partial p$ of T_C at $p = 1$ and $p = 0$, and six (or seven) phases have been obtained from the possible nine phases, while molecular-field theory (MFT) predicts only four possible phases. On the other hand, some attention has been paid to the study of ferrimagnetic disordered binary alloys. In particular, Kaneyoshi *et al* [4–6] have proposed recently the possibility of many compensation points in a disordered Ising ferrimagnetic binary alloy with $S_A = \frac{1}{2}$ and $S_B > \frac{1}{2}$ as well as a thin ferrimagnetic film.

Amorphous ferromagnetic (or ferrimagnetic) alloys, in particular transition metal–metalloid (or rare-earth–transition metal–metalloid) glasses, have been well studied experimentally for the purpose of fundamental research and with a view to technological applications [7, 8]. They can be described by the general formula $(A_p B_{1-p})_r C_{1-r}$ where A and B represent magnetic atoms with concentrations pr and $(1-p)r$, respectively, and C is the non-magnetic metalloid with concentration $1-r$. The concentration dependence of T_C has been intensively investigated experimentally, and a good correspondence between experimental data and mean-field-type predictions can be found in [9]. The temperature dependence of the total magnetization has been analysed by the use of the MFT [7]. As far as we are aware, however, the magnetic properties of a disordered ferrimagnetic Ising ternary alloy have not been discussed so far theoretically using a sophisticated theory superior to the MFT. In particular, the effects of non-magnetic atoms on a compensation point (or points) in the ferrimagnetic alloy have not been discussed.

The aim of this work is to study the theoretical framework for a disordered Ising ternary alloy $(A_p B_{1-p})_r C_{1-r}$ with $S_A = \frac{1}{2}$ and $S_B = S (\geq \frac{1}{2})$ in the effective-field theory with correlations (EFT) [10, 11], which is superior to the MFT. The formulation is discussed in section 2. In section 3, the initial slopes $\partial \ln T_C(p)/\partial p$ at $p = 1$ and $p = 0$ for a disordered Ising ternary alloy with $S_A = S_B = \frac{1}{2}$ are investigated, and the phase diagrams are examined numerically for the system with the coordination number $z = 4$. In section 4, we study the magnetic properties of a disordered Ising ferrimagnetic ternary alloy with $S_A = \frac{1}{2}$ and $S_B = \frac{3}{2}$. The effects of non-magnetic atoms on these properties are clarified numerically in sections 3 and 4.

2. Formulation

We consider a ternary Ising alloy of the type $(A_p B_{1-p})_r C_{1-r}$ with sites randomly occupied by three different species, where A and B are magnetic atoms and the C atoms are non-magnetic. The Hamiltonian of the system is given by

$$H = - \sum_{(ij)} \sum_{v,v'=A \text{ or } B} J_{vv'} S_{iv}^z S_{jv'}^z n_{iv} n_{jv'} \xi_i \xi_j - D \sum_i (S_{iB}^z)^2 n_{iB} \xi_i \quad (1)$$

where the $J_{vv'}$ are the exchange interactions between type- v and type- v' atoms (or $J_{AA} = J_A$, $J_{AB} = J_{BA}$, $J_{BB} = J_B$), the S_{iv}^z are the spin variables of the type- v atoms, $n_{iv} = 1$ if the spin i is of type v , and 0 otherwise, and the $\sum_{(ij)}$ refers to all nearest neighbours. ξ_i is a random variable whose averaged value is given by $\langle \xi_i \rangle_r = r$ when the site i is occupied by a magnetic atom. The averaged value of n_{iv} is then given by $\langle n_{iv} \rangle_r = p$ when $v = A$ and $\langle n_{iv} \rangle_r = 1 - p$ when $v = B$. D is the crystal-field interaction constant of a B atom, appearing when $S_B > \frac{1}{2}$. The total magnetization M of the system is given by

$$\frac{M}{N} = r[p m_A + (1 - p) m_B] \quad (2)$$

where N is the total number of atoms, and the averaged magnetizations are defined by

$$m_A = \frac{\langle n_{iA} \xi_i \langle S_{iA}^z \rangle_r \rangle_r}{\langle n_{iA} \xi_i \rangle_r} \quad m_B = \frac{\langle n_{iB} \xi_i \langle S_{iB}^z \rangle_r \rangle_r}{\langle n_{iB} \xi_i \rangle_r} \quad (3)$$

with

$$\langle n_{iA} \xi_i \rangle_r = r p$$

and

$$\langle n_{iB} \xi_i \rangle_r = r(1 - p).$$

Using both the Ising spin identity and the differential operator technique ([10, 11], and see the review [12]), the averaged magnetizations can be exactly represented in the forms

$$m_A = \frac{1}{\langle n_{iA} \xi_i \rangle_r} \left\langle n_{iA} \xi_i \left\langle \prod_j \left[1 - \xi_j + n_{jA} \xi_j \left\{ \cosh\left(\frac{J_A}{2} \nabla\right) + 2 S_{jA}^z \sinh\left(\frac{J_A}{2} \nabla\right) \right\} \right. \right. \right. \\ \left. \left. \left. + n_{jB} \xi_j \left\{ \cosh(J_{AB} \eta \nabla) + \frac{S_{jB}^z}{\eta} \sinh(J_{AB} \eta \nabla) \right\} \right] \right\rangle_r F_A(x) \Big|_{x=0} \right. \quad (4a)$$

$$m_B = \frac{1}{\langle n_{iB} \xi_i \rangle_r} \left\langle n_{iA} \xi_i \left\langle \prod_j \left[1 - \xi_j + n_{jA} \xi_j \left\{ \cosh\left(\frac{J_{AB}}{2} \nabla\right) + 2 S_{jA}^z \sinh\left(\frac{J_{AB}}{2} \nabla\right) \right\} \right. \right. \right. \\ \left. \left. \left. + n_{jB} \xi_j \left\{ \cosh(J_A \eta \nabla) + \frac{S_{jB}^z}{\eta} \sinh(J_B \eta \nabla) \right\} \right] \right\rangle_r F_B(x) \Big|_{x=0} \right. \quad (4b)$$

where $\nabla = \partial/\partial x$ is a differential operator. The parameter η defined when $S_B > \frac{1}{2}$ is given by

$$\eta^2 = \frac{\langle n_{iB} \xi_i \langle (S_{iB}^z)^2 \rangle_r \rangle_r}{\langle n_{iB} \xi_i \rangle_r} = \frac{1}{\langle n_{iB} \xi_i \rangle_r} \left\langle n_{iB} \xi_i \left[\prod_j \left[1 - \xi_j + n_{jA} \xi_j \left\{ \cosh \left(\frac{J_{AB}}{2} \nabla \right) + 2S_{jA}^z \sinh \left(\frac{J_{AB}}{2} \nabla \right) \right\} \right] + n_{jB} \xi_j \left\{ \cosh (J_B \eta \nabla) + \frac{S_{jB}^z}{\eta} \sinh (J_B \eta \nabla) \right\} \right] \right\rangle_r G_B(x) \Big|_{x=0} \quad (5)$$

The function $F_A(x)$ is

$$F_A(x) = \frac{1}{2} \tanh \left(\frac{\beta x}{2} \right) \quad (6)$$

and the functions $F_B(x)$ and $G_B(x)$ are dependent on the value of S_B , and are given by

$$F_B(x) = \frac{3 \sinh(3\beta x/2) + \exp(-2D\beta) \sinh(\beta x/2)}{2 \cosh(3\beta x/2) + 2 \exp(-2D\beta) \cosh(\beta x/2)} \quad (7)$$

$$G_B(x) = \frac{9 \cosh(3\beta x/2) + \exp(-2D\beta) \cosh(\beta x/2)}{2 \cosh(3\beta x/2) + 2 \exp(-2D\beta) \cosh(\beta x/2)}$$

for $S_B = \frac{3}{2}$, where $\beta = 1/k_B T$.

Here, it is clear that, if we try to treat all of the spin-spin correlations appearing through the expansions of (4) exactly, the problem becomes mathematically intractable. In the EFT, the decoupling approximation, or

$$\langle \langle x_{i\nu} x_{j\nu'} \cdots x_{k\nu''} \rangle \rangle_r \approx \langle \langle x_{i\nu} \rangle \rangle_r \langle \langle x_{j\nu'} \rangle \rangle_r \cdots \langle \langle x_{k\nu''} \rangle \rangle_r \quad (8)$$

with $i \neq j \neq \cdots \neq k$ and $x_{i\nu} = S_{i\nu}^z n_{i\nu} \xi_i$, has been used. In fact, this approximation corresponds to the Zernike approximation for the spin- $\frac{1}{2}$ Ising ferromagnet [12]. The approximation has been successfully applied to a great number of magnetic systems. Within the EFT, the magnetizations (4) and the equation (5) are given by

$$m_A = \left[1 - r + rp \left\{ \cosh \left(\frac{J_A}{2} \nabla \right) + 2m_A \sinh \left(\frac{J_A}{2} \nabla \right) \right\} + r(1-p) \left\{ \cosh (J_{AB} \eta \nabla) + \frac{m_B}{\eta} \sinh (J_{AB} \eta \nabla) \right\} \right]^z F_A(x) \Big|_{x=0} \quad (9a)$$

$$m_B = \left[1 - r + rp \left\{ \cosh \left(\frac{J_{AB}}{2} \nabla \right) + 2m_A \sinh \left(\frac{J_{AB}}{2} \nabla \right) \right\} + r(1-p) \left\{ \cosh (J_B \eta \nabla) + \frac{m_B}{\eta} \sinh (J_B \eta \nabla) \right\} \right]^z F_B(x) \Big|_{x=0} \quad (9b)$$

and

$$\eta^2 = \left[1 - r + rp \left\{ \cosh \left(\frac{J_{AB}}{2} \nabla \right) + 2m_A \sinh \left(\frac{J_{AB}}{2} \nabla \right) \right\} + r(1-p) \left\{ \cosh (J_B \eta \nabla) + \frac{m_B}{\eta} \sinh (J_B \eta \nabla) \right\} \right]^z G_B(x) \Big|_{x=0} \quad (9c)$$

where z is the coordination number.

We are now interested in investigating the magnetic properties of a disordered Ising ternary alloy. The problems are examined in the following sections by selecting separately two values of S_B , namely $S_B = \frac{1}{2}$ and $S_B = \frac{3}{2}$.

3. Phase diagrams of a system with $S_B = 1/2$

In this section, let us study the phase diagram of a disordered Ising ternary alloy with $S_A = S_B = \frac{1}{2}$. With this aim, we use the usual argument that m_α ($\alpha = A$ or B) tends to zero as the temperature approaches a critical temperature, which allows us to consider just terms linear in m_α . In particular, the parameter η for the system with $S_B = \frac{1}{2}$ is exactly given by $\eta = \frac{1}{2}$ [11]. By the use of these procedures, the critical temperature T_C (or phase diagram) of a disordered ternary alloy can be determined by solving the relation

$$[2zrpK_1 - 1][2zr(1 - p)K_4 - 1] = 4(zr)2p(1 - p)K_2K_3 \quad (10)$$

with

$$K_1 = \sinh\left(\frac{J_A}{2}\nabla\right) \left[1 - r + rp \cosh\left(\frac{J_A}{2}\nabla\right) + r(1 - p) \cosh\left(\frac{J_{AB}}{2}\nabla\right)\right]^{z-1} f(x) \Big|_{x=0} \quad (11a)$$

$$K_2 = \sinh\left(\frac{J_{AB}}{2}\nabla\right) \left[1 - r + rp \cosh\left(\frac{J_A}{2}\nabla\right) + r(1 - p) \cosh\left(\frac{J_{AB}}{2}\nabla\right)\right]^{z-1} f(x) \Big|_{x=0} \quad (11b)$$

$$K_3 = \sinh\left(\frac{J_{AB}}{2}\nabla\right) \left[1 - r + rp \cosh\left(\frac{J_{AB}}{2}\nabla\right) + r(1 - p) \cosh\left(\frac{J_B}{2}\nabla\right)\right]^{z-1} f(x) \Big|_{x=0} \quad (11c)$$

$$K_4 = \sinh\left(\frac{J_B}{2}\nabla\right) \left[1 - r + rp \cosh\left(\frac{J_{AB}}{2}\nabla\right) + r(1 - p) \cosh\left(\frac{J_B}{2}\nabla\right)\right]^{z-1} f(x) \Big|_{x=0} \quad (11d)$$

where the function $f(x)$ is defined by $f(x) = F_B(x) = F_A(x)$ given by (6). T_C depends on the values of J_A , J_{AB} , J_B , p , r and z . In particular, one should be aware of the following facts.

(i) T_C determined from (10) is independent of the sign of J_{AB} , or (10) is valid for the ferromagnetic ($J_{AB} > 0$) case as well as for the antiferromagnetic ($J_{AB} < 0$) case.

(ii) When $r = 1$, the relation (10) is equivalent to that for a disordered binary alloy discussed in [2].

The initial slopes $\partial \ln T_C(p)/\partial p$ at $p = 1$ and $p = 0$ can be obtained by differentiating (10) with respect to p . Without loss of generality, we suppose that $T_C(p = 1) > T_C(p = 0)$ (or $J_A > J_B$) and also that $J_{AB} > 0$ for studying the phase diagram. Then, the simplest possible phase boundary is a straight-line extrapolation for $T_C(p)$ between $T_C(0)$ and $T_C(1)$. Furthermore, the three possible types of behaviour can be identified from the initial slopes at $p = 0$: (1) a slope greater than that of the linear extrapolation, (2) a slope less than that of the linear extrapolation but greater than zero, and (3) a slope less than zero. There are also three similar types of behaviour at $p = 1$. These phase boundaries can be given by the following relations:

$$\left[\frac{\partial \ln T_C(p)}{\partial p}\right]_{p=1} = 0 \quad (12a)$$

$$\left[\frac{\partial \ln T_C(p)}{\partial p}\right]_{p=1} = \frac{T_C(p = 1) - T_C(p = 0)}{T_C(p = 1)} \quad (12b)$$




Figure 1. Possible kinds of phase diagram in the space $(J_{AB}/\sqrt{J_A J_B}, J_B/J_A)$ of the Ising ferromagnetic ternary alloy with $z = 4$ (on a square lattice), when the two values of r are selected. In particular, the results for $r = 1$ (solid lines) are equivalent to those for the Ising binary alloy [2]. The dashed lines represent the results for $r = 0.7$. The six kinds of phase diagram (S, S', A, A', B and B₁) are shown, where the nomenclature of [1] is used. The black points a–d are the points for which the complete phase boundaries are shown in figure 2.

$$\left[\frac{\partial \ln T_C(p)}{\partial p} \right]_{p=0} = 0 \tag{12c}$$

$$\left[\frac{\partial \ln T_C(p)}{\partial p} \right]_{p=0} = \frac{T_C(p=1) - T_C(p=0)}{T_C(p=0)}. \tag{12d}$$

Nine phase diagrams may be possible from these phase boundaries. But, one should note the following facts. The initial slopes by no means provide a complete description of the phase diagram obtained by solving (10) numerically, namely obtaining $T_C(p)$ as a function of p . They do however, severely restrict what can occur and so can be used as the basis of a classification scheme.

We are in a position to examine the phase diagrams of a system by solving (10) and (12) numerically. In order to compare them with the previous ones obtained for a disordered Ising binary alloy [2], the numerical results are shown for a square lattice ($z = 4$).

Figure 1 shows a classification of the phase diagrams of the system with $z = 4$ which is plotted in the space $(J_{AB}/\sqrt{J_A J_B}, J_B/J_A)$, for two selected values of r ($r = 1$ and $r = 0.7$).




Figure 2. Complete phase boundaries for $z = 4$. The ratios $(J_{AB}/\sqrt{J_A J_B}, J_B/J_A)$ for the black points a–d marked in figure 1 are as follows: a: (0.2, 0.3); b: (1.0, 0.3); c: (1.5, 0.3) and d: (2.5, 0.3). The dashed lines are to guide the eye only. Parts (a) and (b) are respectively for $r = 1$ and $r = 0.7$.

The results have been determined from the initial slopes (12). In the figure, we used the same notation in describing the kinds of phase diagram as was used in [1–3], namely T, A, A', B, B₁, S, S', S₁ and S'₁. The results for $r = 1$ are equivalent to those found in [2] for the binary Ising alloy with $z = 4$. Only six kinds of phase diagram (A, A', B, B₁, S and S') are permitted from the nine possible phases. Comparing the results for $r = 1$ (solid lines) with those for $r = 0.7$ (dashed lines), the boundaries obtained from (12a) and (12c) are seen to be insensitive to the variation of r . In particular, with the decrease of r the region of parameter space in which S and S' occur are extremely expanded, while the regions in which A and A' occur become narrower in comparison with the corresponding regions for $r = 1$. Features similar to these have been also observed in the phase diagram of a binary alloy with random bonds [3]. Thus, such features may be specific characteristics resulting from the randomness in binary or ternary alloys.

In figure 2, the overall behaviour of $T_C(p)$ as a function of p is depicted; it was obtained by solving (10) numerically for the systems with $r = 1$ (figure 2(a)) and $r = 0.7$ (figure 2(b)), selecting the special values of J_{AB} , J_A and J_B that are labelled in figure 1 (the black points a–d in figure 1). At first sight, the diagrams seem very similar for the




Figure 2. (Continued)

two ($r = 1$ or $r = 0.7$) cases. Looking at them in detail, however, one can find different behaviours of $T_C(p)$, especially in the vicinity of $p = 0$, as is expected from figure 1.

Finally, let us examine the effect of dilution on T_C for the ternary alloy by selecting the typical values of J_{AB} , J_A and J_B ($J_{AB}/J_A = 0.707$ and $J_B/J_A = 0.5$) labelled in figure 1 and changing the value of p . The results are shown in figure 3 for five values of p . In particular, the curves for $p = 1$ and $p = 0$ are equivalent to those for the dilution in the spin- $\frac{1}{2}$ Ising ferromagnet on a square lattice [14]. As discussed in [14], the critical concentration r_C at which $T_C(r)$ reduces to zero is given by $r_C = 0.4284$ for the systems with $p = 1$ and $p = 0$. When $0 < p < 1$, the T_C -curve as a function of r reduces to zero at the same critical concentration r_C as those for $p = 1$ and $p = 0$. This, indicates that the decoupling approximation (or the EFT) gives reasonable results for the present problem.

4. Ferrimagnetism in the system with $S_B = 3/2$

In this part, let us study the role of non-magnetic atoms in the magnetic properties of the disordered Ising ferrimagnetic ternary alloy with $z = 3$ and $S_B = \frac{3}{2}$, since in the previous work [4] the magnetic properties of the corresponding ferrimagnetic binary alloy $A_p B_{1-p}$ have been examined.

The transition temperature T_C of a disordered ternary alloy is then determined from the




Figure 3. The concentration dependence of $T_C(p)$ for the diluted Ising ternary alloy with $z = 4$, when the ratios J_{AB}/J_A and J_B/J_A are fixed at $J_{AB}/J_A = 0.707$ and $J_B/J_A = 0.5$ and various values of p are selected. The results for $p = 1$ and $p = 0$ are equivalent to those for the diluted Ising binary alloy with $z = 4$ [13].

relation

$$[2zrpK_1 - 1] \left[zr(1-p) \frac{R_2}{\eta_0} - 1 \right] = 2(zr)2p(1-p) \frac{R_1 K_2}{\eta_0} \quad (13)$$

with

$$K_1 = \sinh\left(\frac{J_A}{2}\nabla\right) \left[1 - r + r \left\{ p \cosh\left(\frac{J_A}{2}\nabla\right) + (1-p) \cosh(J_{AB}\eta_0\nabla) \right\} \right]^{z-1} F_A(x) \Big|_{x=0} \quad (14a)$$

$$K_2 = \sinh\left(\frac{J_{AB}\eta_0}{2}\nabla\right) \left[1 - r + r \left\{ p \cosh\left(\frac{J_A}{2}\nabla\right) + (1-p) \cosh(J_{AB}\eta_0\nabla) \right\} \right]^{z-1} F_A(x) \Big|_{x=0} \quad (14b)$$

$$R_1 = \sinh\left(\frac{J_{AB}}{2}\nabla\right) \left[1 - r + r \left\{ p \cosh\left(\frac{J_{AB}}{2}\nabla\right) + (1-p) \cosh(J_B\eta_0\nabla) \right\} \right]^{z-1} F_B(x) \Big|_{x=0} \quad (14c)$$

$$R_2 = \sinh\left(\frac{J_B\eta_0}{2}\nabla\right) \left[1 - r + r \left\{ p \cosh\left(\frac{J_{AB}}{2}\nabla\right) + (1-p) \cosh(J_B\eta_0\nabla) \right\} \right]^{z-1} F_B(x) \Big|_{x=0} \quad (14d)$$




Figure 4. The phase diagram (T_C and T_{COMP} versus p curves) of the disordered ferrimagnetic ternary alloy with $z = 3$, when the parameters are fixed at $J_{AB}/J_A = -0.5$, $J_B/J_A = 0.05$, $D/J_A = 0.0$ and the value of r is changed from $r = 1.0$ to 0.6. The solid and dashed lines represent respectively the compensation temperature T_{COMP} and the Curie temperature T_C of the system.




Figure 5. T_C (dashed line) and T_{COMP} (solid line) for the system with $z = 3$ plotted as a function of $|J_{AB}|/J_A$, when the parameters are fixed at $p = 0.745$, $J_B/J_A = 0.5$, $D/J_A = 0.0$, and the value of r is changed from $r = 1.0$ to 0.6.






Figure 6. The $|M|/N$ versus T curves for the system with $p = 0.745$, $J_B/J_A = 0.5$, $D/J_A = 0.0$ and $z = 3$, when the value of r is changed from $r = 1.0$ to 0.6 and the three values of J_{AB}/J_A are selected from the phase diagram of figure 5; $J_{AB}/J_A = -0.45$ for panel (a), $J_{AB}/J_A = -0.54$ for panel (b), $J_{AB}/J_A = -0.59$ for panel (c).



(c)

Figure 6. (Continued)

where the parameter η_0 can be evaluated from

$$(\eta_0)^2 = \left[1 - r + r p \cosh\left(\frac{J_{AB}}{2}\right) + (1 - p) \cosh(J_B \eta_0 \nabla) \right]^z G_B(x) \Big|_{x=0}. \quad (15)$$

A compensation point, at which the total magnetization vanishes below the transition temperature, in the system can be determined by substituting the condition

$$\frac{M}{N} = 0 \quad (16)$$

in (2). Here, the following fact must be noted: the exchange interaction J_{AB} is given by a negative value, in order for the present system to be ferrimagnetic.

Let us now examine the magnetic properties of the ferrimagnetic system with $z = 3$ by solving (13), (9) and (16) numerically. Figure 4 shows a typical phase diagram (T_C and T_{COMP} versus p) for the ferrimagnetic system, when $J_{AB}/J_A = -0.5$, $J_B/J_A = 0.05$, $D/J_A = 0.0$ and the value of r is changed. For real ferrimagnetic ternary alloys based on rare earths (RE) and transition metals (T), the relation $J_A(J_{T-T}) > -J_{AB}(J_{RE-T}) > J_B(J_{RE-RE})$ is normally satisfied. The solid and dashed lines represent the T_{COMP} - and T_C -curves, respectively. When $r = 1.0$, the T_{COMP} -curve reduces to zero at $p = 0.75$, since at $T = 0$ K, $S_A = \frac{1}{2}$ and $S_B = \frac{3}{2}$ in (16). With the decrease of r , the sublattice magnetizations at $T = 0$ K decrease from their saturation values, and hence the critical value of p at which $T_{COMP} = 0$ may decrease a little, moving to the left-hand side, from $p = 0.75$. As shown in figure 4, the region of p in which a compensation point can be obtained becomes narrow, when the concentration of non-magnetic atoms increases. As far as we are aware, such a phenomenon has not previously been reported.

In [4], the possibility of more than one compensation point in a binary ferrimagnetic alloy with $z = 3$ has been discussed within the framework of the EFT, selecting $D/J_A = 0.0$, $J_B/J_A = 0.5$, $p = 0.745$ and changing the value of $|J_{AB}/J_A|$ (see figure 5(a) in [4]). Let us next study the effect of non-magnetic atoms on the T_{COMP} -curve for the ternary alloy system with $D/J_A = 0.0$, $J_B/J_A = 0.5$ and $p = 0.745$. The numerical results are depicted in figure 5. The solid and dashed lines denote the T_{COMP} - and T_C -curves, respectively. The results labelled $r = 1.0$ are equivalent to those in figure 5(a) of [4] and there is a possibility of two compensation points over a rather wide region of $|J_{AB}/J_A|$. The results of figure 5 indicate some interesting facts.

(i) The possibility of two compensation points becomes gradually less with the increase in the number of non-magnetic atoms.

(ii) The region of $|J_{AB}/J_A|$ in which one can find a compensation point becomes wider with the decrease of r from $r = 1$.

In particular, phenomenon (ii) is clearly different to what is shown in figure 4.

In order to clarify the prediction of figure 5, the temperature dependence of the total magnetization $|M|/N$ in the system with $p = 0.745$, $J_B/J_A = 0.5$ and $D/J_A = 0.0$ has been plotted in figure 6, selecting the special values of J_{AB}/J_A chosen in figure 5: -0.45 for figure 6(a), -0.54 for figure 6(b) and -0.59 for figure 6(c). As is seen from the figures, one can find some characteristic magnetization curves not predicted in the Néel theory of ferrimagnetism [15, 16], such as the curve labelled $r = 0.7$ in figure 6(c).




Figure 7. The phase diagram of the ferrimagnetic system obtained with $z = 3$, $J_{AB}/J_A = -2.465$, $J_B/J_A = 0.1$, $D/J_A = -2.0$ and with the concentration near $p = 0.5$, when the value of r is changed from $r = 1.0$ to 0.7 . The solid and dashed lines represent respectively the compensation temperature T_{COMP} and the Curie temperature T_C of the system.

Figure 7 shows the possibility of three compensation points in the system with $J_B/J_A = 0.1$, $J_{AB}/J_A = -2.465$, $D/J_A = -2.0$ and $r = 1.0$; the result is consistent




Figure 8. The $|M|/N$ versus T curves for the system obtained with $p = 0.495$, $J_{AB}/J_A = -2.465$, $J_B/J_A = 0.1$, $D/J_A = -2.0$ and $z = 3$, when the value of r is changed from $r = 1.0$ to 0.7 .

with that of figure 6(a) in [4]. With the decrease of r , the possibility immediately becomes an impossibility. For the systems with $r = 0.9$ and 0.8 , only one compensation point is observed over a wide range of p , although the region in which one can find a compensation point for the system with $r = 0.7$ becomes narrower than that for $r = 0.8$. In particular, the effect of non-magnetic atoms on the temperature dependence of M/N for the system with $p = 0.495$, $J_B/J_A = 0.1$, $J_{AB}/J_A = -2.465$ and $D/J_A = -2.0$ is shown in figure 8, for four selected values of r . The figure also shows that the three compensation points for the system with $r = 1$ quickly become impossible with the decrease of r .

5. Conclusions

In this work, we have discussed the theoretical framework for the magnetic properties of a disordered Ising ternary alloy $(A_p B_{1-p})_r C_{1-r}$ consisting of two kinds of magnetic atom, A and B, with spins $S_A = \frac{1}{2}$ and $S_B = S (> \frac{1}{2})$, and a non-magnetic atom C, on the basis of the effective-field theory with correlations. The formulation given in section 2 can be applied to any system with a certain value of S .

In section 3, the formulation was applied to the examination of phase diagrams for the system with $z = 4$ (the square lattice) and $S_A = S_B = \frac{1}{2}$. As depicted in figures 2 and 3, the numerical results are reasonable, which also implies that the decoupling approximation (8) (or the EFT) has physical meaning. Figure 1 clearly shows that with dilution the regions representing the phases A and A' decrease and instead the regions representing S and S' may increase, although the number of possible phases is always fixed at six. We have compared our model system without non-magnetic atoms to real materials such as

Fe–Co-based amorphous alloys and found good agreement [17].

In section 4, we have examined the effects of non-magnetic atoms on the magnetic properties of the disordered ferrimagnetic Ising ternary alloy with $z = 3$. With the decrease of r , as shown in figure 4, the T_{COMP} -curve for a system with $J_A > -J_{AB} > J_B$ becomes narrow in the region of $|J_{AB}/J_A|$. As shown in figures 5 and 7, the possibility of more than one compensation point in the ferrimagnetic binary alloy with $r = 1$ is easily removed by substituting non-magnetic atoms into the alloy. Some interesting thermal variations of the total magnetization in the ferrimagnetic system are expected with the decrease of r , as depicted in figure 6(c).

Finally, the present formulation discussed in section 2 can be applied to a disordered Ising ternary alloy with an arbitrary value of S_B , while in this work we have discussed only the two systems with $S_B = \frac{1}{2}$ and $S_B = \frac{3}{2}$. We assume that study of a ferrimagnetic ternary alloy system with $S_B =$ an integer spin value will be interesting, since tricritical behaviour may be found for this system with a negative value of D [18]. We hope to investigate this problem in the future.

References

- [1] Thorpe M F and McGurn A R 1979 *Phys. Rev. B* **20** 2142
- [2] Honmura R, Khater A F, Fittipaldi I P and Kaneyoshi T 1982 *Solid State Commun.* **41** 385
- [3] Kaneyoshi T and Li Z Y 1987 *Phys. Rev. B* **35** 1869
- [4] Kaneyoshi T and Jascur M 1993 *J. Phys.: Condens. Matter* **5** 3253
- [5] Kaneyoshi T 1995 *J. Magn. Magn. Mater.* **140–144** 261
Kaneyoshi T 1995 *Physica B* **210** 178
- [6] Kaneyoshi T 1994 *J. Phys.: Condens. Matter* **6** 1069
Jascur M and Kaneyoshi T 1997 *Phys. Status Solidi b* **203** 507
- [7] Kaneyoshi T 1992 *Introduction to Amorphous Magnets* (Singapore: World Scientific)
- [8] Moorjani K and Coey J M D 1984 *Magnetic Glasses* (Amsterdam: Elsevier)
- [9] Luborsky F E 1980 *J. Appl. Phys.* **51** 2808
- [10] Honmura R and Kaneyoshi T 1979 *J. Phys. C: Solid State Phys.* **12** 3979
- [11] Kaneyoshi T, Tucker J W and Jascur M 1992 *Physica A* **186** 495
- [12] Kaneyoshi T 1993 *Acta Phys. Pol. A* **83** 703
- [13] Zernike F 1940 *Physica* **7** 565
- [14] Kaneyoshi T, Tamura I and Sarmento E F 1983 *Phys. Rev. B* **28** 6491
- [15] Néel L 1948 *Ann. Phys., Paris* **3** 137
- [16] Herpin A 1968 *Theorie du Magnetisme* (Saclay: Presses Universitaires de France)
- [17] Kaneyoshi T 1986 *Phys. Rev. B* **34** 7866
- [18] Kaneyoshi T 1984 *Amorphous Magnetism* (Boca Raton, FL: Chemical Rubber Company Press)