

Corrigendum

Corrigendum to “Synthesis, structure, and magnetism of  $\text{Tb}_4\text{PdGa}_{12}$   
and  $\text{Tb}_4\text{PtGa}_{12}$ ”  
[J. Solid State Chem. 178 (2005) 52–57]

Willa M. Williams<sup>a</sup>, M. Moldovan<sup>b</sup>, D.P. Young<sup>b</sup>, Julia Y. Chan<sup>a,\*</sup>

<sup>a</sup>Department of Chemistry, Louisiana State University, 232 Choppin Hall, Baton Rouge, LA 70803, USA

<sup>b</sup>Department of Physics and Astronomy, Louisiana State University, Baton Rouge, LA 70803, USA

Available online 3 May 2005

In Table 2 on page 54, the Ga1 atom which occupies Wyckoff site 12*d* should have the following atomic positions: (1/2,*y*,1/2), where *y* = 0.204366(3) and 0.203989(2) for  $\text{Tb}_4\text{PdGa}_{12}$  and  $\text{Tb}_4\text{PtGa}_{12}$ , respectively. The Ga2 atoms which occupy the 12*e* Wyckoff site should have the following coordinates: (1/2,0,1/4). The correct atomic positions are as follows:

Table 2  
Atomic positions and thermal parameters of  $\text{Tb}_4M\text{Ga}_{12}$  (*M* = Pd, Pt)

		<i>x</i>	<i>y</i>	<i>Z</i>	$U_{\text{eq}}^a$ (Å <sup>2</sup> )
Tb1	8 <i>c</i>	3/4	3/4	3/4	0.00495(4)
Pd1	2 <i>a</i>	0	0	0	0.00739(3)
Ga1	12 <i>d</i>	1/2	0.2037(2)	1/2	0.00968(6)
Ga2	12 <i>e</i>	1/2	0	1/4	0.00713(6)
Tb1	8 <i>c</i>	3/4	3/4	3/4	0.0164(6)
Pt1	2 <i>a</i>	0	0	0	0.0148(4)
Ga1	12 <i>d</i>	1/2	0.2048(2)	1/2	0.0161(5)
Ga2	12 <i>e</i>	1/2	0	1/4	0.0152(5)

<sup>a</sup> $U_{\text{eq}}$  is defined as one-third of the trace of the orthogonalized  $U_{ij}$  tensor.

DOI of original article: [10.1016/j.jssc.2004.10.026](https://doi.org/10.1016/j.jssc.2004.10.026).

\*Corresponding author. Fax: +1225 578 3458.

E-mail address: [jchan@lsu.edu](mailto:jchan@lsu.edu) (J.Y. Chan).