

# JOURNAL OF SOLID STATE CHEMISTRY

## Editor

**Mercouri G. Kanatzidis**

*Northwestern University*

*Evanston, Illinois, USA*

*E-mail: m-kanatzidis@northwestern.edu*

## Associate Editors

**Jing Li**

*Rutgers University*

*Piscataway, New Jersey, USA*

*E-mail: jingli@rutchem.*

*rutgers.edu*

**Wolfgang Tremel**

*Universität Mainz*

*Mainz, Germany*

*E-mail: tremel@uni-*

*mainz.de*

**Patrick M. Woodward**

*The Ohio State University*

*Columbus, Ohio, USA*

*E-mail: woodward@chemistry.*

*ohio-state.edu*

**Hans-Conrad zur Loye**

*University of South Carolina*

*Columbia, South Carolina, USA*

*E-mail: jssc@mail.chem.*

*sc.edu*

## Editorial Board

**John E. Greedan**

*McMaster University*

*Hamilton, Ontario, Canada*

**Martha Greenblatt**

*Rutgers University*

*Piscataway, New Jersey, USA*

**Yuri Grin**

*MPI für Chemische Physik fester Stoffe*

*Dresden, Germany*

**William T. A. Harrison**

*University of Aberdeen*

*Aberdeen, Scotland, UK*

**Jurgen M. Honig**

*Purdue University*

*West Lafayette, Indiana, USA*

**James A. Ibers**

*Northwestern University*

*Evanston, Illinois, USA*

**Shuichi Iida**

*University of Tokyo*

*Tokyo-to, Japan*

**Allan J. Jacobson**

*University of Houston*

*Houston, Texas, USA*

**Martin Jansen**

*MPI für Festkörperforschung*

*Stuttgart, Germany*

**Stéphane Jobic**

*Université de Nantes*

*Nantes Cédex, France*

**Susan M. Kauzlarich**

*University of California, Davis*

*Davis, California, USA*

**Holger Kleinke**

*University of Waterloo*

*Waterloo, Ontario, Canada*

**Kwang-Hwa Lii**

*National Center University*

*Chungli, Taiwan*

**Thomas E. Mallouk**

*Pennsylvania State University*

*University Park, Pennsylvania, USA*

**Jiang-Gao Mao**

*Fujian Institute for Research on  
the Structure of Matter, Fuzhou, China*

**Arthur Mar**

*University of Alberta*

*Edmonton, Alberta, Canada*

**Gordon J. Miller**

*Iowa State University*

*Ames, Iowa, USA*

**Thomas J. Pinnavaia**

*Michigan State University*

*East Lansing, Michigan, USA*

**Kenneth R. Poeppelmeier**

*Northwestern University*

*Evanston, Illinois, USA*

**Rainer Pöttgen**

*Westfälische Wilhelms-Universität Münster*

*Münster, Germany*

**C.N.R. Rao**

*Nehru Centre for Advanced Sci. Res.*

*Bangalore, Karnakata, India*

**Bernard Raveau**

*Laboratoire CRISMAT*

*Caen Cédex 4, France*

**Peter F. Rogl**

*Universität Wien*

*Wien, Austria*

**Matthew J. Rosseinsky**

*University of Liverpool*

*Liverpool, England, UK*

**Wolfgang Schnick**

*Ludwig-Maximilians Universität Münster*

*Münster, Germany*

**Slavi Sevon**

*University of Notre Dame*

*South Bend, Indiana, USA*

**Arthur W. Sleight**

*Oregon State University*

*Corvallis, Oregon, USA*

**Galen D. Stucky**

*University of California, Santa Barbara*

*Santa Barbara, California, USA*

**Mikio Takano**

*Kyoto University*

*Kyoto-fu, Japan*

**Charlie C. Torardi**

*E. I. Du Pont and Company*

*Wilmington, Delaware, USA*

**Gustav van Tenderloo**

*University of Antwerp*

*Antwerp, Belgium*

**Terrell Vanderah**

*National Institute of Standards and  
Technology, Gaithersburg, Maryland, USA*

**Ray L. Withers**

*Australian National University*

*Canberra, ACT, Australia*

Founding Editors: R. E. Hughes M. J. Sienko A. Wold

Editor 1983–1999: J. M. Honig

Cover Art. The crystal structure of  $\text{Pb}_4\text{Mn}_9\text{O}_{20}$  is based on a  $6\text{H}(\text{cch})_2$  close packing of “h”-type ( $\text{O}_{16}$ ) layers alternating with “c”-type ( $\text{Pb}_4\text{O}_{12}$ ) layers. Article by A.M. Abakumov *et al.* on pp. 2231–2238 of this issue.