

Fig. 1.-X-Ray diffraction patterns.

TABLE I

- Sample Method of preparation Results of X-ray analysis 1 An equimolar amount of Amorphous to X-rays InCl₃ solution (0.1 M) was added rapidly to 100 ml. of saturated NH4VO3 solution at room temperature. The yellowish gel was washed in a centrifuge and dried in air
 - 2 An equimolar amount of Amorphous to X-rays InCl₃ solution (0.1 M) was added rapidly to 100 ml. of NH4VO3 solution (saturated at 90°). The gel was washed in a centrifuge, and dried at 120°
 - 3 Sample no. 1 heated for two Pattern consists of hours at 850° numerous lines distinct from
 - Sample no. 2 heated for two 4 hours at 1000°
 - 5 Equimolar quantities of dry In(OH)₃ and dry NH₄VO₃ were ground for two hours in a motor-driven agate mortar, and were heated for two hours at 850°
 - 6 Prepared as no. 5, except the amounts of dry powders were taken to give 40 mole % In₂O₃ and 60 mole % of V_2O_5
 - 7 Prepared as no. 5, except the amounts of dry powders were taken to give 60 mole % of In₂O₃ and 40 mole %V₂O₅

Mole % In2Oa V2Oa Standard In₂O₃

40 Dry way 50Dry way 50Wet way 60 Dry way Standard V₂O₅

any definite evidence concerning the constitution or even the existence of indium vanadates.

The purpose of this present investigation was to attempt to prepare a definite indium vanadate.

Experimental.—Seven samples in the system indium trioxide-vanadium pentoxide were prepared by wet and dry methods as outlined in the table. The samples were examined by standard X-ray diffraction methods, using $Cr K \alpha$ X-radiation. The $K\beta$ X-radiation was removed completely by a supplementary filter of vanadium pentoxide. The results of X-ray analysis are likewise summarized in the table.

Discussion.—It will be noted that both gels prepared by precipitation are amorphous to X-rays. There is no indication of the formation of a definite crystalline indium vanadate. It is not known whether these gels consist of an amorphous indium vanadate or of a mixture of amorphous indium oxide or hydroxide together with amorphous vanadium pentoxide.

Samples heated to temperatures of 850–1000° are sub-microscopically crystalline and yield a diffraction pattern consisting of numerous relatively sharp lines. This pattern is distinct from those of anhydrous In_2O_3 or V_2O_5 , and is therefore assumed to be characteristic of a definite indium vanadate. Since samples containing excess of either component yield diffraction lines from the excess oxide, it is believed that the compound formed is indium orthovanadate, InVO₄. X-Ray diffraction patterns for $InVO_4$, In_2O_3 and V_2O_5 are given in chart form in Fig. 1. The data cannot be indexed in the cubic or tetragonal crystal systems. The numerical data of the observed interplanar spacings and visually estimated intensities have been tabulated and included in the card index file of the American Society for Testing Materials (ASTM).

DEPARTMENT OF CHEMISTRY THE RICE INSTITUTE HOUSTON, TEXAS

sharp

those of In2O3 or

Pattern identical with

Pattern identical with

Pattern consists of all

Pattern consists of all

lines found in no. 5

plus some weak

plus some

V₂O₅ lines

In₂O₃ lines

lines found in no. 5

weak

nos. 3 and 4

V₂O₅

no. 3

RECEIVED JUNE 23, 1948

Absorption Spectra of 4-(4-Diethylamino-1methylbutylamino)-7-phenoxyquinoline and 4-(4-Diethylamino-1-methylbutylamino)-7-ethoxy-3-methylquinoline

By FREDERICK C. NACHOD, EDGAR A. STECK AND GALEN W. Ewing¹

A comparison of the absorption spectra of 4-(4diethylamino - 1 - methylbutylamino) - 7 - phenoxy-

(1) Present address: Department of Chemistry, Union College. Schenectady 8, N. Y.

232(18.9)

TABLE I

COMPARISON OF THE SPECTRA OF 4-(4-DIETHYLAMINO-1-METHYLBUTYLAMINO)-QUINOLINE WITH 7-SUBSTITUTED CON-GENERS, IN 0.1 N HYDROCHLORIC ACID

Compound

4-(4-Diethylamino-1-methylbutylamino)-quinoline

4-(4-Diethylamino-1-methylbutylamino)-7-phenoxyquinoline

228 (33.6) 4-(4-Diethylamino-1-methylbutylamino)-7-ethoxy-3-methylquinoline 233 (28.7) 259^b (17.8)

^a Inflection point. ^b Small secondary maximum.

quinoline^{2,3} (SN 10,663)⁴ and the parent compound, 4-(4-diethylamino-1-methylbutylamino)quinoline (SN 6732)^{4,5} both in 0.01 N hydrochloric acid, shows that there is a slight but definite hypsochromic shift of $4 \text{ m}\mu$ throughout the whole spectrum. This is doubtless due to the combined influences of an ether link and the unconjugated aryl group attached in position 7. As we have earlier noted,6 the views of Irvin and Irvin7 concerning the effect of a 7-substituent upon the tautomerism of the 4-aminoquinoline type are well substantiated. In this instance, the weighting due to the phenoxy group is greater than the halogens and is also more pronounced. The unconjugated phenyl radical behaves very much as the simpler alkoxy substituents in the case of the 4-(4-diethylamino-1-methylbutylamino)-7-ethoxy-3-methylquinoline,⁸ inasmuch as benzene shows no pronounced absorption in this general region.⁹ Since the ethoxy compound also bears a methyl substitution, it also exhibits the slight batho- and hypochromic shift inherent to 3-methyl substitution, as we have shown (cf. Fig. 2, ref. 6).

(2) Drake, et al., THIS JOURNAL, 68, 1208 (1946); Riegel, et al., ibid., 68, 1264 (1946); Clinton and Suter, ibid., 69, 704 (1947).

(3) The authors are indebted to Dr. R. O. Clinton for the sample employed.

(4) All drugs identified by Survey Numbers (SN) in the files of the Antimalarial Survey office have been tabulated, with antimalarial activities, in the work by Wiselogle, editor, "Antimalarial Drugs, 1941-1945," Edwards Bros., Ann Arbor, Mich., 1946.

(5) Steck, Hallock and Suter, THIS JOURNAL, 70, unpublished (1948).

(6) Steck, Ewing and Nachod, ibid., 70, 3410 (1948).

(7) Irvin and Irvin, ibid., 69, 1091 (1947).

(8) Steck, Ewing and Nachod, ibid., forthcoming paper.

(9) Dimroth, Angew. Chem., 52, 548 (1939).

STERLING-WINTHROP RESEARCH INSTITUTE **RECEIVED APRIL 29, 1948** RENSSELAER, NEW YORK

Preparation of Methanesulfonyl Chloride

BY C. R. NOLLER AND P. J. HEARST

Three methods commonly have been used for the preparation of methanesulfonyl chloride, a valuable reagent, namely, by the action of phosphorus pentachloride on sodium methanesulfonate,¹ and by the action of chlorine and water on smethylisothiourea² or on methyl thiocyanate.³

Yields are not very satisfactory by the first method, and it is difficult to remove phosphorus compounds from the product.⁴ The second compounds from the product.⁴

- (1) Marvel, Helfrick and Beasley, THIS JOURNAL, 51, 1272 (1929).
- (2) Johnson and Sprague, ibid., 58, 1348 (1936).
- (3) Johnson and Douglass, ibid., 61, 2548 (1939).

(4) Helferich and Gnüchtei, Ber., 71, 712 (1938).

method is potentially dangerous since violent explosions of products apparently formed by excessive chlorination have been reported.⁵ The third method works well but is disagreeable because cyanogen chloride is one of the products of the reaction.

Maxima, $m\mu$ and $(\epsilon \times 10^3)$

250° (19.0)

So far as the writers are aware, there is no reference in chemical literature to the preparation of sulfonyl chlorides directly from sulfonic acids by the action of thionyl chloride, although this reagent commonly is used to prepare carboxylic acid chlorides from carboxylic acids. With the availability of methanesulfonic acid commercially, the preparation of methanesulfonyl chloride by this reaction was tried. It was obtained in good yield and the procedure developed far excels those previously reported.

ADDED TO PROOF:--- A recent publication⁶ indicates that alkanesulfonyl chlorides may be prepared by the action of either thionyl chloride or phosphorus trichloride on the sulfonic acids. Directions are given for the preparation of methanesulfonyl chloride in 57% yield from methanesulfonic acid and phosphorus trichloride.

Experimental

In a 200-cc., three-necked flask, fitted with a mechanical stirrer, a reflux condenser, a thermometer and a separatory funnel, and set up in a hood, is placed 152 g. (105 cc., 1.5 moles) of 95% methanesulfonic acid (Standard Oil Co. of Indiana). The acid is heated to 95° on a steam-bath, and 146 cc. (238 g., 2.0 moles) of thionyl chloride (Eastman Kodak Co. grade) is added over a period of four hours. The temperature is kept at 95° throughout the addition, and heating is continued for three and one-half hours after the addition has been completed.

The product is transferred to a modified Claisen flask and distilled at reduced pressure, using an oil-bath to supply heat. Most of the thionyl chloride distills at room temperature. A free flame should be avoided, since local superheating causes charring and decomposition. The fumes from the decomposition cause the normally clear product to darken. The bath temperature should not exceed 115° at the end of the distillation. The yield of product distilling at 67–73 ° (20 mm.) is 122 g. (71% of the theoretical amount).

(5) Folkers, Russell and Bost, THIS JOURNAL, 63, 3530 (1941).

(6) Proell, Adams and Shoemaker, Ind. Eng. Chem., 40, 1129 (1948).

DEPARTMENT OF CHEMISTRY STANFORD UNIVERSITY STANFORD, CALIFORNIA

RECEIVED JULY 6, 1948

Reduction of Sugar Epoxides to Desoxysugars

By D. A. PRINS

Derivatives of 2-desoxy-p-allose have been prepared from the convenient and readily available

330 (18.8) 340 (18.5)

330 (18.8) 336 (18.6)

330(14.5)