


A 64-Nuclear Cubic Cage Incorporating Propeller-like Fe Apices and HCOO Edges

Tao Liu, Yan-Juan Zhang, Zhe-Ming Wang, and Song Gao

J. Am. Chem. Soc., **2008**, 130 (32), 10500-10501 • DOI: 10.1021/ja803846z • Publication Date (Web): 18 July 2008

Downloaded from <http://pubs.acs.org> on February 8, 2009



More About This Article

Additional resources and features associated with this article are available within the HTML version:

- Supporting Information
- Access to high resolution figures
- Links to articles and content related to this article



ACS Publications
High quality. High impact.

- Copyright permission to reproduce figures and/or text from this article

[View the Full Text HTML](#)



A 64-Nuclear Cubic Cage Incorporating Propeller-like Fe^{III}_8 Apices and HCOO^- Edges

Tao Liu, Yan-Juan Zhang, Zhe-Ming Wang,* and Song Gao*

Beijing National Laboratory for Molecular Sciences, State Key Laboratory of Rare Earth Materials Chemistry and Applications, College of Chemistry and Molecular Engineering, Peking University, Beijing 100871, People's Republic of China

Received May 29, 2008; E-mail: zmw@pku.edu.cn; gaosong@pku.edu.cn

High nuclearity clusters are currently of great interest, by virtue of their structural beauty and their important role in connecting micro to macro and quantum to classic regimes.^{1–10} While many such systems have been explored, for example, giant polyoxometalates,¹ giant metal-chalcogenide clusters,² inorganic fullerene-like molecules,³ lanthanide hydroxo compounds,⁴ and oxo-clusters containing both d- and f-block metals,⁵ those containing magnetic transition metals attract special and continuous attention regarding their rich magnetism such as high ground-state spin values,⁶ single molecular magnet (SMM)⁷ and coupled SMM behavior by weak linkages,⁸ and their promising applications for data storage,⁷ quantum computing,⁹ and spintronics.¹⁰ Various ligands, especially multipodal ones,¹¹ are widely employed in the syntheses of such high nuclearity species. However, many simple and popular ligands, like acetate, can also afford compounds of high nuclearity.¹² With these serendipities in mind, we are currently exploring the mixed-ligand system of triethanolamine ($\text{N}(\text{CH}_2\text{CH}_2\text{OH})_3$, *teaH*₃), a tripodal ligand having been recently used for synthesizing polynuclear species,^{11,13} and formate HCOO^- , the smallest and simplest carboxylate of small steric hindrance, favoring both formation of metal-oxo clusters and further linkage of them.¹⁴ The outcome is, quite surprising and interesting, a large cubic cage consisting of 64 Fe^{3+} ions of $\{[\text{Fe}_8\text{O}_3(\text{tea})(\text{teaH})_3(\text{HCOO})_6]_8(\text{HCOO})_{12}\}(\text{ClO}_4)_{12} \cdot 3\text{CH}_3\text{OH} \cdot 36\text{H}_2\text{O}$ (**Fe**₆₄) (*tea* = $\text{N}(\text{CH}_2\text{CH}_2\text{O})_3^{3-}$ and *teaH* = $\text{N}(\text{CH}_2\text{CH}_2\text{O})_2(\text{CH}_2\text{CH}_2\text{OH})^{2-}$). Fe^{3+} -oxo-based clusters have been continuously studied.^{15–18} They can display ground state of spin values from 0 up to 25 and pleasing physical properties such as the Néel vector tunneling of Fe_8 wheel¹⁷ and the large magnetocaloric effect in an Fe_{14} cluster.¹⁸

Fe₆₄ was obtained by a very slow crystallization procedure or reaction lasting 2 months (Supporting Information, SI). The structure analysis (SI) revealed a cubic cage (Figure 1) containing 64 Fe^{3+} ions, 24 O^{2-} , 8 *tea*³⁻, 24 *teaH*²⁻, and 60 HCOO^- , thus a total of 180 components. The cubic cage consists of eight corners of octanuclear $[\text{Fe}^{\text{III}}_8\text{O}_3(\text{tea})(\text{teaH})_3(\text{HCOO})_6(\text{HCOO})_{3/2}]$ unit (Fe_8 , Figure 1a,b) with a propeller-like Fe_8O_3 core, linked further by 12 *anti-anti* formate ions as the edges of the cube (Figure 1c). The Fe_8 corner possesses similar structure to $[\text{Fe}_8\text{O}_3(\text{O}_2\text{CPh})_9(\text{tea})(\text{teaH})_3] \cdot \text{MeCN}$ and related octanuclear compounds,¹⁶ and the Fe_8 moiety has been found in some high nuclearity clusters.^{15b} Its propeller-like core has two central axial Fe^{3+} ions bridged by three $\mu_4\text{-O}^{2-}$, and each $\mu_4\text{-O}^{2-}$ further bridges two peripheral Fe^{3+} ions in pair, one upper and one lower (Figure 1b), being one of the three blades of the propeller. The Fe_8O_3 core thus consists of three flattened $[\text{Fe}_4(\mu_4\text{-O})]$ tetrahedra sharing the central Fe–Fe axis of the core. The Fe^{3+} ions are further linked by ligands, *tea*³⁻, *teaH*²⁻, and HCOO^- . The upper axial Fe^{3+} ion is capped by one *tea*³⁻ via the N atom and the three alkoxide O atoms, thus this Fe^{3+} ion is 7-fold coordinated in a face-capped octahedron. Each alkoxide O




Figure 1. The structure of Fe_{64} cubic cage. (a and b) Top and side view of the Fe_8 corner. Atomic scheme: Fe, large green (peripheral) and yellow (central) spheres; O, small red and purple (the three $\mu_4\text{-O}^{2-}$) spheres; N, blue spheres; C, gray spheres. (c) The cubic cage with the corner Fe_8O_3 cores and HCOO^- edges highlighted (O red and C black) while other parts in thin sticks. H atoms, ClO_4^- anions, and lattice solvents are not included.

atom of the *tea*³⁻ connects one upper peripheral Fe^{3+} ion. However, each lower peripheral Fe^{3+} ion is chelated by one *teaH*²⁻ through its N atom and two alkoxide arm O atoms, of which one further links the lower central Fe^{3+} ion, and the other to one upper peripheral Fe^{3+} ion, leaving one alcohol arm free of coordination. Therefore, the lower axial Fe^{3+} ion is octahedrally coordinated by O atoms. In each blade, the two peripheral Fe^{3+} ions are bridged by two *syn-syn* HCOO^- ligands, and the upper peripheral Fe^{3+} ion is finally coordinated by one HCOO^- ligand, which is one edge connecting to other Fe_8 corner of the cube (Figure 1b,c). Each Fe_8 corner thus has three HCOO^- ligands to link the other three Fe_8 corners, and its central axis points to the cube center, with the *tea*³⁻ cap inside the cube. It is noted that the coordinate octahedra of Fe^{3+} ions are face-sharing for the two central axial Fe^{3+} ions ($\text{Fe} \cdots \text{Fe}$ 2.994 Å), edge-sharing between the central and peripheral Fe^{3+} ions ($\text{Fe} \cdots \text{Fe}$ 2.988–3.132 Å), apex-sharing between the central and peripheral Fe^{3+} ions ($\text{Fe} \cdots \text{Fe}$ 3.638–3.902 Å), and apex-sharing between the peripheral Fe^{3+} ions ($\text{Fe} \cdots \text{Fe}$ 3.270–3.539 Å). It could be estimated that the magnetic interaction within the Fe_8 corner should be strong or major. The $\text{Fe} \cdots \text{Fe}$ distances spanned by the *anti-anti* HCOO^- edge are 5.806–5.943 Å, and the cube has edges of 13.2 Å counting the separation between the outer axial Fe atoms of the corners. It is clear that the small steric hindrance of HCOO^- ligand¹⁴ allows the further linkage of the bulk Fe_8 units. The successful synthesis of the Fe_{64} cage reveals that the HCOO^- ligand is indeed beneficial for synthesizing species of high nuclearity. In the lattice, the cationic Fe_{64} cubic cages have their 3-fold axes parallel to the *c* axis, and form the hexagonal




Figure 2. χT versus T plots under 1 kOe field, and M versus H plots (inset) for Fe_{64} and Fe_{6a} . Data are for one Fe^{3+} .

closest packing layer (Figure S1 in SI) along the ab plane, then these layers stack along the c direction in ABCABC style, with interstices occupied by ClO_4^- anions, lattice water and methanol, mostly disordered. The shortest intercage $\text{Fe}\cdots\text{Fe}$ separation is 8.61 Å.

In a different preparation using Fe^{3+} source, we obtained the compound of $[\text{Fe}_8\text{O}_3(\text{tea})(\text{teaH})_3(\text{HCOO})_9]\{[(\text{CH}_3\text{CH}_2)_3\text{NH}^+](\text{ClO}_4^-)\}_3(\text{H}_2\text{O})_{0.5}$ (Fe_{8a}), in quite a high yield (SI). The compound consists of discrete neutral octanuclear $[\text{Fe}_8\text{O}_3(\text{tea})(\text{teaH})_3(\text{HCOO})_9]$ molecules, with similar molecular structure (Figure S2 in SI) to the Fe_8 corner of the Fe_{64} cage. The shortest intercluster $\text{Fe}\cdots\text{Fe}$ separation is 7.05 Å. However, several attempts to prepare Fe_{64} from Fe^{3+} source were unsuccessful (SI).

The magnetic study of Fe_{64} was performed on carefully selected small crystals of Fe_{64} but still containing a very small amount of impurity of the ferrimagnetic $[\text{Fe}_3(\text{HCOO})_6](\text{solvent})^{19}$ and weak ferromagnetic $\text{Fe}(\text{HCOO})_2 \cdot 2\text{H}_2\text{O}^{20}$ probably (SI). As depicted in Figure 2, at 300 K, the χT value is $1.39 \text{ cm}^3 \text{ mol}^{-1} \text{ K}$ per Fe^{3+} , significantly lower than the value of $4.375 \text{ cm}^3 \text{ mol}^{-1} \text{ K}$ expected for the noninteracting high-spin Fe^{3+} ion ($S = 5/2$ and $g = 2.00$). It decreases almost linearly with lowering temperature to $0.016 \text{ cm}^3 \text{ mol}^{-1} \text{ K}$ at 2.0 K. A broad maximum of the corresponding χ is observed at 170 K (Figure S3 in SI). The overall behavior is clearly indicative of strong antiferromagnetic interactions between the Fe^{3+} centers. The rise in χ values and a kink in χT around 16 K is due to the impurity of ferrimagnetic $[\text{Fe}_3(\text{HCOO})_6](\text{solvent})$ with critical temperature of 16.1 K,¹⁹ and further rise in χ values below 5 K might be due to the impurity of weak ferromagnetic $\text{Fe}(\text{HCOO})_2 \cdot 2\text{H}_2\text{O}$ with critical temperature of 3.7 K.²⁰ The impurity is responsible for the rapid rise of the isothermal magnetization in the low field region at 2 K (Figure 2 inset). However, the very low value of $0.08 \text{ N}\beta$ per Fe^{3+} even at 50 kOe, far below the saturation value expected ($5 \text{ N}\beta$ per Fe^{3+} assuming $g = 2.00$), confirms the significant antiferromagnetic interactions within the material. The isothermal magnetization at 30 K, above the critical temperatures of the two assumed impurities, is linear and reaches only $0.06 \text{ N}\beta$ per Fe^{3+} at 50 kOe. The magnetic behavior of the Fe_{64} cage is similar to the related discrete octanuclear species¹⁶ possessing the same propeller-like Fe_8O_3 core. It is clear that in the Fe_{64} cage the antiferromagnetic interaction within the Fe_8 corner is strong and dominant, and the magnetic interaction between Fe_8 corners through the *anti-anti* HCOO^- edge is minor but it could have an effect on the magnetism. The higher peak temperature of 170 K of Fe_{64} versus 80 K of Fe_{8a} in temperature-dependent susceptibility (Figure S3 in SI) revealed that the *anti-anti* HCOO^- bridges in the Fe_{64} cage provide further significant interaction between the Fe_8 corners, compared to Fe_{8a} which contains discrete neutral octanuclear species only. Both Fe_{64}

and Fe_{8a} have $S = 0$ ground state as observed for many even-numbered Fe^{3+} -oxo-based clusters.^{15,16}

In conclusion, a high nuclearity cubic cage involving 64 Fe^{3+} ions has been successfully synthesized, and it displays strong antiferromagnetism. This demonstrates that the combination of the small steric hindrance HCOO^- and polydodal ligands can provide a new route to obtain high nuclearity magnetic clusters and/or further linkage of them, thus giving the opportunity to explore their beautiful structures and interesting magnetism.

Acknowledgment. This work was supported by the NSFC (Grants 20571005, 20221101, 20490210), the National Basic Research Program of China (Grant 2006CB601102), and the Research Fund for the Doctoral Program of Higher Education (Grant 20050001002).

Supporting Information Available: An X-ray crystallographic file in CIF format for Fe_{64} and Fe_{8a} , a PDF file containing further information and Figures S1–S3. This material is available free of charge via the Internet at <http://pubs.acs.org>.

References

- (1) Müller, A.; Henry M. C. R. *Chimie* **2003**, *6*, 1201. and refs cited therein.
- (2) (a) Anson, C. E.; Eichhöfer, A.; Issac, I.; Fenske, D.; Fuhr, O.; Sevillano, P.; Persau, C.; Stalke, D.; Zhang, J. *Angew. Chem., Int. Ed.* **2008**, *47*, 1326. (b) Fenske, D.; Persau, C.; Dehnen, S.; Anson, C. E. *Angew. Chem., Int. Ed.* **2004**, *43*, 305.
- (3) Bai, J.-F.; Virovets, A. V.; Scheer, M. *Science* **2003**, *300*, 781.
- (4) (a) Cheng, J.-W.; Zhang, J.; Zheng, S.-T.; Zhang, M.-B.; Yang, G.-Y. *Angew. Chem., Int. Ed.* **2006**, *45*, 73. (b) Zheng, Z.-P. *Chem. Commun.* **2001**, 2521.
- (5) (a) Kong, X.-J.; Ren, Y.-P.; Chen, W.-X.; Long, L.-S.; Zheng, Z.-P.; Huang, R.-B.; Zheng, L.-S. *Angew. Chem., Int. Ed.* **2008**, *47*, 2398. (b) Kong, X.-J.; Ren, Y.-P.; Long, L.-S.; Zheng, Z.-P.; Huang, R.-B.; Zheng, L.-S. *J. Am. Chem. Soc.* **2007**, *129*, 7016.
- (6) Murugesu, M.; Habrych, M.; Wernsdorfer, W.; Abboud, K. A.; Christou, G. *J. Am. Chem. Soc.* **2004**, *126*, 4766.
- (7) Gatteschi, D.; Sessoli, R.; Villain, J. *Molecular Nanomagnets*; Oxford University Press: New York, 2007.
- (8) (a) Miyasaka, H.; Yamashita, M. *Dalton Trans.* **2007**, 399. (b) Wernsdorfer, W.; Aliaga-Alcalde, N.; Hendrickson, D. N.; Christou, G. *Nature* **2002**, *416*, 406.
- (9) (a) Leuenberger, M. N.; Loss, D. *Nature* **2001**, *410*, 789. (b) Lehmann, J.; Gaita-Ariño, A.; Coronado, E.; Loss, D. *Nat. Nanotechnol.* **2007**, *2*, 312.
- (10) Bogani, L.; Wernsdorfer, W. *Nat. Mater.* **2008**, *7*, 179.
- (11) (a) Aromí, G.; Brechin, E. K. *Struct. Bonding (Berlin)* **2006**, *122*, 1. (b) Brechin, E. K. *Chem. Commun.* **2005**, 5141.
- (12) Tasiopoulos, A. J.; Vinslava, A.; Wernsdorfer, W.; Abboud, K. A.; Christou, G. *Angew. Chem., Int. Ed.* **2004**, *43*, 2117.
- (13) Wang, W.-G.; Zhou, A.-J.; Zhang, W.-X.; Tong, M.-L.; Chen, X.-M.; Nakano, M.; Beedle, C. C.; Hendrickson, D. N. *J. Am. Chem. Soc.* **2007**, *129*, 1014.
- (14) (a) Fang, Q.-R.; Zhu, G.-S.; Jin, Z.; Xue, M.; Wei, X.; Wang, D.-J.; Qiu, S.-L. *Angew. Chem., Int. Ed.* **2006**, *45*, 6126. (b) Wang, Z.-M.; Zhang, B.; Zhang, Y.-J.; Kurmoo, M.; Liu, T.; Gao, S.; Kobayashi, H. *Polyhedron* **2007**, *26*, 2207, and refs cited therein.
- (15) (a) Bagai, R.; Daniels, M. R.; Abboud, K. A.; Christou, G. *Inorg. Chem.* **2008**, *47*, 3318. (b) Foguet-Albiol, D.; Abboud, K. A.; Christou, G. *Chem. Commun.* **2005**, 4282. (c) Murugesu, M.; Clérac, R.; Wernsdorfer, W.; Anson, C. E.; Powell, A. K. *Angew. Chem., Int. Ed.* **2005**, *44*, 6678. (d) Gatteschi, D.; Sessoli, R.; Cornia, A. *Chem. Commun.* **2000**, 725, and refs cited therein. (e) Powell, A. K.; Heath, S. L.; Gatteschi, D.; Pardi, L.; Sessoli, R.; Spina, G.; Del Giallo, F.; Pieralli, F. *J. Am. Chem. Soc.* **1995**, *117*, 2491.
- (16) (a) Ako, A. M.; Waldmann, O.; Mereacre, V.; Klöwer, F.; Hewitt, I. J.; Anson, C. E.; Güdel, H. U.; Powell, A. K. *Inorg. Chem.* **2007**, *46*, 756. (b) Jones, L. F.; Jensen, P.; Moubaraki, B.; Bery, K. J.; Boas, J. F.; Pilbrow, J. R.; Murray, K. S. *J. Mater. Chem.* **2006**, *16*, 2690. (c) Murugesu, M.; Abboud, K. A.; Christou, G. *Dalton Trans.* **2003**, 4552.
- (17) (a) Waldmann, O.; Dobe, C.; Mutka, H.; Furrer, H.; Güdel, H. U. *Phys. Rev. Lett.* **2005**, *95*, 057202. (b) Waldmann, O.; Dobe, C.; Güdel, H. U.; Mutka, H. *Phys. Rev.* **2006**, *B74*, 054429.
- (18) (a) Evangelisti, M.; Luis, F.; de Jongh, L. J.; Affronte, M. *J. Mater. Chem.* **2006**, *16*, 2534. (b) Evangelisti, M.; Candini, A.; Ghirri, A.; Affronte, M.; Brechin, E. K.; McInnes, E. J. L. *Appl. Phys. Lett.* **2005**, *87*, 072504. (c) Low, D. M.; Jones, L. F.; Bell, A.; Brechin, E. K.; Mallah, T.; Rivière, E.; Teat, S. J.; McInnes, E. J. L. *Angew. Chem., Int. Ed.* **2003**, *42*, 3781.
- (19) (a) Wang, Z.-M.; Zhang, Y.-J.; Liu, T.; Kurmoo, M.; Gao, S. *Adv. Funct. Mater.* **2007**, *17*, 1523. (b) Viertelhaus, M.; Adler, P.; Clérac, R.; Anson, C. E.; Powell, A. K. *Eur. J. Inorg. Chem.* **2005**, 692.
- (20) Takeda, K.; Kawasaki, K. *J. Phys. Soc. Jpn.* **1971**, *31*, 1026.

JA803846Z