

Cobalt-Catalyzed Hydroalkylation of [60]Fullerene with Active Alkyl **Bromides: Selective Synthesis of Monoalkylated Fullerenes**

Shirong Lu,^{+,§} Tienan Jin,^{*,†} Ming Bao,[§] and Yoshinori Yamamoto^{*,†}

[†]Department of Chemistry, Graduate School of Science, Tohoku University, Sendai 980-8578, Japan

[‡]WPI-Advanced Institute for Materials Research (AIMR), Tohoku University, Sendai 980-8577, Japan

[§]State Key Laboratory of Fine Chemicals, Dalian University of Technology, Dalian 116012, China

Supporting Information

ABSTRACT: The Co-catalyzed hydroalkylation of C₆₀ with reactive alkyl bromides 1 (RBr) in the presence of Mn reductant and H₂O at ambient temperature gave the monoalkylated C₆₀ (2) in good to high yields. The use of $CoLn/Mn/H_2O$ under Ar atmosphere is crucial for the success of the present transformation. The reaction most probably proceeds through the Co(0 or I)complex-promoted generation of a radical (R[•]) followed by addition to C₆₀. This hydroalkylation method was applied to the synthesis of zinc porphyrin attached C_{60} (21), dendrimer



attached C_{60} (2m), and fullerene dimer (2n), which were not easily available through the previously known methods.

INTRODUCTION

Chemical functionalization of fullerenes provides a variety of potentially useful molecular materials for biological and electronic devices.1 Numerous efforts for chemical modification of fullerenes have been made during the last few decades, involving various cycloadditions,¹ addition of free radicals,^{2,3} and multiaddition of organocoppers.^{1f} The nuclophilic addition of organolithiums or Grignard reagents is one of the classical methods for monofunctionalization of fullerene,⁴ but this method is accompanied by the following drawbacks: low chemical yields, low selectivity of monoalkylation, high loading of organometallic reagents, and low compatibility with a wide range of functional groups. Transition-metal-catalyzed functionalization of fullerenes⁵ has been proved to be a useful method to overcome those disadvantages; for example, Itami and co-workers reported that Rh or Pd catalyst can promote the selective monoarylation of fullerene efficiently by using organoboron compounds.^{5h,i} The addition of nucleophiles through radical intermediates proceeds rapidly, but it is difficult to control its selectivity and reactivity; often polysubstituted fullerenes are obtained.² It occurred to us that the combination between a transition-metal-catalyzed method and radical chemistry may lead to an efficient alkylation procedure for fullerene.^{5e,o} Herein, we report a novel cobaltcatalyzed highly selective hydroalkylation of C₆₀ with active alkyl bromides 1 that affords the monoalkyl-functionalized fullerenes 2 in good to high yields under mild reaction conditions (eq 1). Moreover, we have successfully applied this method to the synthesis of monosubstituted fullerenes bearing Zn-porphyrin, G3-dendrimer, and fullerene dimer in good yields. Porphyrin- or dendrimer-bound fullerenes and fullerene dimer, which were previously prepared through the cycloaddition reactions, have been already proved to be promising materials for the optoelectronic

materials, although an efficient synthetic method of porphyrinor dendrimer-bound monoadducts of C₆₀ derivatives and monosubstituted fullerene dimers has never been reported.^{1d,g,6}



The combination of transition-metal catalysis and free radical reaction has emerged as a novel strategy for new efficient synthetic methodologies.^{9,10} Recently, Oshima and co-workers developed an efficient cobalt-catalyzed radical transformation of alkenes with alkyl halides in the presence of Grignard reagents.^{10a-e} However, this methodology was not applicable for the funtionalization of C₆₀ because of the drawback of Grignard reagents toward the alkylation of C₆₀, as mentioned above.⁴ We envisioned that, due to its facile radical accepting characteristics, the selective monofunctionalization of C60 would become feasible by the proper choice of transition-metal catalysts, alkyl halides, and additives.

RESULTS AND DISCUSSION

Screening of the Reaction Conditions. Screening of various transition-metal catalysts (10 mol %) and additives (3 equiv) in wet 1,2-dichlorobenzene (ODCB) at room temperature for 50 h under Ar atmosphere (Table 1) was carried out using C₆₀ and benzyl bromide (1a, 3 equiv). The reaction did not proceed

Received: May 30, 2011 Published: July 11, 2011

 Table 1. Optimization of the Reaction Conditions^a



		additive	yield of	iccovery of
entry	catalyst	(3.0 equiv)	2a (%) ^b	$C_{60} (\%)^{c}$
1	CoCl ₂ dppe	none	0	96
2	None	Mn	0	94
3	$CoCl_2$	Mn	4	88
4	CoCl ₂ dppe	Mn	$88(76)^d$	$(8)^d$
5	CoCl ₂ dppe	Fe	80 ^e	12
6	CoCl ₂ dppe	Zn	56	25
7	CoCl ₂ dppe	Cu	0	97
8	CoBr ₂ dppe	Mn	40	39
9	CoI ₂ dppe	Mn	45	24
10	CoCl ₂ dppm	Mn	71	17
11	CoCl ₂ dppf	Mn	73	14
12	$CoI_2(PPh_3)_2$	Mn	0	85
13	PdCl ₂ dppe	Mn	0	88
14	$PdCl_2[P(OPh)_3]_2$	Mn	0	93
15	$Pd(PPh_3)_4$	Mn	5	84
16	$RhCl(PPh_3)_3$	Mn	29	58
17	$[Rh(COD)Cl]_2$	Mn	2	89
18	NiCl ₂ dppf	Mn	20	68
19	$NiCl_2(PPh_3)_2$	Mn	24	60

^{*a*} Reaction conditions: A 1,2-dichlorobenzene (ODCB, 4 mL) solution of catalyst (10 mol %) and additive (3 equiv) under Ar atmosphere was stirred for 1 h at 25 °C. Next, C_{60} (21.6 mg), H₂O (10 equiv), and benzyl bromide (3 equiv) were added, and the resulting mixture was stirred for 50 h at 25 °C. ^{*b*} ¹H NMR yield determined using 2,4,6-trimethylpyridine as an internal standard. ^{*c*} HPLC yield determined using C_{70} as an internal standard. ^{*d*} Isolated yield. ^{*e*} The reaction time is 5 days.

without Co catalyst or Mn reductant (entries 1 and 2). Combination of a phosphine-free CoCl₂ catalyst with Mn additive gave a low conversion, producing 2a in a very low yield (entry 3). To our delight, $CoCl_2dppe$ catalyst [dppe = bis(diphenylphosphino)ethane] combined with Mn additive¹¹ showed a high reactivity, affording 2a in 76% isolated yield (entry 4). HPLC analysis and ¹H and ¹³C NMR spectra showed a high selectivity for the monoaddition product 2a. As byproduct, a very small amount of the inseparable multiadducts was produced together with recovered C_{60} (8%) (see the Supporting Information).¹² The high selectivity of the monoadduct should be attributed to the mild reaction conditions. The metal additives other than Mn were also tested. Fe additive gave an appreciable conversion, although a prolonged reaction time (5 days) was needed (entry 5). It should be noticed that under additional prolonged reaction times (5 days plus 1 day), the reaction with Fe additive did not increase the amount of multiadducts, although with Mn additive the amount of multiadducts was slightly increased under a prolonged reaction time (50 h plus 24 h) and the yield of 2a was decreased. Zn powder was also active, although the yield was lower than that of Mn and Fe, while copper additive was completely inactive (entries 6 and 7). The diverse activity of metal additives may be due to the difference of their standard

reduction potentials; the reduction potentials (E^0/V , $M^{x^+} + xe \Rightarrow M^0$)¹³ of Mn (-1.185), Zn (-0.7618), and Fe (-0.447) have abilities enough to reduce Co²⁺ to Co⁰ or ¹ (-0.28), while Cu (0.521) additive cannot reduce Co²⁺. These results indicate that the present catalytic hydroalkylation proceeds via a mechanism involving Co(0 or I).

Other cobalt catalysts having different counteranions and ligands were also examined. In the presence of Mn additive, the reaction gave poorer product conversions when $CoCl_2dppe$ catalyst was replaced with $CoBr_2dppe$ or CoI_2dppe catalyst (entries 8 and 9). The reaction with other cobalt catalysts having bidentate ligands, such as $CoCl_2dppm$ [dppm = bis(diphenyl-phosphino)methane] and $CoCl_2dppf$ [dppf = bis(diphenyl-phosphino)ferrocene], were also active, affording **2a** in 71% and 73% yields, respectively (entries 10 and 11). In contrast to the case for cobalt catalysts bearing bidentate ligands, the cobalt catalyst having monodentate ligand, such as $CoI_2(PPh_3)_2$, was inactive (entry 12).

In addition to cobalt catalysts, we also tested several other transition metal catalysts, such as Pd, Rh, and Ni with Mn additive. Pd catalysts having bidentate ligand (dppe) or monodentate ligands (P(OPh)₃ and PPh₃) were not effective to produce **2a** (entries 13–15). In sharp contrast, the reaction proceeded with Rh- and Ni-catalysts bearing phosphine ligands. For example, RhClPPh₃ catalyst gave 29% yield of **2a**, while the phosphine-free [Rh(COD)Cl]₂ (COD = 1,5-cyclooctadiene) catalyst was inactive (entries 16 and 17). NiCl₂dppf and NiCl₂-(PPh₃)₂ catalysts showed lower product conversions, producing **2a** in 20% and 24% yields, respectively (entries 18 and 19). These results suggest that the high efficiency of present reaction not only depends on the transition metal species, but also highly depends on the attached phosphine ligands.

Overall, the hydroalkylation of C_{60} with $CoCl_2$ dppe catalyst and Mn additive has been proved to be the most efficient condition. It should be noted that without H₂O the reaction did not proceed at all. Moreover, in the presence of oxygen, the reaction results in a very low conversion of C_{60} . Therefore, all of the handlings were conducted in the glovebox under argon gas.

Co-Catalyzed Synthesis of Various Monoalkylated Fullerenes. Under optimized conditions, the scope of Co-catalyzed hydroalkylation of C₆₀ with various active alkyl bromides was examined (Table 2). All of the reactions were monitored by TLC and HPLC analysis, and the corresponding products 2 were isolated by using silica gel column chromatography; it was not necessary to use HPLC for purification of the products. In each case, a very small amount of the inseparable multiadducts was observed as side-products,¹² but they were separated by the silica gel column chromatography. A variety of functional groups, such as ester, cyano, methoxy, and α -methyl groups on benzyl moiety, were tolerated, affording the monoalkylated products 2b-f in good yields with excellent monoalkylation-selectivity (entries 1-5). It should be noted that the products 2b-f showed a high solubility in toluene or o-dichlorobenzene. Moreover, the reaction of C_{60} with benzyl bromides having an ester (1b and 1c) or a cyano group (1d) afforded a small amount of the single bonded fullerene dimers as byproducts (Figure 1).¹² Allyl bromide, cinnamyl bromide, propargyl bromide, and 1-bromo-2-butyne were also active alkyl sources, producing the corresponding products 2g-i in good to high yields (entries 6–9). Ethyl 2-bromoacetate 1k showed a lower reactivity, giving 2k in 36% yield even under longer reaction times (96 h) (entry 10). It should be noted that although the reaction of C₆₀ with benzyl

Table 2.	Co-Catalyzed	Hydroalkylation	of C_{60} with	Various Active Al	kyl Bromides ^a
----------	--------------	-----------------	------------------	-------------------	---------------------------

entry	R-Br	1	amount of 1 (equiv)	time (h)	2	yield of 2 $(\%)^b$	recovery of C_{60} (%) ^b
1	3-CO ₂ Me-C ₆ H ₄ CH ₂ Br	1b	1.5	48	2b	58	30
2	4-CO ₂ Me-C ₆ H ₄ CH ₂ Br	1c	1.5	48	2c	66	15
3	2-NC-C ₆ H ₄ CH ₂ Br	1d	1.5	40	2d	51	39
4	$4-MeO-C_6H_4CH_2Br$	1e	2.0	48	2e	66	21
5	C ₆ H ₅ CH(Me)Br	1f	3.0	50	2f	48	24
6	CH2=CHCH2Br	1g	4.0	86	2g	74	15
7	(E)-C ₆ H ₅ CH=CHCH ₂ Br	1h	1.5	34	2h	78	13
8	CH≡CCH ₂ Br	1i	3.0	86	2i	75	12
9	MeC≡CCH ₂ Br	1j	3.0	60	2j	42	41
10	EtO ₂ CCH ₂ Br	1k	3.0	96	2k	36	38

^{*a*} Reaction conditions: A 1,2-dichlorobenzene (ODCB, 4 mL) solution of CoCl₂dppe (10 mol %) and Mn (3 equiv) under Ar atmosphere was stirred for 1 h at 25 °C. Next, C₆₀ (21.6 mg), H₂O (10 equiv), and RBr (1.5–4.0 equiv) were added, and the resulting mixture was stirred for 34–96 h at 25 °C. ^{*b*} Isolated yields.



Figure 1. Two isomers of single bonded fullerene dimer 3b.

bromides having an electron-withdrawing substituent on benzene ring, such as **1b**, **1c**, and **1d**, produced a small amount of the single bonded fullerene dimers **3** in $\sim 3\%$ yields (for the representative structure **3b**, see Figure 1), the corresponding dimers were unable to identify in the other cases due to their extremely small amounts. In contrast to these active alkyl bromides, inactive alkyl bromides, such as butyl bromide or bromomethylcyclopropane, did not undergo the present catalytic hydroalkylation at elevated temperatures.

Co-Catalyzed Synthesis of Zn-Porphrin- and Dendrimer-Bound Hydrofullerenes, and Fullerene Dimer. The present cobalt catalysis was successfully applied to the construction of fullerene-bound macromolecules, which may be useful for versatile electronic materials.^{1d,6,7} For example, under the standard conditions, C₆₀ reacted with benzyl bromide derivative 11 having a zinc porphyrin (ZnP) moiety at para-position, affording the ZnP-C₆₀ product 2l in 30% yield, while in the presence of Fe additive instead of Mn it gave 21 in 40% yield (eq 2).1d,10 Similarly, the reaction of C₆₀ with single benzylic bromide group at the focal point of the third-generation dendrimer [G-3]-Br 1m gave the fullerene-bound dendrimer 2m in 48% yield (eq 3).^{1d,11} This dendritic macromolecule dramatically improved the solubility of fullerene in various organic solvents. This method also provides an interesting opportunity for synthesis of the potentially useful fullerene dimer containing two fullerene units bridged through electroactive spacer.^{5h,8} The reaction of 1,5bis(bromomethyl)-1,4-bis(3',7'-dimethyloctyloxy)benzene 1n and 2 mol equiv of C_{60} under standard reaction conditions produced fullerene dimer 2n in 39% yield, which showed a good solubility in toluene and ODCB (eq 4).^{Sh,12} It was also noted that the single bonded fullerene dimers produced in the reactions of C_{60} with **2l**, **2m**, and **2n** were unable to identify.



Reaction Mechanism. A plausible mechanism for the present transformation is shown in Scheme 1. Initially, the Co(II) complex is reduced to the electron-rich Co(0) species by Mn reductant.¹¹ A single electron transfer from the Co(0) complex to benzyl bromide 1a generates benzyl radical A along with Co(I) complex B. Addition of the radical A to C₆₀ forms the delocalized fullerenyl-radical intermediate C. Intermediate C would be trapped by the Co(I) complex D. Protonolysis of intermediate D produces the corresponding product 2a along with the Co(0) catalyst upon treatment with Mn reductant. Of course, the reduction of the Co(I) to Co(I) may occur at the beginning, instead of the reduction to Co(0), and the catalytic cycle may proceed through Co(I) species.

Several experimental observations support the proposed mechanism. When C_{60} was treated with 1a under standard conditions by using *n*-Bu₃SnH, instead of H₂O, 2a was obtained in good yield.^{4b} Furthermore, as mentioned in Table 2 (entry 1), the reaction of C_{60} with 1b gave the single bonded fullerene dimer $RC_{60}-C_{60}R$ 3b as a side-product in 3% yield (Figure 1).





¹H NMR spectra showed that this dimer consists of a 1:1 mixture of two isomers.¹² Many experimental and theoretical studies on those dimers demonstrated that they are generally formed by coupling of RC₆₀ radicals.¹⁴ These observations suggest that the present reaction must proceed through the formation of the fullerenyl radical intermediate C. Formation of a very small amount of dimer also indicates the conversion of fullerenylradical C to fullerenyl-cobalt(II or III) complex D is a rapid step. Moreover, the reaction of C_{60} and 1b in the presence of D_2O instead of H₂O under otherwise the standard conditions gave the corresponding product 2b' in 46% yield with 94% deuterium incorporation, implying that a proton in product 2a was derived from the added water (eq 6). A similar reaction was conducted with a 1:1 mixture of H₂O and D₂O, yielding the protonated and deuterated products 2b and 2b' in a 54:46 ratio (eq 5). The yield difference between H₂O and D₂O is due to the isotope effect of O-D and O-H bond,¹⁵ which reflects the hydrolysis step of the intermediate D.



A reason for the yield difference of **2a** depending on transition metals (Co, Pd, Ni, and Rh: Table 1, entries 4, 13–15, 16, and 18,19) is perhaps due to the reactivity difference of the LnM-(n + 1)X (Ln = ligand; X = halogen) complex, which is similar to the intermediate **B** in Scheme 1, toward R[•] (eq 6). To obtain a high product yield, the alkyl radical (R[•]) must react with C₆₀

before its reaction with the MLn(n + 1)X species, which may lead to the formation of the oxidative addition complex R-MLn(n+2)X. The diverse reactivity of the transition metals suggests that the combination of different metals and ligands highly affects the reactivity of LnM(n + 1)X.⁹ It is also known that a certain transition-metal catalyst undergoes facile formation of a transition-metal-C₆₀ complex.^{16,17} It has been reported that Pd complexes having phosphine ligands react readily with C60 under ambient temperature, forming LnPd-C₆₀ complexes in high yields.¹⁵ Indeed, in the reaction with $Pd(PPh_3)_4$ catalyst (Table 1, entry 15), a very small amount of the corresponding Pd- $(PPh_3)_2 - C_{60}$ complex was detected, which was confirmed by HPLC analysis and ¹H NMR spectra as compared to an authentic sample prepared from the reported method.^{16d} Ni, Rh, and Co complexes have also been reported to react with C₆₀, although the use of a higher reaction temperature or special ligands was needed.17

An alternative reaction pathway, such as the initial generation of C_{60} radical anion through the reduction of C_{60} with metal reductant followed by reaction with benzyl bromide,^{3a} is unlikely because the reaction of C_{60} and H_2O in the absence of alkyl bromides under otherwise the standard conditions gave a trace amount of dihydrofullerene ($C_{60}H_2$) as shown in eq 7. This result is completely different from the reported zinc-mediated monoalkylation of C_{60} , in which Meier and co-workers reported that the reaction of C_{60} with H_2O in the presence of excess amounts of zinc dust gave $C_{60}H_2$ in 50% yield.^{3a}



CONCLUSION

We have found a new and efficient Co-catalyzed selective monoalkylation of C_{60} with active alkyl bromides. A wide range of functional groups are tolerated in the present catalytic hydroalkylation. In contrast to the classical organometallic addition methods, the present catalytic reaction is carried out under very mild reaction conditions with remarkably higher yields. Monosubstituted zincporphyrin-fullerene, fullerene-bound dendrimer, and fullerene dimer have thus been synthesized in good yields for the first time, which are otherwise difficult to obtain. The present hydroalkylation of C₆₀ seems to proceed through a Co-catalyzed generation of an active alkyl radical followed by addition to C₆₀. Cobalt catalyst combined with Mn reductant in the presence of H₂O under argon is crucial for the efficient and selective formation of the fullerene monoadducts. Investigation on further catalytic functionalization of fullerenes and application to materials science are in progress.

EXPERIMENTAL PROCEDURES

Materials. Anhydrous 1,2-dichlorobenzene (Aldrich), toluene, carbon disulfide, hexane, (WAKO), transition metal catalysts, reductants (Aldrich), *n*-Bu₃SnH (Aldrich), and alkyl bromides (1) (Aldrich) were purchased and used as received. $CoX_2(ligand)^{18}$ and zinc porphyrin (ZnP) benzyl bromide 11^{19} were prepared following the reported literature. The structures of products were determined by using ¹H NMR, ¹³C NMR, HMRS, and by comparison of representative products 2a, ^{3a,19} 2f, ^{3d} 2g, ^{3a,5j,20} 2i, ²¹ and $2k^{3a}$ with reported literature.

Representative Procedures of Co-Catalyzed Hydroalkylation of C₆₀ and Benzyl Bromide. A suspension of CoCl₂dppe (1.6 mg, 0.003 mmol) and Mn (5 mg, 0.09 mmol) in 1,2-dichlorobenzene (ODCB, 4 mL) was stirred for 1 h under Ar atmosphere at 25 °C. To the suspension were added C₆₀ (21.6 mg, 0.03 mmol), benzyl bromide (11 μ L, 0.09 mmol), and H₂O (5.4 μ L, 0.3 mmol) subsequently in a glovebox. The reaction mixture was stirred at 25 °C for 50 h and monitored by TLC and HPLC analysis (elution with toluene at 0.6 mL/min flow rate, detection at 320 nm, 4 °C). The mixture was filtered through a short florisil pad using 1,2-dichlorobenzene as an eluent. After concentration, the residue was purified with silica gel chromatography (toluene/ hexane = 1/4) to afford 2a in 76% yield (18.5 mg).

Methyl 3-[([60]Fulleren-1(2*H***)-yl)methyl]benzoate (2b).** Dark brown solid; soluble solvents: CHCl₃, toluene, ODCB; ¹H NMR (500 MHz) δ 3.99 (3H, s), 4.81 (2H, s), 6.61 (1H, s), 7.62 (1H, t, *J* = 8.0 Hz), 8.02 (1H, d, *J* = 8.0 Hz), 8.13 (1H, d, *J* = 8.0 Hz), 8.52 (1H, s); ¹³C NMR (125 MHz) δ 52.35, 52.65, 59.12, 65.64, 128.84, 129.05, 130.62, 132.44, 135.85, 136.18, 136.27, 136.33, 139.97, 140.23, 141.61, 141.68, 141.90, 141.99, 142.08, 142.23, 142.58, 142.61, 143.25, 144.57, 144.76, 145.43, 145.46, 145.56, 145.82, 146.18, 146.23, 146.29, 146.44, 146.46, 146.93, 147.37, 147.54, 153.64, 154.83, 166.98; UV-vis λ_{max}/nm (CHCl₃) 256, 307, 327, 433; HRMS (ESI, positive) calcd for C₆₉H₁₀O₂Na [M + Na]⁺, 893.0573; found, 893.0567.

Methyl 3-[([60]Fulleren-1(2D)-yl)methyl]benzoate (2b'). Dark brown solid; soluble solvents: CHCl₃, toluene, ODCB; ¹H NMR (400 MHz, CDCl₃/CS₂ = 1/4) δ 3.96 (3H, s), 4.82 (2H, s), 7.60 (1H, t, *J* = 7.6 Hz), 8.00 (1H, d, *J* = 7.6 Hz), 8.12 (1H, d, *J* = 7.6 Hz), 8.48 (1H, s); ¹³C NMR (100 MHz, CDCl₃/CS₂ = 1/4) δ 51.72, 52.41, 58.47 (C-D, t, *J* = 21.5 Hz), 65.11, 128.42, 128.72, 130.33, 132.02, 135.18, 135.76, 135.78, 135.90, 139.61, 139.84, 141.18, 141.24, 141.43, 141.63, 141.72, 142.15, 142.80, 144.10, 144.28, 144.95, 144.97, 145.06, 145.14, 145.31, 145.63, 145.75, 145.81, 145.96, 145.99, 146.46, 146.86, 147.02, 152.94, 153.01, 154.13, 165.55; UV-vis λ_{max}/nm (CHCl₃) 255, 307, 326, 433; HRMS (ESI, positive) calcd for C₆₉H₉DO₂Na [M + Na]⁺, 894.0636; found, 894.0633.

Methyl 4-[([60]Fulleren-1(2H)-yl)methyl)benzoate (2c). Dark brown solid; soluble solvents: CHCl₃, toluene, ODCB; ¹H NMR (400 MHz, CDCl₃/CS₂ = 1/4) 3.94 (3H, s), 4.85 (2H, s), 6.61 (1H, s), 7.87 (2H, d, *J* = 8.4 Hz), 8.16 (2H, d, *J* = 8.4 Hz); ¹³C NMR (100 MHz, CDCl₃/CS₂ = 1/4) 51.62, 52.85, 59.09, 65.18, 129.40, 129.68, 131.00, 135.72, 135.86, 139.58, 139.91,140.41, 141.20, 141.30, 141.44, 141.58, 141.66, 141.76,142.20, 142.21, 142.86, 144.13, 144.31, 144.98, 145.02, 145.08, 145.17, 145.33, 145.65, 145.79, 145.86, 146.01, 146.03, 146.40, 146.90, 147.06, 152.94, 154.03, 165.47; UV-vis λ_{max}/nm (CHCl₃) 256, 308, 326, 433; HRMS (ESI, negative) calcd for C₆₉H₉O₂ [M - H]⁻, 869.0608; found, 869.0610.

2-[([60]Fulleren-1(2*H***)-yl)methyl]benzonirile (2d).** Dark brown solid; soluble solvents: toluene, ODCB, low in CHCl₃; ¹H NMR (500 MHz, CDCl₃/CS₂ = 1/4) δ 5.05 (2H, s), 6.65 (1H, s), 7.54 (1H, t, *J* = 7.5 Hz), 7.72 (1H, t, *J* = 7.5 Hz), 7.82 (1H, d, *J* = 7.5 Hz), 7.94 (1H, d, *J* = 7.5 Hz); ¹³C NMR (125 MHz, CDCl₃/CS₂ = 1/4) δ 50.56, 59.77, 65.21, 115.06, 117.53, 128.00, 132.12, 132.20, 132.95, 136.01, 136.17, 139.29, 139.46, 140.08, 141.28, 141.46, 141.68, 141.83, 141.86, 142.29, 142.35, 142.96, 144.19, 144.46, 145.09, 145.15, 145.23, 145.34, 145.48, 145.72, 145.91, 145.97, 146.15, 146.47, 147.01, 147.21, 152.78, 153.08; UV—vis λ_{max} /nm (CHCl₃) 255, 309, 325, 432; HRMS (ESI, positive) calcd for C₆₈H₇NNa [M + Na]⁺, 860.0471; found, 860.0469.

2-(4-Methoxybenzyl)-1,2-dihydro[60]fullerene (2e). Dark brown solid; soluble solvents: CHCl₃, toluene, ODCB; ¹H NMR (500 MHz, CDCl₃/CS₂ = 1/4) δ 3.88 (3H, s), 4.71 (2H, s), 6.62 (1H, s), 7.04 (1H, d, *J* = 8.5 Hz), 7.72 (1H, d, *J* = 8.5 Hz); ¹³C NMR (125 MHz, CDCl₃/CS₂ = 1/4) δ 52.24, 54.96, 58.98, 66.08, 114.03, 127.57, 132.28, 135.90, 136.23, 139.84, 140.05, 141.45, 141.51, 141.79, 141.84, 141.90, 142.07, 142.42, 143.09, 144.44, 144.57, 145.24, 145.29, 145.33, 145.65, 146.03, 146.10, 146.23, 146.25, 146.27, 146.83, 147.16, 147.30, 153.75, 155.30, 159.00; UV–vis λ_{max}/mm (CHCl₃) 256, 308, 326, 433; HRMS (ESI, positive) calcd for C₆₈H₁₀ONa [M + Na]⁺, 865.0624; found, 865.0621.

2-((*E***)-Cinnamyl)-1,2-dihydro[60]fullerene (2h).** Dark brown solid; soluble solvents: CHCl₃, toluene, ODCB; ¹H NMR (500 MHz, CDCl₃/CS₂ = 1/4) δ 4.35 (2H, d, *J* = 7.0 Hz), 6.61 (1H, s), 7.18–7.35 (3H, m), 7.44 (2H, t, *J* = 7.5 Hz), 7.64 (2H, d, *J* = 7.5 Hz); ¹³C NMR (125 MHz, CDCl₃/CS₂ = 1/4) δ 50.31, 58.68, 64.71, 124.37, 126.66, 127.98, 128.72, 136.00, 136.21, 136.57, 136.74, 140.13, 140.21, 141.54, 141.56, 141.86, 141.94, 142.16, 142.46, 143.15, 144.47, 144.61, 145.28, 145.30, 145.33, 145.44, 145.70, 146.06, 146.08, 146.13, 146.30, 147.19, 147.34, 153.68, 155.31; UV–vis λ_{max}/nm (CHCl₃) 257, 326, 433; HRMS (ESI, negative) calcd for C₆₉H₁₀–H [M – H]⁻, 837.0710; found, 837.0712.

2-(But-2-ynyl)-1,2-dihydro[60]fullerene (2j). Dark brown solid; soluble solvents: toluene, ODCB, low in CHCl₃; ¹H NMR (500 MHz, CDCl₃/CS₂ = 1/4) δ 2.16 (3H, t, *J* = 2.5 Hz), 4.27 (2H, q, *J* = 2.5 Hz), 6.70 (1H, S); ¹³C NMR (125 MHz, CDCl₃/CS₂ = 1/4) δ 3.96, 37.42, 59.24, 63.92, 74.89, 81.29, 140.02, 140.06, 141.48, 141.60, 141.81, 141.86, 142.18, 142.37, 142.39, 142.87, 143.02, 144.38, 144.52, 145.15, 145.22, 145.25, 145.42, 145.58, 145.88, 145.97, 146.02, 146.21, 146.78, 147.08, 147.26, 153.54, 154.35; UV-vis λ_{max} /nm (CHCl₃) 256, 326, 433; HRMS (ESI, negative) calcd for C₆₄H₆-H [M - H]⁻, 773.0397; found, 773.0395.

2-(4-(ZnP)-benzyl)-1,2-dihydro[60]fullerene (2l). Dark purple red solid; soluble solvents: ODCB, low in CHCl₃ and toluene; ¹H NMR (500 MHz, CDCl₃/CS₂ = 1/4) δ 5.06 (2H, s), 6.80 (1H, s) 7.71–7.76 (9H, m), 8.16–8.18 (8H, m), 8.35 (2H, d, *J* = 8.5 Hz), 8.87–8.90 (8H, m); ¹³C NMR (125 MHz, CDCl₃/CS₂ = 1/4) δ 53.06, 59.18, 65.85, 120.94,126.37, 127.24, 129.38, 131.60, 131.92, 131.99, 134.21, 134.45, 135.83, 136.02, 139.68, 139.97, 141.35, 141.38, 141.65, 141.74, 141.92, 142.30, 142.41, 142.77, 142.92, 144.30, 144.40, 145.10, 145.17, 145.30, 145.46, 145.90, 145.96, 146.05, 146.12, 146.59, 149.72, 149.89, 149.97, 153.42, 154.80; UV–vis λ_{max}/nm (CHCl₃) 291, 299, 425, 550; HRMS (ESI, positive) calcd for C₁₀₅H₃₀N₄ZnNa [M + Na]⁺, 1433.1654; found, 1433.1650.

2-(3,5-Bis(3,5-bis(3,5-dimethoxybenzyloxy)benzyloxy)-benzyl)-1,2-dihydro[60]fullerene (2m). Dark brown solid; soluble solvents: THF, CHCl₃, toluene, ODCB; ¹H NMR (500 MHz, CDCl₃/CS₂ = 1/4) δ 3.77 (24H, s), 4.62 (2H, s), 4.92 (8H, s), 5.10 (4H, s), 6.39 (4H, t, *J* = 2.5 Hz), 6.51–6.54 (11H, m), 6.70 (4H, d, *J* = 2.5 Hz), 6.72 (1H, t, *J* = 2.5 Hz), 7.01 (2H, d, *J* = 2.5 Hz); ¹³C NMR (125 MHz, CDCl₃/CS₂ = 1/4) δ 53.04, 55.36, 58.69, 65.63, 70.01, 70.07, 100.01, 101.60, 101.89, 105.23, 105.36, 106.08, 110.69, 135.84, 136.21, 138.11, 139.00, 139.48, 139.85, 140.06, 141.52, 141.58, 141.79, 141.95, 142.01, 142.19, 142.49, 142.53, 143.09, 144.48, 144.65, 145.29, 145.35, 145.38, 145.80, 146.17, 146.22, 146.31, 146.38, 147.03, 147.30, 147.47, 153.90, 155.40, 159.90, 160.16, 160.96; UV–vis λ_{max} /nm (CHCl₃) 256, 308, 326, 434; HRMS (ESI, positive) calcd for C₁₁₇H₆₀O₁₄Na [M + Na]⁺, 1711.3875; found, 1711.3868.

(2,5-Bis(2,6-dimethylheptyloxy)-1,4-phenylene)bis(methylene)difullerene (2n). Dark brownish red solid; soluble solvents: CHCl₃, toluene, ODCB; ¹H NMR (400 MHz, CDCl₃/CS₂ = 1/4) δ 0.84 (6H, d, *J* = 2.8 Hz), 0.85 (6H, d, *J* = 3.2 Hz), 1.00 (6H, d, *J* = 6.8 Hz), 1.14–1.51 (18H, m), 1.66–1.70 (2H, m), 1.79–1.85 (2H, m), 1.92–1.99 (2H, m), 4.12 (2H, d, *J* = 6.8 Hz), 4.13 (2H, d, *J* = 6.8 Hz), 4.80–4.90 (4H, m), 6.66 (2H, s), 7.37 (2H, s); ¹³C NMR (100 MHz, CDCl₃/CS₂ = 1/4) δ 19.68, 22.71, 22.79, 25.04, 28.14, 30.15. 36.50, 37.58, 39.37, 46.06, 58.89, 65.75, 66.97, 116.73, 124.51, 135.17, 135.25, 135.86, 135.87, 139.37, 139.81, 141.03, 141.20, 141.34, 141.45, 141.56, 141.80, 142.12, 142.83, 144.12, 144.25, 144.90, 144.95, 145.28, 145.70, 145.77, 145.90, 146.53, 146.80, 147.01, 150.75, 153.57

155.22, 155.30; UV–vis λ_{max} /nm (CHCl₃) 255, 326, 435; HRMS (ESI, negative) calcd for C₁₄₈H₄₉O₂ [M – H]⁻, 1857.3732; found, 1857.3733.

Single Bonded Fullerene Dimer (3b). A 1:1 mixture of two isomers; dark brown solid; soluble solvents: ODCB, low in CHCl3 and toluene; ¹H NMR (500 MHz, $CDCl_3/CS_2 = 1/4$) δ 3.87 (6H, s), 4.52 (1H, d, J = 5.5 Hz), 4.55 (1H, d, J = 5.5 Hz), 4.75 (2H, d, J = 13.0 Hz), 7.44 (2H, t, J = 8.0 Hz), 7.78–7.79 (2H, m), 7.98–8.00 (2H, m), 8.30 (1H, s), 8.32 (1H, s); ¹³C NMR $(125 \text{ MHz}, \text{CDCl}_3/\text{CS}_2 = 1/4) \delta$ 48.78, 49.08, 51.77, 60.30,128.13, 128.66, 128.68, 130.20, 131.78, 134.88, 135.58, 138.00, 138.96, 139.00, 139.41, 139.44, 140.97, 141.05, 141.89, 141.93, 142.01, 142.16, 142.38, 142.57, 142.59, 142.61, 142.62, 142.65, 142.95, 142.98, 143.01, 143.04, 143.17, 143.19, 143.23, 143.29, 143.35, 143.70, 143.79, 143.86, 144.09, 144.09, 144.10, 144.14, 144.16, 144.21, 144.23, 144.26, 144.30, 144.32, 144.37, 144.39, 144.52, 144.55, 144.58, 144.77, 144.97, 145.08, 145.54, 145.57, 145.58, 145.61, 145.64, 146.59, 146.79, 146.84, 146.86, 146.93, 147.12, 147.22, 147.24, 147.48, 148.30, 148.42, 148.50, 148.52, 148.59, 148.71, 148.73, 148.96, 149.32, 152.54, 152.83, 153.62, 153.79, 156.12, 165.82; UV–vis λ_{max} /nm (CHCl₃) 257, 331, 445; HRMS (ESI, positive) calcd for $C_{138}H_{18}O_4Na [M + Na]^+$, 1761.1097; found, 1761.1102.

ASSOCIATED CONTENT

Supporting Information. Experimental procedures and characterization data. This material is available free of charge via the Internet at http://pubs.acs.org.

AUTHOR INFORMATION

Corresponding Author

tjin@m.tohoku.ac.jp; yoshi@m.tohoku.ac.jp

ACKNOWLEDGMENT

We thank the faculty members of the Instrumental Analysis Center at Tohoku University for the measurement of NMR and mass spectra. S.L. acknowledges the support of the China Scholarship Council (CSC).

REFERENCES

(1) For reviews, see: (a) Hirsch, A.; Brettreich, M. Fullerenes: Chemistry and Reactions; Wiley-VCH: Weinheim, Germany, 2005. (b) Fullerenes: Chemistry, Physics, and Technology; Kadish, K. M., Ruoff, R. S., Eds.; Wiley: New York, 2000. (c) Fullerenes: Principles and Applications; Langa, F., Nierengarten, J.-F., Eds.; RSC: Cambridge, 2007. (d) Martín, N. Chem. Commun. 2006, 2093. (e) Martín, N.; Altable, M.; Filippone, S.; Martín-Domenech, A. Synlett 2007, 3077. (f) Matsuo, Y.; Nakamura, E. Chem. Rev. 2008, 108, 3016. (g) Giacalone, F.; Martín, N. Adv. Mater. 2010, 22, 4220.

(2) (a) Krusic, P. J.; Wasserman, E.; Keizer, P. N.; Morton, J. R.; Preston, K. F. Science 1991, 254, 1183. (b) Fagan, P. J.; Krusic, P. J.; McEwen, C. N.; Lazar, J.; Parker, D. H.; Herron, N.; Wasserman, E. Science 1993, 262, 404. (c) Morton, J. R.; Negri, F.; Preston, K. F. Acc. Chem. Res. 1998, 31, 63. (d) Taylor, R. Chem.-Eur. J. 2001, 7, 4074.
(e) Kareev, I. E.; Kuvychko, I. V.; Lebedkin, S. F.; Miller, S. M.; Anderson, O. P.; Seppelt, K.; Strauss, S. H.; Boltalina, O. V. J. Am. Chem. Soc. 2005, 127, 8362. (f) Gan, L. C. R. Chimie 2006, 9, 1001.
(g) Subramanian, R.; Kadish, K. M.; Vijayashree, M. N.; Gao, X.; Jones, M. T.; Miller, M. D.; Krause, K. L.; Suenobu, T.; Fukuzumi, S. J. Phys. Chem. 1996, 100, 16327.

(3) For metal-mediated radical reactions, see: (a) Wang, Z.; Meier, M. S. J. Org. Chem. 2003, 68, 3043. (b) Matsuo, Y.; Zhang, Y.; Nakamura, E. Org. Lett. 2008, 10, 1251. (c) Tzirakis, M. D.; Orfanopoulos, M. Org. Lett. 2008, 10, 873. (d) Tzirakis, M. D.; Orfanopoulos, M. J. Am. Chem. Soc. 2009, 131, 4063. (e) Tzirakis, M. D.; Orfanopoulos, M. Angew. Chem., Int. Ed. 2010, 49, 5891. (f) Tzirakis, M. D.; Alberti, M. N.; Orfanopoulos, M. Chem. Commun. 2010, 46, 8228. (g) Li, F.-B.; You, X.; Wang, G.-W. Org. Lett. 2010, 12, 4896. (h) Matsuo, Y.; Iwashita, A.; Abe, Y.; Li, C.-Z.; Matsuo, K.; Hashiguchi, M.; Nakamura, E. J. Am. Chem. Soc. 2008, 130, 15429. (i) Champeil, E.; Crean, C.; Larraya, C.; Pescitelli, G.; Proni, G.; Ghosez, L. Tetrahedron 2008, 64, 10319. (j) Li, F.-B.; Liu, T.-X.; Huang, Y.-S.; Wang, G.-W. J. Org. Chem. 2009, 74, 7743. (k) Wang, G.-W.; Li, F.-B. J. Nanosci. Nanotechnol. 2007, 7, 1162. (l) Li, F.-B.; Liu, T.-X.; Wang, G.-W. J. Org. Chem. 2008, 73, 6417. (m) Li, F.-B.; Liu, T.-X.; You, X.; Wang, G.-W. Org. Lett. 2010, 12, 3258.

(4) For organolithiums and Grignard reagent additions, see: (a) Hirsch, A.; Soi, A.; Karfunkel, H. R. Angew. Chem., Int. Ed. Engl. **1992**, 31, 766. (b) Fagan, P. J.; Krusic, P. J.; Evans, D. H.; Lerke, S. A.; Johnston, E. J. Am. Chem. Soc. **1992**, 114, 9697. (c) Hirsch, A.; Grösser, T.; Skiebe, A.; Soi, A. Chem. Ber. **1993**, 126, 1061. (d) Nagashima, H.; Terasaki, H.; Kimura, E.; Nakajima, K.; Itoh, K. J. Org. Chem. **1994**, 59, 1246. (e) Komatsu, K.; Murata, Y.; Takimoto, N.; Mori, S.; Sugita, N.; Wan, T. S. M. J. Org. Chem. **1994**, 59, 6101.

(5) For transition-metal-catalyzed functionalization of fullerenes, see: (a) Becker, L.; Evans, T. P.; Bada, J. L. J. Org. Chem. 1993, 58, 7630. (b) Shiu, L.-L.; Lin, T.-I.; Peng, S.-M.; Her, G.-R.; Ju, D. D.; Lin, S.-K.; Hwang, J.-H.; Mou, C. Y.; Luh, T.-Y. J. Chem. Soc., Chem. Commun. 1994, 647. (c) Shen, C. K. F.; Chien, K.-M.; Liu, T.-Y.; Lin, T.-I.; Her, G.-R.; Luh, T.-Y. Tetrahedron Lett. 1995, 36, 5383. (d) Hsiao, T.-Y.; Santhosh, K. C.; Liou, K.-F.; Cheng, C.-H. J. Am. Chem. Soc. 1998, 120, 12232. (e) Gan, L.; Huang, S.; Zhang, X.; Zhang, A.; Cheng, B.; Cheng, H.; Li, X.; Shang, G. J. Am. Chem. Soc. 2002, 124, 13384. (f) Martín, N.; Altable, M.; Filippone, S.; Martín-Domenech, A.; Poater, A.; Solà, M. Chem.-Eur. J. 2005, 11, 2716. (g) Matsuo, Y.; Iwashita, A.; Nakamura, E. Chem. Lett. 2006, 35, 858. (h) Nambo, M.; Novori, R.; Itami, K. J. Am. Chem. Soc. 2007, 129, 8080. (i) Mori, S.; Nambo, M.; Chi, L.-C.; Bouffard, J.; Itami, K. Org. Lett. 2008, 10, 4609. (j) Nambo, M.; Wakamiya, A.; Yamaguchi, S.; Itami, K. J. Am. Chem. Soc. 2009, 131, 15112. (k) Nambo, M.; Itami, K. Chem.-Eur. J. 2009, 15, 4760. (1) Zhu, B.; Wang, G.-W. J. Org. Chem. 2009, 74, 4426. (m) Zhu, B.; Wang, G.-W. Org. Lett. 2009, 11, 4334. (n) Filippone, S.; Maroto, E. E.; Martín-Domenech, A.; Suarez, M.; Martín, N. Nat. Chem. 2009, 1, 578. (o) Xiao, Z.; Matsuo, Y.; Nakamura, E. J. Am. Chem. Soc. 2010, 132, 12234.

(6) (a) Imahori, H.; Guldi, D. M.; Tamaki, K.; Yoshida, Y.; Luo, C.; Sakata, Y.; Fukuzumi, S. J. Am. Chem. Soc. **2001**, 123, 6617. (b) Sutton, L. R.; Scheloske, M.; Pirne, K. S.; Hirsch, A.; Guldi, D. M.; Gisselbrecht, J.-P. J. Am. Chem. Soc. **2004**, 126, 10370. (c) Sandanayaka, A. S. D.; Ikeshita, K.; Araki, Y.; Kihara, N.; Furusho, Y.; Takata, T.; Ito, O. J. Mater. Chem. **2005**, 15, 2276. (d) de la Torre, G.; Giacalone, F.; Segura, J. L.; Martín, N.; Guldi, D. M. Chem.-Eur. J. **2005**, 11, 1267. (e) Hizume, Y.; Tashiro, K.; Charvet, R.; Yamamoto, Y.; Saeki, A.; Seki, S.; Aida, T. J. Am. Chem. Soc. **2010**, 132, 6628.

(7) Wooley, K. L.; Hawker, C. J.; Fréchet, J. M. J. J. Am. Chem. Soc. 1993, 115, 9836.

(8) (a) Segura, J. L.; Martín, N. Chem. Soc. Rev. 2000, 29, 13.
(b) Segura, J. L.; Priego, E. M.; Martín, N.; Luo, C.; Guldi, D. M. Org. Lett. 2000, 2, 4021. (c) Sánchez, L.; Sierra, M.; Martin, N.; Guldi, D. M.; Wienk, M. W.; Janssen, R. A. J. Org. Lett. 2005, 7, 1691. (d) Sastre-Santos, Á.; Parejo, C.; Martín-Gomis, L.; Ohkubo, K.; Fernández-Lázaro, F.; Fukuzumi, S. J. Mater. Chem. 2011, 21, 1509.

(9) For reviews of transition-metal-catalyzed radical reactions, see:
(a) Iqbal, J.; Bhatia, B.; Nayyar, N. K. Chem. Rev. 1994, 94, 519.
(b) Stadtmüller, H.; Vaupel, A.; Tucker, C. E.; Stüdemann, T.; Knochel, P. Chem.-Eur. J. 1996, 2, 1204. (c) Clark, A. J. Chem. Soc. Rev. 2002, 31, 1.
(d) Rudolph, A.; Lautens, M. Angew. Chem., Int. Ed. 2009, 48, 2656.
(e) Ford, L.; Jahn, U. Angew. Chem., Int. Ed. 2009, 48, 6386. (f) Pintauer, T. Eur. J. Inorg. Chem. 2010, 2449.

(10) For selected Co-catalyzed radical reactions, see: (a) Wakabayashi, K.; Yorimitsu, H.; Oshima, K. J. Am. Chem. Soc. 2001, 123, 5374.
(b) Ikeda, Y.; Nakamura, T.; Yorimitsu, H.; Oshima, K. J. Am. Chem. Soc. 2002, 124, 6514. (c) Mizutani, K.; Shinokubo, H.; Oshima, K. Org. Lett. 2003, 5, 3959. (d) Ohmiya, H.; Tsuji, T.; Yorimitsu, H.; Oshima, K. Chem.-Eur. J. 2004, 10, 5640. (e) Kobayashi, T.; Ohmiya, H.; Yorimitsu, H.; Oshima, K. J. Am. Chem. Soc. 2008, 130, 11276. (f) Waser, J.;

Carreira, E. M. J. Am. Chem. Soc. 2004, 126, 5676. (g) Waser, J.; Nambu, H.; Carreira, E. M. J. Am. Chem. Soc. 2005, 127, 8294. (h) Waser, J.; Gaspar, B.; Nambu, H.; Carreira, E. M. J. Am. Chem. Soc. 2006, 128, 11693. (i) Gaspar, B.; Carreira, E. M. Angew. Chem., Int. Ed. 2008, 47, 5758. (j) Czaplik, W. M.; Mayer, M.; Jacobi von Wangelin, A. Synlett 2009, 18, 2931.

(11) (a) Amatore, M.; Gosmini, C. Chem.-Eur. J. 2010, 16, 5848.
(b) Shukla, P.; Hsu, Y.-C.; Cheng, C.-H. J. Org. Chem. 2006, 71, 655.

(12) For detailed HPLC analysis and NMR spectra, see the Supporting Information.

(13) Vanylsek, P. Electrochemical Series. *Handbook of Chemistry and Physics*, 88th ed.; Chemical Rubber Co.: 2007.

(14) (a) Morton, J. R.; Preston, K. F.; Krusic, P. J.; Wasserman, E. J. Chem. Soc., Perkin Trans. 2 1992, 1425. (b) Morton, J. R.; Preston, K. F.; Krusic, P. J.; Hill, S. A.; Wasserman, E. J. Am. Chem. Soc. 1992, 114, 5454. (c) Fagan, P. J.; Krusic, P. J.; McEwen, C. N.; Lazar, J.; Parker, D. H.; Horrn, N.; Wasserman, E. Science 1993, 262, 404. (d) Schick, G.; Kample, K. D.; Hirsch, A. J. Chem. Soc., Chem. Commun. 1995, 2023. (e) Oszlanyi, G.; Bortel, G.; Faigel, L.; Granasy, L.; Bendele, G. M.; Stephens, P. W.; Forro, L. Phys. Rev. B 1996, 54, 11849. (f) Murata, Y.; Motoyama, K.; Komatsu, K.; Wan, T. S. M. Tetrahedron 1996, 52, 5077. (g) Osawa, S.; Osawa, E.; Harada, M. J. Org. Chem. 1996, 61, 257. (h) Wang, G.-W.; Komatsu, K.; Murata, Y.; Shiro, M. Nature 1997, 387, 583. (i) Hummelen, J. C.; Bellavia-Lund, C.; Wudl, F. Top. Curr. Chem. 1999, 199, 93. (j) Tanaka, T.; Komatsu, K. J. Chem. Soc., Perkin Trans. 1 1999, 1671. (k) Lee, K. H.; Park, S. S.; Suh, Y.; Yamabe, T.; Osawa, E.; Luthi, H. P.; Gutta, P.; Lee, C. J. Am. Chem. Soc. 2001, 123, 11085. (1) Cheng, F.; Murata, Y.; Komatsu, K. Org. Lett. 2002, 4, 2541. (m) Yoshida, M.; Sultana, F.; Uchiyama, N.; Yamada, T.; Iyoda, M. Tetrahedron Lett. 1999, 40, 735. (n) Zhang, T.-H.; Lu, P.; Wang, F.; Wang, G.-W. Org. Biomol. Chem. 2003, 1, 4403. (o) Wang, G.-W.; Wang, C.-Z.; Zhu, S.-E.; Murata, Y. Chem. Commun. 2011, 47, 6111. (p) Wang, G.-W.; Wang, C.-Z.; Zou, J.-P. J. Org. Chem. 2011, 76, DOI: 10.1021/ jo2007384.

(15) (a) Salomaa, P. Acta Chem. Scand. **1971**, 25, 367. (b) Lee, J.; Chasteen, N. D.; Zhao, G.; Papaefthymiou, G. C.; Gorun, S. M. J. Am. Chem. Soc. **2002**, 124, 3042.

(16) (a) Fagan, P. J.; Calabrese, J. C.; Malone, B. Science 1991, 252, 1160. (b) Fagan, P. J.; Calabrese, J. C.; Malone, B. Acc. Chem. Res. 1992, 25, 134. (c) Chase, B.; Fagan, P. J. J. Am. Chem. Soc. 1992, 114, 2252. (d) Lerke, S. A.; Parkinson, B. A.; Evans, D. H.; Fagan, P. J. J. Am. Chem. Soc. 1992, 114, 7807. (e) Bashilov, V. V.; Petrovskii, P. V.; Sokolov, V. I.; Lindeman, S. V.; Guzey, I. A.; Struchkov, Y. T. Organometallics 1993, 12, 991.

(17) (a) For a review, see: Balch, A. L.; Olmstead, M. M. Chem. Rev. **1998**, 98, 2123. (b) For the synthesis of $C_{60}Co(PPh_3)_2$ complex from $CoCl_2(PPh_3)_2$, see: Wu, Z.-Y.; Yang, S.-G.; Lin, Y.-S.; Dong, Z.-R.; Cheng, D.-D.; Zhan, M.-X. Chin. J. Inorg. Chem. **2003**, 19, 321. (c) Thompson, D. M.; Bengough, M.; Baird, M. C. Organometallics **2002**, 21, 4762. (d) Matsuo, Y.; Maruyama, M.; Gayathri, S. S.; Uchida, T.; Guldi, D. M.; Kishida, H.; Nakamura, A.; Nakamura, E. J. Am. Chem. Soc. **2009**, 131, 12643. (e) Maruyama, M.; Guo, J.-D.; Nagase, S.; Nakamura, E.; Matsuo, Y. J. Am. Chem. Soc. **2011**, 133, 6890. (f) Iwasa, Y.; Arima, T.; Fleming, R. M.; Siegrist, T.; Zhou, O.; Haddon, R. C.; Rothberg, L. J.; Lyones, K. B.; Carter, H. L., Jr.; Hebard, A. F.; Tycko, R.; Dabbagh, G.; Krajewski, J. J.; Thomas, G. A.; Yagi, T. Science **1994**, 264. 1570.

(18) McKinney, R. J. Inorg. Chem. 1982, 21, 2051.

(19) de la Torre, G.; Giacalone, F.; Segura, J. L.; Martín, N.; Guldi, D. M. Chem.-Eur. J. 2005, 11, 1267.

(20) Chen, J.; Cai, R. F.; Huang, Z.-E.; Wu, H.-M.; Jiang, S.-K.; Shao, Q.-F. J. Chem. Soc., Chem. Commun. 1995, 1553.

(21) Meier, M. S.; Bergosh, R. G.; Gallagher, M. E.; Spielmann, H. P.; Wang, Z. J. Org. Chem. **2002**, 67, 5946.