

Incorporation of an A1/A2-Difunctionalized Pillar[5]arene into a Metal–Organic Framework

Nathan L. Strutt,[†] David Fairen-Jimenez,[‡] Julien Iehl,[†] Marianne B. Lalonde,[†] Randall Q. Snurr,[‡] Omar K. Farha,[†] Joseph T. Hupp,[†] and J. Fraser Stoddart^{*†}

[†]Department of Chemistry and [‡]Department of Chemical and Biological Engineering, Northwestern University, Evanston, Illinois 60208, United States

S Supporting Information


ABSTRACT: An efficient synthetic route to an A1/A2-difunctionalized pillar[5]arene containing resolvable planar chirality has been developed and the arene employed as a strut in the synthesis of **PSA-MOF-1**, which has been demonstrated by X-ray powder diffraction analysis—supported by modeling—to be isoreticular with MOF-5. This metal–organic framework has an active domain that expresses good and selective uptake of neutral and positively charged electron-poor aromatic guests, which effect color changes of the cubic crystals from faint yellow to deep orange, arising from charge transfer between the guests and active domain of **PSA-MOF-1**.

Macrocycles such as cyclodextrins,¹ crown ethers,² calixarenes,³ cucurbiturils,⁴ and cyclophanes⁵ have become an integral part of host–guest chemistry.⁶ A relatively new class of macrocycles to enter the field, the pillararenes,⁷ are analogues of calixarenes composed of five, six, or seven hydroquinone rings linked through their para-positions by methylene bridges. Since pillar[5]arene was first introduced as a novel macrocycle by Ogoshi and co-workers in 2008,^{7a} the chemistry of the pillararenes has been developed steadily, and they have been shown to have applications in liquid crystals,^{7q} artificial transmembrane channels,^{7p} nanoparticle formation,^{7o} and sensing.^{7j} Here we report the synthesis of an A1/A2-difunctionalized⁸ pillar[5]arene that undergoes cross-coupling reactions to create a rigid strut which is then incorporated into a metal–organic framework⁹ (MOF) having an active domain¹⁰ containing docking sites for electron-poor guests.

MOFs with organic struts incorporating macrocycles have been used recently¹⁰ to prepare extended frameworks with active domains, which, as a result of highly favorable and specific noncovalent interactions, play host to a well-ordered distribution of guest molecules. In 2009, we described^{10a} the use of a π -electron-rich BPP34C10-functionalized organic strut in the synthesis of MOF-1001 which was shown to soak up the π -electron-poor guest, methyl viologen. MOFs containing active domains show promise in the fields of chromatographic separation¹¹ and sensing,¹² thereby making designer organic struts containing novel macrocycles attractive synthetic targets.

We have developed a synthetic protocol (Scheme 1) to obtain an A1/A2-difunctionalized⁸ pillar[5]arene organic strut, starting from **1**, which is made through the co-cyclization of 1,4-dimethoxybenzene and 1,4-bis(3-bromopropoxy)benzene, sim-

Scheme 1. Synthesis of A1/A2-Difunctionalized Pillar[5]arene Organic Strut^a



^aIn the X-ray crystal structure of **3**, C is gray, O is red, H is white; alkyl H atoms are omitted for clarity.

ilar to our previously reported^{7j} reaction for preparing monofunctionalized pillar[5]arene. Compound **1** undergoes

Received: August 20, 2012

Published: October 1, 2012




Figure 1. Solid-state structure of **5** (C is gray, O is red) which displays planar chirality and does not racemize between the R_p -**5** (left) and S_p -**5** (right) enantiomers. A DMF molecule and hydrogens have been removed from the structure to aid visual clarity.

elimination to give the diallyl ether **2**, which was deprotected using standard conditions¹³ to give the A1/A2-dihydroxy-pillar[5]arene **3**. Single crystals of **3**, suitable for X-ray crystallography, were grown; the solid-state structure¹⁴ (Scheme 1) of **3** shows that the hydroquinone unit is oriented in a direction opposite to that adopted by the 1,4-dimethoxybenzene units to support two intramolecular hydrogen bonds.

Compound **3**, when treated with triflic anhydride, affords the ditriflate **4**. Ogoshi and co-workers^{7c} showed that a pertriflated pillar[5]arene can undergo 10 Pd-catalyzed cross-couplings to give a highly conjugated pillar[5]arene. In similar fashion, **4** can be converted into a rigid strut **5** by means of a Pd-catalyzed Suzuki reaction with 4-(methoxycarbonyl)phenylboronic acid, followed by saponification of the intermediate diester. The solid-state structure of **5** (Figure 1) was elucidated by single-crystal X-ray analysis¹⁵ using crystals grown from diffusion of MeOH into a solution of **5** in DMF. The analysis indicates the presence of enantiomers in the unit cell. In keeping with its molecular C_2 symmetry, the ¹H NMR spectrum (see SI)¹⁶ of **5** displays two pairs of doublets for the two homotopic pairs of constitutionally heterotopic methylene groups—where in each case the protons are diastereotopic,¹⁷ given the fact that **5** is conformationally rigid—and a singlet for the remaining constitutionally heterotopic methylene group lying on the C_2 axis, which renders its methylene protons homotopic. The conformational rigidity of the pillar[5]arene-based strut **5** means that it exists as (potentially resolvable^{18,19}) enantiomers, R_p and S_p (Figure 1) due to the molecule's planar chirality.²⁰ Compound **5** demonstrates that only two bulky monosubstituted phenyl rings are required at the A1/A2 positions on a pillar[5]arene to impart resolvable planar chirality²¹ upon its constitution.

The pillar[5]arene-based strut **5** has been used to synthesize a MOF (Figure 2a) with Zn_4O secondary building units (SBUs) which is isoreticular to MOF-5.^{9b} **PSA-MOF-1** was prepared in a conventional manner by heating a mixture of **5** and $Zn(NO_3)_2 \cdot 6H_2O$ in DMF at 100 °C over 24 h. The crystals (Figure 3a) of **PSA-MOF-1** are cubic and transparent. Powder X-ray diffraction (PXRD) confirmed their crystallinity (Figure 2b), while thermal gravimetric analysis (TGA) was performed to determine their thermal stability: a one-step TGA profile shows that **PSA-MOF-1** is stable to 450 °C. Crystals of **PSA-MOF-1** were activated using supercritical CO_2 , and a NLDFT surface area of 300 m² g⁻¹ was obtained from a CO_2 isotherm (see SI).

Single-crystal X-ray data obtained for **PSA-MOF-1** were not well enough resolved to discern the solid-state structure of the extended framework as a result of disorder within the MOF itself.




Figure 2. (a) Model of **PSA-MOF-1** (pillar[5]arene macrocycles are red, terphenylene moieties are black, zinc SBUs are yellow). (b) Experimental PXRD pattern for **PSA-MOF-1** (black), calculated PXRD patterns for **PSA-MOF-1** in a $P1$ space group (red) and a $Pm3m$ space group (green), and PXRD pattern for IRMOF-16 (blue). See SI for full PXRD of **PSA-MOF-1**.

We believe this disorder arises principally from the rotational freedom of pillar[5]arenes around every terphenylene linker in the extended structure and a random distribution of “enantiomeric” pillar[5]arenes associated with their planar chirality.

The extended structure of **PSA-MOF-1** was modeled (see SI) using non-interpenetrated IRMOF-16^{9e} as the backbone and incorporating pillar[5]arenes with randomly distributed chiralities and orientations with respect to the terphenylene linkers. The geometry of the predicted structure was optimized to give a cubic unit cell with dimensions of $a = b = c = 42.980$ Å and a space group of $P1$. The simulated PXRD pattern of the modeled structure matches closely with the experimental one for **PSA-MOF-1** (Figure 2b). An alternative approach to modeling the extended structure with a $Pm3m$ space group was also pursued to determine if a model with higher symmetry might also fit the experimental MOF data. In this alternative model, each organic strut, ordered throughout the 3D framework, contains four pillar[5]arene rings in the shape of both “enantiomers” in two different orientations, each with a 0.25 occupancy disorder. Although the cubic cell dimensions of the model are identical with those of the first model, the simulated PXRD pattern presents extra peaks (Figure 2b), including a sharp 001 reflection.




Figure 3. (Top) Optical microscopy images of **PSA-MOF-1** (a) with no guest (scale bar, 200 μm), (b) after uptake of $\text{G2} \cdot 2\text{PF}_6$ (scale bar, 100 μm), and (c) after uptake of **G3** (scale bar, 100 μm). (Bottom) Electron-poor compounds used in guest uptake studies with **PSA-MOF-1**: *N*-hexylpyridinium cation (G1^+), *N,N'*-dihexyl-4,4'-bipyridinium dication (G2^{2+}), and 1,4-dinitrobenzene (**G3**).

Thus, it seems that the lower symmetry model provides a better match with the experimental data.

We investigated the ability of **PSA-MOF-1** to take up guests (Figure 3). At the outset, however, we evaluated the ability of the strut **5** to form complexes with three guests:²² the PF_6^- salts of *N*-hexylpyridinium cation (G1^+) and *N,N'*-dihexyl-4,4'-bipyridinium dication (G2^{2+}), as well as the neutral 1,4-dinitrobenzene (**G3**). ^1H NMR titrations in CD_3COCD_3 revealed association constants (K_a) between **5** and $\text{G1} \cdot \text{PF}_6$, $\text{G2} \cdot 2\text{PF}_6$, and **G3** of 43.2 ± 2.9 , 170 ± 50 , and $66.2 \pm 1.9 \text{ M}^{-1}$, respectively.

Samples of **PSA-MOF-1** were suspended in Me_2CO prior to guest uptake experiments to remove excess of DMF from within the framework. The samples were then introduced into saturated solutions of $\text{G1} \cdot \text{PF}_6$, $\text{G2} \cdot 2\text{PF}_6$, and **G3** in Me_2CO . With $\text{G2} \cdot 2\text{PF}_6$ and **G3**, the crystals underwent an immediate color change (Figure 3b,c) from faint yellow to deep orange upon addition of the guests, most likely because of charge-transfer interactions between the guests and **PSA-MOF-1**. The MOF samples were allowed to take up guests for 12 h before they were washed with Me_2CO and dissolved in $\text{DMSO}-d_6/\text{TFA}-d$ and their ^1H NMR spectra recorded. Integration of appropriate probe protons led to quantification of the uptake of guests by the MOF (Table 1). **IRMOF-16-OPX**, prepared from an oligo-*p*-xylene (OPX) derivative²³ (**S3** in SI) of *p*-terphenyl-4,4''-dicarboxylic acid,²⁴ was used as a control. Although both **PSA-MOF-1** and **IRMOF-16-OPX** are isorecticular with **IRMOF-16**, the latter does not have an active domain. The guest uptake experiments were performed under identical conditions for both MOFs.

PSA-MOF-1 takes up $\text{G1} \cdot \text{PF}_6$, $\text{G2} \cdot 2\text{PF}_6$, and **G3** from their saturated solutions in Me_2CO in moderate to high amounts. Table 1 lists the mole ratios of the guest to the organic strut found in the MOF. The fact that, under identical conditions, **PSA-MOF-1** takes up a significantly larger amount of each guest than does **IRMOF-16-OPX** suggests the active domain of **PSA-MOF-1** is able to interact with guest molecules through favorable noncovalent bonding interactions. Uptake of adamantane, which

Table 1. Mole Ratio of Guest to Organic Strut in **PSA-MOF-1** and **IRMOF-16-OPX**, Obtained from ^1H NMR Spectra after Guest Uptake and Digestion of MOF^{4a}

	PSA-MOF-1	IRMOF-16-OPX
	Single-Guest Uptake Experiments	
G1^+	0.755	0.121
G2^{2+}	0.366	0.125
G3	0.293	0.084
	Two-Guest Uptake Experiments	
$\text{G1}^+ + \text{G2}^{2+}$	0.091 G1^+ /0.176 G2^{2+}	0.089 G1^+ /0.069 G2^{2+}
$\text{G1}^+ + \text{G3}$	0.090 G1^+ /0.127 G3	0.027 G1^+ /0.032 G3
$\text{G2}^{2+} + \text{G3}$	0.310 G2^{2+} /0.100 G3	0.068 G2^{2+} /0.014 G3

^aUptake with a single guest was performed with a saturated solution of the guest in Me_2CO . Uptake with two guests was performed in a Me_2CO solution with each guest at 40.0 mM. K_a values of guest with **5** determined by ^1H NMR titration in CD_3COCD_3 : G1^+ , $43.2 \pm 2.9 \text{ M}^{-1}$; G2^{2+} , $170 \pm 50 \text{ M}^{-1}$; **G3**, $66.2 \pm 1.9 \text{ M}^{-1}$.

has been shown^{7a} to be too large to reside inside the cavity of pillar[5]arene, but small enough to pass through the pores of either MOF, was similar for both **PSA-MOF-1** and **IRMOF-16-OPX** (see SI).

In a final experiment, **PSA-MOF-1** was suspended in Me_2CO with equimolar concentrations (40.0 mM) of two different guests to determine if there is preferential uptake of one guest over the other. While we envisioned that the observed guest-to-MOF ratios would depend to some extent on the K_a values of the guests with **5** in solution, other factors, including the sizes and diffusion rates of the guests, might also be significant. **PSA-MOF-1** showed almost twice the uptake of $\text{G2} \cdot 2\text{PF}_6$ compared to $\text{G1} \cdot \text{PF}_6$ (Table 1), reflecting the larger K_a value for the former than the latter in binding **5**. Under identical conditions, the uptake by **IRMOF-16-OPX** of these two guests is very similar, as expected. Comparable results, which reflect ratios of K_a values, can be observed when **PSA-MOF-1** is exposed to equimolar combinations of the other guests (Table 1).

The rigid stereochemistry associated with the planar chirality of the strut **5** means that it should be possible, after resolving **5**, to prepare "enantiomeric" **PSA-MOF-1** samples without fear of **5** racemizing during the synthesis (at 100 °C) of the MOF. The prospect of being able to prepare chiral, enantiomerically pure, pillar[5]arene-containing MOFs to separate racemic mixtures of appropriate analytes is being pursued in our laboratories.

■ ASSOCIATED CONTENT

📄 Supporting Information

Experimental details, modeling, and characterization. This material is available free of charge via the Internet at <http://pubs.acs.org>.

■ AUTHOR INFORMATION

✉ Corresponding Author

stoddart@northwestern.edu

Notes

The authors declare no competing financial interest.

■ ACKNOWLEDGMENTS

The authors thank Benjamin Moritz for performing the chiral HPLC studies, Dr. Amy Sarjeant and Dr. Charlotte Stern for performing the PXRDs and single-crystal X-ray crystallography data collection, and Dr. Saman Shafie for performing the mass spectrometry experiments. This work was supported by the Non-

Equilibrium Energy Research Center, which is an Energy Frontier Research Center funded by the U.S. Department of Energy, Offices of Basic Energy Sciences, under Award No. DE-SC0000989. R.Q.S. acknowledges support from the Defense Threat Reduction Agency (HDTRA1-10-1-0023) J.T.H. and O.K.F. gratefully acknowledge financial support from the Defense Threat Reduction Agency (grant No. HDTRA1-09-1-0007). N.L.S. thanks the National Science Foundation for a Graduate Research Fellowship.

REFERENCES

- (1) Schardinger, F. Z. *Lebensm. Forsch. A* **1903**, *6*, 865. D'Souza, V. T.; Lipkowitz, K. B. *Chem. Rev.* **1998**, *98*, 1741. Harada, A.; Hashidzume, A.; Yamaguchi, H.; Takashima, Y. *Chem. Rev.* **2009**, *109*, 5974.
- (2) Pedersen, C. J. *J. Am. Chem. Soc.* **1967**, *89*, 2495. Truter, M. R. *Struct. Bonding* **1973**, *16*, 71. Pedersen, C. J. *Angew. Chem., Int. Ed.* **1998**, *27*, 1021. Stoddart, J. F. *Top. Stereochem.* **1987**, *17*, 207. Cantrill, S. J.; Pease, A. R.; Stoddart, J. F. *J. Chem. Soc., Dalton Trans.* **2000**, *21*, 3715.
- (3) Gutsche, C. D. *Calixarenes*; Royal Society of Chemistry: Cambridge, UK, 1989. Böhmer, V. *Angew. Chem., Int. Ed.* **1995**, *34*, 713. Kim, H. J.; Lee, M. H.; Mutihac, L.; Vicens, J.; Kim, J. S. *Chem. Soc. Rev.* **2012**, *41*, 1173.
- (4) Freeman, W. A.; Mock, W. L.; Shih, N. Y. *J. Am. Chem. Soc.* **1981**, *103*, 7367. Mock, W. L.; Shih, N. Y. *J. Am. Chem. Soc.* **1988**, *110*, 4706. Masson, E.; Ling, X.; Joseph, R.; Kyeremeh-Mensah, L.; Lu, X. *RSC Adv.* **2012**, *2*, 1213.
- (5) Diederich, F. *Angew. Chem., Int. Ed.* **1988**, *27*, 362. Gleiter, R.; Hopf, H. *Modern Cyclophane Chemistry*; Wiley-VHC: Weinheim, 2004.
- (6) Cram, D. J.; Cram, J. M. *Science* **1974**, *183*, 803. Cram, D. J. *Angew. Chem., Int. Ed.* **1998**, *27*, 1009. Cram, D. J.; Cram, J. M. *Container Molecules and Their Guests*; Royal Society of Chemistry: Cambridge, UK, 1994.
- (7) (a) Ogoshi, T.; Kanai, S.; Fujinami, S.; Yamagishi, T.-a.; Nakamoto, Y. *J. Am. Chem. Soc.* **2008**, *130*, 5022. (b) Cao, D.; Kou, Y.; Liang, J.; Chen, Z.; Wang, L.; Meier, H. *Angew. Chem., Int. Ed.* **2009**, *48*, 9721. (c) Ogoshi, T.; Umeda, K.; Yamagishi, T.-a.; Nakamoto, Y. *Chem. Commun.* **2009**, 4874. (d) Zhang, Z.; Xia, B.; Han, C.; Yu, Y.; Huang, F. *Org. Lett.* **2010**, *12*, 3285. (e) Han, C.; Ma, F.; Zhang, Z.; Xia, B.; Yu, Y.; Huang, F. *Org. Lett.* **2010**, *12*, 4360. (f) Ogoshi, T.; Nishida, Y.; Yamagishi, T.-a.; Nakamoto, Y. *Macromolecules* **2010**, *43*, 7068. (g) Ogoshi, T.; Kitajima, K.; Aoki, T.; Yamagishi, T.-a.; Nakamoto, Y. *J. Phys. Chem. Lett.* **2010**, *1*, 817. (h) Ogoshi, T.; Aoki, T.; Kitajima, K.; Fujinami, S.; Yamagishi, T.-a.; Nakamoto, Y. *J. Org. Chem.* **2011**, *76*, 328. (i) Aoki, T.; Ogoshi, T.; Yamagishi, T. *Chem. Lett.* **2011**, *40*, 795. (j) Strutt, N. L.; Forgan, R. S.; Spruelli, J. M.; Botros, Y. Y.; Stoddart, J. F. *J. Am. Chem. Soc.* **2011**, *133*, 5668. (k) Zhang, H.; Strutt, N. L.; Stoll, R. S.; Li, H.; Zhu, Z.; Stoddart, J. F. *Chem. Commun.* **2011**, *47*, 11420. (l) Hu, X.-B.; Chen, L.; Si, W.; Yu, Y.; Hou, J.-L. *Chem. Commun.* **2011**, *47*, 4694. (m) Strutt, N. L.; Zhang, H.; Giesener, M. A.; Lei, J.; Stoddart, J. F. *Chem. Commun.* **2012**, *48*, 1647. (n) Cragg, P. J.; Sharma, K. *Chem. Soc. Rev.* **2012**, *41*, 597. (o) Yao, Y.; Xue, M.; Chi, X. D.; Ma, Y. J.; He, J. M.; Abliz, Z.; Huang, F. H. *Chem. Commun.* **2012**, *48*, 6505. (p) Hu, C. B.; Chen, Z. X.; Tang, G. F.; Hou, J. L.; Li, Z. T. *J. Am. Chem. Soc.* **2012**, *134*, 8384. (q) Nierengarten, I.; Guerra, S.; Holler, M.; Nierengarten, J.-F.; Deschenaux, R. *Chem. Commun.* **2012**, *48*, 8072.
- (8) A nomenclature system for identifying the hydroxyl groups in pillararenes has been introduced by Ogoshi and co-workers. The letters refer to the hydroquinone units, while the numbers refer to the rims of the macrocycle. Ogoshi, T.; Kitajima, K.; Fujinami, S.; Yamagishi, T.-a. *Chem. Commun.* **2011**, *47*, 10106.
- (9) (a) Yaghi, O. M.; Li, G. M.; Li, H. L. *Nature* **1995**, *378*, 703. (b) Li, H.; Eddaoudi, M.; O'Keeffe, M.; Yaghi, O. M. *Nature* **1999**, *402*, 276. (c) Seo, J. S.; Whang, D.; Lee, H.; Jun, S. I.; Oh, J.; Jeon, Y. J.; Kim, K. *Nature* **2000**, *404*, 982. (d) Eddaoudi, M.; Moler, D. B.; Li, H. L.; Chen, B. L.; Reineke, T. M.; O'Keeffe, M.; Yaghi, O. M. *Acc. Chem. Res.* **2001**, *34*, 319. (e) Eddaoudi, M.; Kim, J.; Rosi, N.; Vodak, D.; Wachter, J.; O'Keeffe, M.; Yaghi, O. M. *Science* **2002**, *295*, 469. (f) Kitagawa, S.; Kitaura, R.; Noro, S. *Angew. Chem., Int. Ed.* **2004**, *43*, 2334. (g) Murray, L. J.; Dinca, M.; Long, J. R. *Chem. Soc. Rev.* **2009**, *38*, 1294. (h) Lee, J.; Farha, O. K.; Roberts, J.; Scheidt, K. A.; Nguyen, S. T.; Hupp, J. T. *Chem. Soc. Rev.* **2009**, *38*, 1450. (i) Wilmer, C. E.; Leaf, M.; Lee, C. Y.; Farha, O. K.; Hauser, B. G.; Hupp, J. T.; Snurr, R. Q. *Nat. Chem.* **2012**, *4*, 83. (j) Deng, H.; Grunder, S.; Cordova, K. E.; Valente, C.; Furukawa, H.; Hmadeh, M.; Gándara, F.; Whalley, A. C.; Liu, Z.; Asahina, S.; Kazumori, H.; O'Keeffe, M.; Terasaki, O.; Stoddart, J. F.; Yaghi, O. M. *Science* **2012**, *336*, 1018. (k) Vukotic, V. N.; Harris, K. J.; Zhu, K.; Schurko, R. W.; Loeb, S. J. *Nat. Chem.* **2012**, *4*, 456.
- (10) (a) Li, Q. W.; Zhang, W. Y.; Miljanic, O. S.; Sue, C. H.; Zhao, Y. L.; Liu, L. H.; Knobler, C. B.; Stoddart, J. F.; Yaghi, O. M. *Science* **2009**, *325*, 855. (b) Valente, C.; Choi, E.; Belowich, M. E.; Doonan, C. J.; Li, Q.; Gasa, T. B.; Botros, Y. Y.; Yaghi, O. M.; Stoddart, J. F. *Chem. Commun.* **2010**, *46*, 4911. (c) Deng, H.; Olson, M. A.; Stoddart, J. F.; Yaghi, O. M. *Nat. Chem.* **2010**, *2*, 439.
- (11) Han, S.; Wei, Y.; Valente, C.; Lagzi, I.; Gassensmith, J. J.; Coskun, A.; Stoddart, J. F.; Grzybowski, B. A. *J. Am. Chem. Soc.* **2010**, *132*, 16358.
- (12) Lu, G.; Hupp, J. T. *J. Am. Chem. Soc.* **2010**, *132*, 7832. Kreno, L. E.; Leong, K.; Farha, O. K.; Allendorf, M.; Van Duyne, R. P.; Hupp, J. T. *Chem. Rev.* **2012**, *112*, 1105.
- (13) Hey, H.; Arpe, H.-J. *Angew. Chem., Int. Ed.* **1973**, *12*, 928.
- (14) Crystal data for **3**: C₄₃H₄₆O₁₀, red prism, 0.070 × 0.207 × 0.219 mm³; monoclinic, space group C2; a = 21.2730(3), b = 11.9713(2), and c = 17.7886(2) Å; β = 99.5880(10)°; V = 4466.8(6) Å³; T = 100(2) K, Z = 4, ρ_{calc} = 1.075 g cm⁻³, μ(Cu Kα) = 0.621 mm⁻¹, F(000) = 1536.0; independent measured reflections, 24 167; R₁ = 0.0645 and wR₂ = 0.2036 for 7579 independent observed reflections [2θ ≤ 124°, I > 2σ(I)]. CCDC 896923.
- (15) Crystal data for **5**: C₅₇H₅₄O₁₂(C₃H₇NO), colorless column, 0.074 × 0.130 × 0.430 mm³, monoclinic, space group P2₁/c; a = 14.5211(2), b = 34.3107(4), and c = 11.87650(10) Å; β = 97.2640(10)°; V = 5869.73(12) Å³; T = 100(2) K, Z = 4, ρ_{calc} = 1.069 g cm⁻³, μ(Cu Kα) = 0.612 mm⁻¹, F(000) = 2128; independent measured reflections, 39 135; R₁ = 0.0669 and wR₂ = 0.1648 for 10 348 independent observed reflections [2θ ≤ 124°, I > 2σ(I)]. CCDC 896924.
- (16) Two-dimensional NOESY was employed in the assignment of the 1-D ¹H NMR spectrum (see SI).
- (17) Even at elevated temperatures (100 °C) exchange between the diastereotopic methylene protons is not observed, indicating that the two benzoic acid substituents of **5** render the strut too large to be able to pass through the middle of the annulus which constitutes pillar[5]arene, implying that the inversion between the R_p and S_p enantiomers (Figure 1) does not occur on the NMR time scale, or indeed it would appear, on the laboratory time scale.
- (18) At room temperature, the ¹H NMR spectra (see SI) for **1–4** all display three singlets corresponding to the constitutionally heterotopic methylene groups, indicating that the enantiomeric pairs of these pillar[5]arene derivatives are inverting rapidly on the ¹H NMR time scale.
- (19) Further proof that the R_p and S_p enantiomers of **5** are resolvable comes from its ¹H NMR spectrum (see SI) after addition of a resolving agent—the alkaloid (–)-cinchonidine—revealing multiple resonances for protons, diastereotopic by external comparison, present in the diastereoisomeric acid–base pair (salts).
- (20) Further discussion on the planar chirality of pillar[5]arene: Ogoshi, T.; Masaki, K.; Shiga, R.; Kitajima, K.; Yamagishi, T.-a. *Org. Lett.* **2011**, *13*, 1264.
- (21) The ¹H NMR spectrum of the dimethyl ester (**S1** in SI) of **5** indicates that it is also, as expected, conformationally rigid and so exists as resolvable enantiomers which, in this instance, have been separated (resolved) by chiral HPLC.
- (22) Guests similar to G1⁺ and G2²⁺ have previously been reported to bind inside the cavity of pillar[5]arene and the electron/poor nature of G3 also makes it a suitable guest for **5**. See: Ogoshi, T. *J. Incl. Phenom. Macro.* **2012**, *72*, 247.
- (23) The four methyl groups present in **S3** enhance its solubility in organic solvents.
- (24) Grunder, S.; Stoddart, J. F. *Chem. Commun.* **2012**, *48*, 3158.