

This article was downloaded by:

On: 25 January 2011

Access details: *Access Details: Free Access*

Publisher *Taylor & Francis*

Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



## Journal of Macromolecular Science, Part A

Publication details, including instructions for authors and subscription information:

<http://www.informaworld.com/smpp/title~content=t713597274>

### Solvent Effects on the Radical Copolymerizabilities of Styrene with p-Substituted N,N-Diethylcinnamamides and of p-Substituted Styrenes with Methyl Vinyl Sulfoxide

Hisashi Fujihara<sup>a</sup>; Takaaki Shindo<sup>a</sup>; Masakuni Yoshihara<sup>a</sup>; Toshihisa Maeshima<sup>a</sup>

<sup>a</sup> Department of Applied Chemistry Faculty of Science and Engineering, Kinki University Kowakae, Higashi-Osaka, Japan

**To cite this Article** Fujihara, Hisashi , Shindo, Takaaki , Yoshihara, Masakuni and Maeshima, Toshihisa(1980) 'Solvent Effects on the Radical Copolymerizabilities of Styrene with p-Substituted N,N-Diethylcinnamamides and of p-Substituted Styrenes with Methyl Vinyl Sulfoxide', *Journal of Macromolecular Science, Part A*, 14: 7, 1029 – 1034

**To link to this Article:** DOI: 10.1080/00222338008056727

**URL:** <http://dx.doi.org/10.1080/00222338008056727>

PLEASE SCROLL DOWN FOR ARTICLE

Full terms and conditions of use: <http://www.informaworld.com/terms-and-conditions-of-access.pdf>

This article may be used for research, teaching and private study purposes. Any substantial or systematic reproduction, re-distribution, re-selling, loan or sub-licensing, systematic supply or distribution in any form to anyone is expressly forbidden.

The publisher does not give any warranty express or implied or make any representation that the contents will be complete or accurate or up to date. The accuracy of any instructions, formulae and drug doses should be independently verified with primary sources. The publisher shall not be liable for any loss, actions, claims, proceedings, demand or costs or damages whatsoever or howsoever caused arising directly or indirectly in connection with or arising out of the use of this material.

## Solvent Effects on the Radical Copolymerizabilities of Styrene with *p*-Substituted *N,N*-Diethylcinnamamides and of *p*-Substituted Styrenes with Methyl Vinyl Sulfoxide

HISASHI FUJIHARA, TAKAAKI SHINDO, MASAKUNI YOSHIHARA,  
and TOSHIHISA MAESHIMA

Department of Applied Chemistry  
Faculty of Science and Engineering  
Kinki University  
Kowakae, Higashi-Osaka, Japan 577

### ABSTRACT

Radical copolymerizations of styrene (St) with *p*-substituted-*N,N*-diethylcinnamamides (I) and also of *p*-substituted styrenes (II) with methyl vinyl sulfoxide (MVSO) have been carried out in benzene, acetic acid or acetonitrile. The monomer reactivity ratios ( $r_1$ ) were found to be affected by the solvents.  $\rho$  values obtained by using the modified Hammett equation, i. e.,  $\log(1/r_1) = \rho\sigma + \gamma E_R$ , were also found to be altered by the solvents. The results are discussed in terms of the solvent effect in the transition state of the propagation reaction.

### INTRODUCTION

Previously we reported that the radical copolymerizability of styrene with vinyl monomers bearing polar groups, i. e., 2,6-dimethylpyridazine-3-one [1], methyl methacrylate [2], and *N,N*-dimethyl-

acrylamide [3], were considerably influenced by such protic solvents as phenol and carboxylic acid, due apparently to the hydrogen-bonding solvation to the polar groups of vinyl monomers, which would stabilize the growing radicals both in the ground state and in the transition state to affect the reactivities of these monomers.

In this work, the authors have re-investigated the effects of solvents on the copolymerizabilities of styrene (St) with *p*-substituted-*N,N*-diethylcinnamamides (I) and also of *p*-substituted styrenes (II) with methyl vinyl sulfoxide (MVSO).

## EXPERIMENTAL

### Materials

Styrene (St) was purified by distillation in a stream of nitrogen before use.

Syntheses of *p*-substituted-*N,N*-diethylcinnamamides (I) were described previously [4, 5]; *p*-CH<sub>3</sub>C<sub>6</sub>H<sub>4</sub>CH=CHCON(C<sub>2</sub>H<sub>5</sub>)<sub>2</sub> had bp 160°C/3 Torr; *p*-ClC<sub>6</sub>H<sub>4</sub>CH=CHCON(C<sub>2</sub>H<sub>5</sub>)<sub>2</sub> had mp 44-45°C; C<sub>6</sub>H<sub>5</sub>CH=CHCON(C<sub>2</sub>H<sub>5</sub>)<sub>2</sub> had mp 68-69°C.

*p*-Substituted styrenes (II) were prepared by the method described elsewhere [6-8]; *p*-CH<sub>3</sub>C<sub>6</sub>H<sub>4</sub>CH=CH<sub>2</sub> had bp 55°C/12 Torr; *p*-ClC<sub>6</sub>H<sub>4</sub>CH=CH<sub>2</sub> had bp 72°C/12 Torr.

Methyl vinyl sulfoxide (MVSO) was prepared by the method of Price et al. [9]; CH<sub>2</sub>=CHSOCH<sub>3</sub> had bp 70-71°C/11 Torr.

The compounds were purified according to the usual method and were characterized by means of infrared (IR) and NMR spectra and elementary analysis.

Benzene, acetonitrile (CH<sub>3</sub>CN), and acetic acid (AcOH) were purified according to the usual method.

### Polymerization

All polymerizations were carried out at 80°C in degassed ampules, into which the required amounts of monomer, solvent, and initiator were placed. The reaction mixture was poured into a large amount of methanol to precipitate the polymer, which was purified by repeated reprecipitation from benzene and methanol. No other impurities in the copolymers were determined by infrared (IR) and NMR spectral analysis and by TLC. The compositions of copolymers for the St-I system were determined by elementary analysis of nitrogen while the copolymer compositions for the II-MVSO system were determined by elementary analysis of carbon.

TABLE 1. Monomer Reactivity Ratios for the Copolymerization of St ( $M_1$ ) with I at 80°C

X	$r_1$	
	In benzene	In AcOH
CH <sub>3</sub>	4.95	6.08
H	4.17	4.92
Cl	2.99	3.56

$$r_2 = 0.01.$$

TABLE 2. Monomer Reactivity Ratios for the Copolymerization of II( $M_1$ ) with MVSO at 80°C

X	$r_1$		
	In benzene	In AcOH	In CH <sub>3</sub> CN
CH <sub>3</sub>	2.73	2.28	6.90
H	3.57	3.20	8.17
Cl	6.46	6.54	10.85

$$r_2 = 0.01.$$

## RESULTS AND DISCUSSION

Tables 1 and 2 show the results of the radical copolymerizations of styrene with I and II with MVSO in a few solvents. Monomer reactivity ratios ( $r_1$ ) obtained in both systems were found to vary with the solvents, implying some solvent effect in the copolymerizations.

The  $r_1$  values were plotted against Hammett  $\sigma$  values by using Otsu's equation [10], i. e.,  $\log(1/r_1) = \rho\sigma + \gamma E_R$ , to give linear relationships as shown in Figs. 1 and 2. The values of  $\rho$  and  $\gamma$  are given in Table 3. It is quite interesting to note that the  $\rho$  values obtained in both systems were altered by the reaction solvents, indicating that the ionic character in the transition state of the  $K_{12}$  step might be influenced by the solvents used. In the case of the St-I system, the  $\rho$  value in benzene was found to be smaller than that in acetic acid. This fact may be explained in the following manner. In the transition state of  $K_{12}$  the drift of an electron to the I unit is accelerated by acetic acid compared with benzene, perhaps due to a hydrogen-bonding




FIG. 1. Hammett plots for the copolymerization of St ( $M_1$ ) with I in benzene and in acetic acid at 80°C.





FIG. 2. Hammett plots for the copolymerization of II ( $M_1$ ) with MVSO in benzene, acetonitrile, and acetic acid at 80°C.


**TABLE 3.**  $\rho$  and  $\gamma$  Values Obtained by Plotting the Values of  $\log(1/r_1)$  against  $\sigma$  Values

$M_1$	$M_2$	Solvent	$\rho$	$\gamma$
St	I	Benzene	0.49	0.31
		AcOH	0.56	0.12
II	MVSO	Benzene	-0.81	-0.73
		AcOH	-1.01	-0.81
		CH <sub>3</sub> CN	-0.46	-0.18

solvation to the carbonyl group of I as shown in the following scheme.




A similar explanation could be applied for the II-MVSO system, in which the largest negative  $\rho$  value was obtained in acetic acid. In other words, acetic acid might accelerate the drift of the charge electron to the MVSO unit at the transition state of  $K_{12}$ , due to the hydrogen bonding solvation to the sulfoxide group of MVSO and hence



increase the  $\rho$  value as compared with benzene. In acetonitrile, the  $\rho$  value was found to be quite small. We do not have any evidence to deduce the mechanism. However, this fact means that the drift of the charge electron to the MVSO unit might be decreased by acetonitrile. We wish to postulate one possibility that this might be caused by a solvation between the sulfoxide and the cyano groups which affects

the charge distribution of the transition state. Actually, Ritchie et al. showed that the sulfoxide group forms a specific solvated complex



with the cyano group [ 11].

#### REFERENCES

- [ 1 ] H. Fujihara, M. Yoshihara, Y. Matsubara, and T. Maeshima, J. Macromol. Sci., in press.
- [ 2 ] H. Fujihara, K. Yamazaki, Y. Matsubara, M. Yoshihara, and T. Maeshima, J. Macromol. Sci., in press.
- [ 3 ] H. Fujihara, M. Yoshihara, T. Maeshima, J. Macromol. Sci., submitted.
- [ 4 ] D. Papa, E. Schwenk, F. Villani, and E. Klingsberg, J. Am. Chem. Soc., **72**, 3885 (1950).
- [ 5 ] E. T. Mccae, W. F. Barthel, S. I. Gertler, and S. A. Hall, J. Org. Chem., **19**, 493 (1954).
- [ 6 ] C. S. Marvel and N. S. Moon, J. Am. Chem. Soc., **62**, 45 (1940).
- [ 7 ] L. A. Brooks, J. Am. Chem. Soc., **66**, 1295 (1944).
- [ 8 ] C. G. Overberger, Org. Syn., **28**, 31 (1949).
- [ 9 ] C. C. Price, R. D. Gilbert, J. Am. Chem. Soc., **74**, 2073 (1952).
- [ 10 ] T. Yamamoto and T. Otsu, Chem. Ind. (London), 1967, 787.
- [ 11 ] C. D. Ritchie, B. A. Bierd, and R. J. Honour, J. Am. Chem. Soc., **84**, 4687 (1962).

Accepted by editor June 28, 1979

Received for publication July 26, 1979