

This article was downloaded by:

On: 24 January 2011

Access details: *Access Details: Free Access*

Publisher *Taylor & Francis*

Informa Ltd Registered in England and Wales Registered Number: 1072954 Registered office: Mortimer House, 37-41 Mortimer Street, London W1T 3JH, UK



## Journal of Macromolecular Science, Part A

Publication details, including instructions for authors and subscription information:

<http://www.informaworld.com/smpp/title~content=t713597274>

### Structural and Biological Characterization of Antimony(V) Polyamines

Charles E. Carraher Jr.<sup>a</sup>; Melissa D. Naas<sup>a</sup>; David J. Giron<sup>a</sup>; Delie Roselyn Cerutis<sup>a</sup>

<sup>a</sup>Departments of Chemistry and Microbiology and Immunology, Wright State University, Dayton, Ohio

**To cite this Article** Carraher Jr., Charles E. , Naas, Melissa D. , Giron, David J. and Cerutis, Delie Roselyn(1983) 'Structural and Biological Characterization of Antimony(V) Polyamines', Journal of Macromolecular Science, Part A, 19: 8, 1101 – 1120

**To link to this Article:** DOI: 10.1080/00222338308081088

**URL:** <http://dx.doi.org/10.1080/00222338308081088>

PLEASE SCROLL DOWN FOR ARTICLE

Full terms and conditions of use: <http://www.informaworld.com/terms-and-conditions-of-access.pdf>

This article may be used for research, teaching and private study purposes. Any substantial or systematic reproduction, re-distribution, re-selling, loan or sub-licensing, systematic supply or distribution in any form to anyone is expressly forbidden.

The publisher does not give any warranty express or implied or make any representation that the contents will be complete or accurate or up to date. The accuracy of any instructions, formulae and drug doses should be independently verified with primary sources. The publisher shall not be liable for any loss, actions, claims, proceedings, demand or costs or damages whatsoever or howsoever caused arising directly or indirectly in connection with or arising out of the use of this material.

## Structural and Biological Characterization of Antimony(V) Polyamines

CHARLES E. CARRAHER, JR., MELISSA D. NAAS,  
DAVID J. GIRON, and DELIE ROSELYN CERUTIS


Departments of Chemistry and Microbiology and Immunology  
Wright State University  
Dayton, Ohio 45435

### ABSTRACT

The condensation of organoantimony(V) dihalides with diamines forming antimony(V) polyamines employing the interfacial technique is described. Structural characterization was accomplished by employing elemental analysis, light-scattering photometry, infrared spectroscopy, control reactions, and mass spectroscopy. The products exhibit mild inhibition to a wide range of bacteria and to HeLa, BHK-21, and L929 cancer-related cell lines.


### INTRODUCTION

The synthesis of polymers containing metal atoms in the backbone of the polymer chain is well known. For instance, polyethers, polyesters, polyamidoximes, and polyoximes have been synthesized based on the Lewis acid-base reaction concept [1-3]. Utilizing an interfacial condensation polymerization technique, Carraher and Blaxall synthesized a number of antimony containing polyesters of form  $\frac{1}{2}$  [4]. These products were of high molecular weight (typically  $> 10^6$ ).



where R = methyl, ethyl, butyl, phenyl  
 R' = aliphatic and aromatic hydrocarbons  
 X = chloride and bromide


Doak and Freedman [5] synthesized monomeric compounds from the condensation of mono-Lewis bases (in particular monoamines) with a number of organometallic halides (including antimony, 2) [5]



where R = methyl, ethyl, phenyl  
 R' = aliphatic and aromatic hydrocarbons  
 X = chloride and bromide

This was extended by Carraher and Moon to include reaction with polyamines derived from arsenic(V) organometallics and diamines (Form 1 where the metal is arsenic [6]). These products exhibited biological activities against selected bacteria and were soluble in several liquids.

The condensation of organoantimony(V) dihalides with diamines is an extension of the work cited above. Here we describe the initial synthesis of antimony(V) polyamines of Form 3, presenting structural evidence and biological assays related to their potential use as additives in medical and coatings applications.



## EXPERIMENTAL

### Chemicals

The following chemicals were used without further purification (from Aldrich Chemical Co., Milwaukee, unless noted otherwise):

2,6-Diamino-5-nitropyrimidine; 2,6-diaminoanthraquinone; 2,5-dichloro-p-phenylenediamine; 2,5-diaminotoluene sulfate; 2,6-diaminopyridine dihydrochloride; 4,4'-diaminodiphenyl amine sulfate; 1,6-diaminohexane; 2,4-diamino-5(3,4-dimethoxybenzyl)pyrimidine (Burroughs Wellcome Co., Research Triangle Park, North Carolina); 1,12-diaminododecane; 2,6-diamino-8-purinol hemisulfate monohydrate; adenine (Chemalog Chemical Dynamics Corp., South Plainfield, New Jersey); 1,9-diaminononane; 4,6-diamino-2-methyl-5-nitrosopyrimidine (Parish Chemical Co., Provo, Utah); 2,4-diamino-6-hydroxypyrimidine; 4,4'-diaminodiphenyl sulfon (Fluka AG, Buchs SG, Switzerland); 2-methoxy-p-phenylenediamine; 4,4'-methylenedianiline; 4,4'-diaminobenzanilide; diaminomaleonitril; Zineb (Pfaltz and Bauer Inc., Stamford, Connecticut); 2,4-diamino-7-hydroxypyrimidine; 4,4'-methylbis(3-nitroaniline); 3,6-diaminoacridine hemisulfate; 1,4-diaminopiperazine; 1,8-diaminooctane; 1,4-diaminobutanone dihydrochloride; 1,3-diamino-2-hydroxypropane;  $\beta$ -(4-aminophenyl)ethyl amine; uracil; histamine dihydrochloride (United States Biochemical Corp., Cleveland, Ohio); 4,4'-diaminooctafluorodiphenyl; triphenylantimony dichloride; trimethylantimony dichloride (Strem Chemicals, Inc., Newburyport, Massachusetts); and tributylantimony.

### Polymerization Apparatus and Procedure

For all the polymerization reactions conducted, a Kimex emulsifying jar was used. The jar was placed on a Waring Blendor (Model 1120) whose speed, without load, is 18,000 rpm.

The lid of the jar has one hole in it for a large mouthed funnel through which a large volume of solution can be added in a short period of time so that the rate of addition of a solution to the jar can be held approximately constant.

Solutions of the antimony organometallic in an organic solvent were added to the blender. Rapid stirring was begun and an aqueous solution of a diamine which also contained an added base, sodium hydroxide, NaOH, or triethylamine, Et<sub>3</sub>N, or other agent was added. Reaction time was begun when the organic phase was fully added to the stirred aqueous phase.

The products were recovered as precipitates by employing suction filtration and washed with water and the organic liquid employed in the nonaqueous phase.

### Instrumentation for Physical and Chemical Characterization

A Perkin-Elmer Model 457 Grating Spectrophotometer was used to obtain infrared spectra of the products. All spectra were taken using potassium bromide pellets. The mass spectral analyses were performed using a DuPont 21-401 MS coupled with a Hewlett-Packard

HP-2216C. The elemental analyses were performed using a Perkin-Elmer 240 Elemental Analyzer.

Molecular weight determinations were done using a Brice-Phoenix Model BP-3000 Universal Light-Scattering Photometer. Molecular weight determinations were carried out in the usual manner using 1% polymer solutions with serial dilutions. Refractive index increments,  $dn/dc$ , were determined using a Bausch and Lomb Abbe Refractometer Model #3-L.

### Preliminary Biological Characterization

Several organisms were chosen to give a wide range of bacterial species. The procedure involved streaking tryptic soy agar (TSA) plates with the organism and then adding a small amount of polymer to a circular area. The plates were then incubated for 24 h at 37°C. After this time period, the plates were checked for inhibition which is indicated by a clear zone on the plate.

Three cell lines were chosen for the cell line studies. Dimethyl-sulfoxide (DMSO) was the solvent of choice for the polymer since it is not appreciably toxic to man and the polyamines are soluble in it.

The polymer was dissolved in DMSO and the resulting solution filtered using a sintered glass filter. Various concentrations of the polymer were prepared by diluting the stock solution.

Confluent flasks of the cell lines L929 (Mouse Connective Tissue Tumor Line), BHK-21 (Baby Hamster Kidney), and HeLa (Epitheloid Carcinoma, Cervix, Human) were trypsinized, suspended, counted (using a Coulter Counter Model Z<sub>BI</sub>), and plated onto 24-well Corning

plates. The plates were incubated overnight at 37°C in 5% CO<sub>2</sub> to allow the cells to form a monolayer. Next, Dulbecco's Modified Eagle Medium (DMEM) was aspirated and replaced with 1 mL of the various polymer dilutions (in DMEM). This was then allowed to incubate overnight at 37°C in 5% CO<sub>2</sub>. The polymer-containing media was then aspirated and replaced with 1 mL of a solution of DMEM and Neutral Red in 0.85% NaCl (concentration  $7.6 \times 10^{-6}$  g/mL Neutral Red/DMEM). The cells were then allowed to take up the dye (incubate) for 2 h (same conditions). The media was then aspirated and the cells washed twice with 1 mL aliquots of 1:1 Sorensen Citrate Buffer (pH 4.20)/EtOH to develop the full acid color of the dye (about 95% extraction efficiency observed).

The effect of the polymer on the cells was measured from the absorbance of the dye since only live (viable) cells will absorb the dye. This was achieved by measuring the absorbance of the extracted dye at a maximum of 540 nm. From the absorbance of the control and polymer concentrations, the percent live cells was calculated as

$$\frac{\text{absorbance of cell solutions treated with polymer}}{\text{absorbance of cell solutions without treatment}} \times 100 = \% \text{ viable cells}$$

## RESULTS AND DISCUSSION

Historical

As cited in the Introduction section, the condensation of polyoximes with organoantimony dihalides, monoamines with organoantimony dihalides, and diamines with organoarsenic dihalides to form the Lewis acid-base adduct is well established. The condensation of organoantimony dihalides with diamines is a logical extension of these reactions.

Control Reactions

Reactions were attempted excluding either triphenylantimony dichloride, diamine, or sodium hydroxide, with all other reaction conditions held constant. The reactions resulted in clear solutions as compared to the precipitates formed when both monomers and added base are present. This is consistent with the product being derived from more than one of the added ingredients, excluding situations such as single reactant precipitation.

Infrared Spectroscopy

Infrared spectral analysis is consistent with a product of Form 3 with the formation of the Sb-N linkage. This linkage is indicated by the presence of a band at about  $1100\text{-}1200\text{ cm}^{-1}$  (Table 1).

Bands characteristic of the organoantimony moiety are present.

TABLE 1. Location of the Antimony-Nitrogen Stretching Band in the Infrared Spectra of Select Condensation Products Derived from the Condensation of Organoantimony(V) Dihalides with Diamines

Organoantimony(V) dihalide	Diamine	Sb-N band ( $\text{cm}^{-1}$ )
Triphenylantimony dichloride	2,6-Diamino-5-nitropyrimidine	1180
"	2,6-Diamino-8-purinol	1100
"	Adenine	1125
"	2,5-Dichloro-p-phenylene	1175
"	1,6-Diaminohexane	1175
"	2,6-Diamino-5(3,4-dimethoxy- benzil)pyrimidine	1150




FIG. 1. The infrared spectrum of the condensation product of triphenylantimony dichloride with 2,6-diamino-5-nitropyrimidine (—) and triphenylantimony dichloride (---).

For instance, for the product from triphenylantimony dichloride and 2,6-diamino-5-nitropyrimidine (Fig. 1), bands characteristic of the antimony-phenyl linkage are present at about  $1425\text{--}1450\text{ cm}^{-1}$ ; bands characteristic of phenyl are present at  $690$  and  $725\text{ cm}^{-1}$ . Bands characteristic of the diamine moiety are also present. For instance, infrared spectra of the product of triphenylantimony dichloride with 2,6-diamino-5-nitropyrimidine exhibit a band characteristic of the nitro group stretch at  $1600\text{ cm}^{-1}$  and a band characteristic of the carbon-nitro bond at  $800\text{ cm}^{-1}$ . The presence of 2,6-diamino-8-purinol moiety is evident from the presence of a band at  $3100\text{--}3500\text{ cm}^{-1}$  characteristic of oxygen-hydrogen stretching. The presence of the  $\text{R-O-CH}_3$  band for the product derived from 2,4-diamino-5-(3,4-dimethoxybenzyl)pyrimidine at about  $1440\text{--}1470\text{ cm}^{-1}$  indicates the presence of the diamine moiety. The product derived from the condensation of triphenylantimony dichloride with 2,5-dichloro-p-phenylenediamine shows a band associated with  $\text{Cl-CH}$  stretching for an aromatic substituent at  $1000\text{ cm}^{-1}$ .

### Elemental Analysis

Elemental analyses for carbon, hydrogen, and antimony are in fair agreement with a product of Form 3 (Table 2). Values for nitrogen are in moderate agreement at best. It should be noted that many organometallic condensation polymers and analogous coordination monomeric and polymeric products have difficulty undergoing combustion, leading to poor results for elemental analysis. A combustion catalyst, tungstanyl carbonyl, was utilized in the present study to assist product combustion.

### Mass Spectrophotometry

The formal description for the procedure employed is pyroprobe chemical mass spectrophotometry.

Mass spectral data are also in agreement with a product containing units derived from the organoantimony and diamine with fragmentation patterns assignable as having originated from both monomeric portions. Further, ion fragments assignable to repeat units are detected (Table 3). For the product from the condensation of triphenylantimony dichloride with 2,6-diamino-5-nitropyrimidine, all of the phenyl unit appear at 77, 78, 79, and 156 biphenyl; all ion fragments are assigned values based on the mass to single charge ( $m/e$  ratio). Fragments 199, 200, 275, 277, 354, and 355 are associated with the antimony-phenyl moiety. Fragments characteristic of the presence of the nitropyrimidine appear at 105, 107, 123, 151, 154, and 155. Fragments assignable to the presence of one repeat unit minus selected moieties are found at 291, 293, 295, 332, 353, 355, 367. Thus the pyroprobe-mass spectral results are consistent with a product of Form 3. Results for the additional






TABLE 2. Carbon, Nitrogen, Hydrogen, and Antimony Elemental Analysis for Select Organoantimony(V) Polyamine Products


Diamine <sup>a</sup>	% C		% N		% H		% Sb	
	Calculated	Found	Calculated	Found	Calculated	Found	Calculated	Found
4,4'-Diaminodiphenyl-sulfon	53.7	53.2			4.2	4.5		
2,6-Diaminoanthraquinone	65.0	66.1			4.6	3.0		
4,4'-Methylenedi-aniline	67.8	70.1			4.9	5.1		
Zineb			4.5	6.1	3.0	3.0	20.3	27.6
1,12-Diaminododecane	65.6	60.8					23.2	24.3
Adenine	56.6	60.6			4.1	4.2	24.3	24.6
2,5-Dichloro-p-phenylene diamine			5.3	5.9	3.6	3.3		

<sup>a</sup> All derived from triphenylantimony dichloride.

TABLE 3. Major Ion Fragments for the Gases Derived from the Thermal Degradation of the Condensation Product of Triphenylantimony Dichloride with 2,6-Diamino-5-nitropyrimidine<sup>a</sup>







$m/e^b$	Ion fragment
79, 78, 77	$\phi$
199, 200	$\phi\phi$
275, 277	$Sb\phi$
354, 355	$Sb\phi_2$ $Sb\phi_3$
105, 107	
123	
151, 154, 155	
338	Repeat unit minus $2\phi$
367	Repeat unit minus $\phi, NO_2$
291, 293, 295	Repeat unit minus $2\phi, NO_2$
353, 355	Repeat unit minus $\phi, NO_2, NH$

<sup>a</sup>Repeat unit








<sup>b</sup>CIMS ( $m/e = 60$  to  $400$ ).

**TABLE 4. Major Ion Fragments for the Gases Derived from the Thermal Degradation of the Condensation Product of Triphenylantimony Dichloride with 2,4-Diamino-5(3,4-dimethoxybenzyl)pyrimidine<sup>a</sup>**

m/e <sup>b</sup>	Ion fragment
79, 78, 77	$\phi$
156	$\phi\phi$
200, 199, 198	$Sb\phi$
275, 277	$Sb\phi_2$
352, 353, 354, 355	$Sb\phi_3$
231, 229, 228, 227	
201, 199, 198	
108, 107, 106	
81, 80	
92, 93, 94	
152, 151, 150, 147	

(continued)

TABLE 4 (continued)

$m/e^b$	Ion fragment
138, 137, 136	
601	Repeat unit
453	Repeat unit minus
	
544	Repeat unit minus $2\phi\text{CH}_3$
493, 495	Repeat unit minus $\phi$ , $\phi\text{CH}_3$
465	Repeat unit minus $\phi$ , $2\phi\text{CH}_3$
719	Repeat unit plus
	
805	Repeat unit plus
	
<sup>a</sup> Repeat unit	


<sup>b</sup>CIMS ( $m/e = 60$  to 815).

compounds are given in Tables 4 and 5. These also exhibit the presence of the repeat unit and various fragments of the repeat unit.

Of importance in applications, which may involve extended (high) temperatures, is the presence of fragments containing antimony. While the toxicity of the particular gaseous species is not known, the threshold limiting value, TLV, for antimony in air is  $0.5 \text{ mg/m}^3$  and the reported fatal dose of antimony compounds by ingestion is 100-200 mg [7]. Antimony toxicity is reversible and, in cases of acute poisoning, survival for 48 h indicates that recovery is probable [7]. Thus antimony and typical antimony compounds are considered only moderately toxic when compared with other metals such as beryllium (TLV =  $2.0 \times 10^{-3} \text{ mg/m}^3$ ), cadmium ( $0.1 \text{ mg/m}^3$ ), chromium ( $0.1 \text{ mg/m}^3$ ), and lead ( $0.15 \text{ mg/m}^3$ ).

TABLE 5. Major Ion Fragments for the Gases Derived from the Thermal Degradation of the Condensation Product of Triphenylantimony Dichloride with 4,4-Diaminodiphenylsulfon<sup>a</sup>

m/e <sup>b</sup>	Ion fragment
79, 78, 77	$\phi$
199, 200	$\text{Sb}\phi$
275, 277	$\text{Sb}\phi_2$
354, 355	$\text{Sb}\phi_3$
216	$\begin{array}{c} \text{O} \\   \\ \phi\text{-S-}\phi \\   \\ \text{O} \end{array}$
508	Repeat unit minus $\phi\text{NH}$
275	$\begin{array}{c} \text{O} \\   \\ \text{Repeat unit minus } \phi, \text{N-}\phi\text{-S-}\phi\text{-N} \\   \\ \text{O} \end{array}$



<sup>b</sup>CIMS (m/e = 60 to 560).

Light-Scattering Photometry

The molecular weight results for selected products appear in Table 6. The products are oligomeric ( $\bar{M}_w \cong 3 \times 10^3$ ,  $\bar{DP} \cong 10$ ) to high polymers ( $\bar{M}_w \cong 4 \times 10^6$ ).

Product Structure Summary

The presence of both moieties derived from the organoantimony and diamine is indicated by results obtained employing infrared and mass spectroscopy and control reactions. Elemental analyses results are in fair agreement with the proposed structure. The formation of the Sb-N linkage is consistent with previous studies and indicated by infrared spectral results. The formation of a repeat unit of Form 3 is further indicated by the presence of ion fragments assigned as being derived from this repeat unit. The polymeric nature of the product is shown by molecular weight determinations. Thus both the circumstantial and physical evidence are in agreement with products containing repeat units as depicted in Form 3.

## BIOLOGICAL ASSAYS

Most antimony-containing products exhibit some toxicity to humans which must be considered when considering applications for antimony-containing products. Antimony-containing materials are fairly readily available and are known for their use in biological systems. Toxicity can be reduced through complexing the antimony in a polymeric-type compound.

The antimony(V) polyamine products were tested as solids regarding their inhibitory nature toward a variety of bacteria described in Table 7 [8]. Results of this study are found in Table 8. The majority of the compounds exhibit no inhibition against the bacteria studied. However, some of the products show slight or good inhibition. Also, of the products tested, Zineb is the only aliphatic diamine which is a known antifungal, and the polymer derived from it exhibits good inhibition. It must be emphasized that these inhibition studies were conducted on the products in the solid state. Future studies should involve studies with the products solubilized in a suitable liquid such as DMSO.

Solutions of the antimony(V) polyamines were used to study their activity against selected cell lines. The results are tabulated in terms of percent of cells that survived (Tables 9-11). For the cell line BHK-21 (Table 9) the majority of the products show an expected decrease in inhibition in cell growth with a decrease in concentration. A few products showed no dependence on concentration for cell sur-

TABLE 6. Results as a Function of Reactants<sup>a</sup>

Organoantimony dihalide	Diamine	% Yield	Molecular weight, $M_w$
Triphenylantimony dichloride	1,6-Diaminohexane	36	
"	2,6-Diamino-8-purinol	39	$3.7 \times 10^3$
"	2,6-Diaminoanthraquinone	40	
"	2,6-Diamino-5-nitropyrimidine	14	
"	2,4-Diamino-5(3,4-dimethoxybenzyl)pyrimidine	21	$4.8 \times 10^3$
"	4,4'-Diaminodiphenylsulfon	18	$4.5 \times 10^3$
"	Adenine	9	$2.6 \times 10^3$
"	p-Phenylenediamine	12	
"	2-Methoxy-p-phenylenediamine	76	
"	2,3,5,6-Tetramethyl p-phenylenediamine	8	
"	2,5-Dichloro-p-phenylenediamine	39	$4.3 \times 10^3$
"	2-Nitro-p-phenylenediamine	23	
"	4,4'-Methylenedianiline	54	
"	4,4'-Diaminobenzanilide	43	
"	Zineb	36	
"	2,5-Dichloro-p-phenylenediamine	40	$9.3 \times 10^3$
Triphenylantimony dibromide	2,6-Diamino-8-purinol	62	$1.0 \times 10^3$
"	4,4'-Diaminodiphenyl	51	$1.2 \times 10^3$
Trimethylantimony dichloride	2,6-Diamino-8-purinol	93	$4.4 \times 10^3$
"	4,4'-Diaminodiphenylsulfon	40.6	$3.7 \times 10^6$

<sup>a</sup>Reaction conditions: organoantimony dihalide (1.00 mmol) in 25 mL carbon tetrachloride is added to a stirred (18,000 rpm, no load) solution of diamine (1.00 mmol) and sodium hydroxide (2.00 mmol) in 25 mL of water for 30 s at 25°C.

TABLE 7. Bacteria Studied for the Effect of Antimony(V) Polyamines

---

<b>Actinobacter calcoaceticus:</b>
Gram-negative rod
Can be an opportunistic pathogen but is part of the normal flora of the skin and mouth
Associated with conjunctivitis, keratitis, and chronic ear infections
<b>Alcaligenes faecalis:</b>
Gram-negative rod
Part of the normal intestinal flora
Has been found to cause urinary tract infections and in debilitated individuals septicemia or meningitis
<b>Branhamella catarrhalis:</b>
Gram-negative diplococcus
Part of the normal oral and nasopharyngeal flora
Has been associated with mucous membrane inflammations, venereal discharges, meningitis, and bacterial endocarditis
<b>Enterobacter aerogenes:</b>
Gram-negative rods
Part of the normal flora of the intestinal tract
Has caused urinary tract infections, endocarditis, pneumonia, and bacteremia
<b>Escherichia coli:</b>
Gram-negative rod
Part of the normal intestinal flora
Most frequent cause of urinary tract infections
May cause cholecystitis, appendicitis, peritonitis, sinusitis, and summer diarrhea
<b>Klebsiella pneumoniae:</b>
Gram-negative rod
Part of the normal flora of the nose, mouth, and intestines
May cause lesions in various parts of the body, pneumonia, chronic lung abscess, sinusitis, and upper respiratory infections
<b>Neisseria mucosa:</b>
Gram-negative cocci
Part of normal flora of the oronasopharynx
Generally nonpathogenic but has been found in rare cases of meningitis
<b>Pseudomonas aeruginosa:</b>
Gram-negative rod
Common inhabitant of soil
Frequently found as part of normal flora of the intestine and skin
Opportunistic pathogen, may infect wounds, contaminates burns, draining sinuses and decubitus ulcers, cause urinary tract infections, eye infections, and meningitis
<b>Staphylococcus epidermis:</b>
Gram-positive cocci
Generally causes mild infections but has caused septicemias, bacterial endocarditis, and urinary tract infections
<b>Staphylococcus aureus:</b>
Gram-positive cocci
Causes "pimples," abscesses, impetigo, wound infections, pyelitis, cystitis, "food poisoning," pneumonia, meningitis, and enteritis

---



TABLE 8. Bacteriological Results of Antimony (V) Polyamines<sup>a</sup>

$\phi_3\text{SbCl}_2$ + diamine	E. coli	Alcal	Staph E	Staph A	Entero	Neiss	Kleb	Bran	Pseu	Actin
4,6-Diamino-2-methyl-5-nitrosopyrimidine	I	I	SI	I	I	I	I	I	I	I
Adenine	N	N	N	N	N	N	N	N	N	N
2-Nitro-p-phenylenediamine	N	N	N	N	N	N	N	N	N	N
4,4'-Diaminodiphenylsulfon	N	I	N	N	N	I	N	I	CI	SI
4,4'-Diaminobenzanilide	N	N	N	N	N	N	N	N	N	N
2,5-Dichloro-p-phenylene-diamine	N	N	N	N	N	N	N	N	N	N
2,4-Diamino-5(3,4-dimethoxy-benzil)pyrimidine	N	N	CI	N	N	N	SI	I	N	N
4,6-Diamino-5-nitroso-pyrimidine	N	N	N	N	N	N	N	N	N	N
4,4'-Methylenedianiline	N	N	CI	N	N	N	N	I	N	N
2,6-Diamino-8-purinol	N	N	N	N	N	N	N	N	N	N
2,6-Diaminopyridine	N	N	N	N	N	N	N	N	N	N
Zineb	SI	I	I	SI	SI	I	SI	I	I	I

<sup>a</sup>N = no inhibition; SI = slight inhibition; CI = inhibition but cloudy zone, I = inhibition, clear zone.

TABLE 9. Results of the Effect of Selected Antimony(V) Polyamines on the Cell Line BHK-21<sup>a</sup>

$\phi_3\text{SbCl}_2$ + diamine	6 $\mu\text{g}/\text{mL}$	5 $\mu\text{g}/\text{mL}$	5 $\mu\text{g}/\text{mL}$	3 $\mu\text{g}/\text{mL}$	2 $\mu\text{g}/\text{mL}$
4,6-Diamino-2-methyl-5-nitrosopyrimidine	20.2	10.3	15.7	50.4	66.4
Adenine	19.7	29.9	36.5	33.6	52.1
2-Nitro-p-phenylenediamine	55.3	56.1	45.3	58.1	79.5
4,4'-Diaminobenzanilide	67.2	51.3	51.3	44.5	58.4
2,5-Dichloro-p-phenylenediamine	79.5	61.5	46.2	49.3	49.6
2,4-Diamino-5(3,4-dimethoxybenzyl)-pyrimidine	0	0	0	0	0
2,6-Diaminoanthraquinone	0	0	0	0	0
2,6-Diamino-8-purinol	33.9	48.1	50.4	51.6	47.0
2,6-Diaminopyridine	44.7	52.4	30.3	40.7	45.9

<sup>a</sup>Values are in % viable cells.

TABLE 10. Results of the Effect of Selected Antimony(V) Polyamines on the Cell Line L929<sup>a</sup>

$\phi_3\text{SbCl}_2$ + diamine	6 $\mu\text{g}/\text{mL}$	5 $\mu\text{g}/\text{mL}$	3 $\mu\text{g}/\text{mL}$	3 $\mu\text{g}/\text{mL}$	2 $\mu\text{g}/\text{mL}$
4,6-Diamino-2-methyl-5-nitrosopyrimidine	10.8	4.2	16.4	18.6	50.6
Adenine	16.7	46.4	30.0	25.0	70.6
2-Nitro-p-phenylenediamine	47.5	51.4	80.8	46.2	70.6
4,4' -Diaminobenzanilide	56.9	49.4	47.2	63.6	71.4
2,5-Dichloro-p-phenylenediamine	56.1	53.9	49.2	46.4	73.9
2,4-Diamino-5(3,4-dimethoxybenzyl)-pyrimidine	64.4	44.2	66.2	55.0	80.3
2,6-Diaminoanthraquinone	22.8	22.8	55.0	42.5	71.2
2,6-Diamino-8-purinol	61.9	53.1	48.4	48.4	57.3
2,6-Diaminopyridine	43.4	81.4	50.8	63.9	66.7

<sup>a</sup> All values are in % viable.

TABLE 11. Results of the Effect of Selected Antimony(V) Polyamines on the Cell Line HeLa<sup>a</sup>

$\phi_3\text{SbCl}_4$ + diamine	6 $\mu\text{g}/\text{mL}$	5 $\mu\text{g}/\text{mL}$	4 $\mu\text{g}/\text{mL}$	3 $\mu\text{g}/\text{mL}$	2 $\mu\text{g}/\text{mL}$
4,6-Diamino-2-methyl-5-nitrosopyrimidine	55.7	38.2	25.7	29.3	67.9
Adenine	15.4	32.9	55.0	64.3	52.8
2-Nitro-p-phenylenediamine	74.3	74.3	75.7	90.0	87.9
4,4'-Diaminobenzanilide	89.3	81.1	83.6	78.6	88.6
2,5-Dichloro-p-phenylenediamine	85.4	70.0	72.5	98.2	92.9
2,4-Diamino-5(3,4-dimethoxybenzyl)-pyrimidine	76.8	68.2	68.9	68.2	83.6
2,6-Diaminoanthraquinone	18.9	42.9	92.1	55.0	74.6
2,6-Diamino-8-purinol	77.9	0	63.8	79.6	83.2
2,6-Diaminopyridine	57.1	0	63.9	78.9	72.9

<sup>a</sup> All values are in % viable cells.

vival. These same findings hold true for results with the cell lines L929 and HeLa (Tables 10 and 11, respectively).

These biological analyses are meant to only briefly evaluate the potential inhibitory nature of the compounds. As noted, all of the antimony-containing compounds exhibited inhibition to some degree. Applications requiring some biological inhibition might be a use for these compounds as typical application and additives to coatings, cloth, and wood products.

#### REFERENCES

- [1] C. E. Carraher, J. Chem. Educ., **58**, 921 (1981).
- [2] C. E. Carraher, in Interfacial Synthesis. Vol. 2: Polymer Applications and Technology (F. Millich and C. Carraher, eds.), Dekker, New York, 1977.
- [3] C. E. Carraher, Inorg. Macromol. Rev., **1**(4), 271 (1972).
- [4] C. Carraher and H. Blaxall, Angew. Makromol. Chem., **83**, 37 (1979).
- [5] G. O. Doak and L. D. Freedman, Organomet. Chem. Rev., **B**, **6**, 574 (1970).
- [6] C. Carraher and W. Moon, Coatings Plast. Chem., **34**(2), 468 (1974).
- [7] R. H. Dreisback, Handbook of Poisoning, 9th ed., Lange, Los Altos, California, 1977.
- [8] D. M. Mikat and K. W. Mikat, A Clinician's Dictionary Guide to Bacteria and Fungi, 3rd ed., Lilly, Indianapolis, Indiana, 1978.

Accepted by editor October 5, 1982

Received for publication November 5, 1982