



Available online at www.sciencedirect.com

SCIENCE @ DIRECT®

Journal of Nuclear Materials 348 (2006) 222

journal of  
nuclear  
materials

www.elsevier.com/locate/jnucmat

## Erratum

## Erratum to 'Defect structural evolution in high purity tungsten irradiated with electrons using high voltage electron microscope' [J. Nucl. Mater. 343 (2005) 308]

S. Fukuzumi <sup>a</sup>, T. Yoshiie <sup>a,\*</sup>, Y. Satoh <sup>b</sup>, Q. Xu <sup>a</sup>, H. Mori <sup>c</sup>, M. Kawai <sup>d</sup><sup>a</sup> Research Reactor Institute, Kyoto University, Kumatori-cho, Sennan-gun, Osaka-fu 590-0494, Japan<sup>b</sup> Institute for Materials Research, Tohoku University, Katahira, Aoba-ku, Sendai 980-8577, Japan<sup>c</sup> Research Center for Ultra-High Voltage Electron Microscopy, Osaka University, Suita 565-0871, Japan<sup>d</sup> High Energy Accelerator Research Organization, Tukuba 305-0801, Japan

Unfortunately, the last two lines in Table 1 were missing. Please find below the correct Table 1.

Table 1  
Impurity elements in tungsten (unit: ppm)

	O	N	C	Na	K	Al	Ca	Cr	Cu	Fe
PF-W	<10	<10	<10	4	<5	3	<1	<1	<1	5
5N-W	<10	<10	<10	0.1	<0.1	<0.1	0.2	0.4	<0.1	1.5
CVD-W	0.065	0.025	0.13	0.011	0.005	0.001	0.04	0.001	0.001	0.047
	Mg	Mn	Mo		Ni		Si		Sn	
PF-W	<1	<1	11		2		<5		<2	
5N-W	<0.1	<0.1	11		0.5		<1		<0.5	
CVD-W	0.001	0.001	0.004		0.001		0.001		0.01	

DOI of original article: 10.1016/j.jnucmat.2004.11.019

\* Corresponding author. Tel.: +81 724 51 2473; fax: +81 724 51 2620.

E-mail address: [yoshiie@rri.kyoto-u.ac.jp](mailto:yoshiie@rri.kyoto-u.ac.jp) (T. Yoshiie).