

A value of $\lambda_{\text{UO}_2^{++}}^0 = 39$ was obtained from uranyl sulfate data² corrected only for the conductance of hydrogen ions.

Values for the dissociation constant, K , given in Table II were calculated from the corrected conductance data using theoretical activity coefficients and assuming that the dissociation reaction was represented by



Although the constancy of the K values at the lower concentrations is believed to be of significance, the dissociation of uranyl fluoride is most probably more complex than was assumed. The agreement may be largely fortuitous.

OAK RIDGE NATIONAL LABORATORY
OAK RIDGE, TENNESSEE

The Heterogeneous Carbon Monoxide-Ozone Reaction on Silver¹


BY DAVID GARVIN

RECEIVED DECEMBER 11, 1953

Both the efficient decomposition of ozone by silver (and silver oxide)² and the reduction of silver oxide by carbon monoxide are well known.³ We have observed that carbon dioxide is produced during the decomposition of ozone in mixtures of CO, O₃, O₂ and N₂ upon passage through beds of ascarite, potassium hydroxide or precipitated silver.⁴ Of these, only silver is capable of producing as much as one CO₂ molecule per ozone molecule decomposed.

The figure summarizes some experiments with various CO, O₃, O₂, N₂ mixtures on precipitated silver at 0° and atmospheric pressure. Contact times ranged from 0.03 to 0.1 second, CO mole fractions from 0.036 to 0.5, and ozone mole fractions from 0.002 to 0.02. Carbon monoxide was in excess in all cases, and the ozone was completely decomposed. No carbon dioxide production was observed in the absence of ozone. At room temperature and above the decomposition of ozone was favored over the production of carbon dioxide.

Empirically the experiments are well correlated by the plot shown, but not by plots of CO₂ or CO₂/O₃ vs. CO. The fact that the carbon dioxide produced is limited by the ozone decomposed, and that ozone decomposes completely on silver suggests a primary process such as



where the surface oxygen may be an oxide or be chemisorbed. The amount of carbon dioxide produced relative to ozone decomposed suggests

(1) This research was supported by the United States Air Force under Contract No. AF33(038)-23976 monitored by the Office of Scientific Research.

(2) W. Manchot and W. Kampschulte, *Ber.*, **40**, 2891 (1907); J. W. Strutt, *Proc. Roy. Soc. (London)*, **87**, 302 (1912).

(3) See, for example, H. A. J. Pieters, *Chem. Weekblad*, **28**, 250 (1931); S. M. Fainshten, *J. Phys. Chem. (U.S.S.R.)*, **21**, 37 (1947); M. Katz, "Advances in Catalysis," Vol. V, Academic Press, Inc., New York, N. Y., 1953, pp. 177-216.

(4) S. Dondes, A. J. Hogan, P. Harteck and H. M. Clark, Report SO-3251 (Chemistry) Rensselaer Polytechnic Institute, March, 1953, have recently reported carbon dioxide production on silver foil in the presence of ozone.






Fig. 1.—Production of carbon dioxide in CO-O₂-O₃-N₂ mixtures on precipitated silver.

that competitive processes consume the surface oxygen. One set, consistent with catalytic oxidation of CO, and with our scant knowledge of the ozone decomposition on silver, is



When the data are analyzed according to this mechanism, they indicate that k_2 and k_3 are of the same magnitude.

These arguments indicate a close relation between this rapid, low temperature oxidation and that of CO on silver at higher temperatures. In the latter, a higher temperature (100° or more) is required for the rate of activated adsorption of O₂ to be appreciable. In the former, ozone serves as an efficient source of oxygen, permitting subsequent reaction at 0°. Thus, this work indicates the correctness of Benton's⁵ conclusion that the activated adsorption of oxygen is the slow step in CO oxidation on silver.

(5) A. F. Benton and R. T. Bell, *THIS JOURNAL*, **56**, 501 (1934).

THE JAMES FORRESTAL RESEARCH CENTER
PRINCETON UNIVERSITY
PRINCETON, NEW JERSEY

The Decomposition of Benzoyl Peroxide in Glacial Acetic Acid

BY MATTHEW T. GLADSTONE¹

RECEIVED OCTOBER 15, 1953

Acetyl peroxide, when decomposed in glacial acetic acid, gives a high yield of succinic acid.² Kharasch, Jensen and Urry,³ however, found that no succinic acid is formed when benzoyl peroxide is slowly added to boiling acetic acid. Gelissen and Hermans⁴ used a somewhat different technique. They added benzoyl peroxide to acetic acid and the whole was heated for 5 hours at about 90°. They isolated biphenyl, benzene, phenyl benzoate, benzoic acid and *p*-phenylbenzoic acid, but the main product was a resinous mass soluble in alkali.

(1) Technical Department, Behr-Manning Corp., Troy, N. Y.

(2) M. S. Kharasch and M. T. Gladstone, *THIS JOURNAL*, **65**, 15 (1943).

(3) M. S. Kharasch, E. V. Jensen and W. Urry, *J. Org. Chem.*, **10**, 386 (1945).

(4) H. Gelissen and P. H. Hermans, *Ber.*, **58**, 770 (1925).