

**ZnO-Templated Synthesis of Wurtzite-Type ZnS and ZnSe Nanoparticles** [*J. Am. Chem. Soc.* **2009**, *131*, 424–425]. Farah Dawood and Raymond E. Schaak\*

We inadvertently omitted the synthetic details for WZ-ZnSe. The procedure is analogous to the synthesis of WZ-ZnS with the following distinctions: selenourea (Alfa Aesar, 99.9%) was used as the selenium source (instead of thiourea), and the reaction was heated to 190 °C (instead of 160 °C).

JA9058316

10.1021/ja9058316

Published on Web 08/05/2009