**841.** High-polymer Solutions. Part II.\* The Determination Number-average Molecular Weights from Measurements of Osmotic Pressure.

By Esmé Ducker, E. C. Fieller, H. T. Hookway, and R. Townsend.

Careful measurements of the osmotic pressures of benzene solutions of polymethyl methacrylate and of polyvinyl thiolacetate have been statistically analysed to find the best equation for extrapolation of the reduced osmotic pressure-concentration relation to infinite dilution. A similar analysis of results obtained with solutions of polystyrene in benzene, toluene, and butanone is also reported. In the concentration range studied there is no advantage in expressing the results by other than the rectilinear relation  $\pi/C = a + bC$  ( $\pi$  = osmotic pressure, C = concentration, a and b = constants).

The limiting value of  $\pi/C$  at infinite dilution may be shown to be a true measure of the molecular weight of a polymer, independent of its size or shape or the nature of the solvent used. Thus the accuracy of determination of the molecular weight of a polymer depends to a considerable extent on the nature and reliability of the extrapolation of experimental measurements to infinite dilution. A number of authors (see, e.g., McMillan and Mayer, J. Chem. Phys., 1945, 13, 276; Zimm, ibid., 1946, 14, 164) have suggested that the concentration dependence of osmotic pressure may be expressed as a convergent series

$$\pi = RT(aC + bC^2 + dC^3 + \cdots)$$
 . . . . (i)

Recently Fox, Flory, and Bueche (J. Amer. Chem. Soc., 1951, 73, 285) have used published osmotic data in support of a theoretically derived equation which has been expressed in equation (iv) (below) as a restricted form of equation (i).

In Part I \* of this series, Hookway and Townsend reported a series of measurements of osmotic pressure with a number of different polymers. In order so far as possible to render the interpretation of these and other results truly objective, the results have been statistically analysed to determine whether they best fit equations of the form (ii), (iii), or (iv).

$$\pi/C = a + bC \qquad . \qquad (ii)$$

$$\pi/C = a + bC + dC^2 \qquad . \qquad (iii)$$

<sup>\*</sup> Part I, J., 1952, 3190.

 $C_2$ , g./100 c.c.

0.0858

0.1424

0.2134

0.0789

0.1314

0.1971

g./cm.2

0.114

0.205

0.335

0.098

0.168

0.265

g./cm.2

0.115

0.207

0.337

0.099

0.170

0.268

Results.—Measurements of osmotic pressure were made by means of the membranes and apparatus described in Part I (loc. cit.). The results presented in Table 1 for polymethyl methacrylate (D), polyvinyl thiolacetate (E), and polystyrenes (A) and (B) are based on data given in Tables 3 and 4 of Part I. In Table 2 the osmotic pressures of solutions of polystyrene in various solvents at  $31.5^{\circ}$  are recorded;  $C_1$  = polymer concentration in g./100 c.c. of solvent;  $C_2$  = polymer concentration in g./100 c.c. of solution;  $\pi_2$  = osmotic pressure based on concentration  $C_2$ ;  $\pi_3$  = osmotic pressure corrected for depth of immersion of osmometer (see Part I for details).

In the calculations underlying Tables 1 and 3, equations (ii) and (iii) were rewritten in the forms

and fitted to the observed data by the ordinary least-squares technique. Equation (iv) was rewritten as

$$\pi = a_1 C + a_1 b_1 C^2 + \frac{5}{8} a_1 b_1^2 C^3$$
 . . . . . (vii)

leading to least-squares estimates of  $a_1$  and  $b_1$  satisfying the pair of equations

$$\Sigma\{(C + b_1C^2 + \frac{5}{8}b_1^2C^3)(\pi - a_1C - a_1b_1C^2 - \frac{5}{8}a_1b_1^2C^3)\} = 0 \qquad . \quad . \quad (viii)$$

$$\Sigma\{(C^2 + \frac{5}{4}b_1C^3)(\pi - a_1C - a_1b_1C^2 - \frac{5}{8}a_1b_1^2C^3)\} = 0 \qquad . \qquad . \qquad . \qquad (ix)$$

where  $\Sigma$  denotes a summation over all pairs of observations  $(\pi, C)$ . Equations (viii) and (ix) are equivalent to the pair (x) and (xi):

$$a_1 \Sigma \{ (C^2 + \frac{5}{4}b_1C^3)(C + b_1C^2 + \frac{5}{8}b_1^2C^3) \} = \Sigma \{ \pi (C^2 + \frac{5}{4}b_1C^3) \} \qquad . \qquad . \qquad . \qquad (x)$$

$$a_1 \Sigma \{ (2C + b_1 C^2)(C + b_1 C^2 + \frac{5}{8}b_1^2 C^3) \} = \Sigma \{ \pi (2C + b_1 C^2) \}$$
 . . (xi

and  $a_1$  may be eliminated from these to yield a quartic equation which  $b_1$  must satisfy. Tables 1 and 3 give for each system the appropriate root of this quartic and the corresponding value of

TABLE 1.

			THERE I.		
					Mean-squared deviation,
Polymer	Equation	a	$\boldsymbol{b}$	d	$ imes 10^6$
$\mathbf{D}$	ii	1.8394 + 0.003	0.9334 + 0.0045		1.486
	iii	$1.8407 \mp 0.008$	$0.9282 \pm 0.0315$	0.0043 + 0.0260	1.844
	iv	$1.8929 \pm 0.009$	$0.3826 \pm 0.0066$	_	17.053
E	ii	$2.5790 \pm 0.002$			0.535
	iii	$2.5871 \pm 0.004$			0.182
	iv	$2.6153 \pm 0.008$	$65  0.3605 \pm 0.0037$		2.786
$\mathbf{A}$	ii	16.3068 + 0.009	70  2.2557 + 0.0280		0.546
	iii	$16.2908 \pm 0.018$	$2 \cdot 4346 \pm 0.1873$	$-0.4341 \pm 0.4487$	0.634
В	ii	6.1066 + 0.013	0.9894 + 0.0341		6.188
	iii	$6.1610 \pm 0.019$	$0.6160 \pm 0.1281$	$0.5574 \pm 0.1894$	1.732
			T 0		
			TABLE $2$ .		
		;	Solvent: benzene.		
$C_1$ ,	$C_2$ ,	$\pi_1$ , $\pi_2$ ,	$\pi_3$ , $C_1$ ,	$C_2$ , $\pi_1$ ,	$\pi_2$ , $\pi_3$ ,
g./100 c.c.	g./100 c.c.	g./cm. <sup>2</sup> g./cm. <sup>2</sup>	$g./cm.^{2}$ $g./10\bar{0}$ c.c.	g./100 c.c. g./cm. <sup>2</sup>	g./cm.2 g./cm.2
0.0861	0.0861	0.108 0.108	$0.109 \qquad 0.4303$	0.4307 0.681	0.682  0.687
0.1437	0.1437	0.188  0.188	0.190 0.5767	0.5776 $0.996$	0.997   1.003
0.2511	0.2152	0.294  0.295	0.297 0.8665	0.8682   1.741	1.744   1.753
0.2881	0.2883	0.417  0.417	0.420		

Solvent: toluene.

g./cm.2

0.487

0.836

Solvent: butanone.

0.369

0.595

g./100 c.c.

0.2851

0.4247

0.2640

0.3943

 $\pi_3$ ,

g./cm.2

0.490

0.841

0.373

0.601

 $\pi_2$ ,

g./cm.2

1.372

2.371

1.000

1.473

g./100 c.c.

0.5985

0.8546

0.5918

0.7897

 $g./cm.^2$ 

1.379

2.381

1.008

1.484

 $a_1$  as determined by (x) or (xi). Convenient expressions for the sampling variances of  $a_1$  and  $b_1$  were obtained, as may always be done for maximum likelihood estimates (Kendall, "Advanced Theory of Statistics," 1946, Vol. II, Charles Griffin & Co. Ltd.), from the Hessian of the sum of squared residuals

$$\Sigma(\pi - a_1C - a_1b_1C^2 - \frac{5}{8}a_1b_1^2C^3)^2$$
 . . . . . (xii)

The values of a, b, and d entered in Tables 1 and 3 are given in each case in the form estimate  $\pm$  standard error. The final column in these tables gives the mean-squared deviation of the observed values of  $\pi$  from those calculated from the fitted curve. These entries were computed by dividing the sum of squared deviations by the appropriate degrees of freedom [2 less than the number of observations in the case of equations (v) and (vii); 3 less in the case of equation (vi)].

TABLE	3.
-------	----

						Mean-squared
Solvent	π, C	Equation	a	b	d	deviation,
Benzene	$\pi_1$ , $C_1$	ii iii iv	$egin{array}{l} 1 \cdot 1637 \pm 0 \cdot 0023 \ 1 \cdot 1634 \pm 0 \cdot 0061 \ 1 \cdot 2374 \pm 0 \cdot 0122 \end{array}$	$\begin{array}{l} 0.9759 \pm 0.0032 \\ 0.9771 \pm 0.0225 \\ 0.5557 \pm 0.0132 \end{array}$	$-0.0010 \pm 0.0187$	0.741
	$\pi_2$ , $C_2$	ii iii iv	$egin{array}{l} 1.1651 \pm 0.0012 \ 1.1667 \pm 0.0032 \ 1.2385 \pm 0.0117 \end{array}$	$\begin{array}{c} 0.9716 \pm 0.0017 \\ 0.9655 \pm 0.0119 \\ 0.5532 \pm 0.0127 \end{array}$	$0.0051 \pm 0.0099$	$0.221 \\ 0.262 \\ 29.292$
	$\pi_3$ , $C_2$	ii iii iv	$\begin{array}{c} 1 \cdot 1764  \pm  0 \cdot 0019 \\ 1 \cdot 1781  \pm  0 \cdot 0049 \\ 1 \cdot 2493  \pm  0 \cdot 0117 \end{array}$	$\begin{array}{c} 0.9705 \pm 0.0026 \\ 0.9639 \pm 0.0180 \\ 0.5491 \pm 0.0125 \end{array}$	$0.0055 \pm 0.0149$	$0.494 \\ 0.596 \\ 29.064$
Toluene	$\pi_2$ , $C_2$	ii iii iv	$egin{array}{l} 1 \cdot 1711 \pm 0 \cdot 0015 \ 1 \cdot 1740 \pm 0 \cdot 0034 \ 1 \cdot 3552 \pm 0 \cdot 0284 \end{array}$	$\begin{array}{l} 1.8758 \pm 0.0021 \\ 1.8639 \pm 0.0128 \\ 0.8485 \pm 0.0295 \end{array}$	0.0101 ± 0.0108	$0.289 \\ 0.296 \\ 186.138$
	π <sub>3</sub> , C <sub>2</sub>	ii iii iv	$egin{array}{l} 1 \cdot 1821 \pm 0 \cdot 0017 \ 1 \cdot 1844 \pm 0 \cdot 0042 \ 1 \cdot 3657 \pm 0 \cdot 0285 \end{array}$	$\begin{array}{l} 1.8766 \pm 0.0024 \\ 1.8674 \pm 0.0155 \\ 0.8441 \pm 0.0294 \end{array}$	$0.0079 \pm 0.0131$	$0.379 \\ 0.435 \\ 186.608$
Butanone	$\pi_2$ , $C_2$	ii iii iv	$egin{array}{l} 1 \cdot 1623 \pm 0 \cdot 0031 \ 1 \cdot 1674 \pm 0 \cdot 0072 \ 1 \cdot 2167 \pm 0 \cdot 0093 \end{array}$	$\begin{array}{c} 0.8901 \pm 0.0047 \\ 0.8671 \pm 0.0291 \\ 0.5366 \pm 0.0111 \end{array}$	$0.0215 \pm 0.0268$	1.072 $1.154$ $13.497$
	$\pi_3$ , $C_2$	ii iii iv	$1.1777 \pm 0.0028$ $1.1840 \pm 0.0060$ $1.2315 \pm 0.0089$	$\begin{array}{c} 0.8880 \pm 0.0042 \\ 0.8597 \pm 0.0243 \\ 0.5306 \pm 0.0105 \end{array}$	$0.0265 \pm 0.0224$	$0.864 \\ 0.801 \\ 12.303$

Discussion.—The principal object of this work has been to find the best method of determining the coefficient a. In view of the hetero-disperse nature of the polymers studied, no attempt has been made to attach any physical significance to the coefficients b and d.

The close agreement between the observed and calculated values of  $\pi$ , in the case of equations (v) and (vi), is at once apparent from the small size of the mean-squared deviations, and is illustrated in detail for polymer E in Table 4.

Table 4. Observed and calculated values of  $\pi$ .

	π, g./cm.²			
C, g./100 c.c.	Obs.	Eqn. (v)	Eqn. (vi)	Eqn. (vii)
0.0866	0.232	0.2318	0.2323	0.2337
0.1454	0.399	0.3990	0.3994	0.4008
0.2165	0.612	0.6115	0.6117	0.6126
0.2892	0.841	0.8407	0.8406	0.8403
0.4332	1.329	1.3300	1.3293	1.3271
0.6481	$2 \cdot 148$	$2 \cdot 1477$	$2 \cdot 1479$	2.1487

It can be seen from the values of the mean-squared deviations in Tables 1 and 3 that in no case is the unrestricted parabola [equation (iii)] significantly superior to the straight line [equation (ii)]; indeed, to discriminate between them would appear to demand more precise measurements of  $\pi$  than can as yet be made. The virtual agreement between equations (ii) and (iii) is indicated also by the agreement between the pairs of values of a

that they supply, and also by the relatively high values found for the standard error of the coefficients d. In the light of the results found, Fox, Flory, and Bueche's equation (iv) appears to have little to recommend it. It is true that, if we ignore the results of fitting (ii) and (iii), (iv) appears to explain the experimental data reasonably well; but (ii) and (iii) explain them better, and involve less complicated calculations. Cleverdon and Laker (Chem. and Ind., 1951, 272) and McLeod and McIntosh (Canadian J. Chem., 1951, 29, 1104) have also made measurements which suggest that equation (iv) may not be of general application.

The data for polystyrene in three solvents presented in Tables 2 and 3 show that the values of a cover a range of  $\pm 0.0044$  for equation (ii) and  $\pm 0.0036$  for equation (iii). The uncertainty in molecular weight is thus about 0.75%—a satisfactory indication of the soundness of the experimental technique. Conversion of concentration units from g./100 c.c. of solvent  $(\pi_1C_1)$  to g./100 c.c. of solution  $(\pi_2C_2)$  does not affect the results appreciably. Similarly, correction of the osmotic pressure to allow for the depth of immersion of the osmometer  $(\pi_3C_2)$  causes a change of less than 1% in the value of a and causes no significant change in the mean-squared deviations.

The experimental work described in this paper forms part of the programme of the Chemical Research Laboratory and this account is published by permission of the Director.

CHEMICAL RESEARCH LABORATORY AND M.O.S. STATISTICAL ADVISORY UNIT,
TEDDINGTON, MIDDLESEX. [Received, August 16th, 1952.]