

## Ferroelectric Polarization Mechanisms in Nylon 11

J. I. Scheinbeim, J. W. Lee,\* and B. A. Newman

*Department of Mechanics and Materials Science, College of Engineering, Rutgers University, P.O. Box 909, Piscataway, New Jersey 08855-0909**Received October 4, 1991*

**ABSTRACT:** The combined results of piezoelectric coefficient ( $d_{31}$ ,  $e_{31}$ ) measurements, FTIR spectroscopy, and X-ray diffraction studies of three-dimensionally oriented Nylon 11 films reveal that the polarization occurs in the crystalline regions. In addition, the orientation of dipoles in a poled Nylon 11 film is not altered by a high-temperature annealing treatment (185 °C). This unique high-temperature stability of dipole orientation in the crystalline regions provides a method to investigate the polarization mechanism for poled Nylon 11 films. Our results indicate that the difference in observed X-ray diffraction patterns from unpoled and poled films results from an initial 90° field-induced dipole reorientation mechanism. Further dipole reorientation appears to result from a 180° switching mechanism.

## Introduction

A ferroelectric material is a material with a spontaneous polarization, which can be changed in direction by the application of an electric field.<sup>1</sup> Until recently, poly(vinylidene fluoride) (PVF<sub>2</sub>) and its copolymers were the only polymers shown conclusively to be ferroelectric. The bulk polarization of poled phase I PVF<sub>2</sub> films is now known to arise from dipole orientation in the crystalline regions toward the direction of the applied poling field.<sup>1-3</sup> Following wide-angle X-ray diffraction studies and infrared absorbance measurements, two different dipole reorientation models based on 60° and 180° rotations about the chain axis were proposed.<sup>4-7</sup> Hysteresis loops between the electric displacement  $D$  and the applied electric field  $E$  have been observed for phase I PVF<sub>2</sub> using conventional ac techniques,<sup>8,9</sup> and the switching times for polarization reversal have also been measured.<sup>10</sup>

A number of studies of piezoelectricity in the odd-numbered nylons has culminated recently in the demonstration of clear hysteresis loops of electric displacement  $D$  and applied electric field  $E$ , typical of ferroelectric materials, for Nylon 11 and Nylon 7 films prepared by quenching from the melt, followed by cold drawing.<sup>11-13</sup> This new class of ferroelectric polymer, the odd-numbered nylons, has a crystal structure based on the packing of hydrogen-bonded sheets.<sup>14,15</sup> From previous studies,<sup>12,16</sup> and the lack of observed ferroelectricity in the even-numbered nylons, it is apparent that the ferroelectric response originates in the crystalline regions. Both the hydrocarbon sections and the amide groups play an important role in the ferroelectric behavior of these semicrystalline nylons.

The purpose of the present study is to present an analysis of the initial and subsequent polarization mechanisms of Nylon 11 films, based on measurements of the piezoelectric coefficients, FTIR absorbance studies, and wide-angle X-ray diffraction measurements.

## Experimental Section

As-stretched Nylon 11 films were produced by quenching the molten film (210 °C) into an ice bath, cold drawing to a draw ratio of 3:1 at room temperature, and evaporating aluminum on opposing sides of the film as electrodes. As-poled Nylon 11 films were prepared using the same method as above, except that the films were polarized using a triangular electric pulse with a period of 640 s and a maximum amplitude of 150 MV/m. As-annealed and poled-annealed samples were made by annealing the as-stretched and as-poled samples, respectively, at 185 °C under vacuum at a fixed length for 2 h.

Piezoelectric coefficients for the as-poled and poled-annealed samples were measured at 3 Hz at room temperature using a Rheograph Solid (Toyo Seiki).


Infrared spectra were obtained using a Perkin-Elmer Fourier transform infrared spectrometer (Model 1720-X). The film samples used in this study were sufficiently thin to be within the absorbance range where the Beer-Lambert law is obeyed. By use of a polarized infrared light source, the absorbed intensity of C=O stretching and N-H stretching modes was examined to determine changes in dipole orientation after poling and annealing.

X-ray diffraction photographs were taken using nickel-filtered Cu K $\alpha$  radiation. Flat-plate camera photographs were used to record the wide-angle X-ray diffraction patterns. In the flat-plate camera study, transmission mode (incident X-ray beam perpendicular to the plane of the film), edge-on mode (incident X-ray beam parallel to the plane of the film and perpendicular to the draw direction), and end mode (incident X-ray beam along the draw direction) diffraction patterns were obtained.

## Results and Discussion

The electric displacement  $D$  and applied field  $E$  hysteresis studies carried out previously clearly indicate that Nylon 11 films, prepared by quenching and cold-drawing, behave as a ferroelectric material.<sup>11,12</sup> Further, previous studies also showed that annealing prior to poling significantly decreased the spacing between hydrogen-bonded sheets and that this annealed structure showed a reduced reorientation of dipoles with applied field. It was found that the coercive field increased from 62 to 115 MV/m and the remanent polarization decreased from 51 to 17.3 mC/m<sup>2</sup> for films with increasing annealing temperature histories (25–145 °C). Films annealed at the melting temperature 185 °C (before poling) did not show any hysteresis behavior at all, presumably because the coercive field values required exceeded the dielectric strength of the material.<sup>17</sup>

These results clearly suggest that dipole reorientation in Nylon 11 films is inhibited by annealing. If this is true, then it suggests that the effect of increased temperatures (below the melting point) on Nylon 11 films which have been already poled to give a resultant dipole orientation might not be the randomization of dipoles and subsequent depolarization, observed in PVF<sub>2</sub>. In Table I the piezoelectric strain coefficients,  $d_{31}$ , and stress coefficients,  $e_{31}$ , measured at 3 Hz at room temperature, are compared for as-poled and poled-annealed films. The effect of annealing the poled films at 185 °C under vacuum for 2 h was to increase the measured values of  $d_{31}$  and  $e_{31}$  at room temperature slightly. This clearly supports the suggestion



**Figure 1.** Infrared spectra of as-stretched, as-poled, and poled-annealed Nylon 11 films.

**Table I**  
Piezoelectric Coefficients of As-Poled and Poled-Annealed Nylon 11 Film


	$d_{31}$ (pC/N)	$e_{31}$ (mC/m <sup>2</sup> )
as-poled	2.2	6.0
poled-annealed	2.3	7.5

that the effect of annealing poled Nylon 11 films is not to randomize the dipoles. The implication of these results for the thermal stability of remanent polarization in poled odd-numbered nylons is clear and is the subject of a separate publication.<sup>13</sup>


In Figure 1 are presented the results of the FTIR measurements for the as-stretched, as-poled, and poled-annealed films. Large differences in the absorbed intensities of the C=O stretching modes at 1650 cm<sup>-1</sup> and the N-H stretching modes at 3300 cm<sup>-1</sup> between the as-stretched and the as-poled films strongly suggest that the hydrogen bonds break and the dipoles are rotated toward the field direction to re-form bonds in a new direction, which remains when the applied field is removed. More importantly, when the absorbance spectrum obtained from the as-poled films is compared with the spectrum obtained from the poled-annealed films, and in particular the absorbance intensities of the C=O stretching modes and also the N-H stretching modes, very little difference is observed. This confirms the suggestion that annealing in vacuum at 185 °C for 2 h (under tension) does not cause any significant change in dipole orientation. Infrared band assignments were made on the basis of previous studies.<sup>18</sup>

Since the nylon films, as prepared, possess a three-dimensional texture,<sup>19</sup> with the molecular chains oriented in the draw direction and the hydrogen-bonded sheets in the plane of the film, it would be expected that the re-orientation of dipoles caused by the application of high electric fields would lead to clear and unambiguous changes in the X-ray diffraction patterns confirming this. Although differences in the X-ray diffraction patterns obtained from as-stretched films and as-poled films were observed, the crystallites resulting from the preparation treatment were not sufficiently large and well-formed to give a diffraction pattern suitable for making an unambiguous confirmation.

However, the X-ray patterns obtained from films which had been subsequently annealed to increase crystallite perfection were, as expected, much improved. The combined results of the studies of the effect of annealing on FTIR absorbance and piezoelectric properties show that it is possible to investigate polarization mechanisms using wide-angle X-ray diffraction studies of as-annealed



**Figure 2.** Flat-plate photograph, end mode, of three-dimensionally oriented Nylon 11 film.



**Figure 3.** Flat-plate photograph, of three-dimensionally oriented Nylon 11 film: edge-on mode (a, top), transmission mode (b, bottom).

and poled-annealed films, since the hydrogen bonds do not break and the orientation of hydrogen-bonded sheets does not change during the high-temperature annealing treatment.

Figures 2, 3a,b, 4a,b show flat-film photographs together with a schematic representation of the wide-angle X-ray diffraction patterns of as-annealed and poled-annealed Nylon 11 films. Most of the reflections observed could be indexed using the unit cell proposed by Hasegawa.<sup>20</sup> On Figures 3a and 4b we notice streaks of diffracted intensity between certain important reflections which suggest either a large degree of structural disorder or a small crystal size in certain directions. It is well-known that this phenomenon can give a number of anomalous reflections at incorrect  $d$ -spacing values and some reflections of this type can be observed on some of the photographs. They can be distinguished from normal reflections by their appearance, which is much more diffuse, as well as being of weak intensity. These reflections are not included on the schematic representations and will be the subject of a separate publication. It should be further noted that the fact of a three-dimensional crystal texture does not entail a unique single-crystal orientation with respect to the film axes. In fact, the unit cell proposed by Hasegawa is triclinic, and four different orientations of this cell with respect to film axes are consistent with the texture proposed by Norholt. This further complicates the




Figure 4. Flat-plate photograph of poled-annealed Nylon 11 film: edge-on mode (a, top), transmission mode (b, bottom).

Table II  
Diffraction Data of End Mode Flat-Plate Photograph

label	intensity	$d_{\text{obs}}$ (Å)	index
A	vs	3.89	(020)
B	vs	4.27	(200)
C	m	3.87	(220)
D	vw	2.39	(220)
E	vw	2.32	(420)

interpretation of the diffraction photographs, and a complete discussion of these issues will also be deferred to a later publication. Here we present those results relevant to the issues of the polarization mechanisms important to the ferroelectric behavior of Nylon 11 films.

Figure 2 shows the flat-film photograph and the corresponding schematic representation for the as-annealed samples, when the incident X-ray beam is along the direction of draw (end mode orientation). The meridional direction (vertical) on this photograph corresponds to the plane of the film. If the only orientation present in these films was uniaxial along the draw direction, then the diffraction pattern anticipated for the geometry of this orientation would be a series of concentric rings. Figure 2 shows clearly that additional orientation is present, since all reflections are rather small arcs of circles with an angular spread of  $\sim \pm 20^\circ$ . The very strong equatorial reflection with  $d_{\text{obs}} = 3.89$  Å, indexed as (020), corresponding to the spacing between hydrogen-bonded sheets, confirms that the hydrogen-bonded sheets are parallel to the plane of the film.

The pattern is approximately hexagonal. The (200) and (220) reflections occurring on the first layer line in the  $60^\circ$  positions are consistent with the two different crystal orientations with  $a$ -axis in the plane of the film and perpendicular to the  $c$ -axis (the draw direction), as is also the position of the reflection on the first observed layer line ( $\sim 30^\circ$  from the equator), and the meridional reflection, which are consistent with an assignment of (220) and (420). Table II shows a list of index assignments and measured values of the  $d$ -spacings for the reflections observed. So, to summarize, Figure 2 clearly confirms that after annealing the Nylon 11 films are well-

Table III  
Diffraction Data of Edge-On Mode Flat-Plate Photograph

label	intensity	$d_{\text{obs}}$ (Å)	index
A	vs	3.89	(020)
B	m	2.39	(220)
C	vs	12.80	(001)
D	m	6.35	(002)
E	m	4.29	(003)
F	m	2.36	(126)
G	m	2.21	(106)

Table IV  
Diffraction Data of Transmission Mode Flat-Plate Photograph

label	intensity	$d_{\text{obs}}$ (Å)	index
A	vs	4.27	(200)
B	m	2.39	(420)
C	s	4.35	(201)
D	m	3.95	(202)
E	w	3.45	(203)
F	w	2.36	(126)
G	m	2.21	(106)

crystallized, with crystal orientations consistent with the  $c$ -axis in the draw direction and hydrogen-bonded sheets in the plane of the film.

Figure 3a shows the X-ray flat-film photograph obtained and a schematic representation when the incident beam is perpendicular to the draw direction and in the plane of the film (edge-on mode). Assuming the previous orientation assignment is correct, the incident X-ray beam is parallel to the  $a$ -axis for Figure 3a. In the figure, the draw direction is vertical, while the normal to the plane of the sample is horizontal. Thus, the (020) reflection, corresponding to the space between hydrogen-bonded sheets, should be and is observed on the equatorial line. The second equatorial reflection can be indexed as (220). The meridional reflections, and reflections symmetrically disposed to either side of the meridian, can be indexed (001), (002), (003), (126), and (106). The complete indexing is summarized in Table III and is also consistent with the previous three-dimensional orientation proposed, two different crystal orientations being possible with the reciprocal lattice vector  $C^*$  symmetrically disposed to either side of the meridian.

Figure 3b shows the X-ray plot film photograph obtained and a schematic representation when the incident beam is perpendicular to the draw direction and perpendicular to the plane of the film (transmission mode). The sample draw direction is again vertical, but the equatorial line is perpendicular to both the draw direction and the normal to the plane of the sample. Assuming the previously determined orientation, the equatorial line is parallel to the  $a$ -axis. The equatorial reflections observed are (200) and (420). The other reflections observed are (202), with the exception of several meridional reflections different in appearance from all others. The complete indexing is shown in Table IV and is consistent with the crystal orientations already discussed. However, the subject of the special meridional reflections best seen in Figure 3 will be discussed in a later publication.

Figure 4a shows the flat-film photograph and the corresponding schematic representation for the poled-annealed samples, when the incident X-ray beam is perpendicular to the draw direction and in the plane of the film (edge-on mode); that is, the geometrical arrangement is similar to that used to obtain Figure 3a. The draw direction is vertical, while the normal to the plane of the sample is horizontal. Figure 4b shows the flat-film photograph and the corresponding schematic representation




Figure 5. 180° dipole switching (antiparallel packing) of chains in the hydrogen-bonded sheet structure.

tation for the poled-annealed samples when the incident X-ray beam is perpendicular to the plane of the sample. The draw direction is vertical and the equatorial line is perpendicular both to the draw direction and to the normal to the plane of the sample; that is, the geometrical arrangement is similar to that used to obtain Figure 3b.

The most striking feature of Figure 4a and b is that, although the geometry used to obtain these photographs compares with that used to obtain Figure 3a and b for the unpoled samples, Figure 4a shows a diffraction pattern similar to Figure 3b, and Figure 4b shows a diffraction pattern similar to Figure 3a. Since the different diffraction patterns of parts a and b of Figure 3 are obtained from geometrical arrangements which differ only by a rotation of 90° about the draw direction (*c*-axis), this fact is strong evidence for the claim that following poling and then annealing, the samples still show a three-dimensional texture, but now rotated by 90° about the *c*-axis with respect to the initial orientation. Thus, following the poling procedure and annealing treatment, the hydrogen-bonded sheets are perpendicular to the plane of the poled films, having rotated 90° from their initial orientation in the plane of the films. This is easily understood when it is realized that the strong dipoles associated with the hydrogen bonds are, of course, in the plane of the hydrogen-bonded sheets. Clearly, under the high electric fields used for poling, these dipoles rotated in the direction of the field, the state of lowest energy, and after removal of the field this crystal orientation remained. This orientation continued to remain even during the annealing treatment, as evidenced by the FTIR data and the piezoelectric activity of the film measured after poling.

The observed hysteresis behavior during field reversal strongly suggests 180° switching of dipoles, and it is clear from Figure 5 that this can be accomplished without dramatic changes in crystal structure. It is evident, however, that the initial dipole reorientation must be a 90° switch, since it is known that the initial dipole orientation is in the plane of the film.

## Conclusions

As a result of a study of crystal orientation in both poled and unpoled Nylon 11 films, which had been initially prepared by quenching from the melt, drawing, and finally annealing, using both X-ray diffraction methods and FTIR, we conclude the following:

- (1) The orientation of NH and C=O dipoles does not significantly change after annealing treatments, even annealing at temperatures close to the melting point.
- (2) A dipole switching of 90° occurs with the initial application of electric field, to switch dipoles in the plane of the film into the field direction.
- (3) Subsequent dipole switching of 180° occurs with electric field reversals.
- (4) The piezoelectric coefficients are not decreased by annealing treatments, even at temperatures close to the melting points.

**Acknowledgment.** This work was supported by DARPA and the Office of Naval Research.

## References and Notes

- (1) Naegle, D.; Yoon, D. Y. *Appl. Phys. Lett.* **1978**, *33*, 132.
- (2) Fukada, E.; Date, M.; Furukawa, T. *Org. Coat. Plast. Chem.* **1978**, *38*, 262.
- (3) Tamura, M.; Hagiwara, S.; Matsumoto, S.; Ono, N. *J. Appl. Phys.* **1977**, *48*, 513.
- (4) Kepler, R. G.; Anderson, R. A. *J. Appl. Phys.* **1978**, *49*, 1232.
- (5) Aslaksen, E. W. *J. Chem. Phys.* **1972**, *57*, 2358.
- (6) Broadhurst, M. G.; Davis, G. T. *Annu. Rep., Conf. Electr. Insul. Dielectr. Phenom.* **1979**, *48*, 447.
- (7) Devy-Aharon, H.; Sluckin, T. J.; Taylor, P. L.; Hopfinger, A. J. *J. Phys. Rev. B* **1980**, *21*, 3700.
- (8) Tamura, M.; Ogasawara, K.; Ono, N.; Hagiwara, S. *J. Appl. Phys.* **1974**, *45*, 3768.
- (9) Furukawa, T.; Date, M.; Fukada, E.; Tajitsu, Y.; Chiba, A. *Jpn. J. Appl. Phys.* **1980**, *19*, 1109.
- (10) Furukawa, T.; Date, M.; Fukada, E. *J. Appl. Phys.* **1980**, *51*, 1135.
- (11) Lee, J. W.; Takase, Y.; Newman, B. A.; Scheinbeim, J. I. *J. Polym. Sci., Part B: Polym. Phys.* **1991**, *29*, 273.
- (12) Lee, J. W.; Takase, Y.; Newman, B. A.; Scheinbeim, J. I. *J. Polym. Sci., Part B: Polym. Phys.* **1991**, *29*, 279.
- (13) Takase, Y.; Lee, J. W.; Newman, B. A.; Scheinbeim, J. I. *Macromolecules*, in press.
- (14) Slichter, W. P. *J. Polym. Sci.* **1959**, *36*, 259.
- (15) Newman, B. A.; Sham, T. P.; Pae, K. D. *J. Appl. Phys.* **1977**, *48*, 4092.
- (16) Lee, J. W. Ph.D. Thesis, Rutgers University, 1990.
- (17) Kohan, M. I. *Nylon Plastics*; John Wiley & Sons: New York, 1973.
- (18) Skrovanek, D. J.; Painter, P. C.; Coleman, M. M. *Macromolecules* **1986**, *19*, 699.
- (19) Northolt, M. G. *J. Polym. Sci., Part C: Polym. Symp.* **1972**, *38*, 205.
- (20) Hasegawa, R. H., private communication.

**Registry No.** 11-Aminoundecanoic acid (homopolymer), 25587-80-8; nylon 11 (SRU), 25035-04-5.