

CORRECTIONS

Won Seok Lyoo,* John Blackwell, and Han Do Ghim: Structure of Poly(vinyl alcohol) Microfibrils Produced by Saponification of Copoly(vinyl pivalate/vinyl acetate). Volume 31, Number 13, June 30, 1998, p 4253.

The data in the last two columns of Table 1 are reversed. Below is the corrected table.

Table 1. Copolymerization Results and Molecular Parameters of PVA

ADMVN concentration, mol/mol of monomer	VPi mol % in feed	conv, %	VPi mol % in copolymer	$[\eta]$ of copolymer	P_n of PVA	triad tacticity (%)			diad tacticity (%)	
						<i>mm</i>	<i>mr</i>	<i>rr</i>	<i>m</i>	<i>r</i>
2.0×10^{-5}	100	18.2	100	3.65	16500	13.2	49.6	37.2	38.5	61.5
1.0×10^{-4}	100	29.5	100	3.81	14300	13.7	49.2	27.1	38.3	61.7
4.3×10^{-4}	100	38.3	100	3.55	8100	13.8	49.4	36.8	38.5	61.5
2.0×10^{-5}	90	16.1	97.5	4.35	15200	13.8	50.5	35.7	39.1	60.9
1.0×10^{-4}	90	30.9	96.6	4.76	12600	14.5	49.9	35.6	39.4	60.6
3.5×10^{-4}	90	35.9	95.1	4.67	7900	14.5	50.2	35.3	39.6	60.4
2.0×10^{-5}	80	16.6	90.8	4.06	13800	14.8	50.8	34.4	40.2	59.8
1.0×10^{-4}	80	32.1	88.8	4.33	10200	15.2	50.8	34.1	40.5	59.5
2.6×10^{-4}	80	36.6	86.4	4.31	8200	14.9	51.0	34.1	40.4	59.6
2.0×10^{-5}	70	17.6	82.5	3.88	10700	15.4	50.9	33.7	40.8	59.2
1.0×10^{-4}	70	33.6	79.7	4.04	8100	15.8	50.6	33.6	41.1	58.9
2.0×10^{-5}	60	19.4	71.6	4.11	10100	15.9	50.6	33.5	41.2	58.8
1.0×10^{-4}	60	25.1	69.5	3.67	8300	15.9	51.0	33.1	41.8	58.6
2.0×10^{-5}	50	12.8	58.5	3.29	8300	16.1	51.1	32.8	41.6	58.4
1.0×10^{-4}	50	23.6	58.6	3.44	6700	16.1	51.1	32.8	41.6	58.4
2.0×10^{-5}	40	15.3	49.7	3.36	8100	16.7	51.4	31.9	42.4	57.6
1.0×10^{-4}	40	26.4	47.4	3.51	6800	16.7	51.2	32.1	42.3	57.7
2.0×10^{-5}	30	16.1	35.2	3.17	7800	18.6	50.4	31.0	43.8	56.2
1.0×10^{-4}	30	28.5	36.4	3.50	7100	18.1	50.8	31.1	43.5	56.5
2.0×10^{-5}	20	13.5	26.3	3.25	7800	19.6	50.2	30.2	44.7	55.3
1.0×10^{-4}	20	22.9	24.8	2.99	6900	20.1	49.6	30.3	44.9	55.1
2.0×10^{-5}	10	13.7	14.7	3.11	7700	20.6	50.3	29.1	45.7	54.3
1.0×10^{-4}	10	25.2	13.5	2.90	6600	20.7	50.8	28.8	46.1	54.2
2.0×10^{-5}	0	10.8	0	2.61	6500	21.4	51.0	27.6	46.9	53.1
1.0×10^{-4}	0	23.5	0	2.59	5600	21.8	50.8	27.4	47.2	52.8

MA981985W