

Model Transient Networks from Strongly Hydrogen-Bonded Polymers [*Macromolecules* **2009**, *42*, 9072].
 Kathleen E. Feldman, Matthew J. Kade, E. W. Meijer,
 Craig J. Hawker,* and Edward J Kramer*

Page 9079. The activation energies given in Figure 11 are incorrect. A corrected figure is given below, and the values are given in Table 1.




Figure 11. Activation energies E_a calculated from the temperature dependence of a_T (l : average degree of polymerization between UPy's; in the case of triblocks l is calculated based on the local UPy concentration within the random copolymer end blocks).

Table 1. Flow Activation Energies for UPy-Based Thermoplastic Elastomers (l : Average Degree of Polymerization between UPy's)

sample	$1/l$	E_a (kJ/mol)
R-24-4.0	0.0385	91.4
R-21-5.5	0.0500	94.4
R-25-7.2	0.0667	107.1
R-24-9.6	0.0833	115.4
R-21-13.3	0.1111	119.8
T-27-3.5-55	0.0625	106.2
T-28-3.6-45	0.0769	105.5
T-28-3.3-39	0.0833	116.8

DOI: 10.1021/ma1004327

Published on Web 03/05/2010