



Molecular Crystals and Liquid Crystals

Publication details, including instructions for authors and subscription information:

<http://www.tandfonline.com/loi/gmcl20>

Transmittance and Reflectance of an Imprinted Cholesteric Elastomer During a Segregation Process

P. Castro-Garay^{a b}, J. A. Reyes^b & R. Ramos-García^a

^a Depto de Óptica, Instituto Nacional de Astrofísica, Óptica y Electrónica, Puebla, Pue, México

^b Física Química, Instituto de Física, Universidad Nacional Autónoma de México, México DF, México

Version of record first published: 30 Jan 2009

To cite this article: P. Castro-Garay, J. A. Reyes & R. Ramos-García (2008): Transmittance and Reflectance of an Imprinted Cholesteric Elastomer During a Segregation Process, *Molecular Crystals and Liquid Crystals*, 495:1, 234/[586]-246/[598]

To link to this article: <http://dx.doi.org/10.1080/15421400802430141>

PLEASE SCROLL DOWN FOR ARTICLE

Full terms and conditions of use: <http://www.tandfonline.com/page/terms-and-conditions>

This article may be used for research, teaching, and private study purposes. Any substantial or systematic reproduction, redistribution, reselling, loan, sub-licensing, systematic supply, or distribution in any form to anyone is expressly forbidden.

The publisher does not give any warranty express or implied or make any representation that the contents will be complete or accurate or up to date. The accuracy of any instructions, formulae, and drug doses should be independently verified with primary sources. The publisher shall not be liable for any loss, actions, claims, proceedings, demand, or costs or damages whatsoever or howsoever caused arising directly or indirectly in connection with or arising out of the use of this material.

Transmittance and Reflectance of an Imprinted Cholesteric Elastomer During a Segregation Process

P. Castro-Garay^{1,2}, J. A. Reyes², and R. Ramos-García¹

¹Depto de Óptica, Instituto Nacional de Astrofísica, Óptica y Electrónica, Puebla, Pue, México

²Física Química, Instituto de Física, Universidad Nacional Autónoma de México, México DF, México

We have calculated the reflectance and transmittance of obliquely incident circularly polarized light on a distorted cholesteric elastomer slab distorted. The distortion is achieved by variations of the chiral order parameter, which is defined as the imprinting efficiency of the volume fraction of the absorbed molecules from the racemic solvent, having the preferably absorbed chirality. We have found a right-handed band reflection whose bandwidth increases and blue-shifts as incidence angle increases. A thinner left-handed band reflection also is observed. The slab is used in a chemically controlled optical filter or optically traced chiral pump.

Keywords: band structure; cholesteric elastomer; liquid crystals

1. INTRODUCTION

The interest in the separation of enantiomers of organic compounds has been recently increased in the food, medicine and cosmetic industries. As it is well known, the chirality is extremely important for living systems, because most of the biomolecules are chiral ones. For example, glucose, a sugar exists in one conformation; while the opposite enantiomer cannot be used as a food source. Biochemistry uses only one hand and not the other however the reason for this has not been understood, so far. Over half of the organic compounds

J. Adrian Reyes acknowledges the partial support from Grant DGAPA-PAPITT IN117606-3 Mexico.

Address correspondence to P. Castro-Garay, Depto de Óptica, Instituto Nacional de Astrofísica, Óptica y Electrónica, Apdo Post. 51, Puebla, Pue 72 000, México. E-mail: caspaoga@hotmail.com

in drugs are chiral whose different enantiomers have different effects. For instance, Ritalin prevents hyperactivity in children in one enantiomer, whereas it has no effect when the opposite enantiomer is used. Another example is thalidomide: one enantiomer of thalidomide can cure morning sickness of pregnant women, whereas the other causes birth defects. The sense of smell is also sensitive to the chirality of the odor molecules. For instance, limonene has an orange smell whereas the opposite enantiomer smells like lemon [1]. This exemplifies the fact that separation of molecules by chirality is an important process in biochemistry and in the pharmaceutical industry. In this paper we suggest a method to optically monitor the chiral sorting of molecules performed by an elastomer liquid crystal.

Liquid crystal elastomers combine the rubbery elastic properties with the liquid crystals (LC) anisotropy [2]. When these stiff molecules are joined to a large and flexible polymer chain, they leave their muddy liquid macroscopic form and acquire the appearance of a rubbery network. Particularly, imprinted cholesteric elastomers acquire their chirality from an induced chiral structure instead of chiral molecules. Upon cross-linking nematic polymers in a chiral solvent forms a gel. The chiral solvent, which causes a natural twist to the nematic is thus removed but nonetheless leaves behind an imprinted cholesteric elastomer [3]. A spectacular property of imprinted networks is their capacity to preferentially absorb and retain right or left molecules from a racemic solvent which renders them chiral pumps. Moreover the elastomers are photonic materials in the sense that exhibit an optical band structure just as the one shown by electrons in metals and semiconductors. Elastomers provide a large spectrum of applications that exploit the possibility of externally handling a band structure by various types of agents like mechanical stress, electric fields and chemical solvents for designing devices such as optical sensors, mirrors, laser and filters [2,4].

The purpose of this paper is to propose an optical method to determine the volume fraction of preferentially absorbed molecules by measuring the transmittance and reflectance spectra during a preferentially absorbing process. Specifically, we are interested in calculating the reflectance and transmittance of circularly polarized light for oblique incidence due to a cholesteric elastomer, assuming arbitrary values of chiral order parameter, α . We have thoroughly discussed the solution of the boundary value problem for cholesteric elastomers in sections 4 and have determined the optical spectra of the system in Sec. 5.

2. ELASTIC FORMULATION

A cholesteric elastomer has locally a nematic structure. Consequently, the director vector $\hat{n} = (\cos \phi(z), \sin \phi(z), 0)$ is at $x - y$ plane and $\phi(z)$ is the angle between director vector and x axis (see Fig. 1). The director vector has a continuous rotation as function of z , which describes a periodic helical structure characterized by a pitch p (or equivalent by wave number $q_0 = 2\pi/p$) [5,6].

The chiral order parameter $\alpha = \xi q_0$ is related with the imprinting efficiency of the cholesteric phase, where $\xi = \sqrt{K_2/D_1}$ is the nematic penetration depth in rubbery networks, K_2 is the twist elastic constant and D_1 is local anchoring of the director to the rubbery network. Variations in the chiral order parameter imply changes in the robustness of chiral imprinting, which can be controlled by varying the density of cross-links in the network (affecting D_1) [7].

The energy for an elastomer formed under the presence of a chiral solvent which is subsequently replaced with an achiral one is




FIGURE 1 Schematic representation of a liquid crystal cholesteric elastomer. The circular components of the obliquely incident beam as well as the components of the transmitted and reflected parts are shown.

given by [8],

$$F = \frac{1}{2} \int \left[K_2 \left(\frac{d\phi}{dz} \right)^2 + D_1 \sin^2(\phi - q_0 z) \right] dz. \quad (1)$$

The Frank free energy to twist the material is given by

$$F_f = \frac{1}{2} K (\hat{n} \cdot \nabla \times \hat{n})^2 \quad (2)$$

associated with the first term of the Eq. (1) tend to unwind the cholesteric helix but it finds resistance to rotate in the anchoring of the rubbery network- associate with the second term of Eq. (1). D_1 is proportional to rubbery elasticity modulus and the rubbery elasticity modulus is related with cross-linked density [7]. The scale length or nematic penetration depth rubbery at which the two energy contributions are comparable is usually small $\xi \simeq 10^{-8}$ m for a typical $K_2 \simeq 10^{-11}$ J/m, $D_1 \simeq \mu(r-1)^2/r$, where $r \sim 0.9$ is the anisotropy chain number or cross-linked number and $\mu \simeq 10^5$ J/m³ is the elasticity rubber modulus. The pitch is 10^3 larger than nematic penetration depth ξ , then

$$\xi \ll p = \frac{\pi}{q_0}. \quad (3)$$

There are two forms of modifying this relation, (i) by increasing the nematic penetration depth which amounts to have a weaker gel or one with smaller anisotropy, (ii) by increasing the Frank free energy. The chiral imprinting will be lost if D_1 diminish, i.e., so that the director vector anchoring to rubbery will be almost null. Similarly, if the wave number q_0 or twist elastic constant K_2 are larger the chiral imprinting will be also lost. The imprinting efficiency is reached for values of chiral parameter order $\alpha_c = \xi q_0$ lower than $2/\pi$.

Equation (1) can be expressed in terms of chiral parameter order as,

$$F = \frac{1}{2} \int \left[\frac{\alpha^2}{q_0^2} \left(\frac{d\phi}{dz} \right)^2 + \sin^2(\phi - q_0 z) \right] dz \quad (4)$$

The equilibrium configuration can be obtained by minimizing F with respect to the angle, then we have got the Euler-Lagrange equations,

$$-\partial_z \left(\frac{\partial F}{\partial_z \phi} \right) = 0, \quad (5)$$

which in this case turns out to be

$$\frac{\alpha^2}{q_0^2} \frac{d^2 \phi}{dz^2} + \sin 2(q_0 z - \phi) = 0. \quad (6)$$

Notice that if $\alpha = 0$ the solution of Eq. (6) is $\phi_0(z) = q_0 z$ which corresponds to an ideal or undistorted cholesteric helix. By introducing the variable $w = q_0 z - \phi + \pi/2$, Eq. (6) transforms in the expression

$$\frac{d^2 w}{dz^2} + \frac{q_0^2}{\alpha^2} \sin 2w = 0. \quad (7)$$

which is the simple pendulum equation. Hence, for large values of α , small harmonic oscillations of frequency q_0/α around $\phi = q_0 z + \pi/2$ are expected. Nevertheless, for smaller values of α anharmonic oscillations take place until w abandons its oscillatory dependence and grows without limit following the dependence corresponding to a rotatory motion in a simple pendulum. This behavior can be inferred by using the general solution of Eq. (6) which is given by

$$\phi(z) = q_0 z - Am(cz/\xi, 1/c^2) + \pi/2, \quad (8)$$

where $Am(z, m)$ is the Jacobian amplitude and c is a constant related with the reduced elastic energy [8] $g = 2\xi F/TD_1$. In the Figure 2 we




FIGURE 2 Director vector angle as function of the position for different values of chiral order parameter, α .

show the director vector angle $\phi(z)$ against position for different values of chiral order parameter α . It is interesting to note that by increasing ξ from zero, $\phi(z)$ presents oscillations without changing its amplitude, around the undistorted solution $\phi_0(z)$ whose spatial period increases, until ξ reaches the critical values: $\xi_c = 3$. After this value $\phi(z)$ deviate considerably from $\phi_0(z)$ and enlarges its effective q -value for $\xi \geq \xi_c$ which is equivalent to have an untwisted helix than that of $\phi_0(z)$.

3. OPTICAL DESCRIPTION

As any chiral material whose axis of chiral nonhomogeneity is along the z -axis, the optical relative permittivity matrix of the chiral elastomer may be stated as

$$\bar{\epsilon}(z) = \begin{pmatrix} 0 & 0 & 0 \\ \epsilon_{\perp}^{(0)} + \epsilon_a \cos^2 \phi & \epsilon_a \sin \phi \cos \phi & 0 \\ \epsilon_{\perp} \sin \phi \cos \phi & \epsilon_{\perp}^{(0)} + \epsilon_a \sin^2 \phi & \epsilon_{\perp}^{(0)} \end{pmatrix} \quad (9)$$

where $\epsilon_a = \epsilon_{\parallel} - \epsilon_{\perp}$ is the dielectric anisotropy with ϵ_{\parallel} and ϵ_{\perp} the dielectric constants in the optical regime parallel and perpendicular to the director $\hat{\mathbf{n}}$, respectively.

Maxwell curl equations (in MKS units) for media whose dielectric tensor is only z -dependent, are given by

$$\left. \begin{aligned} \nabla \times \mathbf{E}(x, y, z) &= i\omega\mu_0 \mathbf{H}(x, y, z) \\ \nabla \times \mathbf{H}(x, y, z) &= -i\omega\epsilon_0 \bar{\epsilon}(z) \cdot \mathbf{E}(x, y, z) \end{aligned} \right\}, \quad 0 < z < L, \quad (10)$$

where ϵ_0 and μ_0 are the permittivity and the permeability of free space (i.e., vacuum). If a plane wave were to be incident obliquely on a Cholesteric Elastomer slab of thickness L , we can describe the fields in terms of the column vector [9]

$$\bar{\psi}(x, y, z) = \exp[i\kappa(x \cos u_1 + y \sin u_1)] \begin{pmatrix} e_x(z) \\ e_y(z) \\ h_x(z) \\ h_y(z) \end{pmatrix}. \quad (11)$$

where u_1 the angle formed by the propagation vector and the y -axis in the $x - y$ plane. Thus, the essential part of Maxwell curl equations can then be written as [10].

$$\frac{d}{dz} \bar{\psi}(x, y, z) = i\bar{A}'(z) \cdot \bar{\psi}(x, y, z), \quad 0 < z < L, \quad (12)$$

In this equation, the 4×4 matrix can be factorized as $\bar{A}' = B(z) \cdot \bar{A} \cdot B(-z)$ where the 4×4 matrix

$$\begin{aligned} \bar{A}(z) = & \begin{pmatrix} 0 & 0 & 0 & \omega\mu_o \\ 0 & 0 & -\omega\mu_o & 0 \\ 0 & -\omega\epsilon_o\epsilon_2^{(0)} & 0 & 0 \\ \omega\epsilon_o\epsilon_d & 0 & 0 & 0 \end{pmatrix} \\ & + \frac{\kappa^2}{\omega\epsilon_o\epsilon_1^{(0)}} \begin{pmatrix} 0 & 0 & -\sin u \cos u & -\cos^2 u \\ 0 & 0 & \sin^2 u & \sin u \cos u \\ 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 \end{pmatrix} \\ & + \frac{\kappa^2}{\omega\mu_o} \begin{pmatrix} 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 \\ \sin u \cos u & \cos^2 u & 0 & 0 \\ -\sin^2 u & -\sin u \cos u & 0 & 0 \end{pmatrix}, \end{aligned} \quad (13)$$

with $u = \frac{h\pi z}{\Omega} - u_1$ and

$$B(z) = \begin{pmatrix} \cos \phi(z) & \sin \phi(z) & 0 & 0 \\ -\sin \phi(z) & \cos \phi(z) & 0 & 0 \\ 0 & 0 & \cos \phi(z) & \sin \phi(z) \\ 0 & 0 & -\sin \phi(z) & \cos \phi(z) \end{pmatrix}. \quad (14)$$

Equation (12) can be solved by a variety of techniques. We chose to implement the piecewise homogeneity approximation method. The final result is the computation of a transfer matrix \bar{U}' such that

$$\bar{\psi}(L) = \bar{M}^T(L) \cdot \bar{U}' \cdot \bar{M}(0) \cdot \bar{\psi}(0) \equiv \bar{U} \cdot \bar{\psi}(0). \quad (15)$$

4. BOUNDARY VALUE PROBLEM

Suppose that plane waves are obliquely incident on a cholesteric of finite thickness from both half-spaces $z \leq 0$ and $z \geq L$, which are taken to be vacuous. As a result, the total electric and magnetic fields in these half-spaces may be written as

$$\left. \begin{aligned} \mathbf{e}(z) &= (a_L \hat{\mathbf{u}}_+ + a_R \hat{\mathbf{u}}_-) \exp[ik_0 z + i\kappa(x \cos u_1 + y \sin u_1)] \\ &\quad + (r_L \hat{\mathbf{u}}_- + r_R \hat{\mathbf{u}}_+) \exp[-ik_0 z + i\kappa(x \cos u_1 + y \sin u_1)] \\ \mathbf{h}(z) &= i(-a_L \hat{\mathbf{u}}_+ + a_R \hat{\mathbf{u}}_-) \exp[ik_0 z + i\kappa(x \cos u_1 + y \sin u_1)] \\ &\quad + i(-r_L \hat{\mathbf{u}}_- + r_R \hat{\mathbf{u}}_+) \exp[-ik_0 z + i\kappa(x \cos u_1 + y \sin u_1)] \end{aligned} \right\}, \quad z \leq 0, \quad (16)$$

and

$$\left. \begin{aligned} \mathbf{e}(z) &= (t_L \hat{\mathbf{u}}_+ + t_R \hat{\mathbf{u}}_-) \exp[ik_0(z-L) + i\kappa(x \cos u_1 + y \sin u_1)] \\ &\quad + (b_L \hat{\mathbf{u}}_+ + b_R \hat{\mathbf{u}}_-) \exp[-ik_0(z-L) + i\kappa(x \cos u_1 + y \sin u_1)] \\ \mathbf{h}(z) &= i(-t_L \hat{\mathbf{u}}_+ + t_R \hat{\mathbf{u}}_-) \exp[ik_0(z-L) + i\kappa(x \cos u_1 + y \sin u_1)] \\ &\quad + i(-b_L \hat{\mathbf{u}}_+ + b_R \hat{\mathbf{u}}_-) \exp[-ik_0(z-L) + i\kappa(x \cos u_1 + y \sin u_1)] \end{aligned} \right\}, \quad z \geq L. \quad (17)$$

where

$$\hat{\mathbf{u}}_{\pm} = \frac{\hat{\mathbf{u}}_x \pm i\hat{\mathbf{u}}_y}{\sqrt{2}}, \quad (18)$$

and $(\hat{\mathbf{u}}_x, \hat{\mathbf{u}}_y, \hat{\mathbf{u}}_z)$ is the triad of Cartesian unit vectors. In these equations, the complex-valued amplitudes $a_{L,R}$ and $b_{L,R}$ of the left- and right-circularly polarized (LCP and RCP) components of incident plane waves are assumed to be known, whereas the reflection amplitudes $r_{R,L}$ and transmission amplitudes $t_{L,R}$ are not known.

Continuity of the tangential components of the electric and the magnetic fields across the planes $z = 0$ and $z = L$ leads to the prescriptions of the boundary values

$$\bar{\psi}(0) = \bar{\mathbf{Q}} \cdot \begin{pmatrix} a_R \\ a_L \\ r_R \\ r_L \end{pmatrix}, \quad \bar{\psi}(L) = \bar{\mathbf{Q}} \cdot \begin{pmatrix} t_R \\ t_L \\ 0 \\ 0 \end{pmatrix}, \quad (19)$$

where the matrix

$$\bar{\mathbf{Q}} = \begin{pmatrix} 1 & 1 & 1 & 1 \\ -i & i & i & -i \\ i & -i & i & -i \\ 1 & 1 & -1 & -1 \end{pmatrix}. \quad (20)$$

By virtue of Eqs. (16), (17) and (19), we obtain the matrix algebraic equation

$$\begin{pmatrix} t_R \\ t_L \\ b_R \\ b_L \end{pmatrix} = T \cdot \begin{pmatrix} a_R \\ a_L \\ r_R \\ r_L \end{pmatrix}, \quad (21)$$

where the so called transfer matrix is given by

$$T = \frac{1}{4} \bar{\mathbf{Q}}^{\dagger} \cdot \bar{\mathbf{U}} \cdot \bar{\mathbf{Q}} \quad (22)$$

and the symbol \dagger denotes the conjugate transpose.

The result of solving Eq. (21) is best arranged as

$$\begin{pmatrix} t_R \\ t_L \\ r_R \\ r_L \end{pmatrix} = S \cdot \begin{pmatrix} a_R \\ a_L \\ b_R \\ b_L \end{pmatrix} \quad (23)$$

$$S = \begin{pmatrix} t_{RRa} & t_{RLa} & t_{RRb} & t_{RLb} \\ r_{LRa} & r_{LLa} & r_{LRb} & r_{LLb} \\ t_{RRa} & t_{RLa} & t_{RRb} & t_{RLb} \\ r_{LRa} & r_{LLa} & r_{LRb} & r_{LLb} \end{pmatrix} \quad (24)$$

where t_{LRa} and t_{LRb} , etc., are the transmission coefficients and r_{LRa} and r_{LRb} , etc., are the reflection coefficients. The co-polarized transmittances engendered by the waves coming from the left-hand side are denoted by $T_{LLa} = |t_{LLa}|^2$ and $T_{RRa} = |t_{RRa}|^2$, and the cross-polarized ones by $T_{LRa} = |t_{LRa}|^2$ and $T_{RLa} = |t_{RLa}|^2$; and similarly for the reflectances $R_{RRa} = |r_{RRa}|^2$, etc. similar definitions are valid for the waves generated by the waves coming from the right-hand side $T_{LLb} = |t_{LLb}|^2$, $T_{RRb} = |t_{RRb}|^2$ and $T_{LRb} = |t_{LRb}|^2$. The matrix involved S in Eq. (23) is known as the scattering matrix and contains the same information of the transfer matrix but order in different way. It can be straightforwardly shown by writing explicitly the algebraic equations defined by Eq. (21) and solving them for t_R , t_L , r_R and r_L that both matrices are related by the expression

$$S = (T \cdot P_f - P_b)^{-1} \cdot (P_f - T \cdot P_b), \quad (25)$$

where P_f and P_b are the forward and backward projectors given by

$$P_f = \begin{pmatrix} 1 & 0 & 0 & 0 \\ 0 & 1 & 0 & 0 \\ 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 \end{pmatrix}, \quad P_b = \begin{pmatrix} 0 & 0 & 0 & 0 \\ 0 & 0 & 0 & 0 \\ 0 & 0 & 1 & 0 \\ 0 & 0 & 0 & 1 \end{pmatrix}.$$

In what follows we shall restrict our calculation to the case in which the incident waves are coming only from the left hand side that is we take $b_R = b_L = 0$.

5. SPECTRA

In our calculations we have chosen the physical amounts of a real cholesteric elastomer material ($p_0 = 218 \text{ nm}$) [5,11]. Figure 3 shows that in the absence of solvent ($\alpha = 0$) there is only a band reflection for right-circularly copolarized light R_{RR} with the bandwidth of $\simeq 50 \text{ nm}$




FIGURE 3 Circularly polarized reflectance R_{RR} and R_{LL} as function of the wavelength and angle incidence for the ideal helix case $\alpha = 0$ (left column) and $\alpha = 0.4$ (right column). Other parameters are: $\epsilon_{\perp} = 1.91$, $\epsilon_{\parallel} = 2.22$, $h = 1$ and $q_0 = 218$ nm.




FIGURE 4 Circularly polarized transmittance R_{RR} and R_{LL} as function of the wavelength and angle incidence for $\alpha = 0$ (left column) and $\alpha = 0.4$ (right column).

and maximum amplitude. The center of the reflection band blue-shift whereas the width and amplitude band remain constant as the incidence angle θ increases. The corresponding reflectances R_{RL} and R_{LL} do not exhibit practically any band. In contrast, when $\alpha = 0.4$ there appear bands for both left- and right-copolarized reflectances R_{RR} and R_{LL} whereas the cross-polarized reflectance R_{RL} is almost zero. In this case the R_{RR} is not as well formed as in the absence of solvent because it is amplitude present various peaks and the bandwidth varies as a function of the incidence angle, reaching its smaller value for angles around 45 degrees. Differently, R_{LL} is very thin since its bandwidth is around 15 nm and contained in the interval where the R_{RR} band lies.

Figure 4 presents the corresponding transmittances to Figure 3. The case without solvent ($\alpha = 0$) confirms consistently the complementary behavior of an undistorted cholesteric. The co-polarized T_{RR} and T_{LL} exhibit troughs where the transmittance diminishes, the one for T_{RR} is well defined whereas that of T_{LL} changes with thickness a deep. The blue-shift of the trough for large incident angles is also observed.

6. CONCLUSIONS

We have obtained the circularly polarized reflectances and transmittances as function of the chiral order parameter of a cholesteric elastomer immersed in a racemic solvent. We have found considerably changes in the bandwidth of the reflectance for left- and right-copolarized light under the presence of the solvent which are susceptible to be detected experimentally. We have obtained a R_{RR} bandwidth larger than that for an undistorted elastomer ($\alpha = 0$) for $\alpha = 0.4$ and obliquely incidence for angles larger than 60° . Also in this value we have observed a thin band reflection for both polarizations R_{RR} and R_{LL} for oblique incidence.

The modifications of the transmittance and reflectance spectra during a preferentially absorbing process suggest to utilize the optical spectra as an indirect method to determine the concentration of preferentially absorbed molecules during a segregation process.

REFERENCES

- [1] Jakli, A. *et al.* (2006). *One and Two Dimensional Fluids: Properties of Smectics, Lamellar and Columnar Liquid Crystals (Condensed Matter Physics)*, Taylor and Francis: Florida, EU.
- [2] Singh, B. (2007). *J. Phys. D: Appl. Phys.*, 40, 584.
- [3] Mao, Y. & Warner, M. (2001). *Phys. Rev. Lett.*, 86, 5309.

- [4] Warner, M. *et al.* (2007). *Liquid Crystal Elastomers*, Oxford Science Publications: Oxford, EU.
- [5] Rivera, M. & Reyes, J. A. (2007). *Appl. Phys. Lett.*, 90, 023513.
- [6] Cicuta, P., Tajbakhsh, A. R., & Terentjev, E. M. (2004). *Phys. Rev. E.*, 70, 011703.
- [7] Courty, S., Tajbakhsh, A. R., & Terentjev, E. M. (2003). *Phys. Rev. Lett.*, 91, 085503.
- [8] Mao, Y. & Warner, M. (2000). *Phys. Rev. Lett.*, 84, 5335.
- [9] Lakhtakia, A. & Weiglhofer, W. S. (1997). *Proc. R. Soc. Lond. A.*, 453, 93; correction: (1998). 454, 3275.
- [10] Marcuvitz, N. & Schwinger, J. (1951). *J. Appl. Phys.*, 22, 806.
- [11] Cicuta, P., Tajbakhsh, A. R., & Terentjev, E. M. (2002). *Phys. Rev. E.*, 65, 051704.