

## Wells-Dawson Type Heteropolyacid Catalyzed Synthesis of Quinoxaline Derivatives at Room Temperature

Majid M. Heravi<sup>1,\*</sup>, Khadijeh Bakhtiari<sup>1</sup>, Fatemeh F. Bamoharram<sup>2</sup>, and Maryam H. Tehrani<sup>1</sup>

<sup>1</sup> Department of Chemistry, School of Sciences, Azzahra University, Vanak, Tehran, Iran

<sup>2</sup> Department of Chemistry, Azad University of Mashhad, Mashhad, Iran

Received January 13, 2007; accepted (revised) January 18, 2007; published online March 16, 2007

© Springer-Verlag 2007

**Summary.** *Wells-Dawson* heteropolyacid ( $H_6P_2W_{18}O_{62} \cdot 24H_2O$ ) was used as an effective catalyst for the synthesis of biologically active quinoxaline derivatives from the condensation of *o*-phenylenediamines with 1,2-dicarbonyl compounds at room temperature in excellent yields.

**Keywords.** Quinoxalines; 1,2-Diketones; *o*-Phenylenediamines; Heteropolyacid  $H_6P_2W_{18}O_{62} \cdot 24H_2O$ ; *Wells-Dawson*.

### Introduction

In the past ten years, the average number of publications including the keywords ‘synthesis’ and ‘quinoxaline’ has doubled. A large part of these papers concerns highly functionalized molecules with a quinoxaline skeleton designed for biological activities. Quinoxaline derivatives are an important class of nitrogen-containing heterocycles and have shown a broad spectrum of biological activities, such as antibacterial and anti-inflammatory activities [1, 2]. They have been reported for their applications in dyes [3], pharmaceuticals [4, 5], and have also been used as building blocks for the synthesis of organic semiconductors [6, 7]. Quinoxaline ring is part of various antibiotics such as Echinomycin, Levomycin, and Actinoleutin [8, 9] that are known to inhibit growth of *Gram* positive bacteria, and are active against various transplantable tumors [10].

A number of synthesis strategies has been developed for the preparation of substituted quinoxalines


[11–14]. Their synthesis on solid phase has also been reported [15]. By far the most common method relies on the condensation of an aryl 1,2-diamine with a 1,2-dicarbonyl compound in refluxing ethanol or acetic acid for 2–12 h giving 34–85% yields [16].

The problems associated with the handling and disposal of inorganic acids, and their environmental and potential hazards have raised our interest in the development of alternative procedures using solid acid catalysts [17, 18]. Due to their super-acidic properties, heteropolyacids, *HPAs*, can be used in reactions requiring electrophilic catalysis. *HPAs* are applied both in bulk or supported form, with homogeneous and heterogeneous catalysis being possible. The structure of the *Wells-Dawson* heteropolyacid ( $H_6P_2W_{18}O_{62} \cdot 24H_2O$ ) consists of a close-packed framework of  $WO_6$  octahedra surrounding a central P atom, two identical ‘half units’  $PW_9$  are linked through the oxygen atoms [19].

As a part of a research project to develop environmentally friendly organic reactions [20, 21], we have recently applied a variety of heteropolyacid catalysts to different reactions, such as *Biginelli* reaction [22], synthesis of 1,1-diacetates [23], and others [24, 25].

Very recently, we have reported the synthesis of quinoxaline derivatives catalyzed by  $CuSO_4 \cdot 5H_2O$  [26], IBX [27] and  $Zn[(L)\text{-proline}]$  [28]. In this article, we wish to report the catalytic activity of the *Wells-Dawson* heteropolyacid  $H_6P_2W_{18}O_{62} \cdot 24H_2O$

\* Corresponding author. E-mail: mmh1331@yahoo.com



Scheme 1

in a sustainable, simple preparation of functionalized quinoxalines at room temperature in excellent yields (Scheme 1).

## Results and Discussion

The synthesis strategy involves the preparation of quinoxalines **3** from diamines **1** and 1,2-dicarbonyl compounds **2** using  $H_6P_2W_{18}O_{62} \cdot 24H_2O$  as the catalyst. The reaction proceeds very cleanly at room temperature and no undesirable side reactions were observed. In the absence of the catalyst, the reaction did not complete, even after 24 h. The results are shown in Table 1.

The optimum yield of the product **3** was obtained when 1 mol% of HPA was used. Among the solvents tested for this reaction  $CHCl_3$ ,  $CH_3CN$ ,  $H_2O$ , and  $AcOH$ , the latter was found to be the most efficient with respect to short reaction times and maximum yield of the products.

Although water is a desirable solvent for chemical reactions for reasons of cost, safety, and environmental concerns, use of water in this reaction gave only moderate yields of products (30% after 24 h).

**Table 1.** Synthesis of quinoxaline derivatives using the Wells-Dawson heteropolyacid  $H_6P_2W_{18}O_{62} \cdot 24H_2O$  as the catalyst

Product	R	R <sup>1</sup>	Time/min	Yield/% <sup>a,b</sup>	mp/°C
<b>3a</b>	H	H	5	98	128–129
<b>3b</b>	H	CH <sub>3</sub>	5	98	117–118
<b>3c</b>	H	NO <sub>2</sub>	5	98	193–194
<b>3d</b>	H	COOH	10	97	272
<b>3e</b>	OCH <sub>3</sub>	H	20	98	151–152.5
<b>3f</b>	OCH <sub>3</sub>	CH <sub>3</sub>	20	97	125–127
<b>3g</b>	OCH <sub>3</sub>	NO <sub>2</sub>	20	98	192–194
<b>3h</b>	F	H	5	99	135–137
<b>3i</b>	F	CH <sub>3</sub>	5	98	165–167
<b>3j</b>	F	NO <sub>2</sub>	2	99	174–176
<b>3k</b>	F	COOH	5	97	230

<sup>a</sup> All products were well characterized using <sup>1</sup>H NMR and IR spectra; <sup>b</sup> Yields refer to isolated pure products

**Table 2.** Reuse of the catalyst for synthesis of 2,3-diphenyl-quinoxaline **3a**

Run	1	2	3	4	5
Yield/% <sup>a</sup>	99	97	94	92	89

<sup>a</sup> Yields were analyzed by GC

*o*-Phenylenediamines and 1,2-dicarbonyl compounds which have electron-donating or electron-withdrawing groups were used and, as expected, in all cases quinoxalines were obtained in good yields.

It is noteworthy to mention that the catalyst is recyclable and could be reused without significant loss of activity. Even after five runs the catalytic activity of  $H_6P_2W_{18}O_{62} \cdot 24H_2O$  was almost the same as that of the freshly used catalyst (see Table 2).

In conclusion, we developed the use of the Wells-Dawson heteropolyacid  $H_6P_2W_{18}O_{62} \cdot 24H_2O$  as an inexpensive, reusable, easy to handle, non-corrosive, and environmentally benign catalyst for the synthesis of biologically active quinoxalines from aromatic *o*-diamines and 1,2-dicarbonyl compounds. The advantages of the present procedure are simplicity of operation, the high yields of products, and the recyclability of the catalyst. In this reaction the catalyst can be recovered by filtration and washing with *n*-hexane, and subjected to further reaction. Thus, the recycled catalyst could be used for five successive reactions without appreciable loss of activity.

## Experimental

All chemicals were purchased from commercial suppliers and were used as received. All products were identified by their spectra and physical data. Melting points were measured by using the capillary tube method with an electrothermal 9100 apparatus. IR spectra were recorded from KBr disks on the FT-IR Bruker Tensor 27. Mass spectra were recorded on MS 5973 Network Mass Selective detector. All yields were calculated from isolated products, and GC was used to establish their purities. All products were well characterized by comparison of TLC, spectral and physical data with data of authentic samples [26–30].

*Preparation of Quinoxalines Catalyzed by Wells-Dawson Heteropolyacid (General Procedure)*

In this condensation reaction, 1 mmol *o*-phenylenediamine and 1 mmol 1,2-dicarbonyl compound were dissolved in 3 cm<sup>3</sup> acetic acid. The mixture was stirred at room temperature in the presence of a catalytic amount of Wells-Dawson H<sub>6</sub>P<sub>2</sub>W<sub>18</sub>O<sub>62</sub>·24H<sub>2</sub>O (1 mol%, 0.03 g). The progress of the reaction was monitored by TLC. After completion of the reaction, the catalyst was filtered off and washed with 5 cm<sup>3</sup> Et<sub>2</sub>O. The filtrate then was washed with 5% NaHCO<sub>3</sub> (5 cm<sup>3</sup>) and brine (2 × 5 cm<sup>3</sup>) successively, and dried over MgSO<sub>4</sub>. The solvent was evaporated under reduced pressure and the pure product was obtained. A variety of substituted *o*-phenylenediamines were condensed with different 1,2-dicarbonyl compounds. The results are shown in Table 1.

*Reusability of the Catalyst*

At the end of the reaction, the catalyst was filtered off, washed with diethyl ether, dried at 130°C for 1 h, and re-used in another reaction (Table 2).

**Acknowledgements**

The authors are thankful to Azzahra University Council for the partial financial support.

**References**

- [1] He W, Meyers MR, Hanney B, Spada A, Blider G, Galzeinski H, Amin D, Needle S, Page K, Jayyosi Z, Perrone H (2003) *Bioorg Med Chem Lett* **13**: 3097
- [2] Kim YB, Kim YH, Park JY, Kim SK (2004) *Bioorg Med Chem Lett* **14**: 541
- [3] Brock ED, Lewis DM, Yousaf TI, Harper HH (1999) The Procter & Gamble Company, USA WO9951688
- [4] Gazit A, App H, McMahon G, Chen J, Levitzki A, Bohmer FD (1996) *J Med Chem* **39**: 2170
- [5] Sehlstedt U, Aich P, Bergman J, Vallberg H, Norden B, Graslund A (1998) *J Mol Biol* **278**: 31
- [6] Dailey S, Feast WJ, Peace RJ, Sage IC, Till S, Wood EL (2001) *J Mater Chem* **11**: 2238
- [7] O'Brien D, Weaver MS, Lidzey DG, Bradley DDC (1996) *Appl Phys Lett* **69**: 881
- [8] Dell A, William DH, Morris HR, Smith GA, Feeney J, Roberts GCK (1975) *J Am Chem Soc* **97**: 2497
- [9] Bailly C, Echepare S, Gago F, Waring MJ (1999) *Anti-Cancer Drug Des* **15**: 291
- [10] Sato S, Shiratori O, Katagiri K (1967) *J Antibiot* **20**: 270; and reference cited therein
- [11] Porter AE (1984) In: Katritzky AR, Rees CW (eds) *Comprehensive Heterocyclic Chemistry*, vol 3, part 2B, 157 pp
- [12] Sato N (1996) In: Katritzky AR, Rees CW, Scriven EFV (eds) *Comprehensive Heterocyclic Chemistry II*, vol 6. Pergamon, Oxford, 233 pp
- [13] Cheeseman GWH, Werstiuk ESG (1978) *Adv Heterocycl Chem* **22**: 367
- [14] Woo GHC, Snyder JK, Wan ZK (2002) *Prog Heterocycl Chem* **14**: 279
- [15] Wu Z, Ede NJ (2001) *Tetrahedron Lett* **42**: 8115
- [16] Brown DJ (2004) Quinoxalines: Supplement II. In: Taylor ECP, Wipf P (eds) *The Chemistry of Heterocyclic Compounds*. John Wiley & Sons, New Jersey
- [17] Romanelli GP, Autino JC, Baronetti G, Thomas H (2004) *Synth Commun* **34**: 3909
- [18] Romanelli G, Autino JC, Baronetti G, Thomas H (2001) *Molecules* **6**: 1006
- [19] Baronetti G, Briand L, Sedran U, Thomas H (1998) *Appl Catal A* **172**: 265
- [20] Heravi MM, Tajbakhsh M, Ahmadi AN, Mohajerani B (2006) *Monatsh Chem* **137**: 175
- [21] Heravi MM, Bakhtiari KH, Taheri SH, Oskooei HA (2005) *Green Chem* **7**: 867
- [22] Heravi MM, Bakhtiari KH, Bamoharram FF (2006) *Catal Commun* **7**: 373
- [23] Heravi MM, Bakhtiari KH, Bamoharram FF (2006) *Catal Commun* **7**: 499
- [24] Bamoharram FF, Heravi MM, Roshani M, Jahangir M, Gharib A (2006) *Appl Catal A* **302**: 42
- [25] Heravi MM, Motamedi R, Siefi N, Bamoharram FF (2006) *J Mol Catal A Chemical* **249**: 1
- [26] Heravi MM, Taheri SH, Bakhtiari KH, Oskooie HA (2007) *Catal Commun* **8**: 211
- [27] Heravi MM, Bakhtiari KH, Tehrani MH, Javadi NM, Oskooie HA (2006) *Arkivoc* (xvi) 16
- [28] Heravi MM, Tehrani MH, Bakhtiari KH, Oskooie HA (2006) *Catal Commun*, in press
- [29] Bhosale RS, Sarda SR, Ardhapure SS, Jadhav WN, Bhusare SR, Pawar RP (2005) *Tetrahedron Lett* **46**: 7183
- [30] More SV, Sastry MNV, Wang CC, Yao CF (2005) *Tetrahedron Lett* **46**: 6345