

Corrigendum

Corrigendum to “Crystal structures of α and β forms of poly(tetramethylene succinate)” (Polymer 2000:41;4719–27)[☆]

Y. Ichikawa^{a,1,2,*}, H. Kondo^a, Y. Igarashi^a, K. Noguchi^a, K. Okuyama^a, J. Washiyama^b

^a*Faculty of Technology, Tokyo University of Agriculture and Technology, Koganei, Tokyo 184-8588, Japan*

^b*Japan Polyolefins Co. Ltd, Kawasaki Development Center, 2-3-2, Yoko, Kawasaki-ku, Kawasaki 210-3584, Japan*

The authors regret that errors were included in the β form molecular coordinates in Table 4, p. 4722. The correct table

is shown below. These changes do not alter the results and discussion of this paper.

Table 4
The final fractional atomic coordinates of the α and β forms of PTMS

Atom	α form			β form		
	<i>x</i>	<i>y</i>	<i>z</i>	<i>x</i>	<i>y</i>	<i>z</i>
C ₁	0.0839	0.0711	0.5389	0.0401	0.0372	0.5700
C ₂	-0.0117	0.1387	0.6360	0.0049	-0.0916	0.6496
C ₃	-0.0195	0.0832	0.8352	-0.0286	-0.0630	0.8347
C ₄	0.0690	-0.0216	0.9564	0.0697	0.0284	0.9670
O ₁	0.0696	0.0351	0.7495	0.0852	-0.0075	0.7753
O ₂	-0.1536	0.1964	0.8164	-0.1948	-0.1766	0.7837
H _{1a}	0.0392	0.1534	0.4566	-0.1116	0.1372	0.5383
H _{1b}	0.3308	0.0504	0.6104	0.2728	0.0802	0.6432
H _{2a}	0.1104	0.2419	0.6821	0.1563	-0.1914	0.6803
H _{2b}	-0.2591	0.1590	0.5696	-0.2280	-0.1343	0.5754
H _{4a}	0.3190	-0.0237	1.0322	0.0077	0.1541	0.9370
H _{4b}	-0.0138	-0.1308	0.9106	0.3143	0.0186	1.0552

[☆] PII of original article: S0032-3861(99)00659-X

* Corresponding author. Tel.: +81-44-277-7186; fax: +81-44-299-2763.

E-mail address: ichikawa@kpl.sdk.co.jp (Y. Ichikawa).

¹ Present address: Kawasaki Plastics Laboratory, Showa Denko K.K., 3-2, Chidori-cho, Kawasaki-ku, Kawasaki 210-0865, Japan.

² On leave from Showa Denko K.K., Kawasaki Plastics Laboratory.