



Available online at www.sciencedirect.com



Thermochimica Acta 467 (2008) 121

thermochimica
acta

www.elsevier.com/locate/tca

Erratum

Erratum to “Enthalpy-based determination of crystalline, mobile amorphous and rigid amorphous fractions in semicrystalline polymers. Poly(ethylene terephthalate)” [Thermochim. Acta 462 (2007) 15–24]

Maria Cristina Righetti ^{a,*}, Elpidio Tombari ^a, Marco Angiuli ^a, Maria Laura Di Lorenzo ^b

^a Istituto per i Processi Chimico-Fisici (Consiglio Nazionale delle Ricerche), Area della Ricerca, Via G. Moruzzi, 1, 56124 Pisa, Italy

^b Istituto di Chimica e Tecnologia dei Polimeri (Consiglio Nazionale delle Ricerche), c/o Comprensorio Olivetti,

Via Campi Flegrei, 34, 80078 Pozzuoli (NA), Italy

Received 30 October 2007; accepted 31 October 2007

The original article contains imperfections in Eqs. (15)–(18).

The correct equations are shown below:

$$h(T) = h(T_1) + \int_{T_1}^T c_p(T') dT' \quad (15)$$

$$h(T) = w_C(T)h_C(T) + [1 - w_C(T)]h_A(T) + \int_{T_1}^T w_{RA}(T')[c_{p,C}(T') - c_{p,A}(T')]dT' \quad (16)$$

$$h_{RA}(T) - h_A(T) = \frac{1}{w_{RA}(T)} \int_{T_1}^T w_{RA}(T')[c_{p,C}(T') - c_{p,A}(T')]dT' \quad (17)$$

$$w_C(T) = \frac{h_A(T) - h(T)}{h_A(T) - h_C(T)} + \frac{\int_{T_1}^T [w_S(T') - w_C(T')][c_{p,C}(T') - c_{p,A}(T')]dT'}{h_A(T) - h_C(T)} \quad (18)$$

DOI of original article:10.1016/j.tca.2007.06.003.

* Corresponding author. Tel.: +39 050 3152068; fax: +39 050 3152230.

E-mail address: righetti@ipcf.cnr.it (M.C. Righetti).