

# The Temperature Dependence of the Viscosity of Suspensions of Polystyrene Latices in LiCl Solutions

A. Bonincontro, C. Cametti, and A. Di Biasio  
Istituto di Fisica, Università di Roma, Rome, Italy

Z. Naturforsch. **36a**, 329–331 (1981); received December 20, 1980

The viscosities of suspensions of polystyrene particles in aqueous LiCl solutions (about  $3.5 \cdot 10^{-4}$  M) at temperatures from 0 to 60 °C were measured and fitted to relations of the form  $\eta = \eta_0(1 + K_1\Phi + K_2\Phi^2)$ , where  $\Phi$  is the volume fraction of the particles.

In contradiction to existing theories the coefficients  $K_1$  and  $K_2$  were found to be temperature dependent.

It is well known that aqueous suspensions of spherical colloidal particles exhibit a pronounced viscosity increase when the electrolyte content in the aqueous phase is reduced. This effect, existing even in extremely diluted suspensions (first electroviscous effect), is due to a distortion, under a gradient of shear, of the electrical double layer surrounding the dispersed particles. Theoretical treatments of this effect have been proposed by several authors [1], [2], [3], and especially Stone-Masui and Watillon [4] have reported extensive viscosity measurements of polystyrene suspensions at a fixed temperature of 25 °C.

Recently we have observed that the dielectric properties of polystyrene suspensions at microwave frequencies are affected by the ionic species and ionic strength of the continuous medium and show thermal anomalies [5]. As the parameters which influence the dielectric properties are the same as those responsible for the electroviscous effects, in the present study the viscosity of colloidal suspensions of polystyrene particles in LiCl solutions was measured in the temperature range from 0 to 60 °C.

A suspended level Ubbelohde type viscometer with an average shear rate of about  $650 \text{ sec}^{-1}$  was employed. Five efflux times were measured for each volume concentration and temperature. The mean deviation did not exceed 0.02%.

The average particle diameter was  $0.091 \mu\text{m}$ , standard deviation  $0.0053 \mu\text{m}$ . The fractional volumes of the dispersed phase were kept low (from

0.5 to 1.5%) to avoid secondary electroviscous effects. Volume concentrations were determined from dry weights, using a density of  $1.052 \text{ g/ml}$  for polystyrene.

In order to control the salt contents of the suspensions and to obtain isoionic samples, an ultrafiltration cell Amicon mod. 12 with membrane XM 100 was used. The polystyrene latices were first dialyzed at a temperature of 60 °C against deionized water ( $\sigma < 10^{-6} \Omega^{-1} \cdot \text{cm}^{-1}$ ) to remove all free and adsorbed electrolytes, essentially leaving only surface charges. The ionic conductivity was then changed to the desired value ( $3.3510^{-5} \Omega^{-1} \cdot \text{cm}^{-1}$  at 25 °C) by adding LiCl solution and measured as a function of temperature both before and after each investigation to ensure that contamination did not take place.

The temperature was defined within 0.01 °C.

The surface charge density was calculated from the electrophoretic mobilities at the ionic strengths corresponding to those used in the viscosity measurements. The relation between the charge on the particle and the  $\zeta$ -potential at the plane of shear, using the simplified method given by Stigter and Mysels [6], yielded a surface charge density of about  $750 \text{ statcoulomb/cm}^2$ , largely independent of temperature and ionic strength.

Viscosity data are usually analyzed on the basis of equations of the form

$$\eta = \eta_0(1 + K_1\Phi + K_2\Phi^2),$$

where  $\eta_0$  is the viscosity of the continuous medium and  $\Phi$  the volume fraction of the particles.

The coefficients  $K_1$  and  $K_2$  (first and second order electroviscous coefficients, respectively) are obtained from the intercept and slope of  $(\eta/\eta_0 -$

Reprint requests to Dr. C. Cametti, Istituto di Fisica, Università di Roma, Piazzale Aldo Moro 5, I-00185 Rom, Italien.

0340-4811 / 81 / 0400-0329 \$ 01.00/0. — Please order a reprint rather than making your own copy.



Dieses Werk wurde im Jahr 2013 vom Verlag Zeitschrift für Naturforschung in Zusammenarbeit mit der Max-Planck-Gesellschaft zur Förderung der Wissenschaften e.V. digitalisiert und unter folgender Lizenz veröffentlicht: Creative Commons Namensnennung-Keine Bearbeitung 3.0 Deutschland Lizenz.

Zum 01.01.2015 ist eine Anpassung der Lizenzbedingungen (Entfall der Creative Commons Lizenzbedingung „Keine Bearbeitung“) beabsichtigt, um eine Nachnutzung auch im Rahmen zukünftiger wissenschaftlicher Nutzungsformen zu ermöglichen.

This work has been digitalized and published in 2013 by Verlag Zeitschrift für Naturforschung in cooperation with the Max Planck Society for the Advancement of Science under a Creative Commons Attribution-NoDerivs 3.0 Germany License.

On 01.01.2015 it is planned to change the License Conditions (the removal of the Creative Commons License condition “no derivative works”). This is to allow reuse in the area of future scientific usage.




Fig. 1.  $[\eta]/\Phi$  vs. temperature for polystyrene particles in LiCl electrolyte solution.  $[\eta] = \eta/\eta_0 - 1$ ,  $\Phi$  = fractional volume of dispersed phase. Specific conductivity  $\sigma_m = 3.35 \cdot 10^{-5} \Omega^{-1} \text{ cm}^{-1}$  at 25 °C. Particle diameter 0.091  $\mu\text{m}$ . The solid lines represent least-squares fits of the data to straight lines and the dashed lines define a confidence level of 95%.

1)/ $\Phi$  vs.  $\Phi$  plots. Figure 1 shows  $[\eta]/\Phi = (\eta/\eta_0 - 1)/\Phi$  as a function of temperature for various volume fractions of the particles, and the solid lines represent a least-squares fit of the data to the equation

$$[\eta]/\Phi = \alpha + \beta T. \quad (1)$$

The coefficients  $K_1$  and  $K_2$  for each temperature, were determined by a least-squares fit to the equation  $[\eta]/\Phi = K_1 + K_2\Phi$ . This procedure gave the temperature dependence of the electroviscous coefficients with sufficiently small errors, as shown in Figs. 2 and 3 (curves a).

For colloidal suspensions of undeformable spherical charged particles, Booth [2] derived the expression

$$K_1 = 2.5 \left\{ 1 + q^* \left( \frac{Ze^2}{\epsilon a K_B T} \right)^2 F(K_D, a) \right\}, \quad (2)$$

where  $\epsilon$  is the static dielectric constant of the continuous medium,  $a$  the particle radius,  $K_B$  the




Fig. 2. First-order electroviscous coefficient  $K_1$  vs. temperature. Curve a) values derived from experimental data with statistical error margins. Curve b) values calculated from Equation (2).

Boltzmann constant,  $T$  the absolute temperature,  $Ze$  the charge of the electrokinetic unit,  $1/K_D$  the




Fig. 3. Second-order electroviscous coefficient  $K_2$  vs. temperature.

Curve a) values derived from experimental data with statistical error margins.

Curve b) values calculated from Equation (3).

Debye-Hückel double layer thickness,  $F(K_D a)$  and  $q^*$  functions given by Booth in [2].

The second order electroviscous coefficient  $K_2$  has been treated by Chan, Blachford, and Goring [3] on the basis of a model taking into account a particular collision process between the charged particles.

In this theory, the coefficient  $K_2$  is given by

$$K_2 = 0.18[K_0]^2 \left( \frac{a + \delta_c}{a} \right)^5, \quad (3)$$

where  $[K_0]$  is the Einstein coefficient and  $\delta_c$  is the collision distance evaluated by equilibrating the

electrostatic repulsive force and the hydrodynamic compressive force.

The coefficient  $K_1$  calculated from (2) as a function of temperature is shown in Fig. 2 (curve b). As can be seen, the Booth theory predicts values independent of temperature and lower than those derived from the experimental data (curve a).

The coefficient  $K_2$  as a function of temperature, calculated from (3) is shown in Fig. 3 (curve b). Also in this case, the calculated values of  $K_2$  are largely independent of temperature.

The discrepancy between the calculated and measured absolute values of  $K_1$  and  $K_2$  may be meaningless owing to the approximations involved in the determination of the surface charge density from electrophoretic mobilities and the temperature dependence of the  $\zeta$ -potential from the Debye-Hückel theory. However the temperature dependences of  $K_1$  and  $K_2$  are certainly significant.

In this connection it must be mentioned that in the models the particles are assumed to exhibit no Brownian motion. This assumption seems to be unrealistic for the sample under investigation, and perhaps the effect of temperature on the Brownian motion in shear flow may be the reason for the striking temperature dependence of  $K_2$ .

#### Acknowledgement

The authors wish to thank Prof. C. Ballario for his continuous interest in this work.

- [1] M. von Smoluchowski, *Kolloid-Z.* **18**, 194 (1916). — W. Krasny-Ergen, *Kolloid-Z.* **74**, 172 (1936).
- [2] F. Booth, *Proc. Roy. Soc. London A* **203**, 53 (1950).
- [3] F. S. Chan, J. Blachford, and D. A. I. Goring, *J. Colloid Inter. Sci.* **22**, 378 (1966).
- [4] J. Stone-Masui and A. Watillon, *J. Colloid Inter. Sci.* **28**, 187 (1968).

- [5] C. Ballario, A. Bonincontro, and C. Cametti, *J. Colloid Inter. Sci.* **63**, 567 (1978). C. Ballario, A. Bonincontro, and C. Cametti, *J. Colloid Inter. Sci.* **54**, 415 (1976).
- [6] D. Stigter and K. J. Mysels, *J. Phys. Chem.* **59**, 45 (1955).