(No Model.)

G. EASTMAN.

PHOTOGRAPHIC FILM.

No. 306,594.

Patented Oct. 14, 1884.

C A Million Company B

WITNESSES= HG Phierips. a.y. alling INVENTOR:
George Eastman,
by Geo. B. Selden.
atty-

## United States Patent Office

GEORGE EASTMAN, OF ROCHESTER, NEW YORK, ASSIGNOR TO THE EASTMAN DRY PLATE COMPANY, OF SAME PLACE.

## PHOTOGRAPHIC FILM.

SPECIFICATION forming part of Letters Patent No. 306,594, dated October 14, 1884.

Application filed March 7, 1884. (No model.)

To all whom it may concern:

Be it known that I, GEORGE EASTMAN, of Rochester, New York, have invented an Improvement in Photographic Films, of which the following is a specification, reference being

had to the accompanying drawing.

My invention relates to an improvement in photographic films having for their object the production for the market of sensitized films, 10 which are capable of being used in making positives and negatives in place of the sheets of glass coated with emulsion, now known in the trade as "dry-plates;" and to this end my invention consists in the new article of manu-15 facture formed by my improved sensitized films, and in the process or mode of manufacture of my said films, all as more fully described in the following specification, and specified in the claims thereunto annexed.

In the accompanying drawing, the figure represents a section of one of my improved

sensitized films on an enlarged scale.

In the practical operations of manufacturing my improved sensitized gelatine films I apply 25 to a suitable paper or other fabric a coating of a solution of gelatine dissolved in water of a strength of about fifty grains to the ounce, and allow the same to dry either spontaneously or by artificial heat. I prefer to use Rives' pa-30 per-such as is ordinarily albumenized for the manufacture of silver prints-on account of its freedom from chemical impurities, fine even grain, and translucency, which permits the close examination of the image during the de-35 velopment; but any other suitable kind of paper may be employed.

The operation of coating the paper with the gelatine solution may be performed by floating, by applying it with a brush or dabber, or 40 by suitable machinery, in all cases the requisite care being taken to exclude the access of dust. The gelatinized paper is now coated with a layer of any ordinary gelatine argentic emulsion the gelatine of which has been ren-45 dered more or less insoluble relative to that forming the layer next the paper by any appropriate means. The requisite degree of insolubility relative to that of the first layer may be attained by adding to the finished emulsion, 50 when ready for the coating operation, a suit-

able quantity of any substance which possesses the property of rendering the gelatine insoluble when dried, and which will not cause any chemical decomposition of the emulsion. Chrome-alum answers this purpose effectually, 55 and it may be employed in quantities varying with the character of the particular gelatine employed in the emulsion, the season of the year, or other circumstances, as the judgment of the operator may indicate; but which pro- 60 portion may be stated generally as approximating five ounces of a solution of chrome alum of ten grains to the ounce of water to one gallon of the finished emulsion. The preparation of the sensitive gelatine emulsion 65 is now too well understood to require particular description. The operation of coating the gelatinized paper with the sensitized emulsion may be performed in any preferred way in a sufficiently non-actinic light, and, after the 70 coating thus applied has been dried, the film is ready for exposure, either in the camera or under a negative, as the operator may desire to produce a positive or negative image. For exposure in the camera the film is temporarily 75 affixed to some rigid support, which may be done in any preferred manner.

It is unnecessary to remark to those accustomed to the preparation and coating of gelatine emulsions that the gelatine layer B and 80 the emulsion layer C should be applied to the support at a suitable temperature, which may be about 90° to 110°, the object being to use the lowest temperature at which the gelatine will remain fluid, which is lower with the solu- 85 ble substratum than with the emulsion hardened by a suitable chemical. The temperature will vary also somewhat with the particular samples of gelatines employed. After exposure, the development of the film may 90 be carried out by any suitable development, although I recommend the well-known ferrousoxalate development, or the so-called sulphiteof-soda development, in which sulphite of soda, carbonate of soda, and pyrogallic acid are em- 95 ployed. The fixing is accomplished in a solution of hyposulphite of soda, as usual. After being thoroughly washed, the film is detached from the paper in the following or in some equivalent manner: The fixed and washed 100

film is floated face downward in water, and a glass plate being introduced under it and lifted out of the water, the plate will lift the film with it, which is then caused to adhere 5 closely to its surface by pressure on the back on the paper. The adhesion is preferably secured by the sliding pressure of the edge of a straight piece of rubber or other flexible substance carried along the back of the film. 10 The application of the pressure should be repeated until contact is secured at all points by the entire removal of the water between the glass and the film. The paper support is now detached from the film by the application 15 of the requisite degree of heat to the glass plate, the effect of which is to soften the gelatine layer between the paper and the relatively-insoluble gelatine layer containing the image, so that the paper may be readily 20 stripped off or removed, leaving the image adhering to the glass. The heat may be applied uniformly by placing the glass on a heated plate of metal or on a water bath, or by the application of hot water to the plate. 25 Any remaining traces of the soluble gelatine layer may be sponged or washed off with warm water, and the glass and adhering film, when dried and varnished, if desired, is ready for the printer.

In the accompanying drawing, which represents a section through one of my improved sensitive films, A is the paper or other support; B, the soluble gelatine layer, and C the relatively-insoluble layer of sensitized gela-

By the use of wax on the glass or other support, the film may be stripped and used or preserved independently. Thus the glass having been coated with beeswax dissolved in tur-40 pentine and subsequently polished, the gelatine image may be removed therefrom by applying a moist gelatine sheet to it and allowing it todry, after which the two gelatine sheets may be removed together from the glass or 45 other support, and may be subsequently used to print from, or mounted or preserved in any preferred manner.

The operations may be performed in different order. Thus the paper may be stripped 50 from the film before development or after development, and before fixing or after fixing.

I prefer to use Cox's transparent, or Nelson's No. 1, or other soft gelatines for the first coating, and to make the emulsion with Simeon's 55 or Heinrich's hard gelatine. In case the lastmentioned gelatines are employed, the quantity of chrome-alum may be diminished. The quantity of chrome-alum which is to be added to the finished emulsion will depend on the 60 hardness of the particular sample of gelatine employed; but I have not observed any gelatine in which the requisite degree of insolubility could be obtained after drying without the addition of at least three ounces of a ten-65 grain solution.

Glycerine may be added to either or both

dering the film flexible. The quantity of glycerine added should be about one-half of the weight of the gelatine employed, although a 7c greater or less proportion may be used. The support A may also be treated with glycerine or a solution of glycerine in water; but I prefer to add it to the emulsion.

The advantages which my improved sensi-75 tized films possess over the ordinary glass dryplates are too obvious to require description. Thus I am enabled to dispense entirely with the glass, the original cost and the expense arising from the handling, cleaning, breakage, 80 and transportation of which I save. I am also able to effect a considerable economy in the amount of emulsion used, as the glass, owing to its curvature and uneven surface, requires to be coated thicker than the gelatinized pa-85 per; and, as the operation of coating the gelatinized paper with the emulsion may in manufacturing operations be carried on by machinery in absolute darkness, the highest sensitiveness may be given to the emulsion employed 90 in my improved films without danger of fog from too much light; and the operations necessary to secure the desired image by the use of my improved films, in so far as they differ from the ordinary process now employed, are 95 so simple as to be readily learned by the most inexperienced person.

The substratum or intermediate attaching film I prefer should be composed of gelatine, as described, as I have found in practice that 100 said material possesses in an eminent degree the qualities necessary to carry into execution my invention; but it is evident other substances which possess the quality of resisting the solvent action of the developing-fluids at 105 the normal temperatures, but will yield and dissolve under the action of heat in watery solutions, may be employed without departing

from the spirit of my invention.

By the expressions "insoluble gelatine film" 110 and "relatively insoluble gelatine film," as herein employed, is meant a film which will withstand the solvent action of water for a greater time or to a greater degree than the intermediate or soluble film.

In speaking of an insoluble film I do not mean to be confined to a film which is absolutely insoluble in water, the invention embracing any film which is adapted to withstand the solvent action of water in a marked 120 degree.

I claim—

1. As a new article of manufacture, a sensitive photographic film consisting of a coating of insoluble sensitized gelatine, a paper or 125 equivalent support, and an interposed coating of soluble gelatine.

2. In a photographic film, the combination of the support A, the insoluble sensitive gelatino-argentic-emulsion film C, and the soluble 130 interposed gelatine layer B, substantially as described.

3. In a film for photographic purposes, the of the layers B and C, for the purpose of ren- combination of a backing sheet or support of

115

paper or like material, a film of sensitized gelatine adapted to withstand the solvent action of water, and an intermediate film of soluble

4. The herein-described sensitive flexible photographic film, consisting of the support A, having a layer of insoluble sensitized gelatine, C, attached thereto by means of an interposed soluble gelatine substratum, said film 10 being rendered flexible by means of glycerine,

substantially as described.

5. As an improvement in the art of photography, the process consisting in, first, providing an insoluble sensitive gelatine film affixed

by solvent material to a supporting-sheet; second, in exposing and developing said film; third, attaching the developed film to a rigid plate by means of wax or its equivalent; fourth, in detaching the support from the film 20 by the application of heat; and, fifth, strip-

ping the film from the waxed surface.

6. As a new article of manufacture, a sensitive photographic film composed of a paper or equivalent support, an insoluble sensitized film, and an intermediate soluble attaching- 25 film insoluble in the developing-fluids, and at normal temperatures, but rendered soluble by the application of heat in watery solutions, substantially as described.

7. As a new article of manufacture, a sensi- 30 tive photographic film composed, essentially, of a paper or equivalent support, a film of sensitized gelatine, and an interposed attachingfilm, the said sensitized film being insoluble, and the said intermediate attaching-film being 35. insoluble with respect to the developing-fluids but rendered soluble in water by the application of heat, substantially as described.

GEORGE EASTMAN.

Witnesses:

GEO. B. SELDEN, O. W. ALLISON.