

LA-6063

6.2

UC-21

Reporting Date: August 1975

Issued: October 1975

**Laser-Fusion Target Fabrication:
 Application of a Polymeric Ablator Coating to a
 Ball-and-Disk Target Design by the
 Physical Vapor Deposition of Polyethylene**

by

Gary A. Simonsic *CMB'6*

LOS ALAMOS NATIONAL LABORATORY



DO NOT CIRCULATE

PERMANENT RETENTION

REQUIRED BY CONTRACT



**los alamos
 scientific laboratory**

of the University of California

LOS ALAMOS, NEW MEXICO 87545

An Affirmative Action/Equal Opportunity Employer

5.2

Printed in the United States of America. Available from
National Technical Information Service
U S Department of Commerce
5285 Port Royal Road
Springfield, VA 22151
Price: Printed Copy \$4.00 Microfiche \$2.25

This report was prepared as an account of work sponsored by the United States Government. Neither the United States nor the United States Energy Research and Development Administration, nor any of their employees, nor any of their contractors, subcontractors, or their employees, makes any warranty, express or implied, or assumes any legal liability or responsibility for the accuracy, completeness, or usefulness of any information, apparatus, product, or process disclosed, or represents that its use would not infringe privately owned rights.

**LASER-FUSION TARGET FABRICATION:
APPLICATION OF A POLYMERIC ABLATOR COATING TO A
BALL-AND-DISK TARGET DESIGN BY THE
PHYSICAL VAPOR DEPOSITION OF POLYETHYLENE**

by

Gary A. Simonsic

ABSTRACT

A technique for applying polyethylene by physical vapor deposition is described. The ball-and-disk target design requires the application of a thin film of polyethylene on the front surface of the ball and substrate upon which the ball is mounted. Disk-shaped films, typically 200- μm -diam by 1- μm -thick, are successfully applied by this method.



INTRODUCTION

Thin-film technology is being widely used in the fabrication of targets for laser-initiated fusion. The fabrication of laser-fusion targets, which are made individually, requires that thin films be applied to various microsize substrates. A prime area of interest is organic thin films, which are used in various target designs. Because of the size and nature of laser-fusion targets, unique techniques for the deposition of organic coatings from the vapor state had to be developed and evaluated.

This report describes a technique developed for the ball-and-disk target design, which is shown in Fig. 1. This design consists of a nominal 50- μm -diam glass microballoon containing 50-100 atm of DT gas. The microballoon is mounted on a 1000- \AA -thick polymeric film. A 1- μm -thick polyethylene coating is applied to the front surface of the microballoon and to the polymeric substrate for a radial distance of about 100 μm from the center of the microballoon.

PHYSICAL VAPOR DEPOSITION OF THE POLYETHYLENE DISK

The physical vapor deposition (PVD) of polyethylene is somewhat analogous to the PVD of

metal; the main difference is the relatively low vaporization temperature ($<500^\circ\text{C}$) of the polyethylene. The coating is applied in a vacuum-evaporator station under an operating pressure of $<1 \times 10^{-5}$ mm Hg. A small, weighed charge of polyethylene* is vaporized from an alumina crucible, which is heated by a wrapping of nichrome, resistance heating wire, as shown in Fig. 2. The polyethylene is maintained at $\sim 425^\circ\text{C}$ during vaporization. Splattering of the polyethylene from the crucible is prevented by placing boiling stones in the crucible and a 30-mesh stainless steel screen over the mouth of the crucible. The shape of the polyethylene film is produced by placing a mask with a 200- μm -diam hole over the ball and film mount. The source-to-substrate distance established for this process was 50 mm. Eleven milligrams of polyethylene completely vaporized with the above conditions will yield a 1- μm -thick disk. Figure 3 is a photomicrograph of a ball-and-disk laser-fusion target.

*Alathon 4275, E. I. Du Pont de Nemours and Company, Wilmington, DE.

