

UNCLASSIFIED

SPECIAL RE-REVIEW  
FINAL DETERMINATION  
UNCLASSIFIED, DATE: 7/8/80

VERIFIED UNCLASSIFIED

271




*E.M.S 7/10/79*  
*JFW 7/8/80*



DO NOT CIRCULATE  
Retention Copy

*C.1*



FOR REFERENCE

NOT TO BE TAKEN FROM THIS ROOM


LIBRARY BUREAU

CAT. NO. 1935

LOS ALAMOS NATIONAL LABORATORY



3 9338 00407 6583




CLASSIFIED

UNCLASSIFIED

UNCLASSIFIED

UNCLASSIFIED


UNCLASSIFIED



VERIFIED UNCLASSIFIED

Per E.M.S. 7-10-79  
By M. Baltes 4-29-96

LA REPORT - 271



May 4, 1945

This document contains 14 pages

Classification changed to UNCLASSIFIED  
by authority of the U. S. Atomic Energy Commission,

Per LD R, ID-1381 Suppl. 12-31-71

By RNPORT LIBRARY Adamantini 7-26-72

EFFECT OF RIGIDITY ON SHOCK WAVES IN SOLIDS

PUBLICLY RELEASABLE  
LANL Classification Group  
Mahavir Jani  
4-11-96

WORK DONE BY:

R. E. Peierls

P. R. Stein

REPORT WRITTEN BY:

R. E. Peierls



VERIFIED UNCLASSIFIED

E.M.S. 7-10-79  
JLW 7/8/80

LOS ALAMOS NATL. LAB. LIBS.



3 9338 00407 6583



UNCLASSIFIED

UNCLASSIFIED

U. S. G. O.  
 O. F. I. S. I.  
 A B S T R A C T

**UNCLASSIFIED**

Passage of a plane shock wave in a solid causes a change in shape as well as a compression of each mass element. The deformation produces a shear stress with a component normal to the plane of the wave front; this acts in addition to the hydrostatic pressure which is usually assumed as the only important force. For small displacements this has the same effect as increasing the bulk modulus by an amount of the order of 15 to 30 percent depending on Poisson's ratio. When the plastic yield strength is reached, the shear stress ceases to increase and from there on the total force differs from the hydrostatic pressure by a constant amount. As a result the curve representing this force as a function of specific volume will have a point of inflection. Hence the velocity of a weak shock (pressures of the order of 0.1 to 0.4 megabars) can be less than the longitudinal sound velocity. Such a shock starting from normal density would not be stable and would not, in fact, be formed. Instead, the material will be compressed in two stages, an initial compression from zero pressure to about the yield limit, and a second compression from then to the shock pressure. The first compression is continuous, and travels with the longitudinal sound velocity. If the compression is caused by impact, this first compression wave has a very steep front. The second part is by shock and travels with a velocity depending on this final pressure. When the pressure is high enough to make this velocity equal to or greater than longitudinal sound velocity the two compression waves coalesce into a single shock. Figures are given to show this effect for Al, Cd, Cu, Fe, and tuballoy. During expansion the strength reduces, rather than increases, the effective compression modulus on compression and expansion, and one obtains a hysteresis loop in a pressure-volume diagram, the area of the loop being equal to the energy lost irreversibly.

U. S. G. O.

O. F. I. S. I.

**UNCLASSIFIED**



which, for small displacements becomes

$$\tau'_{xx} = \frac{2}{3} \left( \frac{v}{v_0} - 1 \right) \quad (3)$$

In any event since, in our one-dimensional case, the deformation of each volume element depends only on one parameter,  $\tau'_{xx}$  is a unique function of  $v$ .

Within the elastic limits,

$$\sigma'_{xx} = 2G \tau'_{xx} \quad (4)$$

where  $G$  is the rigidity modulus, and for higher strains the stress becomes constant. We shall assume the stress-strain relation to be given by

$$\sigma'_{xx} = \begin{cases} 2G \tau'_{xx} & \tau'_{xx} \leq Y/2G \\ Y & \tau'_{xx} > Y/2G \end{cases} \quad (5)$$

where  $Y$  is the yield stress. This relation is not far from the truth.

The stress above the yield point cannot depend on the strain, since, once plastic flow sets in, the initial shape is no longer relevant. It may however depend on the rate of strain. The effect of this dependence is rather like that of viscosity in a gaseous shock and we will not investigate it here.

We can now plot the stress  $\sigma_{xx}$  against the specific volume  $v$  and the curve we obtain is shown schematically in Fig. 1.  $v_0$ -A is the hydrostatic pressure only,  $v_0$ -B is the shear stress, and  $v_0$ -C is the sum of the two, and hence  $\sigma_{xx}$ .

Consider now a discontinuous transition by shock from the normal state (volume  $v_0$ ) to a state given by the point P. From the relations of Hugoniot we can see as usual that the slope of the line  $Pv_0$  is equal to  $U^2/v_0^2$  where  $U$  is the shock velocity. For a liquid with  $Y = 0$ ,  $G = 0$  the line would lead to  $P'$  instead, and it is seen that, in the case shown, the difference is small if the

1) LA-165 p.74

shock strength is large compared to  $\gamma_0$

However, for a somewhat weaker shock, as shown by Q in the figure, the line  $v_0Q$  intersects the curve  $v_0c$  at an intermediate point s. Since the line  $v_0Q$  now lies partly below the curve, such a shock would be unstable according to the criterion of von Neumann.<sup>1)</sup> What actually happens then is that the shock will extend only from T to Q, where T is the point of contact with the curves from Q.

The initial compression from  $v_0$  to T will in general also be discontinuous. This follows if we take our definition (5) as exactly valid, since the function  $\sigma'(v)$  is linear, whereas  $p(v)$  is always convex towards the v-axis, so that the resultant is also slightly convex and a stable shock from  $v_0$  to T is possible.

Actually even if the line from  $v_0$  to T were exactly straight, the compression would be discontinuous, since we would then have the acoustic case in which the pressure distribution propagates without change of shape. If, therefore, the shock is caused, for example, by an impact, it will have a discontinuous rise initially and then be propagated without change.

We find, therefore, that a shock which is not too strong will consist of an initial small compression to the yield limit, and a final shock. The velocity of the first part is given by the slope of the line  $v_0-T$ , which evidently is

$$- (dp/dv)_0 + (4/3)G$$

or since

$$- (dp/dv)_0 = \mu$$

where  $\mu$  is the compression modulus, it is

$$\mu + (4/3)G$$

This is equal to the square of velocity times density, hence the velocity of the initial shock is

$$\sqrt{\frac{\mu + (4/3)G}{\rho_0}}$$

1) LA-166 p. 74.

•••••

This is the velocity of a longitudinal sound signal.

It is evident from the figure that conditions will be as exemplified by the point P or Q respectively according to whether the velocity of the main shock is greater or less than longitudinal sound velocity.

Figs. 2 to 6 show the quantitative pictures for a number of metals. The hydrostatic pressures are taken from the report by Metropolis (LA-208). For the elastic constants values were collected from the literature. In general the value of Poisson's ratio and Young's modulus given in Kaye and Laby's tables, were most nearly consistent with Bridgman's values for the compressibility on which LA-208 is based. In each case two slopes are shown for the longitudinal sound velocity, using either the published value of Poisson's ratio or of Young's modulus, to give an idea of the consistency. In the case of Al only one curve is shown, since in this case the data are exactly consistent.

Elastic constants for tuballoy were taken from measurements by Birch. The data are summarized in the following table. The first column gives the hydrodynamic sound velocity, the second the longitudinal velocity, which is also equal to the critical shock velocity, for which the shock just ceases to be preceded by a sound signal. The next column gives the pressure corresponding to the pressure belonging to this shock if strength is negligible. Actually since the strength raises the curve  $v_0P$  of Fig. 1 somewhat above the curve  $v_0P'$ , the actual critical shock pressure is slightly less than the figure given in the table.

The fourth column gives the corresponding compression, again neglecting strength.

The last column gives, approximately, the shock pressure expected to be caused in each material by a detonation wave in Comp. B striking the metal normally.

•••••

7

SECRET

It is seen that this exceeds the critical pressure for Al, Cd, Cu, that it is below  $P_{crit}$  in Fe, and about equal to it for Tu. Hence the effect described here ought to exist in steel, might exist to a very small extent in tuballoy, and should be absent in normal conditions in all other metals included in the table.

Experiments by Group G-8 have shown strong indications of such an effect in steel and none in the other metals; this agrees therefore with our expectation. In all cases, the effect might be expected in thick plates and with very small amounts of H.E., since the shock attenuation will reduce the shock strength so that the sound signal will detach itself from the shock after some initial run as a single shock. It would, however, be necessary to use very high weight ratios of metal to H.E. to make the effect observable.

Material	hydro. velocity m/sec.	longit. velocity m/sec.	$P_{crit}$ megabars	$\frac{P_{crit}}{P_0}$	$P_{shock}$ Megabars
Al	6210	6320	.17	1.19	.28
Cd	2270	2880	.101	1.18	.35
		2790	.097	1.15	
Cu	3920	4780	.216	1.12	.37
		4580	.184	1.11	
Fe	4630	6020	.438	1.18	.36
		6290	.388	1.16	
Tu	2440	3240	.40	1.26	.39

The part of the curve  $v_0 P$  in Fig. 1 which lies above the yield point T is irreversible, and on expansion the material will follow a curve which instead

SECRET



SECRET



SECRET

of lying above the hydrostatic curve, will lie below it since the plastic stress will again oppose deformation and will now act in a direction opposite to the hydrostatic pressure.

The shape of the descending part of this curve is of great importance for the theory of spalling.



SECRET

SECRET

DECLASSIFIED





FIG. 1

DECLASSIFIED

DECLASSIFIED

FIG. 2. ALUMINUM



DATA SHEET

NO. 730-4

CHARLES BRUNNEN COMPANY, INC.  
Millimeters, 1/32 inch (0.857)

FIG 3 CADMIUM




FIG. 4: COPPER

DATA 5-5775

CHARLES BRUSHING COMPANY, INC. NO. 700-M  
Millington, Tenn. 37555




FIG. 5 IRON

DATA SHEET

CHARLES BRUNING COMPANY, INC. NO. 720-4  
Millimeters, 1/4th line every





FIG. 6 TUBALOY



APPROVED FOR PUBLIC RELEASE

APPROVED FOR PUBLIC RELEASE

UNCLASSIFIED

UNCLASSIFIED

UNCLASSIFIED

03713

DOCU

DATE 5-11-45

REC. NO. REC.



03713

UNCLASSIFIED